MIL-C-915/3D
5 April 1973
SUPERSEDING
MIL-C-915/3C
1 August 1972

MILITARY SPECIFICATION SHEET

CORD, ELECTRICAL, 300 VOLTS, TYPES DCOP AND TCOP

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cord described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:
Qualification required.

Construction

First - Copper conductor, uncoated, (see Details for size). See note 2.
Second - Polyvinyl chloride insulation, (80°C) Nominal wall thickness 0.015 inch. Standard Identification Code, applied by Method 3.
(D) Third - The specified number of conductors (see Details) shall be cabled together with the lay not greater than that specified (see Details). A tie cord shall be laid straight as a central core in DCOP-1-1/2. Fibrous fillers shall be employed, where necessary, to obtain a firm, well-rounded assembly.
Fourth - A braid of minimum No. 60/2 ply cotton or alternate shall be used over the conductor assembly of DCOP-1 and is permitted, but not required, on DCOP-1-1/2. A binder shall be used over the conductor assembly of DCOP-2 and TCOP-2.
Fifth - Standard thermoplastic jacket. (Black)

Note 1 - Because of peculiar lay-up of DCOP-1-1/2 cord, the centering and circularity requirements shall not apply, provided the minimum thickness requirements are met.
Note 2 - At the manufacturer's option, the conductors in type and size DCOP-1 may consist of eight strands, each having a nominal diameter of 0.010-inch, around one strand having a nominal diameter of 0.0142-inch.

Details

Type and Size	Conductors			Overall diameter		Voltage withstand min. (volts)	Condr. res. per 1000 ft. max. (ohms)
	No.	Size Navy Standard	Cabling Lay Maximum (inches)	min. (inch)	max. (inch)		
DCOP-1	2	1(10)	1	0.235	0.250	1000	11.60
DCOP-1-1/2	2	1-1/2(16)	3/8	.300	.315	1500	13.10
DCOP-2	2	1-1/2(16)	2	.310	.330	1500	7.22
TCOP-2	3	1-1/2(16)	2	.325	.345	1500	7.22

(D) Denotes changes.

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:04Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS:

	Requirements
Basic Electrical:	
Conductor resistance - Ohms/1000 ft. at 25°C., Maximum	(See Details)
Voltage Withstand - Volts, rms, minimum.	(See Details)
Insulation resistance - Megohms/1000 ft., minimum.	100
Group A:	
Visual and dimensional	
Group B:	
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - psi, minimum.	1800
Elongation - Percent, minimum	125
Jacket (cord)	
Tensile strength - psi, minimum.	1800
Elongation - Percent, minimum.	225
Twisting and bending endurance - (Note 1)	
At 75°C., cycles, minimum	6000
At minus 30° ± 2°C., cycles, minimum.	2000

NOTE 1: Roller diameters for bending endurance test shall be as follows:

Cord type and size	Roller diameter (inch, maximum)
DCOP-1	0.75
DCOP-1-1/2	0.95
DCOP-2	1.00
TCOP-2	1.00

Group C:	
Physicals (aged)	
Insulation (conductor)	
Air oven	
Elongation - Percent of unaged, minimum	80
Jacket (cord)	
Hot oil immersion	
Tensile strength - psi, minimum	1400
Elongation - Percent, minimum	50

QUALIFICATION INSPECTION:

Qualification inspection shall include basic electrical plus all of Groups A, B, and C.

UNIT ORDERING LENGTHS:

All sizes 500 feet per coil (nominal).

Custodians:
Army - MI
Navy - SH
Air Force - 80

Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80

User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0648-2)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:04Z
Check the source to verify that this is the current version before use.