MIL-C-915/10B
1 August 1972
SUPERSEDING
MIL-C-00915/10A(SHIPS)
20 March 1972
MIL-C-915/10
15 March 1968

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, 600 VOLTS, TYPE MCSF

(B) This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:
Qualification required.

Construction (Watertight)

First - Two sealed, uncoated bronze conductors (approximately No. 6 AWG) each consisting of 7 x 7/0.023-inch, (0.185-inch min. to 0.224 max. conductor diameter) and two sealed, uncoated bronze conductors (approximately No. 1 AWG) each consisting of 7 x 19/0.025-inch, (0.380-inch min. to 0.400-inch max. conductor diameter).
Second - Tape over each conductor at manufacturer's option.
Third - Synthetic rubber insulation. Nominal wall thickness 0.070 inch for each size. Standard Identification Code, applied by Method 3. One black and one white conductor of each size.
Fourth - Four conductors (one black and one white of each size) cabled together with a lay not greater than 20 inches. All interstices of the core shall be made watertight with rubber filler and a minimum amount of fibrous material. Outer valley filler may be integral with the cable jacket.
Fifth - Reinforcement under cable jacket.
Sixth - Polychloroprene jacket (black), nominal wall thickness, 0.125 inch.
Seventh - Cable surface marking in addition to standard marker tape.

NOTE 1: Weight of finished cable shall not exceed 1625 pounds per 1000 feet.
NOTE 2: Fillers and jacket shall be readily removable from the completed cable without damage to the insulation and without destroying the conductor identification.

Details

Type and size	Conductor stranding	Number of conductors	Overall diameter maximum (inches)
MCSF-4	49/0.023 133/0.025	2 2	1.50

(B) Denotes changes

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:06Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS:

	Requirements
Basic electrical:	
(B) Conductor resistance - Ohms/1000 ft. at 25°C., maximum	0.573 for No. 6 AWG 0.175 for No. 1 AWG
Voltage withstand - Volts, rms, minimum	2500
Insulation resistance - Megohms/1000 ft., minimum	1000
Group A:	
Visual and dimensional	
Watertightness - At 25 psi, cu.in., 6 hours, maximum desired	10.0
NOTE: Leakage of 10.1 to 12.0 cu. in. is acceptable at a 10-percent price reduction; leakage of 12.1 cu. in. or over will be subject to review by the Government for acceptability.	
Group B:	
(B) Cold bending, cable - At minus 30° ± 2°C., two turns around a mandrel with diameter twice that of specimen	No damage
Tension - 12,000 pounds load, minimum	
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - psi, minimum	700
Elongation - Percent, minimum	300
Jacket (cable)	
Tensile strength - psi, minimum	1800
Elongation - Percent, minimum	300
Set - Inch, maximum	3/8
Group C:	
Physicals (aged)	
Insulation (conductor)	
Air pressure heat	
Tensile strength - Percent of unaged, minimum	50
Elongation - Percent of unaged, minimum	50
Oxygen pressure	
Tensile strength - Percent of unaged, minimum	50
Elongation - Percent of unaged, minimum	50
Jacket (cable)	
Oxygen pressure	
Tensile strength - Percent, of unaged, minimum	50
Elongation - Percent of unaged, minimum	50
Hot oil immersion	
Tensile strength - Percent of unaged, minimum	60
Elongation - Percent of unaged, minimum	60
Permanence of printing, cable jacket, cycles, minimum	250

QUALIFICATION INSPECTION

Qualification inspection shall include basic electrical plus all of Groups A, B, and C.

UNIT ORDERING LENGTHS:

1590 feet, minimum to 1650 feet, maximum

(B) Custodians:
Army - MI
Navy - SH
Air Force - 80

(B) Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80

(B) User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0609-7)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:06Z
Check the source to verify that this is the current version before use.