MIL-C-915/10D
18 June 1985
SUPERSEDING
MIL-C-915/10C
4 March 1982

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, 600 VOLTS, TYPE MCSF-4

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the cable described herein shall consist of this document and the latest issue of MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction (watertight)

First - Two conductors AWG no. 6, class G stranding, and two conductors AWG no. 1, class G stranding. Stranding shall be 7 by 7 for the no. 6 and 7 by 19 or 19 by 7 for the no. 1. Strands shall be 0.025-inch nominal diameter drawn copper alloy in accordance with ASTM B 105 alloy 85.

Second - A separator tape over each conductor.

Third - Synthetic rubber insulation, 0.070-inch nominal wall thickness on all conductors. Color code one black and one white conductor of each size.

Fourth - Insulation jacket, of clear polyamide, in accordance with ASTM D 4066. Nominal wall thickness of 0.003 inch.

Fifth - The four conductors (one black and one white of each size) cabled together - maximum length of lay 20 inches. The no. 6 conductors shall be diametrically opposite to each other. Either nonfibrous or a combination of nonfibrous and fibrous fillers may be used to form a firm, well rounded assembly.

Sixth - Binder or combination binder and barrier.

Seventh - Reinforced polychloroprene jacket required. Nominal jacket thickness 0.125 inch. Cable surface marking required.

NOTES:
1. Finished cable diameter shall be 1.5-inch maximum.
2. Weight of finished cable shall not exceed 1625 pounds per 1000 feet.
3. Fillers and jacket shall be removable without damage to conductor insulation.

FSC 6145

DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited

Source: https://assist.dla.mil -- Downloaded: 202610-16T12:06Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS:

	Requirements
Basic electrical:	
Conductor resistance - ohms/1000 feet at 25°C, maximum	
No. 6 AWG (class G) conductor	0.423
No. 1 AWG (class G) conductor	0.134
Voltage withstand - volts, root mean square, minimum	2500
Insulation resistance - megohms/1000 feet, minimum	1000
Conductor to conductor and conductor to water	1000
Group A:	
Visual and dimensional	No failure
Watertightness - leakage at 25 lbf/in^2, in 6 hours, in^3, maximum	10.0
(Leakage between 10.0 and 12.0 in^3 shall be considered acceptable, at a 10-percent price reduction.)	
Group B:	
Cold bending, cable - at minus 30 ± 2°C; two complete turns around a mandrel having a diameter 10 times specimen diameter	No damage
Tension - under load of 12,000 pounds, minimum	No damage
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - lbf/in^2, minimum	700
Elongation - percent, minimum	300
Jacket (cable)	
Tensile strength - lbf/in^2, minimum	1800
Elongation - percent, minimum	300
Set - inch, minimum	3/8
Drip - at 95 ± 1°C	Zero
Group C:	
Physicals (aged)	
Insulation (conductor)	
Air pressure heat	
Tensile strength - percent of unaged, minimum	50
Elongation - percent of unaged, minimum	50
Oxygen pressure	
Tensile strength - percent of unaged, minimum	50
Elongation - percent of unaged, minimum	50
Jacket (cable)	
Oxygen pressure	
Tensile strength - percent of unaged, minimum	50
Elongation - percent of unaged, minimum	50

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:06Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS: (Continued)

	Requirements
Hot oil immersion	
Tensile strength - percent of unaged, minimum	60
Elongation - percent of unaged, minimum	60
Permanence of printing (jacket) - cycles, minimum	250
Cable filler removability	No failure

QUALIFICATION INSPECTION:
Qualification inspection shall include basic electrical, plus all of groups A, B, and C.

UNIT ORDERING LENGTHS:
1590 feet, minimum to 1650 feet, maximum.

Revision letters are not used to denote changes due to the extensiveness of the changes.

NOTE: Not for Air Force use.

Custodians:
Army - MI
Navy - SH

Preparing activity:
Navy - SH
(Project 6145-0885-8)

Review activities:
Army - CR, ER
Navy - EC
DLA - IS

User activities:
Army - AL, AR, ME
Navy - CG

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:06Z
Check the source to verify that this is the current version before use.