MIL-C-915/1C
5 April 1973
SUPERSEDING
MIL-C-915/1B
1 August 1972

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, 600 VOLTS, TYPE CVSF

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:
Qualification required.

Construction

Insulated Conductors (Three)

First - Copper conductor, Navy Standard size 53 (532), uncoated.
Second - Separator.
Third - Synthetic rubber insulation. Minimum wall thickness 0.070 inch. Standard Identification Code, applied by Method 3.

Uninsulated Conductor (One)

First - Copper conductor, Navy Standard size 33 (336), uncoated.

Assembly

First - Three insulated conductors cabled with a lay not greater than 14 inches. The uninsulated conductor shall be placed in one valley. Fibrous fillers shall be used in all valleys as necessary to form a round cable.
Second - Rubber-filled cotton tape binder.
Third - Polychloroprene jacket. Nominal wall thickness 0.125 inch.

Details

Cable type and size	Conductors		Overall Diameter Maximum (inches)
	Number	Size Navy Standard	
CVSF-4	3 1	53 (532) 33 (336)	1.45

(C) Denotes changes

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:04Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS:

	Requirements
Basic Electrical:	
Voltage withstand - Volts, rms, minimum	2500
Insulation resistance - Megohms/1000 ft., minimum	150
Conductor resistance - Ohms/1000 ft. at 25°C. maximum . . . . Size 53	0.217
(C) Size 33	.351
Group A:	
Visual and dimensional	
Group B:	
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - psi, minimum	600
Elongation - Percent, minimum	225
Jacket (cable)	
Tensile strength - psi, minimum	1800
Elongation - Percent, minimum	350
Bending endurance - 4 inch maximum diameter roller, at minus 30° ± 2°C., cycles, minimum.	500
Group C:	
Flammability - Inches, maximum.	2
Physicals (aged)	
Insulation (conductor)	
Air pressure heat	
Tensile strength - Percent of unaged, minimum.	50
Elongation - Percent of unaged, minimum.	50
Oxygen pressure	
Tensile strength - Percent of unaged, minimum.	50
Elongation - Percent of unaged, minimum.	50
Jacket	
Air pressure heat	
Tensile strength - Percent of unaged, minimum	50
Elongation - Percent of unaged, minimum	50
Hot oil immersion	
Tensile strength - Percent of unaged, minimum	60
Elongation - Percent of unaged, minimum	60

QUALIFICATION INSPECTION:
Qualification inspection shall include basic electricals plus all of Groups A, B, and C.

UNIT ORDERING LENGTH: 1000 feet (nominal)

Custodians:
Army - MI
Navy - SH
Air Force - 80
Review Activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80
User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0648-1)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:04Z
Check the source to verify that this is the current version before use.