MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, 600 VOLTS, TYPE CVSF

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the cable described herein shall consist of this document and the latest issue of MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction (non-watertight)

Insulated conductors (three)

First - Copper conductor, AWG size 3, class K stranding, uncoated.
Second - Separator.
Third - Synthetic rubber insulation. Minimum wall thickness 0.070 inch. Standard identification code applied by method 3.

Uninsulated conductor (one)

First - Copper conductor, AWG size 5, class K stranding, uncoated.

Assembly

First - Three insulated conductors cabled with a lay not greater than 14 inches. The uninsulated conductor shall be placed in one valley. Fibrous fillers shall be used in all valleys as necessary to form a round cable.
Second - Rubber filled cotton tape binder.
Third - Polychloroprene jacket. Nominal wall thickness 0.125 inch.

FSC 6145

DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:04Z
Check the source to verify that this is the current version before use.

TABLE I. Details.

Type and size	Conductors		Overall diameter maximum (inches)
	Number	Size AWG	
CVSF-4	3 1	3 (class K) 5 (class K)	1.45

EXAMINATION AND TESTS:

	Requirements
Basic electrical:	
Conductor resistance - ohms/1000 feet at 25°C, maximum	
AWG no. 3	0.215
AWG no. 5	0.339
Voltage withstand - volts, root mean square, minimum....	2500
Insulation resistance - megohms/1000 feet, minimum	
Conductor to conductor and conductor to water.....	150
Group A:	
Visual and dimensional.....	No failure
Group B:	
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - lbf/in^2, minimum.....	600
Elongation - percent, minimum.....	225
Jacket (cable)	
Tensile strength - lbf/in^2, minimum.....	1800
Elongation - percent, minimum.....	350
Bending endurance - 4 inches maximum diameter roller, at minus 30 ± 2°C, cycles, minimum.....	500
Group C:	
Flammability - inches, maximum.....	2
Physicals (aged)	
Insulation (conductor)	
Air pressure heat	
Tensile strength - percent of unaged, minimum.....	50
Elongation - percent of unaged, minimum..	50
Oxygen pressure	
Tensile strength - percent of unaged, minimum.....	50
Elongation - percent of unaged, minimum..	50

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:04Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS: (Continued)

	Requirements
Jacket	
Air pressure heat	
Tensile strength - percent of unaged, minimum.....	50
Elongation - percent of unaged, minimum.....	50
Hot oil immersion	
Tensile strength - percent of unaged, minimum.....	60
Elongation - percent of unaged, minimum.....	60

QUALIFICATION INSPECTION:
Qualification inspection shall include basic electrical, plus all of groups A, B, and C.

UNIT ORDERING LENGTH: 1000 feet (nominal).

Revision letters are not used to denote changes due to the extensiveness of the changes.

Custodians:
Army - MI
Navy - SH
Air Force - 85

Review activities:
Army - CR, ER
Navy - EC
Air Force - 99
DLA - IS

User activities:
Army - AL, AR, ME
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0885-1)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:04Z
Check the source to verify that this is the current version before use.