INCH-POUND

MIL-C-915/1E
29 September 1989
SUPERSEDING
MIL-C-915/1D
18 June 1985

MILITARY SPECIFICATION SHEET

CABLE, POWER ELECTRICAL, 600 VOLTS, FOR OUTBOARD USE ONLY (NOT FOR INBOARD USE), TYPE CVSF

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of the following specification listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation: MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction (non-watertight)

Insulated conductors (three)

First - Copper conductor, AWG size 3, class K stranding, uncoated.
Second - Separator.
Third - Synthetic rubber insulation. Minimum wall thickness 0.070 inch. Standard identification code applied by method 3.

Uninsulated conductor (one)

First - Copper conductor, AWG size 5, class K stranding, uncoated.

AMSC N/A FSC 6145
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-16T12:04Z
Check the source to verify that this is the current version before use.

Assembly

First - Three insulated conductors cabled with a lay not greater than 14 inches. The uninsulated conductor shall be placed in one valley. Fibrous fillers shall be used in all valleys as necessary to form a round cable.
Second - Rubber filled cotton tape binder.
Third - Polychloroprene jacket. Nominal wall thickness 0.125 inch.

TABLE I. Details.

Type and size	Conductors		Overall diameter maximum (inches)
	Number	Size AWG	
CVSF-4	3 1	3 (class K) 5 (class K)	1.45

EXAMINATION AND TESTS:

	Requirements
Basic electrical:	
Conductor resistance - ohms/1000 feet at 25°C, maximum	
AWG no. 3	0.215
AWG no. 5	0.339
Voltage withstand - volts, root mean square, minimum	2500
Insulation resistance - megohms/1000 feet, minimum	
Conductor to conductor and conductor to water	150
Group A:	
Visual and dimensional	No failure
Group B:	
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - lbf/in², minimum	600
Elongation - percent, minimum	225
Jacket (cable)	
Tensile strength - lbf/in², minimum	1800
Elongation - percent, minimum	350
Bending endurance - 4 inches maximum diameter roller, at minus 30 ± 2°C, cycles, minimum	500
Group C:	
Flammability - inches, maximum	2
Physicals (aged)	
Insulation (conductor)	

Source: https://assist.dla.mil -- Downloaded: 202610-16T12:04Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS - Continued

	Requirements
Air pressure heat	
Tensile strength - percent of unaged, minimum	50
Elongation - percent of unaged, minimum	50
Oxygen pressure	
Tensile strength - percent of unaged, minimum	50
Elongation - percent of unaged, minimum	50
Jacket	
Air pressure heat	
Tensile strength - percent of unaged, minimum	50
Elongation - percent of unaged, minimum	50
Hot oil immersion	
Tensile strength - percent of unaged, minimum	60
Elongation - percent of unaged, minimum	60

QUALIFICATION INSPECTION:

Qualification inspection shall include basic electrical, plus all of groups A, B, and C.

UNIT ORDERING LENGTH: 1000 feet (nominal).

NOTE: Not for Air Force use.

Revision letters are not used to denote changes due to the extensiveness of the changes.

Custodians:
Army - MI
Navy - SH

Preparing activity:
Navy - SH
(Project 6145-1127-01)

Review activities:
Army - CR, ER
Navy - EC
DLA - IS

User activities:
Army - AL, AR, ME
Navy - CG

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:04Z
Check the source to verify that this is the current version before use.