INCH-POUND
MIL-DTL-915/1F
22 August 2002
SUPERSEDING
MIL-C-915/1E
29 September 1989

DETAIL SPECIFICATION SHEET

CABLE, POWER ELECTRICAL, 600 VOLTS, FOR OUTBOARD USE ONLY (NOT FOR INBOARD USE), TYPE CVSF

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of MIL-DTL-915 listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation.

REQUIREMENTS:

Qualification required.

Construction (non-watertight)

Insulated conductors (three)

First - Copper conductor, AWG size 3, class K stranding, uncoated.
Second - Separator.
Third - Synthetic rubber insulation. Minimum wall thickness 0.070 inch. Standard identification code applied by method 3.

Uninsulated conductor (one)

First - Copper conductor, AWG size 5, class K stranding, uncoated.

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:04Z
Check the source to verify that this is the current version before use.

Assembly

First - Three insulated conductors cabled with a lay not greater than l4 inches. The uninsulated conductor shall be placed in one valley. Fibrous fillers shall be used in all valleys as necessary to form a round cable.
Second - Rubber filled cotton tape binder.
Third - Polychloroprene jacket. Nominal wall thickness 0.125 inch.

TABLE I. Details.

Type and size	Conductors		Overall diameter maximum (inches)
	Number	AWG Size	
CVSF-4	3 1	3 (class K) 5 (class K)	1.45

EXAMINATION AND TESTS:

Requirements

Basic electrical:

Conductor resistance - ohms/1000 feet at 25°C, maximum
AWG No. 3 ..... 0.215
AWG No. 5 ..... 0.339
Voltage withstand - volts, root mean square, ... 2500
Insulation resistance – megohms-1000 feet, minimum
Conductor to conductor and conductor to water 150

Group A:
Visual and dimensional ..... No failure

Group B:
Physicals (unaged)
Insulation (conductor)
Tensile strength - lbf/in^2, minimum 600
Elongation - percent, minimum 225
Jacket (cable)
Tensile strength - lbf/in^2, minimum 1800
Elongation - percent, minimum 350
Bending endurance - 4 inches maximum diameter roller, at minus 30 ± 2°C, cycles, minimum 500

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:04Z
Check the source to verify that this is the current version before use.

Group C:
Flammability - inches, maximum 2
Physicals (aged)
Insulation (conductor)
Air pressure heat
Tensile strength - percent of unaged, minimum..... 50
Elongation- percent of unaged, minimum..... 50
Jacket
Air pressure heat
Tensile strength - percent of unaged, minimum..... 50
Elongation - percent of unaged, minimum..... 50
Hot oil immersion
Tensile strength - percent of unaged, minimum..... 60
Elongation- percent of unaged, minimum..... 60

QUALIFICATION INSPECTION:

Qualification inspection shall include basic electrical, plus all of groups A, B, and C.

UNIT ORDERING LENGTH:
1000 feet (nominal).

PART OR IDENTIFYING NUMBER (PIN): The PIN consists of the letter M, the general specification number along with the specification sheet, and a dash number representing type and size. Refer to MIL-DTL-915 for an example.

PART OR IDENTIFYING NUMBER (PIN): The PIN consists of the letter M, the general specification number along with the specification sheet, and a dash number representing type and size. Refer to MIL-DTL-915 for an example.

M	**915**	**/1-**	**X-X**
Prefix for Military Specification	Specification Number	Specification Sheet Number	Type and Size

CHANGES FROM PREVIOUS ISSUE: Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Custodians:
Army – MI
Navy – SH

Preparing activity:
Navy - SH
(Project 6145-2317-001)

Review activities:
Army – AR, CR
Navy - CG, EC
DLA - CC

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:04Z
Check the source to verify that this is the current version before use.