INCH-POUND

MIL-C-915/6J
29 September 1989
SUPERSEDING
MIL-C-915/6H
3 October 1986

MILITARY SPECIFICATION SHEET

CABLE, POWER ELECTRICAL, 600 VOLTS, FOR OUTBOARD USE ONLY
(NOT FOR INBOARD USE), TYPE THOF

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of the following specification listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation: MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction (non-watertight)

First - Copper, conductor, uncoated, (see table I for size).
Second - Separator.
Third - Ethylene propylene rubber insulation, (see table I for wall thickness). Standard identification code applied by method 3 or 4. A colored rubber filled cotton tape may be used.
Fourth - Three conductors cabled together with a left-hand lay (see table I for length of lay). Fibrous fillers shall be employed to obtain a firm, well rounded assembly.
Fifth - Binder tape applied helically with overlap on multi-conductor cables.
Sixth - Jacket of polychloroprene. Jacket shall be black. Cable surface marking required.

Note: For types SHOF, DHOF, FHOF, and THOF sizes not listed refer to MIL-C-24643/3.

AMSC N/A FSC 6145
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:05Z
Check the source to verify that this is the current version before use.

TABLE I. Details.

Type and size	Conductor size		Insulation thickness nominal (inch)	Lay of conductor max (inches)
	Navy standard	AWG		
THOF-400	400(2052)		.090	30
THOF-500		500MCM (class K)	.090	33

Type and size	Overall diameter		Conductor resistance per 1000 feet (max) (ohms)	Insulation resistance per 1000 feet (min) (megohms)
	min (inches	max (inches)		
THOF-400	2.680	2.800	.0283	100
THOF-500	2.920	3.100	.0230	100

EXAMINATION AND TESTS:

Requirements

Basic electrical:

Conductor resistance - ohms/1000 feet at 25°C, maximum. (see table I)
Voltage withstand - volts, root mean square, minimum... (2500)
Insulation resistance - megohms/1000 feet, minimum
Conductor to conductor..... (see table I)
Conductor to water..... (see table I)

Group A:

Visual and dimensional..... No failure

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:05Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS - Continued

	Requirements
Group B:	
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - lbf/in^2, minimum	700
Elongation - percent, minimum	250
Jacket (cable)	
Polychloroprene:	
Tensile strength - lbf/in^2	1800
Elongation - percent, minimum	300
Set - inch, maximum	3/8
Group C:	
Flammability - inches, maximum	2
Physicals (aged)	
Insulation (conductor)	
Air oven	
Tensile strength - percent of unaged, minimum	75
Elongation - percent of unaged, minimum	75
Jacket (cable) (polychloroprene)	
Air pressure heat	
Tensile strength - percent of unaged, minimum	50
Elongation - percent of unaged, minimum	50
Hot oil immersion	
Tensile strength - percent of unaged, minimum	60
Elongation - percent of unaged, minimum	60
Permanence of printing (jacket) - cycles, minimum	250

QUALIFICATION INSPECTION:

Qualification inspection shall include basic electrical, all of groups A, B, and C.

UNIT ORDERING LENGTHS:

Type	Size	Feet (nominal)
THOF	400 and 500	500

NOTE: Not for Air Force use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:05Z
Check the source to verify that this is the current version before use.

Revision letters are not used to denote changes due to the extensiveness of the changes.

Custodians:
Army - MI
Navy - SH

Preparing activity:
Navy - SH
(Project 6145-1127-03)

Review activities:
Army - CR, ER
Navy - EC
DLA - IS

User activities:
Army - AL, AR, ME
Navy - CG

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:05Z
Check the source to verify that this is the current version before use.