MIL-C-915/7E
18 June 1985
SUPERSEDING
MIL-C-915/7D
5 April 1973

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, TYPE DSWS

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the cable described herein shall consist of this document and the latest issue of MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction (watertight)

First - Copper conductor, AWG size 14, class B stranding, tin coated.
Second - Synthetic rubber insulation. Nominal wall thickness 0.073 inch. Standard identification code applied by method 3. An additional covering of clear polyamide may be employed at the manufacturer's option.
Third - Two conductors shall be cabled together with a lay not greater than 5 inches. Fillers of synthetic rubber-like compound shall be used to attain a firm, well rounded cross section. Fillers may be laid in the valleys during the cabling operation or may be extruded into the valleys separately. Fillers shall be readily separable from the insulation without damage thereto and without destroying the conductor identification.
Fourth - Binder tape over the conductor assembly, at manufacturer's option.
Fifth - Shielding braid of AWG no. 34, tin coated copper, with an angle of 30 to 40 degrees and minimum coverage of 88 percent.
Sixth - An overall jacket (black), nominal wall thickness 0.060 inch. If needed to meet electrical tests, the jacket may comprise an inner layer of rubber insulation, such as synthetic rubber and an outer layer of rubber insulation, such as synthetic rubber and an outer layer of polychloroprene. The jacket shall be readily separable from the underlying shield, leaving the shield adequately clean for soldering. Cable surface marking required.

FSC 6145

DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:05Z
Check the source to verify that this is the current version before use.

TABLE I. Details.

Type and size	Overall diameter	
	minimum (inch)	maximum (inch)
DSWS-4	0.770	0.800

EXAMINATION AND TESTS:

	Requirements
Basic electrical:	
Conductor resistance - ohms/1000 feet at 25°C, maximum..	2.78
Voltage withstand - volts, root mean square, minimum	
Conductor to conductor (5 minutes).....	10,000
Conductor to shield (5 minutes).....	10,000
Shield to water (5 minutes).....	500
Voltage withstand - volts, dc, minimum	
Conductor to conductor (15 minutes).....	25,000
Conductor to shield (15 minutes).....	25,000
Shield to water (15 minutes).....	1,500
Insulation resistance - megohms/1000 feet, minimum.....	100
Conductor to conductor.....	200
Conductor to shield.....	200
Shield to water.....	100
Group A:	
Visual and dimensional.....	No failure
Hydrostatic (open end) - 1000 lbf/in^2, in 2 hours, in^3, maximum.....	0
Mutual capacitance - picofarad per feet (pF/ft) at 1 kilohertz (kHz).....	40 ± 10
Group B:	
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - lbf/in^2, minimum.....	600
Elongation - percent, minimum.....	350
Jacket (cable)	
Tensile strength - lbf/in^2, minimum.....	1,800
Elongation - percent, minimum.....	300
Set - inch, maximum.....	3/8
Drip - at 95 ± 1°C.....	Zero
Group C:	
Physical (aged)	
Insulation (conductor)	
Air pressure heat	
Tensile strength - percent of unaged, minimum.....	70
Elongation - percent of unaged, minimum..	75

Source: https://assist.dla.mil -- Downloaded: 202610-16T12:05Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS: (Continued)

	Requirements
Jacket (cable)	
Air pressure heat	
Tensile strength - percent of unaged, minimum	50
Elongation - percent of unaged, minimum	50
Hot oil immersion	
Tensile strength - percent of unaged, minimum	60
Elongation - percent of unaged, minimum	60
Permanence of printing (jacket) cycles, minimum	250
Cable filler removability	No failure
Shield - conformance to material, coverage and construction	No failure

QUALIFICATION INSPECTION:

Qualification inspection shall include basic electrical, all of groups A, B, and C, plus the following:

Insulation resistance per 1000 feet at room temperature from shield to water, 50 megohms, minimum after 90 days continuous submergence in water; values recorded at 1-week intervals.

Flexing endurance - 1000 cycles of bending a specimen, 4-inch maximum diameter mandrel at minus 40 $\pm$ 2°C. Upon successful completion of this test, specimen shall meet the voltage withstand test and the hydrostatic (open end) test.

UNIT ORDERING LENGTH: 500 feet (nominal).

NOTE: Not for Air Force use.

Revision letters are not used to denote changes due to the extensiveness of the changes.

Custodians:
Army - MI
Navy - SH

Preparing activity:
Navy - SH
(Project 6145-0885-5)

Review activities:
Army - CR, ER
Navy - EC
DLA - IS

User activities:
Army - AL, AR, ME
Navy - CG

Source: https://assist.dla.mil -- Downloaded: 202640-16T12:05Z
Check the source to verify that this is the current version before use.