INCH-POUND

MIL-C-915/8G
29 September 1989
SUPERSEDING
MIL-C-915/8F
18 June 1985

MILITARY SPECIFICATION SHEET

CABLE, POWER ELECTRICAL, 600 VOLTS, FOR OUTBOARD USE ONLY (NOT FOR INBOARD USE), TYPES DSS, TSS, FSS AND 7SS

This specification sheet is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of the following specification listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation: MIL-C-915.

REQUIREMENTS:

Qualification required.

Construction (watertight)

First - Copper conductor, class B stranding, tin coated. (See table I for size.)
Second - Synthetic rubber insulation. (See table I for thickness.) Special identification code applied by method 3.
Third - The required number of conductors (see table I) cabled together with a lay length not greater than that specified in table I. The insulated conductors shall not adhere to one another. Rubber fillers as necessary in order to form a firm, round assembly. Fillers in outer valleys may be extruded in order to be integral with the belt (see fourth).
Fourth - Belt of synthetic rubber, nominal wall thickness 0.030 inch, over the assembled conductors. Belt and fillers shall be capable of removal from the assembly without damaging the insulation on conductors.
Fifth - Braided shield of AWG no. 34 tin-coated copper. Braid angle of 50-degrees minimum; coverage of 90-percent minimum.

AMSC N/A FSC 6145
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-16T12:05Z
Check the source to verify that this is the current version before use.

REQUIREMENTS - Continued

Sixth - Jacket of either polychloroprene of chlorosulfonated polyethylene, black. (See table I for thickness.) If necessary in order to meet the electrical requirements for the completed cable, the jacket may consist of two layers bonded together, with the inner layer consisting of synthetic rubber insulation. Cable surface marking required.

NOTE: Manufacturer's identification tape may be omitted, at the manufacturer's option, from all types and sizes.

TABLE I. Details.

Type and size	Conductors		Insulation 1/ thickness minimum (inch)	Lay length (inch)	Jacket 1/ thickness minimum (inch)	Overall diameter		Conductor resistance per 1000 feet (max) (ohms)
	Number	Size AWG				min (inch)	max (inch)	
DSS-2	2	18(class B)	0.020	2.0	0.050	0.370	0.390	7.36
DSS-3	2	16(class B)	.025	2.0	.080	.480	.500	4.61
DSS-4	2	14(class B)	.025	2.5	.065	.480	.500	2.8
TSS-2	3	18(class B)	.020	2.0	.050	.385	.400	7.3
TSS-3	3	16(class B)	.025	2.5	.070	.480	.500	4.61
TSS-4	3	14(class B)	.025	2.5	.055	.480	.500	2.84
FSS-2	4	18(class B)	.020	2.5	.080	.480	.500	7.3
FSS-3	4	16(class B)	.025	2.5	.060	.480	.500	4.61
FSS-4	4	14(class B)	.025	3.0	.085	.600	.625	2.84
7SS-2	7	18(class B)	.020	3.0	.085	.600	.625	7.36

1/ Because of the compact construction necessary in order for these cables to meet the required hydrostatic tests, centering and circularity requirements for insulation and jacket are waived, provided that the finished cable complies with the value specified in table I for minimum thickness of insulation and jacket and for overall cable diameter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:05Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS:

	Requirements
Basic electrical:	
Conductor resistance - ohms/1000 feet at 25°C, maximum.	(see table I)
Voltage withstand - volts, root mean square, minimum	
Conductor to conductor (5 minutes).....	3000
Conductor to shield (5 minutes).....	1000
Shield to water (5 minutes).....	500
Insulation resistance - megohms/1000 feet, minimum	
Conductor to conductor.....	500
Conductor to shield.....	500
Shield to water.....	250
Group A:	
Visual and dimensional.....	No failure
Hydrostatic (open end) - 500 lbf/in^2, in 2 hours, in^3, maximum.....	0
Conductor capacitance (type DSS only) - pF/ft at 1 kHz maximum..... (measurement shall be made with black conductor connected to shield at one end of specimen)	45
Drip - at 95 ± 1°C.....	Zero
Group B:	
Bending endurance - at minus 40 ± 2°C on 4-inch maximum diameter mandrel, cycles, minimum.....	1000
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - lbf/in^2 minimum.....	600
Elongation - percent, minimum.....	300
Jacket (cable)	
Tensile strength - lbf/in^2 minimum.....	1800
Elongation - percent, minimum.....	300
Set - inch, maximum.....	3/8
Group C:	
Physicals (aged)	
Insulation (conductor)	
Air pressure heat	
Tensile strength - percent of unaged, minimum.....	65
Elongation - percent of unaged, minimum.	65
Jacket	
Hot oil immersion	
Tensile strength - percent of unaged, minimum.....	65
Elongation - percent of unaged, minimum.	65

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:05Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS - Continued

	Requirements
Permanence of printing (jacket) - cycles, minimum.....	250
Cable filler removability.....	No failure
Shield - conformance to material coverage and construction.....	No failure

QUALIFICATION INSPECTION:

Qualification inspection shall include basic electrical, all of groups A, B, and C, plus the following:

Hydrostatic (open end), after bending endurance - at 500 lbf/in², in 2 hours, in³, maximum.....	0
Pressure cycling (DSS-3 only) - at 500 lbf/in² percent of variation in mutual capacitance, maximum.....	10
Insulation resistance (after 90-day immersion in tap water) - megohms/1000 feet, minimum	
Conductor to conductor.....	500
Conductor to shield.....	500
Shield to water.....	250

UNIT ORDERING LENGTH:

All types and sizes: 500 feet (nominal).

NOTE: Not for Air Force use.

Revision letters are not used to denote changes due to the extensiveness of the changes.

Custodians:
Army - MI
Navy - SH

Preparing activity:
Navy - SH
(Project 6145-1127-05)

Review activities:
Army - CR, ER
Navy - EC
DLA - IS

User activities:
Army - AL, AR, ME
Navy - CG

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:05Z
Check the source to verify that this is the current version before use.