MIL-C-915/9C
1 August 1972
SUPERSEDING
MIL-C-00915/9B(SHIPS)
20 March 1972
MIL-C-915/9A
25 September 1968

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, 600 VOLTS, TYPE JAS

Ⓒ This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of Specification MIL-C-915.

REQUIREMENTS:
Qualification required.

Construction

Conductor Size 250 (Two required)

First - Copper conductor, Navy standard size 250(6384), uncoated.
Second - Separator.
Third - Synthetic rubber insulation. Nominal wall thickness 0.070 inch. Standard Identification Code, applied by Method 3, if not accomplished under fourth.
Fourth - Tape or braid at manufacturer's option. Standard Identification Code, applied by the tape or braid if not accomplished under third.

Conductor Size 6 (Two required)

First - Copper conductor Navy standard size 6(65), uncoated.
Second - Separator.
Third - Synthetic rubber insulation. Nominal wall thickness 0.031 inch.
Fourth - Marker braid. Standard Identification Code, applied by Method 4.
Fifth - Two conductors cabled with 3.5 to 4.24-inch lay. Fillers shall be used to form a round assembly.

Assembly

First - Two conductors, size 250, laid parallel with the pair of size 6 laid between them. Fillers of synthetic elastomer or polychloroprene shall be used to fill all spaces and to hold the pair well centered. At manufacturer's option, fillers may be integral with the jacket.
Second - Nylon reinforcement over the assembly.
Third - Polychloroprene jacket (black). Nominal wall thickness 0.156 inch.
Fourth - Cable surface marking in addition to standard marker tape.

NOTE 1: Fillers and jacket shall be readily removable from the completed cable without damage to the insulation on the conductors.
NOTE 2: When the insulation on size 250 is applied as a "D" shaped section, the centering and circularity requirements shall not apply.

Ⓒ

Details

Type and size	Conductors			Overall diameter oval shape maximum (inches)
	Size Navy Standard	Number	Diameter nominal (inch)	
JAS-250	6(65)	2	0.097	1.260 Minor and 2.480 Major
	250(6384)	2	0.713	

Ⓒ Denotes changes

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:06Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS:

	Requirements
Basic electrical:	
Conductor resistance - Ohms/1000 ft. at 25°C., maximum	
Size 6(65)	1.72
Size 250(6384)	0.0461
Voltage withstand - Volts, rms, minimum	2000
Insulation resistance - Megohms/1000 ft., minimum	
Conductor size 6(65)	200
Conductor size 250(6384)	100
Group A:	
Visual and dimensional	
(C) Bending endurance - At 25°C., (performed on one specimen from each lot); 14-inch maximum diameter mandrel, flatwise, cyles, minimum	100,000
Group B:	
Physicals (unaged)	
Insulation (conductor)	
Tensile strength - psi, minimum	600
Elongation - Percent, minimum	300
Jacket (cable)	
Tensile strength - psi, minimum	1800
Elongation - Percent, minimum	300
Group C:	
Flammability - inches, maximum	2
Physicals (aged)	
Insulation (conductor)	
Air pressure heat	
Tensile strength - Percent of unaged, minimum	50
Elongation - Percent of unaged, minimum	50
Jacket (cable)	
Air pressure heat	
Tensile strength - Percent of unaged, minimum	50
Elongation - Percent of unaged, minimum	50
Hot oil immersion	
Tensile strength - Percent of unaged, minimum	60
Elongation - Percent of unaged, minimum	60
Permanence of printing (jacket) - cycles, minimum	250

QUALIFICATION INSPECTION
Qualification inspection shall include basic electrical plus all of Groups A, B and C.

UNIT ORDERING LENGTHS:
500 feet (Nominal)

(C) Custodians:
Army - MI
Navy - SH
Air Force - 80
(C) Review activities:
Army - EL, MI, AV
Navy - EC
Air Force - 80
(C) User activities:
Army - ME, MU, WC
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-0609-6)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T12:06Z
Check the source to verify that this is the current version before use.