[Metric]
A-A-2958
December 19, 1995

COMMERCIAL ITEM DESCRIPTION
FILM, COPYING, XEROGRAPHIC PROCESS
(TRANSPARENT)

This General Services Administration has authorized the use of this commercial item description by all federal agencies.

1. Scope: This commercial item description covers dry-toner plain paper copier transparency film that uses the xerographic process.

2. Classification:

Type: I. Film Without Sensing Strip
II. Film With Sensing Strip

3. Salient Characteristics:

3.1 The film shall be constructed of (4 mil ± 0.4 mil per ASTM D-374) polyester with both sides coated and suitable for use with the xerographic copying process.

3.2 The film shall be 215.9 mm (8 1/2 inches) by 279.4 mm (11 inches) long and shall provide trouble free feeding.

3.3 The film shall accept markings from felt tip transparency markers without beading or smearing. The toner shall adhere well and not scuff off during normal use.

3.4 Type II film shall have a removable 14.3 mm ± 1.6 mm (9/16 inch ± 1/16 inch) wide tape, flush along one long edge.

3.5 The film shall be provided in the following colors: Clear (with sensing strip), Clear (without sensing strip), and an assortment of Red, Blue, Green, and Yellow which shall be packaged as specified in the ordering information section paragraph 8.2.,and or contract.

3.6 Feed Reliability. Finished sheets shall be capable of feeding through a copy machine (adjusted to factory specifications) without feeding more than one sheet at a time or shutting the machine down.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to General Services Administration, Federal Supply Service, Engineering Branch, 26 Federal Plaza, New York, NY 10278.

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:27Z
Check the source to verify that this is the current version before use.

3.7 Workmanship. The film shall have no creases, scratches, blemishes, foreign substances, or other visible imperfections that may affect the appearance, durability, serviceability or which may present a hazard to the user.

4. Regulatory Requirements:

The offerer/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

5. Quality Assurance Requirements:

5.1 Contractor Certification. The contractor shall certify and maintain substantiating evidence that the product offered meets the salient characteristics of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices. The government reserves the right to require proof of such conformance prior to first delivery and therefore as may be otherwise provided for under the provisions of the contract.

5.2 Examination and Testing.

5.2.1 Suppliers are encouraged to use quality control (QC) techniques that exhibit control over their processes (e.g. (Statistical Process Control) SPC Techniques) as defined in American National Standards Institute (ANSI) Z1.1, Z1.2 and Z1.3 / American Society for Quality Control (ASQC) B.1, B.2 and B.3 that systematically reduce excess variations. If used, objective evidence shall be available that demonstrates overall measurement adequacy techniques and controls. These techniques shall ensure quality levels equal to, or greater than, those cited in applicable technical document or, herein.

5.2.2 End item inspection / testing may be used by the offerer or the Government representative, as a means to determine the effectiveness of the in process quality controls. In process controls shall not be substituted for end item performance testing.

5.2.3 For those characteristics for which there are no such controls, or for end item performance test, lot by lot sampling for inspection / test shall be required. The sample unit shall be one film. Sampling shall be in accordance with the American National Standards Institute (ANSI) / American Society for Quality Control (ASQC) Z1.4, Sampling Procedures and Tables for Inspection by Attributes.

5.2.4 An inspection lot shall consist of all like items submitted for inspection at one time. The inspection level for visual and dimensional defects shall be S-3 with an AQL of 4.0 percent defective. The inspection level for performance tests shall be S-2 with an AQL of 4.0 percent defective. The supplier must provide objective evidence (tests and inspection records) that the presented material meets the requirements of the sampling plan as indicated above

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:27Z
Check the source to verify that this is the current version before use.

6. **Performance Tests:** Unless otherwise specified, the tests shall be conducted in accordance with table I. below and in an atmosphere of 23° ± 2° C (73.4 ± 3.6° F) and at a relative humidity of 50% ± 5%.

TABLE I

Tests:	
Dimensional Stability:	1.0% maximum shrinkage after 15 min. at 150 C
Haze:	7% max. as per ASTM D1003
Static Coefficient of Friction:	0.31 ± 0.11 as per ASTM D1894
Surface Smoothness (Bekk Method):	1500 sec. max. per. as per TAPPI T479
Surface Resistivity (log 10):	10.3 to 12.7 at 500 volts as per ASTM D4949
Dimensions:	
Thickness:	As per ASTM D374
Length:	279.4 mm (11 inches) ± 1.6 mm (1/16 inch)
Width:	215.9 mm (8 1/2 inches) ± 1.6 mm (1/16 inch)
Squareness:	± 1.6 mm (1/16 inch) along the long side
Width of Sensor Strip:	14.9 mm (9/16 inch) ± 1.6 mm (1/16 inch)

7. **Packaging:** Preservation, packing, and marking shall be specified in the contract or order.

8. **Notes:**

8.1 Applicable Documents. Issues of the following documents, in effect on the date of invitation for bids or request for proposal form a part of this document to the extent specified herein.

8.1.1 Federal Acquisition Regulation (FAR) may be obtained from the Superintendent of Documents, Government Printing Office, Washington. DC 20402.

8.1.2 Application for copies of (ANSI) Z1.1, Z1.2 and Z1.3 and (ASQC) B.1, B.2 and B.3 may be obtained from the American Society for Quality Control, PO Box 3005, 611 E. Wisconsin Avenue, Milwaukee, WI 53201-4606.

8.1.3 Federal Standards and Specifications may be obtained from the General Services Administration Specifications Section (3FBO-W) in Suite 8100 at 490 L'Enfant Plaza, SW Washington DC 20407

8.1.4 American Standards for Testing Methods may be obtained at 1916 Race Street, Philadelphia, PA 19103

8.1.5 Technical Association of the Pulp and Paper Industry (TAPPI). may be obtained from TAPPI, Technology Park / Atlanta, PO Box 105113, Atlanta, Georgia, 30348-5113

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:27Z
Check the source to verify that this is the current version before use.

8.2 Ordering Information. Purchaser should select the required options permitted herein, and include the following information in procurement documents.

A. Title, number, and date of this commercial item description.
B. Purchasers shall specify the type of transparency required.
C. Purchasers shall specify arrangement for inspection and inspection facilities, if other than specified.
D. Purchasers shall specify packaging, packing, and any special marking for shipment, if other than required
E. Purchasers shall specify identification marking, if other than required.
F. Purchasers shall specify if bar code marking is not required.
G. Purchasers should specify palletization, if required.

8.3 National Stock Number Listing.

7530-01-386-2356
7530-01-386-2371
7530-01-386-2376

MILITARY INTERESTS:
NONE: DoD has determined that no military activity has an interest in this CID.

PREPARING ACTIVITY
GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:27Z
Check the source to verify that this is the current version before use.