MIL-O-60371A (AR)
7 March 1986
SUPERSEDING
MIL-O-60371 (MU)
29 June 1966

MILITARY SPECIFICATION

OXAMIDE EXPLOSIVE COMPOSITION

This Specification is approved for use within the US Army Armament, Munition and Chemical Command and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers a high explosive composition designated as Oxamide Explosive intended for use in a bursting charge.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. Unless otherwise specified, the following specifications and standards of the issue listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation form a part of this specification to the extent specified herein.

SPECIFICATIONS

MILITARY

MIL-T-248	-	Trinitrotoluene (TNT)
MIL-R-398	-	RDX
MIL-C-401	-	Composition B
MIL-W-20553	-	Wax, Desensitizing
MIL-O-60863	-	Oxamide

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, US Army Armament Research and Development Center, Attn: AMSMC-QA, Dover, New Jersey 07801-5001 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 1376

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:33Z
Check the source to verify that this is the current version before use.

STANDARDS

MILITARY

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-109	-	Quality Assurance Terms and Definitions
MIL-STD-650	-	Explosives: Sampling, Inspection and Testing
MIL-STD-1168	-	Lot Numbering of Ammunition
MIL-STD-1171	-	Acceptable and Description Sheets (for propellants and explosives)
MIL-STD-1218	-	ACS Chemicals
MIL-STD-1235	-	Single and Multilevel Continuous Sampling Procedures and Tables for Inspection by Attributes

2.1.2 Other government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein. Unless otherwise specified, the issues shall be those in effect on the date of the solicitation.

DRAWINGS

US ARMY ARMAMENT RESEARCH AND DEVELOPMENT CENTER (ARDC)

7548644	-	Box, Packing for High Explosives, Assembly, Details, Packing and Marking
7548645	-	Box, Fiberboard, Packing, Reusable, Collapsible for High Explosives
9257923	-	Box, Fiberboard, Packing, Reusable, Collapsible, for High Explosives, Single Piece

PUBLICATIONS

CODE OF FEDERAL REGULATIONS

49 CFR 100-199	-	Department of Transportation Rules and Regulations for the Transportation of Explosives and Other Dangerous Articles

(The Interstate Commerce Commission Regulations are now a part of the Code of Federal Regulations, available from the Superintendent of documents, US Government Printing Office, Washington, DC 20402.)

(Copies of specifications, standards, drawings and publications, required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:33Z
Check the source to verify that this is the current version before use.

2.2 Other publications. The following other publications form a part of this specification to the extent specified herein. The issue of the documents which are indicated as DoD adopted shall be the issue listed in the current DoDISS and the supplement thereto, if applicable.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM Designation E300	-	Recommended Practice for Sampling Industrial Chemicals
ASTM D2905	-	Statement of Number of Specimens Required to Determine the Average Quality of a Textile Material

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA. 19103.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence.

3. REQUIREMENTS

3.1 Material.

3.1.1 Made with composition B. The Oxamide Explosive composition shall be made with Composition B in accordance with Table I.

TABLE I Oxamide explosive composition (with comp B)

MATERIAL	PERCENT	SPECIFICATIONS
Composition B	83.3 ± 2.0	MIL-C-401 Type II
TNT	6.7 ± 0.5	MIL-T-248 Type I
Oxamide	10.0 ± 0.5	MIL-O-60863 Type I

3.1.2 Made with RDX. The Oxamide explosive composition shall be made with RDX in accordance with Table II.

TABLE II Oxamide explosive composition (with RDX)

MATERIAL	PERCENT	SPECIFICATIONS
RDX	49.5 ± 2.0	MIL-R-398 Type I or II Class I
TNT	39.6 ± 2.0	MIL-T-248 Type I
Oxamide	10.0 ± 0.5	MIL-O-60863 Type I
Wax, Desensitizing	0.9 ± 0.5	MIL-W-20553

3.2 Physical and chemical properties. Oxamide Explosive shall conform to the requirements specified in Table III when tested by the applicable test methods.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:33Z
Check the source to verify that this is the current version before use.

TABLE III Applicable test method composition

PROPERTY	REQUIREMENT	TEST PARAGRAPH
Composition		
RDX, percent	49.5 ± 2.0	4.6.3
TNT, percent	39.6 ± 2.0	4.6.1
Oxamide, percent	10.0 ± 0.5	4.6.2
Wax, percent	0.9 ± 0.5	4.6.2
Moisture, percent, max.	0.25	4.6.4
Viscosity, efflux, seconds, max.	1/	4.6.5

1/ To be determined. Report for informational purposes only.

3.3 Data requirements. Description sheets for each lot of Oxamide explosive tested shall be provided to the technical agency in accordance with 4.5.3.2.

3.4 First article inspection. This specification contains technical provisions for first article inspection. Requirements for the submission of first article samples by the contractor shall be as specified in the contract (see 4.5).

3.5 Workmanship. The manufacturer shall use procedures and controls which assure that the Composition B produced does not contain foreign material such as dirt, rust, paint or metal chips, etc., and that the safety and reliability of the explosive are not compromised. Compliance with this requirement shall be as specified in 4.6.6.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection and standard quality assurance provisions. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspections specified herein. Except as otherwise specified in the contract or purchase order, the supplier may use his own or any other facilities suitable for the performance of the inspections specified herein, unless disapproved by the government. The government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to the prescribed requirements. Reference shall be made to MIL-STD-109 to define terms used herein.

4.2 Process control data. A Process Control Document shall be submitted to the Technical Agency AMSMC-QAR-R (D) in accordance with Data Item Description, DI-P-10392. The document shall contain a description of the process, all materials used, process conditions/procedures and production/inspection equipment used to

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:33Z
Check the source to verify that this is the current version before use.

produce Oxamide Explosive meeting the requirements of this specification (see 6.2.2). In addition, whenever there is a change (change in source of materials, process conditions, procedures, etc.) from previously reported process control data, the Technical Agency shall be notified of the new process control data and the reason for the change.

4.3 Classification of inspections. The following types of inspections shall be conducted on this item:

a. First article inspection (see 4.4).

b. Quality conformance inspection (see 4.5).

4.4 First article inspection.

4.4.1 Submission. The contractor shall submit a first article sample as designated by the contracting officer for evaluation in accordance with provisions of 4.4.2. The first article sample shall be ten (10) pounds of Oxamide explosive. The sample shall be obtained from the first production lot which has been produced by the contractor using the same production processes, procedures and equipment as will be used in fulfilling the contract. All materials shall be obtained from the same sources of supply as will be used in regular production.

4.4.2 Inspections to be performed. The sample may be subjected by the government to any or all of the examinations and tests specified in 4.5 and 4.6 of this specification and any or all requirements of the applicable drawings.

4.4.3 Rejection. If any sample fails to comply with any of the applicable requirements, the first article quantity shall be rejected. The government reserves the right to terminate its inspection upon any failure of a sample to comply with any of the stated requirements.

4.5 Quality conformance inspection.

4.5.1 Lot formation. A lot shall consist of one or more batches of Oxamide Explosive composition produced by one manufacturer in accordance with the same specification, and same specification revision under one continuous set of operating conditions. Each lot shall consist of that quantity of Oxamide explosive composition which has been subjected to the same unit chemical or physical process intended to make the final product homogeneous. In addition, each lot shall contain:

a. TNT from one interfix lot only, from one manufacturer.

b. RDX from one interfix lot only, from one manufacturer.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:33Z
Check the source to verify that this is the current version before use.

c. Wax, one type only, from one manufacturer.

d. Oxamide from one lot only, from one manufacturer.

The product shall be submitted for inspection in accordance with MIL-STD-105 unless otherwise specified. The criteria and procedures for the assignment of lot numbers shall be in accordance with MIL-STD-1168.

4.5.2 Examination. Sampling plans and procedures for the following classifications of defects shall be in accordance with MIL-STD-105. Contractor's sampling plans, if used, shall be approved by the government and shall provide as a minimum, the protection afforded the government by the sampling plans in MIL-STD-105. Continuous sampling plans in accordance with MIL-STD-1235 may be used if approved by the contracting officer. Also at the option of the contracting officer, AQLs and sampling plans may be applied to the individual characteristics listed, using an AQL of 0.40 percent for each major defect and an AQL of 0.65 percent for each minor defect.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:33Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE	SHEET	OF	DRAWING NUMBER
4.5.2.1	Wooden or fiberboard box	1	1	7548644/7548645
				NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major					
101	Foreign matter		1.0		Visual
102	Liner pierced or torn		1.0		Visual
103	Liner improperly closed		1.0		Visual
Minor					
201	Type of liner incorrect		1.0		Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:33Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-O-60371A (AR)

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.5.2.2	Sealed wooden box	1 OF 1	7548644
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major					
101	Box damaged		1.5		Visual
102	Lot number incorrect or illegible		1.5		Visual
103	Board broken or split		1.5		Visual
104	Strapping missing, broken or loose		1.5		Visual/Manual
105	Top improperly assembled		1.5		Visual/Manual
Minor					
201	Nail protruding		1.5		Visual
202	Marking incorrect or illegible		1.5		Visual
203	Strapping improperly assembled		1.5		Visual/Manual

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:33Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-O-60371A (AR)

PARAGRAPH	TITLE	SHEET	OF	DRAWING NUMBER
4.5.2.3	Sealed fiberboard box	1	1	7548645
				NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major					
101	Assembly torn or pierced		1.0		Visual
102	Lot number incorrect or illegible		1.0		Visual
103	Binding strips broken, missing or loose		1.0		Visual
Minor					
201	Marking incorrect or illegible		1.5		Visual
202	Stitches missing or loose (when required)		1.5		Visual/Manual
203	Banding strips improperly assembled		1.5		Visual/Manual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:33Z
Check the source to verify that this is the current version before use.

4.5.3 Testing.

PRECAUTION WARNING

This specification covers sampling and testing of toxic or hazardous materials. Accordingly, it is emphasized that all applicable safety rules, regulations and procedures must be followed in handling and processing these materials.

4.5.3.1 Sampling. A representative sample of approximately one kg taken in accordance with ASTM Procedure E300 for solids shall be taken from each batch of Oxamide Explosive. The selection of batches for testing shall be in accordance with MIL-STD-1235, CSP-1 Plan, AQL 6.5%. If any sample fails to meet any test requirement, the batch represented by the sample shall be rejected. All batches produced between the time that the last batch was tested and accepted and the batch which failed shall be tested in accordance with the applicable methods given in paragraph 4.6. If any of these batches fail to meet any of the test requirements, that batch shall also, be rejected. In addition, after any failure of a batch the contractor will return to 100% inspection until "i" successive batches are accepted in accordance with MIL-STD-1235. Classification of defects shall be as given in Table IV.

4.5.3.2 Product testing. Unless otherwise specified, the samples obtained in 4.5.3.1 shall be subjected to the tests listed in Table III. Unless otherwise specified in the contract (see 6.1) the results of the tests shall be reported in accordance with MIL-STD-1171.

TABLE IV. Classification of defects

Inspection Requirement	Defect Classification	Test Method
Composition	Major defect	
RDX content		4.6.3
TNT content		4.6.1
Oxamide content		4.6.2
Wax content		4.6.2
Moisture	Major defect	4.6.4
Viscosity	Major defect	4.6.5

4.5.4 Inspection equipment. For the performance of all tests and examinations specified in 4.5 and 4.6, commercial inspection equipment should be employed. The contractor shall have available, and utilize correctly, this equipment and is charged with the responsibility of assuring that proper calibration procedures are followed. Government approval of all inspection equipment is required prior to its use for acceptance purposes (see 6.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:33Z
Check the source to verify that this is the current version before use.

4.6 Methods of inspection. The following tests shall be performed using prescribed analytical procedures for replicate determinations given in standard analytical textbooks or ASTM Method D2905. Also, unless otherwise specified herein, all chemicals and reagents shall be ACS grade in accordance with MIL-STD-1218 or reagent grade (see 6.2 for use of equivalent test methods).

4.6.1 TNT content. Prepare TNT calibrations standards for the Oxamide Explosive analyses as follows: Weigh out approximately 0.3960g of TNT which is at least 99.8% pure to the nearest 0.1 mg and transfer to a 100 mL volumetric flask. Add 80 mL of HPLC grade acetonitrile and shake the flask until the TNT is completely dissolved. Add additional acetonitrile to the mark and invert the flask several times to assure that the solution is thoroughly mixed. Pipet 1.00 mL of solution from the flask. Transfer to a second 100 mL volumetric flask. Make up to volume with the HPLC grade acetonitrile and invert several times to thoroughly mix the solution.

Repeat the above procedure with approximately 0.3760g and 0.4160 portions of TNT. Reserve the calibration standards for use in establishing the HPLC response factors for TNT.

The Oxamide Explosive sample shall be prepared as follows: Crush and screen a portion of Oxamide Explosive and collect the portion which passes through a US Std No. 4 sieve. Accurately weigh to the nearest 0.1 mg approximately one gram of the sample and transfer to a 100 mL volumetric flask. Add 80 mL of HPLC grade acetonitrile to the flask and place the flask in an ultrasonic bath for at least fifteen minutes. Allow the solution to cool to room temperature and dilute the solution to the mark with additional acetonitrile. Invert the flask several times to mix the solution thoroughly. Pipet one mL of the solution to a second 100 mL volumetric flask and dilute to the mark with acetonitrile. Invert the flask several times to thoroughly mix the solution.

A high performance liquid chromatograph (HPLC) shall be used for the TNT analysis. The HPLC shall be equiped with a C18 reverse phase analytical column or equal, a UV detector set at 254 nm, and a 20 microliter sampling loop. The column oven shall be set at 30 $\pm$ 1°C and the mobil phase, 98% HPLC grade methanol and 2% HPLC grade acetonitrile which has been degassed with an inert gas, shall have a flow rate of 1.0 mL per minute. The HPLC shall be equiped with an electronic integrator.

Filter one of the calibration standard samples through a 0.5 micron HPLC sample filter into a sample vial. Introduce the standard into the HPLC through the 20 microliuter sampling loop. Record the area for the TNT in integrator area units. Repeat the procedure for the remaining calibration standards and plot the TNT integrator areas for the calibration standards against their TNT contents.

Repeat the procedure for the solution containing the Oxamide Explosive sample.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:33Z
Check the source to verify that this is the current version before use.

Determine the weight of TNT in the sample by comparing the peak area for the sample with the plot obtained from the calibration standards.

Calculate the % TNT using the following equation.

$$\text{TNT } \% = \frac{100\ A}{W - (WM)}$$

Where: A = The weight of TNT in the Oxamide Explosive sampling.
W = The Oxamide Explosive sample weighting.
M = The percent moisture in the sample as determined in 4.6.4, expressed as a decimal.

4.6.2 Desensitizing wax and oxamide contents. Into a tared medium porosity filtering crucible accurately weigh to the nearest 0.1 mg approximately 5.0g sample of the Oxamide Explosive. Place approximately 15 mL of acetone into the crucible and allow to stand for five minutes with occasional stirring. Apply vaccuum to the crucible to draw the acetone through the crucible. Repeat the extraction with nine more 15 mL portions of acetone. Aspirate the residue for five minutes and place in a vacuum oven at 55 $\pm$ 2°C and 2.75 to 3.55 inches Hg for fifteen minutes. Place in a desiccator until cool and weigh to the nearest 0.1 mg.

Place the crucible and vacuum filtration apparatus in a fume hood and add 25 mL of 90°C toluene to the residue in the crucible. Allow the toluene to remain in contact with the residue for one minute and apply vacuum. Repeat the filtration procedure five more times. Place fifteen mL of acetone in the crucible for about five seconds and apply vacuum. Aspirate the crucible contents for five minutes and place the crucible in a vacuum oven at 55 $\pm$ 2°C and 2.75 to 3.55 inches Hg for fifteen minutes. Place in a desicator until cool and weigh to the nearest 0.1 mg.

Calculate the wax and oxamide percents as follows:

$$\% \text{ wax} = \frac{100\ (A-B)}{W - (MW)} \quad \text{and}$$

$$\% \text{ oxamide} = \frac{100\ (B-C)}{W - (MW)}$$

Where: A = The weight in g of the crucible and contents after the acetone extraction.
B = The weight in g of the crucible and contents after the toluene extraction.
C = The tare weight in g of the crucible.
W = The weight in g of the Oxamide Explosive sample.
M = The percent moisture in the sample as determined in 4.6.4, expressed as a decimal.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:33Z
Check the source to verify that this is the current version before use.

4.6.3 RDX content. Determine the RDX content using the following equation:

RDX % = 100 - A + B + C

Where: A = The percent TNT as determined in 4.6.1.
B = The percent wqax as determined in 4.6.2.
C = The percent oxamide as determined in 4.6.2.

4.6.4 Moisture. Determine moisture content in accordance with Method 101.4 of MIL-STD-650. The special solvent used in this determination shall be equal volumes of anhydrous methanol and toluene thoroughly mixed. If necessary the mixed special solvent may be dried by distillation.

4.6.5 Viscosity. Determine the viscosity in accordance with Method 212.1 of MIL-STD-650. The viscosity shall be determined at 90.0 ± 0.1°C.

4.6.6 Workmanship. Visually examine the production of the explosive and all samples submitted for testing for compliance with the requirements given in 3.5.

5. PACKAGING

5.1 Packing.

5.1.1 Level A. Oxamide Explosive shall be packed in accordance with drawing 7548644.

5.1.2 Level B. Oxamide Explosive shall be packed in accordance with Level A packing requirements.

5.1.3 Level C. Oxamide Explosive shall be packed in accordance with drawing 7548645 or 9257923.

5.2 Marking.

5.2.1 Level A. Oxamide Explosive shall be marked in accordance with drawing 7548644.

5.2.2 Level B. Oxamide Explosive shall be marked in accordance with Level A marking requirements.

5.2.3 Level C. Oxamide Explosive shall be packed in accordance with drawing 7548645 and 9257923.

6. NOTES

6.1 Ordering data.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:33Z
Check the source to verify that this is the current version before use.

6.1.1 Acquisition requirements.

a. Title, number and date of this detail specification.

b. Quantity required and delivery schedules.

c. First article requirements sample provisions (see 3.4 and 4.3).

d. Level of packing protection required.

e. Description sheets shall be prepared for each submitted lot in accordance with MIL-STD-1171 or DRSAR-P-702-109 unless otherwise directed in the contract.

6.1.2 Data requirements. When this specification is used in a procurement contract which incorporates DD Form 1423, acceptance and description sheets prepared in accordance with MIL-STD-1171, DRSAR-P-702-109 or as directed in the contract shall be supplied by the contractor.

6.2 Equivalent test methods. The test methods given in this specification are the official methods to be used. The contractor may request using other methods providing that the proposed method is equivalent (accuracy and precision) to the method given in this specification. Prior approval of the contracting officer is required for use of equivalent test methods. A description of the proposed method should be submitted through the contracting officer to: Commander, ARDC, ATTN: AMSMC-QAR-R(D), Dover, NJ 07801. This description should include, but not be limited to, the procedures used, the accuracy and precision of the method, test data to demonstrate the accuracy and precision and drawings of any special equipment required (see MIL-I-45208).

6.3 Drawings. Drawings listed in Section 2 under the heading US Army Armament Research and Development Center (ARDC) may also include drawings prepared by and identified as, US Army Armament Research and Development Command (ARRADCOM), Edgewater Arsenal, Frankford Arsenal. Rock Island Arsenal or Picatinny Arsenal drawings. Technical data originally prepared by these activities are now under the cognizance of ARDC.

6.4 Change from previous issue. Asterisks are not used in this revision to identify changes with respect to the previous issue, due to the extensiveness of the changes.

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 1376-A280)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:33Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-O-60371A	OXAMIDE EXPLOSIVE COMPOSITION

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR ☐ USER ☐ MANUFACTURER ☐ OTHER *(Specify)*: _____
b. ADDRESS *(Street, City, State, ZIP Code)*	

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:33Z
Check the source to verify that this is the current version before use.