MIL-S-83430A
INTERIM AMENDMENT 1(USAF)
8 May 1987

MILITARY SPECIFICATION

SEALING COMPOUND, INTEGRAL FUEL TANKS AND FUEL CELL CAVITIES, INTERMITTENT USE TO 360°F (182°C)

This interim amendment is approved for use within the Department of the Air Force with MIL-S-83430A, dated 12 April 1982.

PAGE 2

2.1.1, add the following:

"MIL-A-9962 - Abrasive Mats, Non-woven, Non-metallic".

PAGE 13

4.6.1.1, add the following:

"4.6.1.1 Special cleaning of stainless steel and titanium peel strength panels. Two stainless steel panels and four titanium panels that are used for peel strength testing have to receive special cleaning. These are the panels that are immersed in jet reference fluid/salt water for 7 days for the stainless steel and for 7 and 70 days for the titanium (See Table VI). The special cleaning shall be scrubbing with abrasive mats and MIL-C-38736 solvent. After scrubbing, the panels shall be rinsed using MIL-C-38736 solvent and clean gauze. The panels shall be wiped dry. The abrasive mats shall conform to MIL-A-9962, Type I, Class 1, Grade A for the stainless steel and MIL-A-9962, Type III, Class 1, Grade A for the titanium. After final cleaning, PR-148 adhesion promoter shall be applied."

Preparing Activity:
Air Force 20

(Project 8030-F040)

AMSC N/A 1 of 1 FSC 8030

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T08:06Z
Check the source to verify that this is the current version before use.