COMMERCIAL ITEM DESCRIPTION


MARLINESPIKE (NONSPARKING AND NONMAGNETIC)

The General Services Administration has authorized the use of this commercial item description.

This commercial item description covers one marlinespike assigned National Stock Number (NSN) 5120-00-288-7769 made of a nonferrous alloy having a low sparking hazard and a low magnetic permeability.

Salient characteristics:

Design and dimensions as follows:



Dimensions in inches:

A - 16, + or - 3/8	B - 1-1/2, + or - 1/8	C - 3/8, + or - 1/8
D - 1, +1/16 or -0	E - 5/16, + or - 1/16	F - 2, + or - 3/8
G - 5/16, + or - 1/16	H - 1-1/4, + or - 1/8	

Material. The marlinespike shall be made of beryllium copper or aluminum bronze alloy having an iron content not over five percent, and when present, it shall be well diffused throughout the alloy. When tested with a magnetic permeability indicator conforming to Military Specification MIL-I-17214, the magnetic permeability shall not be above 1.2 on the indicator scale.

Workmanship. The marlinespike shall be smoothly finished and free from burrs and rough edges or other imperfections which may impair the appearance, serviceability, or durability.

Marking. Each marlinespike shall be marked in a plain and permanent manner with name, abbreviation, or chemical symbol of the alloy, the manufacturer's name or trademark of such known character that the source of manufacture may be readily determined, and the country of origin.

FSC 5120

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:23Z
Check the source to verify that this is the current version before use.

Quality assurance provisions. Sampling for inspection shall be in accordance with MIL-STD-105, Sampling Procedures and Tables for Inspection by Attributes, except where otherwise indicated herein. The lot size shall consist of all marlinespikes offered for acceptance at one time. A sample unit shall be one marlinespike.

A. Examination for design, dimensions and workmanship. The inspection level shall be S-2 with an acceptable quality level (AQL) of 4.0 percent defective.

B. Material. Material shall be ascertained by manufacturer's certification.

Regulatory requirements. In accordance with the section 23.403 of the Federal Acquisition Regulations, the Government's policy is to acquire items composed of the highest percentage of recovered materials practicable, consistent with maintaining a satisfactory level of competition without adversely affecting performance requirements or exposing suppliers' employees to undue hazards from the recovered materials.

Preservation, packaging, packing, labeling, and marking. The preservation, packaging, packing, labeling, and marking shall be as specified in the contract or order.

Notes:

The issue of referenced documents in effect on the date of invitation for bid or request for proposals shall be used to determine compliance with the stated requirements. Sources for obtaining referenced documents may be determined by contacting the Contracting Officer.

MILITARY INTERESTS:

NONE: DoD has determined that no military activity has an official interest in this commercial item description.

PREPARING ACTIVITY:

GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:23Z
Check the source to verify that this is the current version before use.