METRIC

DOD-P-63245A (AR)
AMENDMENT 2
19 April 1991
SUPERSEDING
AMENDMENT 1
9 March 1982

MILITARY SPECIFICATION

PROJECTILE, HE, 155MM, XM795
METAL PARTS ASSEMBLY

This Amendment forms a part of Military Specification DOD-P-63245A (AR) dated 28 September 1981 and is approved for use by the U.S. Army Armament, Munitions, and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

Delete "XM795" wherever it appears and substitute: "M795".

PAGE 20

4.4.2.7: Add Critical defect 4:

"4	Missing base plate, broken base plate weld or perforated base plate	100%	Visual"

PAGE 26

* Delete paragraph 4.4.3.5 in its entirety and substitute the following:

"4.4.3.5 Salt spray. After qualification in accordance with TT-C-490, two (2) salt spray samples shall be taken each week, one during the first 30 minutes of production and a second at any other time. Failure to comply with the requirements of the applicable drawing shall be cause for taking the corrective action prescribed in TT-C-490."

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:28Z
Check the source to verify that this is the current version before use.

PAGE 28

* Delete paragraph 4.5.3.4 in its entirety and substitute the following:

"4.5.3.4 Operator qualifications. For operation of ultrasonics equipment, personnel shall be qualified and certified in accordance with MIL-STD-410, Level I. For set-up and calibration of ultrasonics equipment, personnel shall be qualified and certified in accordance with MIL-STD-410, Level II, in all respects, but need not include experience."

PAGE 30

* Delete paragraph 4.5.8 in its entirety and substitute the following:

"4.5.8 Salt spray testing. Salt spray testing shall be accomplished on production projectiles or sectioned projectiles that were acceptable at the time of painting and were sectioned subsequent to painting. If sectioned projectiles are used, sectioning shall be accomplished to allow testing of all major areas of the projectiles on an alternating basis. The salt spray test shall be performed utilizing the equipment and procedures specified by Federal Test Method Standard No. 141 and TT-C-490 with the exception that test samples shall be selected in accordance with 4.4.3.5 and test samples shall be dried in accordance with Drawing 9326055."

4.5.10: Delete in its entirety and substitute:

"4.5.10 Magnetic particle inspection. The procedures for performing this test utilizing the wet fluorescent method shall be as specified in Specification MIL-I-6868 after hydro test, for indirect magnetization by the continuous method. The suspension shall be applied to the entire body inside and outside. The body shall be drained, then thoroughly inspected inside and outside, after inducing a circular magnetic field and then a longitudinal magnetic field in a darkened area under the ultraviolet light which will produce adequate fluorescence of the magnetic particles. The solids content of the suspension shall be maintained at a level recommended by the manufacturer. The suspension shall be checked at the start of each days' production and at intervals of not over 4 hours continuous operation, utilizing

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:28Z
Check the source to verify that this is the current version before use.

the procedures and the equipment prescribed by specification MIL-I-6868. When performing the test for the solids content of suspension, if it is determined that it does not comply, all assemblies that have been accepted since the last satisfactory test shall be retested after the suspension has been brought to the proper level. After acceptance, the body assembly shall be demagnetized and cleaned, then stamped as required by the applicable drawing. The magnetic particle test shall be performed on equipment that complies with the requirements of Specification MIL-I-6867."

PAGE 31

* Add the following new paragraph 4.5.10.1:

"4.5.10.1 Operator qualifications. For operation of magnetic particle equipment, personnel shall be qualified and certified in accordance with MIL-STD-410, Level I. For set-up and calibration of magnetic particle equipment, personnel shall be qualified and certified in accordance with MIL-STD-410, Level II."

The margins of this amendment are marked with an asterisk to indicate where changes from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army - AR

Preparing activity:
Army - AR

(Project 1320-AC40)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:28Z
Check the source to verify that this is the current version before use.