MIL-P-51104A(MU)
AMENDMENT 1
18 June 1987

MILITARY SPECIFICATION

PROTECTOR, INFANT, M2

This amendment forms a part of MIL-P-51104A(MU), dated 16 February 1970, and is approved for use within the Chemical Research, Development and Engineering Center, Department of the Army and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 2

2.1:

Under "DRAWINGS" delete ""DLB136-42-102-8 - Penetrometer, Filter Testing, DOP, Q127."

Under "PUBLICATIONS" delete "197-51-350 - Vinyl Chloride Polymer and Copolymer Flexible Sheets."

PAGE 3

Add the following new paragraph in sequence:

"3.1.1.6 Clarity. The material shall be uniformly colorless and clear with a polished finish. The transparency shall be equal to or better than the referee standard sample."

3.1.2, 3.1.2.1, and 3.1.2.2: Delete in their entirety.

3.1.4: Delete in its entirety.

PAGE 4

4.1.2, line 2: Delete "4.2.4.1" and substitute "4.2.4.1.3 and 4.2.4.1.4".

4.1.2: Delete "Test specified in 4.2.4.2 will be observed by the Government."

MSC N/A

FSC 4240

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:50Z
Check the source to verify that this is the current version before use.

4.2.2.2.2:

Line 2: Delete "vinyl to window".

Lines 3 and 4: Delete "window material".

PAGE 5

4.2.3.2.1, line 2: Delete "and 3.1.2".

PAGE 6

4.2.4.2:

Lines 2 and 3: Delete "vinyl to window".

Line 5: Delete "method 4311 of FED-STD-601." and substitute "method 1013, method B of FED-STD-406 using a pendulum (Scott) type of machine except that no autographic stress strain curve is needed. The test specimens shall be 1-inch wide."

4.2.4.3: Delete in its entirety and substitute the following:

"4.2.4.3 DOP smoke penetration. The assembled protector shall be tested in a clean atmospheric vertical flow area of approximately 100 square feet for DOP smoke penetration by introducing DOP aerosol into the protector using a single Laskin nozzle type, air operated DOP aerosol generator for a period of 25 ± 5 seconds. The protector shall inflate slightly. The entire surface, including all seams, seals, edges and filter panels shall be scanned with the probe of a particulate detection apparatus of the forward light scattering type having a linear readout sensitivity to 0.001 percent penetration, and 3-inch diameter scan area at a traverse rate of not more than 10 linear feet per minute. All leaks shall be marked and recorded. At the conclusion of the test, the protector shall be opened and the residual DOP smoke purged."

PAGE 7

4.2.5.1, line 3: Delete "and 3.1.2".

Custodian:

Army - EA

Preparing activity:

Army - EA

Project No. 4240-A909



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:50Z
Check the source to verify that this is the current version before use.