FEDERAL SPECIFICATION

SOUND CONTROLLING MATERIALS
(TROWEL AND SPRAY APPLICATIONS)

This amendment, which forms a part of Federal Specification SS-S-111a, dated January 12, 1968, was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal Agencies.

PAGE 5

Paragraph 3.5.2, line 2: Delete "0.01" and substitute "0.025".

PAGE 7

Paragraph 4.4.3.3 delete and substitute:

4.4.3.3 Test apparatus. The test apparatus shall consist of a tight metal duct approximately 17 inches wide by 24 inches high by 7 feet long. A centrifugal blower, driven by a 7.5 h.p. motor, shall be coupled to the duct. One side of the duct shall have an opening large enough to insert a test sample 16 inches wide by 48 inches long, having an exposed surface area to the air flow of approximately 4 square feet (see figure 1). A vane anemometer shall be mounted in front of the test panel area for measurement of the air flow velocity. Two dust collecting filters, having a 95 percent efficiency in filtering particles 5 microns in size and larger, shall be installed upstream of the opening for the test sample (see 6.7). A black dust collecting cloth shall be placed downstream of the opening for the test sample. The cloth fabric shall be made of 30 denier nylon having a thread count of 102 warp ends per inch and 82.3 filler picks per inch. The cloth shall be dried at 120° ± 1° F. to a constant weight before each weighing.

Paragraph 4.4.3.4 delete and substitute:

4.4.3.4 Procedure. The test for dusting shall be conducted in a reasonably dust-free environment. The test specimen shall be inserted in the test opening in the duct side wall. The complete

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:12Z
Check the source to verify that this is the current version before use.

system shall be purged for 6 hours at a minimum impinging velocity of 800 feet per minute over the entire surface of the test specimen. After the system has been purged for 6 hours, the dust cloth shall be removed and dried at 120° F. and weighed until the weight is constant within the nearest 0.001 gram. The dust collecting cloth shall be reinserted in the test apparatus and the system again purged for 24 hours. The dust collecting cloth shall then be removed and dried and weighed as before. The net difference in weight between the 6 hour purging and the 24 hour purging shall constitute the dust removed from the acoustical material. The weight of the dust removed shall not exceed the amount specified in 3.5.2.

MILITARY INTEREST:

Custodians:

Army - ME
Navy - YD
Air Force - 84

User activity:

Army - CE

Preparing activity:
Navy - YD

CIVIL AGENCY INTEREST:

GSA - FSS
VA
COM - NBS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:12Z
Check the source to verify that this is the current version before use.