FEDERAL SPECIFICATION

SLAG AND STONE, CRUSHED; GRAVEL, CRUSHED AND UNCRUSHED (FOR SEWAGE TRICKLING FILTER MEDIA)

This amendment, which forms a part of Federal Specification SS-S-448; dated August 12, 1966, was approved by the Commissioner, Federal Supply Service, General Services Administration for the use of all Federal agencies.

PAGE 2

Table I. Delete in its entirety and substitute:

TABLE I. Grading sizes

| Nominal size square openings | Amount passing sieve (square openings) by weight, percent | | | | | | |
|---|---|---|---|---|---|---|---|
| Inches | 4 | 3 1/2 | 3 | 2 1/2 | 2 | 1 1/2 | 1 |
| Mm | 102 | 89 | 76 | 63 | 51 | 38 | 25 |
| 3 1/2 to 2 1/2 inches 89 to 63 mm | 100 | 90-100 | -- | 0-10 | 0-5 | -- | -- |
| 3 1/2 to 2 inches 89 to 51 mm | 100 | 90-100 | -- | -- | 0-10 | 0-5 | -- |
| 3 to 2 inches 76 to 51 mm | 100 | 100 | 90-100 | -- | 0-10 | 0-5 | -- |
| 3 to 1 1/2 inches 76 to 38 mm | 100 | 100 | 90-100 | -- | -- | 0-10 | 0-5 |
| 2 1/2 to 1 1/2 inches 63 to 38 mm | 100 | 100 | 100 | 90-100 | -- | 0-10 | 0-5 |

Paragraph 3.4. Delete in its entirety and substitute:

3.4 Particle shape. The individual pieces of the material shall be as nearly equidimensional as practical. The media shall not have more than 30 percent of the pieces of such shape that the maximum dimension exceeds the least dimension by a ratio of 3 to 1. The dimension shall be taken as the length and the width or depth whichever is lesser of an imaginary circumscribed rectangular prism of the piece of media.

Paragraph 3.5. Delete in its entirety and substitute:

3.5 Soundness.

Source: https://assist.dla.mil -- Downloaded: 2026-04-26T12:13Z
Check the source to verify that this is the current version before use.

3.5.1 Grade A, for freezing temperatures. Grade A filter media, in addition to having the other properties specified herein, shall be resistant to disintegration caused by freezing and thawing. Except as hereafter indicated determination of resistance to disintegration caused by freezing and thawing shall be by the soundness test described in 4.4.2. When subjected to 20 cycles of the soundness test, the weight loss due either to breaking or to crumbling and flaking shall not exceed 10 percent and the combined loss shall not exceed 15 percent. Stone from a quarry which has previously furnished stone for trickling filters subject to freezing and thawing will be considered as meeting this requirement provided that the service record is satisfactory to the purchaser, and provided that the stone in the quarry is uniform throughout and of the same quality as that on which the service record is based.

3.5.2 Grade B, for temperatures above freezing. Grade B filter media shall be the same as grade A in all essentials, except that resistance to deterioration caused by freezing and thawing is not required.

PAGE 3

Paragraph 4.4.2. Delete in its entirety and substitute:

4.4.2 Soundness, grade A. Test for soundness using a saturated solution of sodium sulfate in accordance with ASTM C88, except as modified by the following:

PAGE 4

Add a new paragraph as follows:

6.5 Metric equivalents. The metric equivalents are for information only, and are not intended to be used for determining acceptance or rejection of items otherwise conforming to the requirements of this amendment.

Custodian:

Army - ME
Navy - YD
Air Force - 01

User Interest: CE

Military Coordinating Activity:

Army - ME

Preparing activity:

GSA-FSS

Civil Agency Coordinating Activities:

DOT-FIS
USDA-AFS
COM-NBS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:13Z
Check the source to verify that this is the current version before use.