AMENDMENT

TO

FEDERAL SPECIFICATION

WOOD PRESERVATION: TREATING PRACTICES

This amendment, which forms part of Federal Specification TT-W-571I, dated October 28, 1968 was approved by the Commissioner, Federal Supply Service, General Services Administration for the use of all Federal agencies.

PAGE 9

Table III. Delete, and in its place substitute the new table below.

PAGE 10

Footnote 1. Add the following at the beginning of the paragraph.

"All retentions are based on compositions composed of oxide formulations."

TABLE III. Treatment of wood with water-borne preservatives

Form of product and service conditions	Assay zone	Minimum net retention of solid preservative [1]					Treating specifications [2] (AWPA Standard C1 and others listed below)
		Acid copper chromate (Fed. Spec. TT-W-546)	Amoniacal copper arsenite (Fed. Spec. TT-W-549)	Chromated copper arsenate (Fed. Spec. TT-W-550) Type I, II, or III	Chromated zinc chloride (Fed. Spec. TT-W-551)	Fluor-chrome-arsenate-phenol mixture (Fed. Spec. TT-W-535) Type I or Type II	
	In.	Pcf.	Pcf.	Pcf.	Pcf.	Pcf.	
Timbers [2] For use under moderate weathering conditions [11]	gage only	0.50	0.40	0.40	0.61	0.31	C2
For use in protected locations not in ground contact.	gage only	.25	.25	.25	.46	.22	
Timbers, glued laminated (including laminates prior to gluing) For use under moderate weathering conditions [11]	(5)	.50	.40	.40	.61	.31	C28
For use in protected locations not in ground contact	(5)	.25	.25	.25	.46	.22	
Lumber [2] For use under moderate weathering conditions [11]	0-5/8	.50	.40	.40	.61	.31	C2

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:17Z
Check the source to verify that this is the current version before use.

TABLE III. Treatment of wood with water-borne preservatives (continued)

Form of product and service conditions	Assay zone	Minimum net retention of solid preservative [1]					Treating specifications [2] (AWPA Standard C1 and others listed below)
		Acid copper chromate (Fed. Spec. TT-W-546)	Amoniacal copper arsenite (Fed. Spec. TT-W-549)	Chromated copper arsenate (Fed. Spec. TT-W-550) Type I, II, or III	Chromated zinc chloride (Fed. Spec. TT-W-551)	Fluor-chrome-arsenate-phenol mixture (Fed. Spec. TT-W-535) Type I or Type II	
	In.	Pcf.	Pcf.	Pcf.	Pcf.	Pcf.	
For use in protected locations not in ground contact	0-5/8	0.25	0.25	0.25	0.46	0.22	
Plywood							C9
For use under moderate weathering conditions [11]	(6)	.50	.40	.40	.61	.31	
For use in protected locations not in ground contact	(6)	.25	.25	.25	.46	.22	
Poles, round [7]							
Utility							C4
Southern and ponderosa pines	0.5-2.0	----	.6	.6	----	----	
Red pine	.1-1.6	----	.6	.6	----	----	
Jack and lodgepole pines	.1-.75	----	.6	.6	----	----	
Pacific Coast Douglas-fir	.25-1.0	----	.6	.6	----	----	
Inland Douglas-fir	.1- .6	----	.6	.6	----	----	
Western larch	.1- .6	----	.6	.6	----	----	
Western redcedar	.1- .6	----	.6	.6	----	----	
Building [9]	0-1.5	----	.70	.70	----	----	C23
Posts, round							
Fence [7]	gage only	.50	.40	.40	----	----	C5
Building [9]	0-1.5	----	.70	.70	----	----	C23

MILITARY CUSTODIANS:

Army - ME
Air Force - 84

Review Interest:
Army - MD, AT

User Interest:
Navy - SH, YD

Military Coordinating Activity

Army - ME

Preparing activity

AGR - FS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:17Z
Check the source to verify that this is the current version before use.