INCH-POUND
MIL-PRF-22262C(SH)
w/AMENDMENT 1
18 April 2025
SUPERSEDING
MIL-PRF-22262C(SH)
24 August 2023

PERFORMANCE SPECIFICATION

ABRASIVE BLASTING MEDIA, SHIP BLAST CLEANING

This specification is approved for use by the Naval Sea Systems Command and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers inorganic abrasive media used in the blast cleaning of metal surfaces, such as ship hulls and tanks, to remove corrosion, scale, old paint, and other foreign matter resulting in surfaces that are clean and suitable for painting. Examples of inorganic abrasive materials are minerals, recycled materials like crushed glass, by-products of metal or energy production such as slags, and engineered materials that are manufactured to serve as industrial abrasives.

1.2 Classification. Inorganic abrasive materials covered in this specification are of the following types, classes, and grades as specified (see 6.2).

1.2.1 Types.

a. Type I – Naturally occurring minerals.

b. Type II – By-product, engineered, and manufactured materials.

1.2.2 Classes.

a. Class 1 – Glass abrasive material.

b. Class 2 – Garnet abrasive material.

c. Class 3 – Aluminum oxide abrasive material.

d. Class 4 – Other metal oxide abrasive material.

e. Class 5 – Metal silicate abrasive material.

f. Class 6 – Silicon carbide abrasive material.

g. Class 7 – Coal slag abrasive material.

h. Class 8 – Other slag abrasive material.

i. Class 9 – Blend of the above.

1.2.3 Grades.

a. Grade A – Total beryllium content is not greater than 0.00001 percent by weight.

b. Grade B – Total beryllium content is not greater than 0.0075 percent by weight.

Comments, suggestions, or questions on this document should be addressed to Commander, Naval Sea Systems Command, ATTN: SEA 05S, 1333 Isaac Hull Avenue, SE, Stop 5160, Washington Navy Yard, DC 20376-5160 or emailed to CommandStandards@navy.mil, with the subject line “Document Comment”. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil.

AMSC N/A FSC 5350

Distribution Statement A. Approved for public release: distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:44Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

CALIFORNIA AIR RESOURCES BOARD (CARB)

Test Method No. California 371-A - Method of Test for Abrasive Media Evaluation

(Copies of this document are available online at https://ww2.arb.ca.gov/abrasive-blasting-test-procedures.)

CALIFORNIA CODE OF REGULATIONS

Title 17, Division 3, Chapter 1, Subchapter 6, Article 4, Section 92530 - Certified Abrasives

Title 22, Division 4.5, Chapter 11, Article 3, Section 66261.24 - Characteristic of Toxicity

(Copies of these documents are available online at https://govt.westlaw.com/calregs/.)

DELETED

U.S. ENVIRONMENTAL PROTECTION AGENCY (EPA)

EPA Method 901.1 - Gamma Emitting Radionuclides in Drinking Water

EPA SW-846, Chapter 3 - Inorganic Analytes

(Copies of these documents are available online at www.epa.gov.)

2.3 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

ASSOCIATION FOR MATERIALS PROTECTION AND PERFORMANCE (AMPP)

SSPC-AB 1 - Mineral and Slag Abrasives

(Copies of this document are available online at www.ampp.org.)

ASTM INTERNATIONAL

ASTM C702/C702M - Standard Practice for Reducing Samples of Aggregate to Testing Size

ASTM D75/D75M - Standard Practice for Sampling Aggregates

(Copies of these documents are available online at www.astm.org.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:44Z
Check the source to verify that this is the current version before use.

INTERNATIONAL AGENCY FOR RESEARCH ON CANCER (IARC)

IARC Monographs on the Identification of Carcinogenic Hazards to Humans

(Copies of this document are available online at https://monographs.iarc.who.int/.)

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION (ISO)

ISO 11127-7 - Preparation of Steel Substrates Before Application of Paints and Related Products – Test Methods for Non-Metallic Blast-Cleaning Abrasives – Part 7: Determination of Water-Soluble Chlorides

(Copies of this document are available online at www.iso.org.)

2.4 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Qualification. The abrasive materials furnished under this specification shall be products that are authorized by the qualifying activity for listing on the applicable qualified products list before contract award (see 4.2 and 6.4).

3.2 Materials. The abrasive material shall comply with all the requirements of this specification. The abrasive may be composed of any material meeting the requirements of this specification.

3.2.1 Toxicity and restricted materials.

3.2.1.1 Toxicity. When evaluated in accordance with 4.5.1.1, the abrasive material shall pose no serious or high risk to the health of personnel or the environment when used for its intended purpose (see 4.5.1.1 and 6.7).

3.2.1.2 Restricted materials. The materials used in the abrasive media, unless specific material maximum levels are cited herein, shall have no known carcinogenic or potentially carcinogenic materials identified in the latest International Agency for Research on Cancer (IARC) monographs, the latest annual report of the National Toxicology Program (NTP), or those identified by the Occupational Safety and Health Administration (OSHA) as regulated carcinogens. The material, unless specific material maximum levels are cited herein, shall not have known or suspected carcinogens intentionally added to the abrasive mix. When known or suspected carcinogens are present as a result of a trace or impurity in another ingredient, the concentration of the agent in the final product shall not equal or exceed 0.1 percent by weight of the abrasive media (see 4.5.1.2 and 6.7).

3.2.2 Hazardous constituents.

3.2.2.1 Soluble and total metal content. When tested in accordance with 4.5.2.1, the soluble metal content and total metal content of the abrasive shall not exceed the values listed in table I or in California Code of Regulations, Title 22, Division 4.5, Chapter 11, Article 3, Section 66261.24, (a),(2),(A).

TABLE I. Metals content of abrasive material.

Metal and its compounds	Soluble maximum (mg/L)	Total maximum (%WT)
Antimony	5	0.05
Arsenic	5	0.05
Barium (excluding barite)	100	1.00
Beryllium (grade A)	0.001	0.00001
Beryllium (grade B)	0.75	0.0075
Cadmium	1	0.01

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:44Z
Check the source to verify that this is the current version before use.

TABLE I. Metals content of abrasive material – Continued.

Metal and its compounds	Soluble maximum (mg/L)	Total maximum (%WT)
Chromium (VI)	5	0.05
Chromium and chromium (III)	5	0.25
Cobalt	80	0.09
Copper	25	0.25
Fluoride salts	180	1.80
Lead	1.0	0.01
Mercury	0.2	0.002
Molybdenum	35	0.35
Nickel	10	0.09
Selenium	1	0.01
Silver	5	0.05
Thallium	7	0.07
Vanadium	24	0.24
Zinc	50	0.50

NOTES:

1. Some of the metal limits specified in this specification are lower than required by the State of California Department of Health Services. Users may require lower metal limits as deemed necessary to comply with local environmental and occupational safety and health regulatory requirements.
2. DELETED.
3. The lower limit of quantitation (as defined by EPA SW-846, Chapter 3) for the instrumentation used to determine metal content shall not exceed the values in the table.

3.2.2.2 Maximum concentration of contaminants. When evaluated in accordance with 4.5.2.2, the contaminant content of the abrasive material shall not exceed the values listed in table II or in California Code of Regulations, Title 22, Division 4.5, Chapter 11, Article 3, Section 66261.24, (a),(1),(B) (see 4.5.2.2).

TABLE II. Contaminant content of abrasive material.

Contaminant (soluble)	Maximum (mg/L)
Benzene	0.5
Carbon tetrachloride	0.5
Chlordane	0.03
Chlorobenzene	100.0
Chloroform	6.0

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:44Z
Check the source to verify that this is the current version before use.

TABLE II. Contaminant content of abrasive material – Continued.

Contaminant (soluble)	Maximum (mg/L)
o-Cresol	200.0
m-Cresol	200.0
p-Cresol	200.0
2,4-Dichlorophenoxyacetic acid	10.0
1,4-Dichlorobenzene	7.50
1,2-Dichloroethane	0.50
1,1-Dichloroethylene	0.70
2,4-Dinitrotoluene	0.13
Endrin	0.02
Heptachlor (and its epoxide)	0.008
Hexachlorobutadiene	0.05
Hexachloroethane	3.0
Lindane	0.40
Methoxychlor	10.0
Methyl ethyl ketone	200.0
Nitrobenzene	2.0
Pentachlorophenol	100.0
Pyridine	5.0
Tetrachloroethylene	0.70
Toxaphene	0.50
Trichloroethylene	0.50
2,4,5-Trichlorophenol	400.0
2,4,6-Trichlorophenol	2.0
2-(2,4,5-trichlorophenoxy)propionic acid (2,4,5-TP, Silvex or Fenoprop)	1.0
Vinyl chloride	0.20

NOTES:

1. Some of the contaminant limits specified in this specification are lower than required by the State of California Department of Health Services. Users may require lower than specified contaminant limits as deemed necessary to comply with local environmental and occupational safety and health regulatory requirements.
2. DELETED.

3.2.3 Radioactivity. When tested in accordance with 4.5.2.3, the maximum gross gamma radioactivity of the abrasive material shall be no greater than 20.0 picocuries per gram.

3.2.3.1 Cobalt-60. When tested in accordance with 4.5.2.3, the concentration of Cobalt-60 shall be no greater than 0.05 picocuries per gram.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:44Z
Check the source to verify that this is the current version before use.

3.3 Identification (ID) characteristics. Values for ID characteristics shall be those established for the product at the time of submission for qualification testing (see 4.2 and 6.2). The purpose of these values is to serve as a basis for determining that the abrasive material being offered is essentially the same as that which was approved under qualification testing. Unless otherwise specified herein, ID characteristics testing for all types shall be conducted at 60 to 80 °F (16 to 27 °C) and below 85 percent relative humidity. The manufacturer shall provide the ASTM method(s), other consensus standards, or a copy of unique test methodology, or any other necessary information on methodology used to determine the following ID characteristics:

a. Material (see 1.2.1, 1.2.2, and 1.2.3).

b. Unit of issue.

c. Average particle size (see 3.4.1 and 4.5.3).

d. Surface profile that can be achieved (see 3.4.11 and 4.5.13).

3.4 Quantitative requirements. When tested in accordance with 4.2 and 4.3, the abrasive shall conform to the quantitative requirements and as specified in 3.2.1.1, 3.2.1.2, 3.2.2.1, 3.2.2.2, 3.2.3, 3.2.3.1, and 3.4.1 through 3.4.12.

3.4.1 Particle size distribution. When tested in accordance with 4.5.3, the particle size distribution of the abrasive material shall be the size distribution of the material used to achieve the surface profile of 3.4.11.

3.4.2 Friability. When tested in accordance with 4.5.4, the spent abrasive shall meet the friability requirements of California Code of Regulations, Title 17, Division 3, Chapter 1, Subchapter 6, Article 4, Section 92530. The abrasive shall be listed on the most recent list of abrasives approved for use in open air blasting in the state of California in accordance with California Code of Regulations, Title 17, Division 3, Chapter 1, Subchapter 6, Article 4, Section 92530.

3.4.3 Moisture content. When tested in accordance with 4.5.5, the moisture content of abrasive material shall be less than 0.5 percent by weight.

3.4.4 Weight change on ignition. When tested in accordance with 4.5.6, the abrasive material weight change as a result of ignition shall be within the range of minus 1.0 percent (weight loss) to plus 5.0 percent (weight gain).

3.4.5 Crystalline silica. When tested in accordance with 4.5.7, the crystalline silica content of the abrasive material shall not exceed 1.0 percent by weight. Crystalline silica shall not be intentionally added to the abrasive material.

3.4.6 Specific gravity. When tested in accordance with 4.5.8, the minimum specific gravity of the abrasive material shall be 2.3.

3.4.7 Conductivity. When tested in accordance with 4.5.9, the conductivity of the abrasive material shall not exceed 290 microsiemens per centimeter.

3.4.8 Chloride content. When tested in accordance with 4.5.10, the chloride content of the abrasive material shall be less than 0.03 percent by weight.

3.4.9 Oil content. When tested in accordance with 4.5.11, there shall be no oil visible.

3.4.10 Hardness. When tested in accordance with 4.5.12, the minimum hardness of the abrasive material shall be 6 on the Mohs scale.

3.4.11 Surface profile. When tested in accordance with 4.5.13, the abrasive material shall produce a surface profile between 1 and 5 mils (see 3.3).

3.4.12 Recycled abrasives. When tested in accordance with 4.5.14, the recycled abrasives (see 6.3.2) shall conform to the quality control tests for recycled work mix requirements in accordance with SSPC-AB 1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:44Z
Check the source to verify that this is the current version before use.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Conformance inspection (see 4.3).

4.2 Qualification inspection. Qualification inspection shall consist of all the tests specified in table III and all requirements listed in section 3. Qualification inspection for abrasive blast material shall be conducted at a laboratory acceptable to the qualifying activity (see 6.3.1).

TABLE III. Qualification and conformance tests.

Characteristic	Requirement paragraph	Test paragraph	Applicable test standard	Conformance testing required
Toxicity	3.2.1.1	4.5.1.1	---	No
Restricted material	3.2.1.2	4.5.1.2	---	No
Metal content	3.2.2.1	4.5.2.1	1/	No
Contaminant content	3.2.2.2	4.5.2.2	2/	No
Radioactivity	3.2.3	4.5.2.3	EPA Method 901.1	No
Cobalt-60	3.2.3.1	4.5.2.3	EPA Method 901.1	No
Particle size distribution	3.4.1	4.5.3	SSPC-AB 1	Yes
Friability	3.4.2	4.5.4	Test Method No. California 371-A	No
Moisture content	3.4.3	4.5.5	SSPC-AB 1	Yes
Weight change on ignition	3.4.4	4.5.6	SSPC-AB 1	No
Crystalline silica	3.4.5	4.5.7	SSPC-AB 1	No
Specific gravity	3.4.6	4.5.8	SSPC-AB 1	No
Conductivity	3.4.7	4.5.9	SSPC-AB 1	Yes
Chloride content	3.4.8	4.5.10	ISO 11127-7	No
Oil content	3.4.9	4.5.11	SSPC-AB 1	Yes
Hardness	3.4.10	4.5.12	SSPC-AB 1	No
Surface profile	3.4.11	4.5.13	SSPC-AB 1	No
Recycled abrasives	3.4.12	4.5.14	SSPC-AB 1	No

NOTES:

1/ California Code of Regulations, Title 22, Division 4.5, Chapter 11, Article 3, Section 66261.24, (a),(2).

2/ California Code of Regulations, Title 22, Division 4.5, Chapter 11, Article 3, Section 66261.24, (a),(1).

4.2.1 Change approval. Failure to maintain listing on California Air Resources Board's (CARB) list of Current Certified Abrasives in accordance with California Code of Regulations (see 3.4.2), or changes in the raw materials, manufacturing process, or manufacturing location of qualified products may require requalification. Unless otherwise specified by the qualifying activity, loss of CARB certification or changes in the raw materials, manufacturing process, or manufacturing location of qualified products requires written approval by NAVSEA to maintain listing as a qualified product.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:44Z
Check the source to verify that this is the current version before use.

4.2.2 Sampling for qualification inspection.

4.2.2.1 Bulk shipment. A 110-pound (50-kilogram) composite sample shall be obtained from the blended, finished product in accordance with ASTM D75/D75M. The sample shall be sealed in a plastic bag and identified (see 4.4).

4.2.2.2 Shipment in sacks. Two or more sacks of abrasive shall be randomly selected from each inspection lot. The sacks shall be mixed and separated to create a 110-pound (50-kilogram) composite sample prepared in accordance with ASTM C702/C702M. The sample shall be sealed in a plastic bag and identified (see 4.4).

4.2.3 General inspection. The abrasive material's ID characteristics shall be reviewed to ensure conformance to the requirements in 3.3.

4.3 Conformance inspection. Conformance inspection shall consist of the tests specified in 4.5.3, 4.5.5, 4.5.9, and 4.5.11, which are also specified in table III. Conformance testing shall be performed on the first lot and every 110,000 pounds (50,000 kilograms) thereafter.

4.3.1 Sampling for conformance inspection. A 6.6-pound (3-kilogram) composite sample shall be obtained from the blended, finished product in accordance with ASTM D75/D75M. The sample shall be sealed in a plastic bag and identified (see 4.4).

4.3.2 Lot. For purposes of conformance inspection, a lot shall consist of abrasive materials of the same type, all from a single uniform batch that is produced and offered for delivery at one time. The addition of any substance to a batch shall constitute a new lot.

4.4 Disposition of samples. All samples prepared in accordance with 4.2.2.1, 4.2.2.2, and 4.3.1 shall be forwarded to the test activity. The plastic sample bag shall be plainly marked with the following:

a. Sample for verification of acceptance tests.
b. Title, number, and date of specification.
c. Classification of material.
d. Lot number.
e. Commercial and Government Entity (CAGE) code and name of manufacturer.
f. Date.

4.5 Test methods.

4.5.1 Toxicity and restricted materials.

4.5.1.1 Toxicity. A Health Hazard Assessment (HHA) will be conducted to ensure conformance to 3.2.1.1 as required by the qualifying activity. The Navy and Marine Corps Force Health Protection Command (NMCFHPC) will evaluate the abrasive material using data provided by the manufacturer/distributor to the NMCFHPC (see 3.2.1.1 and 6.7).

4.5.1.2 Restricted materials. Restricted materials shall be verified for conformance to 3.2.1.2 as required by the qualifying activity.

4.5.2 Hazardous constituents.

4.5.2.1 Soluble and total metal content. Soluble and total metal content of the abrasive material shall be determined in accordance with California Code of Regulations, Title 22, Division 4.5, Chapter 11, Article 3, Section 66261.24, (a),(2). The results shall meet the requirements of 3.2.2.1.

4.5.2.2 Maximum concentration of contaminants. The contaminant content of the abrasive material shall be determined in accordance with California Code of Regulations, Title 22, Division 4.5, Chapter 11, Article 3, Section 66261.24, (a),(1). The results shall meet the requirements of 3.2.2.2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:44Z
Check the source to verify that this is the current version before use.

4.5.2.3 Radioactivity. Gross gamma radioactivity and Cobalt-60 radioactivity shall be determined in accordance with EPA Method 901.1 on solid, undigested abrasive and reported as picocuries per gram. Gross gamma radioactivity shall be determined by summing the net gamma photons of energies from 0.1 Million electron volts (MeV) to 2.1 MeV. The specific Cobalt-60 activity shall be based on the photo peak produced by the 1.332 MeV gamma photon. Limits of detectability, such as minimum detectable activity, shall be determined at the 90 percent confidence level. The results shall meet the requirements of 3.2.3 and 3.2.3.1.

4.5.3 Sieve analysis. The sieve analysis shall be performed in accordance with SSPC-AB 1. The results shall meet the requirements of 3.4.1.

4.5.4 Friability. The friability test shall be performed in accordance with Test Method No. California 371-A and the California Code of Regulations, Title 17, Division 3, Chapter 1, Subchapter 6, Article 4, Section 92530. The results shall meet the requirements of 3.4.2.

4.5.5 Moisture content. The moisture content shall be determined in accordance with SSPC-AB 1. The results shall meet the requirements of 3.4.3.

4.5.6 Weight change on ignition. Weight change on ignition shall be determined in accordance with SSPC-AB 1. The results shall meet the requirements of 3.4.4.

4.5.7 Crystalline silica. The crystalline silica contents shall be determined in accordance with SSPC-AB 1. The results shall meet the requirements of 3.4.5.

4.5.8 Specific gravity. Specific gravity of the abrasive material shall be determined in accordance with SSPC-AB 1. The results shall meet the requirements of 3.4.6.

4.5.9 Conductivity. Glassware used in this test shall be rinsed with deionized water. The conductivity shall be determined in accordance with SSPC-AB 1. The results shall meet the requirements of 3.4.7.

4.5.10 Chloride content. Chloride content shall be determined in accordance with ISO 11127-7. The results shall meet the requirements of 3.4.8.

4.5.11 Oil content. Oil content shall be determined in accordance with SSPC-AB 1. The results shall meet the requirements of 3.4.9.

4.5.12 Hardness. Hardness shall be determined in accordance with SSPC-AB 1. The results shall meet the requirements of 3.4.10.

4.5.13 Surface profile. The surface profile shall be determined in accordance with SSPC-AB 1. The results shall meet the requirements of 3.4.11.

4.5.14 Recycled abrasives. Recycled abrasive quality control tests shall be performed in accordance with SSPC-AB 1. The results shall meet the requirements of 3.4.12.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the military service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:44Z
Check the source to verify that this is the current version before use.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. Abrasives covered by this specification are intended for use in dry or wet abrasive blasting operation on interior or exterior surfaces of U.S. Navy ship hulls, tanks, and other components prior to painting. Whenever these products are used, the work plan must comply with all local, state, and federal environmental and worker health and safety regulations. Navy personnel conducting, or in proximity to, abrasive blasting operations must comply with all Navy worker health and safety requirements. Current stock of abrasive blast media may be used until depleted; future requisitions for abrasive blast media should refer to the current version of this specification.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.

b. Type, class, and grade required (see 1.2).

c. ID characteristics (see 3.3).

d. Total size of shipment.

e. Packaging requirements (see 5.1).

f. When a Safety Data Sheet (SDS) is required (see 6.6).

6.3 Definitions.

6.3.1 Qualifying activity. The activity that has been given responsibility to develop, implement, and maintain the qualification program as specified in the applicable specification, and authorized by its Departmental Standardization Officer (DepSO) to input information into the Qualified Products Database (QPD) (see 4.2).

6.3.2 Recycled abrasive. Abrasive material collected during or after blast cleaning that has been cleaned for reuse or blended with new media (see 3.4.12 and 4.5.14).

6.4 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Products List QPL No. 22262 whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from Commander, Naval Sea Systems Command, ATTN: SEA 05S, 1333 Isaac Hull Avenue, SE, Stop 5160, Washington Navy Yard, DC 20376-5160 or emailed to CommandStandards@navy.mil. An online listing of products qualified to this specification may be found in the Qualified Products Database (QPD) at https://assist.dla.mil.

6.5 Manufacturer's trade names. The manufacturer's trade name or designation, which identifies the finished product, is regarded as a permanent and unique identification of the materials tested and cannot be applied to any other material submitted under this specification. Therefore, it is advisable to identify the compound by a code number rather than by the trade name, which may be desired for permanent identification of the material. The use of the specification number in the trade name or designation is prohibited.

6.6 Safety data sheets (SDS). When specified (see 6.2), contracting officers will identify those activities requiring copies of completed SDSs prepared in accordance with appendix D of 29 CFR 1910.1200. In order to obtain the SDS, federal acquisition regulation clause 52.223-3 must be in the contract. The contracting activity should be given an SDS at the time of contract award.

6.7 Toxicity evaluation. The NMCFHPC requires sufficient information to permit an HHA of the product. Upon completion of the HHA, a copy will be provided by the NMCFHPC to the Government for evaluation. The HHA process is described on the NMCFHPC's website, https://www.med.navy.mil/Navy-Marine-Corps-Public-Health-Center/.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:44Z
Check the source to verify that this is the current version before use.

6.8 Subject term (key word) listing.

Aluminum oxide
Amorphous metal oxide
Coal slag
Copper slag
Crushed glass
Garnet
Hematite
Inorganic material
Mineral
Nickel slag
Organic material
Recycled glass
Sand
Silicon carbide
Slag
Staurolite

6.9 Amendment notations. The margins of this specification are marked with vertical lines to indicate modifications generated by this amendment. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations.

CONCLUDING MATERIAL

Custodian:
Navy – SH

Review activity:
DLA – GS

Preparing activity:
Navy – SH
(Project 5350-2025-001)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:44Z
Check the source to verify that this is the current version before use.