NNH-T-001476A(GSA-FSS)
AMENDMENT-2
July 15, 1977
SUPERSEDING
Amendment-1
March 23, 1976

AMENDMENT

TO

INTERIM FEDERAL SPECIFICATION

TEST TUBE (GLASS, DISPOSABLE)

This amendment was developed by the General Services Administration, Federal Supply Service, Washington, DC 20406, based upon currently available technical information. The General Services Administration has authorized this amendment as a part of Interim Federal Specification NNH-T-001476A(GSA-FSS), dated January 30, 1976.

Table I: Delete in its entirety and substitute the following:

Table I. Dimensional requirements

Size	Outside diameter, millimeter (mm) 1/	Length (mm) 2/	Wall Thickness (mm Side	Minimum end
1	6	60	.63 ± .10	.51
2	10	75	.61 ± .08	.51
3	12	75	.69 ± .08	.51
4	13	100	.71 ± .10	.51
5	15	85	.79 ± .10	.53
6	15	125	.79 ± .10	.53
7	16	100	.81 ± .10	.56
8	16	125	.81 ± .10	.56
9	16	150	.81 ± .10	.56
10	18	150	.89 ± .10	.64
11	20	125	.96 ± .10	.69
12	20	150	.96 ± .10	.69

1/ Tolerance ± 0.50 mm
2/ Tolerance ± 2.5 mm

3.9 Delete in its entirety and substitute the following:

"3.9 Workmanship. The test tubes shall be symmetrical in shape, of uniform thickness, and free from striae, streaks, chips, cracks, bubbles, or other defects which detract from their appearance or impair serviceability. The test tubes shall be ready for use free from dirt, cloudiness, or foreign matter on the inside diameter."

Table IV, Category 107: After the work matter, delete the period and add "on the inside diameter."

Table IV, Category 108: Delete in its entirety:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:49Z
Check the source to verify that this is the current version before use.