A-A-2323
September 27, 1985

COMMERCIAL ITEM DESCRIPTION

FILE, HAND (AMERICAN PATTERN), WARDING

The General Services Administration has authorized the use of this commercial item description in preference to Type XX, Styles A, B, and C of Federal Specification GGG-F-325.

This commercial item description covers hand files used for filing ward notches in keys and for filing narrow slots and in close spaces.

Salient characteristics:

Material:	Carbon alloy steel.
Width:	Tapered from heel to point with relatively sharp taper toward the point.
Thickness:	Uniform throughout the length.
Design:	Double-cut on each flat (two sets of parallel cuts on the surface, one set crossing the other). Two square edges single-cut (one set of parallel cuts on the surface). Furnished in either bastard-cut, second-cut, or smooth-cut as shown in table.
Tang:	Of a conventional shape and size suitable for attachment to a wood handle. Tempered to a maximum hardness of 45 on the Rockwell C scale at a point approximately midway of its length and width.
Teeth:	Uniformly cut or etched and of uniform height throughout the fully cut portion. Cutting surfaces hardened to a uniform hardness. The distance between the heel and point of the file, excluding the tang, shall be hardened to not greater than 68 nor less than 64 on the Rockwell C scale. Free from decarburization and brittleness.
Marking:	Marked with the country of origin and the name of the manufacturer or with a trademark of such known character that the source of manufacture may be readily determined.
Workmanship:	The teeth of the file shall be well-defined, sharp, and uniform in height and form. There shall be no evidence of rust or other defect which may impair serviceability, durability, or appearance.



FSC 5110

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:21Z
Check the source to verify that this is the current version before use.

National Stock Number	Length	Dimensions at largest section A	Dimensions at largest section B	Number of teeth per inch Min.	Number of teeth per inch Max.	Allowable distortion (maximum)	Allowable warpage (maximum)
	Inches	Inch	Inch			Inch	Degrees
			Bastard-cut				
5110-00-243-8099	6	5/8	5/64	41	45	0.008	5
5110-00-204-0719	8	25/32	3/32	34	37	.010	5
5110-00-204-0720	10	15/16	1/8	28	31	.015	7
			Second-cut				
5110-00-204-0722	6	5/8	5/64	55	59	.008	5
5110-00-238-9649	8	25/32	3/32	44	48	.010	5
5110-00-204-0723	10	15/16	1/8	36	39	.015	7
			Smooth-cut				
5110-00-204-0726	6	5/8	5/64	68	73	.008	5
5110-00-243-8100	8	25/32	3/32	55	60	.010	5
5110-00-204-0725	10	15/16	1/8	43	48	.015	7

Length dimension: Measured from the point (free or front end) to the heel (junction of the tang with the body of the file) and have a tolerance of plus or minus 1/8 inch.

Tolerance: Width (A) - plus or minus 1/16 inch.
Thickness (B) - files 6 inches in length - plus or minus 1/32 inch. Files over 6 inches in length - plus or minus 1/16 inch.

Regulatory requirements. In accordance with the section 23.403 of the Federal Acquisition Regulations, the Government's policy is to acquire items composed of the highest percentage of recovered materials practicable, consistent with maintaining a satisfactory level of competition without adversely affecting performance requirements or exposing suppliers' employees to undue hazards from the recovered materials.

Preservation, packaging, packing, labeling, and marking. The preservation, packaging, packing, labeling, and marking shall be as specified in the contract or order.

PREPARING ACTIVITY:

GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:21Z
Check the source to verify that this is the current version before use.