P-R-1760
October 6, 1972
SUPERSEDING
Fed. Spec. P-R-201B
March 29, 1961

FEDERAL SPECIFICATION

REMOVER, FLOOR POLISH (RESIN-TYPE AND WAX)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers a material which will remove water emulsion floor finish and floor wax from impermeable floor surfaces.

1.2 Classification. This specification covers one grade of floor polish remover.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

P-F-00430 - Floor Finish, Water Emulsion, Slip Resistant.
P-W-155 - Wax, Floor, Water-Emulsion.
SS-T-312 - Tile, Floor; Asphalt, Rubber, Vinyl, Vinyl-Asbestos.
PPP-B-636 - Box, Fiberboard.
PPP-C-96 - Cans, Metal, 28 Gauge and Lighter.
PPP-C-186 - Containers, Packaging and Packing for Drugs, Chemicals and Pharmaceuticals.
PPP-C-569 - Containers, Plastic, Molded (for Liquid, Pastes and Powders) Overpacked.
PPP-D-729 - Drums; Metal 55-Gallon (For Shipment of Concorrosive Materials.
PPP-D-1152 - Drum-Steel 55-Gallon (24 Gage) Reinforced.
PPP-F-320 - Fiberboard: Corrugated and Solid, Sheet Stock (Container Grade) and Cut Shapes.
PPP-P-704 - Pails, Metal: Shipping, Steel (1 through 12 Gallon).

Federal Standard:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civil Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

☆U.S. GOVERNMENT PRINTING OFFICE: 1981—703-023/3120

FSC 7930

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:19Z
Check the source to verify that this is the current version before use.

Military Standard:

MIL-STD-105 - Sampling Procedures and Tables for Inspection for Attributes.
Mil-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

National Motor Freight Traffic Association, Inc., Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Association, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 202, Union Station, 516 W. Jackson Blvd., Chicago, IL 60606.)

American Society For Testing and Materials (ASTM):

D 1436 - Application of Emulsion Floor Polishes to Substrates for Testing Purposes.
D 1792 - Potential Long-Term Removability Properties of Conventional Type Water-Emulsion Floor Polishes.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Material. The compound shall be an homogenous, free-flowing liquid. When put on the floor being stripped, it should form a uniform layer or sheet of liquid, without beading or puddling.

3.1.1 Ammonia. The compound shall contain no volatile ammonia when tested as specified in 4.2.

3.2 Removal efficiency. The compound shall completely remove single layers of the standard sample floor finish for P-F-00430 and the standard sample floor wax for P-W-155 when tested as specified in 4.3. The determination of complete removal shall be made visually (see 6.3).

3.3 Deleterious action. The surfaces of linoleum, vinyl-asbestos and asphalt tile shall not show softening, swelling, blistering, cracking, pitting, solvent action or color change when tested as specified in 4.4.

3.4 Storage life. The compound shall not deteriorate or lose its original effectiveness when stored for one year in a closed shipping container at room temperature.

3.5 Odor. The compound shall have no objectionable odor, nor shall it develop an objectionable odor in water solutions, in use, or when stored in the original container.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:19Z
Check the source to verify that this is the current version before use.

utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Ammonia. Mix 2 ml. of compound with 10 ml. of 10-percent sodium hydroxide. Distill and catch the distillate (1-2 ml) in a tube containing 5 ml. of ammonia-free distilled water. Add a few ml. of Nessler's reagent to the tube containing the distillate. A brown color indicates ammonia. Yellow or white colors indicate volatile amines, and are not cause for rejection.

4.2.1 Nessler's reagent. Dissolve 50 g. of potassium iodide in 50 ml of cold distilled water. Add a saturated solution of mercuric chloride (about 22 g. in 350 ml. will be needed) until an excess is indicated by the formation of a precipitate. Then add 200 ml. of 5N sodium hydroxide and dilute to one liter. Let settle and draw off the clear liquid.

4.3 Removal efficiency. Removal efficiency shall be determined in accordance with ASTM D 1792, except (1) the substrate shall be black OTVAT 1/, (2) the compound, diluted 12 to 1 with tap water, shall be used in place of the standard soap solution, (3) the diluted compound shall have a 5-minute presoak on the substrate, (4) the total number of strokes required for complete removal shall be not more than 20, and (5) the substrate shall be coated with the standard sample of wax and floor finish in accordance with ASTM D 1436, method D, applying 0.4 ml. of sample to each 6 x 6 inch panel of substrate. Allow to dry for 24 hours at 23° + 2°C. and 50 + 5 percent relative humidity. The standard samples shall be for P-W-155A for the wax and for P-F-00430 for the floor finish (see 6.3).

1/ Official Test Vinyl Abestos Tiles (OTVAT) may purchased from the Chemical Specialties Manufacturer's Association, 50 East 41st Street, New ~~New~~, NY 10017.

4.4 Deleterious action. Prepare 2 x 4 x 1/8 inch test coupons from asphalt and vinyl asbestos tile conforming to SS-T-312, and from OTL linoleum 2/. Place these coupons in separate 250 ml. beakers and add 150 ml. of compound, diluted 12 to 1 to each beaker. Prepare the 12 to 1 solution by adding 50 ml. of compound to 600 ml. of distilled water. Allow to stand for 4 hours at room temperature (70°-80°F.), rinse thoroughly with distilled water and allow to dry for one hour at room temperature. Examine the dry coupons and residual solution for evidence of deleterious action.

2/ Official Test Linoleum (OTL) may be purchased from the Chemical Specialties Manufacturer's Association, address above.

4.5 Examination of preparation for delivery. An examination shall be made to determine whether the packaging, packing, and marking comply with the requirements of section 5. Defects shall be scored as specified in table I. Sampling shall be in accordance with MIL-STD-105. The sample unit shall be one container fully prepared for delivery. The lot shall be the number of containers offered for inspection at one time. The inspection level shall be S-2 with an AQL of 4.0 expressed in terms of defects per hundred units.

TABLE I. Examination for preparation for delivery

Examine	Defects
Contents	Not as specified.
Container	Not as specified.
Markings	Omitted; incorrect; illegible; improper size, location, sequence or method of application.
Materials	Component missing or damaged.
Workmanship	Bulging or distortion of containers.
	Cushioning inadequate, improper or missing.

4.5.1 Examination for closure and reinforcement of containers. When shipping containers are required to comply with PPP-B-636, examination for defects in closure and reinforcement shall be in accordance with the appendix of that specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:19Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B, or C, as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Unit Containers. One gallon of polish remover shall be packaged in a container conforming to PPP-C-96, type V, class 4 or 5 with exterior coating, plan B for level A.

5.1.1.2 Bulk containers. Five-gallons of polish remover shall be packaged in containers conforming to PPP-B-704, type 1, class 3 with container equipped with spout or nozzle closure, with outer seal. Color of exterior coating shall be olive drab. Fifty-five gallons of polish remover shall be packaged containers conforming to PPP-D-729, type II or IV.

5.1.2 Level B.

5.1.2.1 Unit containers. One gallon of polish remover shall be packaged in a container conforming to PPP-C-96, type V, class 4 or 5 and Level B of the appendix. Alternatively, one gallon of polish remover shall be packaged in a high density polyethylene bottle (0.95 density minimum) with handle. The cap shall conform to closure A with seal A of PPP-C-186.

5.1.2.2 Bulk containers.

5.1.2.2.1 Five gallons of polish remover shall be packaged in containers conforming to PPP-P-704, type 1, class 3 with container equipped with spout or nozzle closure, with outer seal except the exterior color of the pail is optional. Alternatively, five gallons of polish remover shall be packed in a container conforming to PPP-C-569.

5.1.2.2.2 Fifty-five gallons of polish remover shall be packaged in a drum conforming to PPP-D-729, type II. Alternatively, fifty-five gallons of polish remover shall be packaged in a drum conforming to PPP-D-001152.

5.1.3 Level C. Polish remover shall be packaged to afford adequate protection against damage during shipment from the supply source to the first receing agency.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 Level A.

5.2.1.1 Unit containers. Six filled metal cans shall be packed in accordance with PPP-C-96, appendix, level A, unpackaged cans.

5.2.1.2 Bulk containers. Five or 55-gallon containers shall require no additional packing.

5.2.2 Level B.

5.2.2.1 Unit containers. Six filled metal cans shall be packed in accordance with PPP-C-96, appendix, Level B unpackaged cans. Six filled plastic bottles shall be packed in a box conforming to PPP-B-636, class domestic, type CF, variety DW, grade 275 which shall be fitted with an angle "H" fiberbard divider forming four cells for the bottles, the full depth of the box. This divider shall conform to PPP-F-320, type CF, variety DW, grade 200, class domestic. A 3/8 inch clearance shall be provided between the top of the bottles and the surface of the inner flaps. Alternatively, six filled plastic bottles shall be packed in a box conforming to PPP-B-636, type CF, variety SW, grade 200, class domestic with top and bottom pads, an inner liner and regular slotted partitions.

5.2.2.2 Bulk containers. Five or 55-gallon containers shall require no additional packing.

5.2.3 Level C. Polish remover, in quantities as specified (see 6.2), packaged as specified in 5.1, shall be packed in containers to assure carrier acceptance and safe arrival at destination in compliance with Uniform Freight Classification or National Motor Freight Classification, as applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:19Z
Check the source to verify that this is the current version before use.

5.3 Marking. In addition to any special markings required in the procurement documents, marking of the interior packages and exterior shipping containers shall be in accordance with Fed. Std. No. 123 for civil agencies or MIL-STD-129 for military agencies, as applicable (see 6.2).

5.3.1 Labels on polish remover containers shall prominently display the legend: DILUTE 12 to 1 FOR USE.

6. NOTES

6.1 Intended use. The compound covered by this specification is intended to remove films of water emulsion wax and floor finish from impermeable floor surfaces.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Size of container required.
(c) Quantity of removing compound required.
(d) Levels of packaging and packing required (see 5.1 and 5.2).
(e) Special marking required (see 5.3).

6.3 Standard sample. The standard samples specified in 3.2 are available at cost in 1-gallon cans. Inquiry should be addressed to the Director, Standardization Division, Federal Supply Service, General Services Administration, Washington, DC 20406.

MILITARY INTEREST:

Army - GL
Navy - SH
Air Force - 84

Preparing activity:

GSA-FSS

Coordinating activities

HEW-FDA
NASA-JFK

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See Section 2 of this specification to obtain extra copies and other documents referenced herein. Price 10 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:19Z
Check the source to verify that this is the current version before use.