[METRIC]
A-A-2858
January 18, 1994

COMMERCIAL ITEM DESCRIPTION

TAPE, PAPER, COMPUTING MACHINE

The General Services Administration has authorized the use of this commercial item description, for all Federal Agencies. This document replaces Federal Specification UU-T-110C, which is cancelled.

1. Scope. This Commercial Item Description covers four types of tapes that are used with various adding and computing machines, including electronic printing calculators.

2. Classification. Paper tapes shall be furnished in the following types:

Type I - Chemical wood
Type II - Fibrous cellulosic material
Type III - Chemical transfer, carbonless
Type IV - Chemical Self-Imaging, Carbonless

3. Requirements.

3.1 Material. Materials used shall conform to the requirements specified herein. No polychlorinated biphenyls (PCB's) shall be added or used during the manufacture of the paper or in any coating operation on the base paper. As evidence of compliance, the contractor shall submit a certificate stating that no polychlorinated biphenyls have been added or used during the manufacturing or converting operations.

3.1.1 Type I. The paper stock shall be 100% chemical wood pulp, free from groundwood.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to General Services Administration Federal Supply Service, Engineering Branch, 26 Federal Plaza New York, N.Y. 10278.

Distribution Statement A:
Approved for public release;
Distribution is unlimited.

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.

3.1.2 Type II. The paper stock shall be made from fibrous cellulosic material.

3.1.3 Type III. Carbonless paper tape shall be of the chemical transfer type to be used with machine ribbon.

3.1.4 Type IV. Carbonless paper tape shall be of the chemical self-imaging type to be used without machine ribbon.

3.2 Physical properties. The physical properties of tapes shall be as specified in Table I. The tape shall be white.

TABLE I

Characteristic	Type I	Type II	Types III & IV	Test Method
Basis weight g/m2 (lbs) (17x22-500) +/- 5%	60 (16#)	60 (16#)	45-60 (12-16)*	T410
Burst, min. Kpa (psi)	110 (16)	69 (10)	83 (12)	T403
Tear,gms.,min. CD MD	50 44	28 23	21 18	T404
Brightness,min percent	75	60	72	T452
Thickness, microns (inches)	74-99 (0029-.0039)	74-114 (.0029-.0045)	64-102 (.0025-.0040)	T411

*Tolerance does not apply.

3.3 Widths. The width of the tape shall be as specified in the ordering data. A tolerance of +/- 0.8mm (+/- 1/32 inch) shall be allowed.

3.4 Rolls. The paper tape shall be wound evenly and tightly on a core conforming to 3.4.1. Types I and II rolls shall be wound with the felt side facing out. Type III rolls shall consist of two plies of chemically-coated carbonless transfer paper. The top

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.

(outer) ply of the roll shall be coated on the back side with a transmitting chemical. The bottom ply of the roll shall be coated on the front side with a receiving chemical and shall be positioned to react with the transmitting chemical of the top ply to produce an image on the bottom ply. Type IV rolls shall be wound with the coated side facing out. The overall outside diameter for Type I rolls shall be 8.25 cm (3 1/4 inches) maximum and for types II, III and IV rolls shall be 8.89 cm (3 1/2 inches) maximum. The minimum length of tape for a Type I tape shall be 48.8 meters (160 feet); for Type II the minimum shall be 50.3 meters (165 feet); for Type III the minimum length shall be 34.1 meters (112 feet) (two-ply only) and for Type IV the minimum length shall be 56.4 meters (185 feet) (one-ply only). The paper tape shall be one continuous length without splices, joints, seams or tears. The roll shall advance properly in use.

3.4.1 Cores. The core may be wooden, fiber, hard wound paper, plastic or any other materials which are not susceptible to cracking, splitting or shrinkage under ordinary conditions of shipment and use. The round core shall be approximately 2.2 cm (7/8 inch) in outside diameter with a 0.95 to 1.1 cm (3/8 to 7/16 inch) diameter spindle hole in the center of the core. The length of the core shall be the same as the width of the tape, with a +/- 0.79 mm (1/32 inch) tolerance.

3.4.2 Construction. The inside end of the paper shall be tucked or attached to the core at the time of winding. The outside end of the paper tape shall be sealed in such a manner as to allow enough unglued paper to serve as a pull tab for unsealing the roll at time of initial use, or spot-sealed by use of button style, latex-coated, or gummed labels.

3.4.3 Warning signal. A warning signal, 0.9 to 3 meters (3 to 10 feet) long, not less than 0.3 cm (1/8 inch) wide, shall be applied starting within 1.5 meters (5 feet) from the core end of the tape to warn the operator of the approaching end of the tape. The color of the warning signal shall be a distinguished color which will not affect the readability of the printed figures.

3.5 Printing quality. When printed by means of a computing machine ribbon, the ink shall be quickly absorbed without smearing or blurring of the printed figures. Print shall be clear-cut and legible. Image production shall be by chemical interaction on the carbonless types III and IV tapes and the prints shall be legible.

3.6 Writing quality. The paper tape shall be suitable for writing on with ink, or ball point pen. To be considered acceptable, the lines or characters shall be clear-cut and legible without feathering, spreading, beading, visible discontinuities or fading of ink.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.

3.7 Workmanship. The paper tape shall be clean and free of holes, tears, wrinkles, creases, dirt, foreign particles, fluff, lint, paper dust, grit, spots, slime spots, calendered scorches, or other imperfections that may adversely affect appearance or serviceability. The finish of the tape shall be smooth, uncockled and nonglazed. The edges of the rolls shall be cut cleanly and smoothly without nicks or ragged edges.

4. Quality Assurance Provisions.

4.1 Inspection.

4.1.1 Contractor Certification. The contractor shall certify and maintain substantiating evidence that the product offered meets the salient characteristics of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices. The government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

4.1.2 Responsibility for Inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all the inspection requirements as specified herein. Except as otherwise specified, the contractor may utilize his own facilities or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government.

Sampling for examination and tests shall be performed in accordance with MIL-STD-105, using the plans specified in Table II, unless otherwise stated. For the purposes of sampling, a lot shall consist of all rolls of paper tape of one size and type offered for delivery at one time. A unit of production shall be one roll, unless otherwise specified. The sample unit shall be one roll of tape, unless otherwise specified.

TABLE II

Examine	Inspection Level	AQL (%defect)/ acceptance
Workmanship/general	S-3	4.0
Dimensions/Type	S-4	2.5
Writing/printing	S-2	2.5
Physical Properties	per Tappi*	per Tappi

* Sampling and testing shall be in accordance with Tappi methods.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.

5. Regulatory Requirements. The contractor shall certify that Type I and Type II paper tape offered shall contain a minimum of 50% recovered paper, including a minimum of 20% postconsumer materials and Type III and Type IV paper tape offered shall contain a minimum of 20% postconsumer materials, in accordance with Executive Order 12873, dated Oct. 20, 1993. If the core is a paper or paperboard product, it shall be made from a minimum of 90% postconsumer recovered materials, in accordance with CFR 40 Part 250. If the core is plastic, it shall contain reclaimed material to the maximum extent possible. The minimum percentages of recovered paper and postconsumer materials cited as requirements in this paragraph shall be marked in a suitable manner, such as stamping, printing, or applied with a pressure sensitive label, on the boxes in which the rolls of tape are packed. The exact manner and location of this labelling on the boxes shall be at the discretion of the contractor. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

6. Applicable Documents and Document Sources. The following documents form a part of this Commercial Item Description to the extent specified herein. Unless otherwise indicated, the issue in effect on the date of invitation for bids or request for proposal shall apply:

6.1 Tappi Standards.

Copies of Tappi Standards are available from the Technical Association of the Pulp and Paper Industry, PO Box 105113, Atlanta, Ga. 30348.

6.2 Federal Standards.

Single copies of Commercial Item Descriptions, federal standards or specifications required by activities outside the Federal Government for bidding purposes are available without charge from General Services Administration Business Service Centers in Boston; New York; Philadelphia; Washington, D. C.; Atlanta; Chicago; Kansas City, MO; Fort Worth; Houston; Denver; Los Angeles; San Francisco; and Auburn, WA.

6.3 Military Standards.

MIL-STD-105, Sampling Procedures and Tables for Inspection by Attributes

Copies of Military Specifications and Standards are available from the Standardization Documents Order Desk, Bldg. 4D, 700 Robbins Ave., Philadelphia, PA 19111-5094.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.

6.4 Code of Federal Regulations, Title 40, Protection of Environment.

Part 250, Guideline for Federal Procurement of Paper and Paper Products containing Recovered Materials. Copies of the U.S. Code of Federal Regulations may be purchased with a VISA, Master CArd, or prepaid check through:

Government Printing Office, Washington, DC 20402
Phone (202) 783-3238
When ordering, ask for:
Title 40, Parts 190-250
Stock Number: 869-013-00-146-0

6.5 Executive Order 12873. Copies of the Federal Register dated Oct. 20, 1993, citing the Executive Order 12873 may be purchased with a VISA, Master Card, check or money order for $4.50 made payable to the Superintendent of Documents and mailed to:
New Orders, Superintendent of Documents, PO Box 371954, Pittsburgh, Pa 15250-7954, or call (202) 783-3238. When ordering, cite: "Volume 58, No. 203, Federal Register, Pages 54911-54919".

7. Bleaching. To obtain an acceptable brightness, or color, in accordance with this document, a chemical bleaching process may be used. When specified in the ordering data, the bleaching process shall not include the use of chlorine, chlorine dioxide, hypochlorite, or other chlorine containing compound. Certification of compliance shall be made available upon request by the Government.

8. Packaging, Packing, and Marking. Packaging, packing, and marking shall be as specified in the contract or order.

9. Notes.
A. Ordering Data. Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:

(1) Title, number, and date of this Commercial Item Description
(2) Type of roll
(3) Width
(4) If non-chlorine bleaching is desired (see Paragraph 7)
(6) Packaging, packing, and marking

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.

B. Item Identifiers/Reference Part Number System (For Cataloging Use Only).

AA2858-1 : This example describes a chemical wood paper tape
: for computing machines.

1- Type I - Chemical wood
2- Type II - Fibrous cellulosic material
3- Type III - Chemical transfer, carbonless
4- Type IV - Chemical Self-Imaging, carbonless

MILITARY INTEREST:

NONE: DoD has no registered interest in revisions and amendments to this Commercial Item Description until further notice.

PREPARING ACTIVITY:

GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.