INCH-POUND

MIL-C-17/196B
20 February 1991
SUPERSEDING
MIL-C-17/196A(EC)
10 August 1987

MILITARY SPECIFICATION SHEET

CABLE, RADIO FREQUENCY, FLEXIBLE, COAXIAL, 50 OHMS, M17/196-00001

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of the following specification listed in that issue of the Department of Defense Index of Specifications and Standards (DODISS) specified in the solicitation: MIL-C-17.




FIGURE 1. Configuration.

TABLE I. Description.

Components	Construction details
Inner conductor	Seven strands of copper-covered steel wire, each strand .0063 inch diameter. Overall diameter: .0189 inch ±.0010.
Dielectric core	Type A-1: Solid polyethylene. Diameter: .060 inch ±.003.
Outer conductor	Single braid of AWG No. 38, tinned copper wire. Diameter: .083 inch maximum. Coverage: 85.6% nominal Carriers: 16 Ends: 4 Picks/inch: 16.3 ±10%

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:30Z
Check the source to verify that this is the current version before use.

TABLE I. Description - Continued.

Components	Construction details
Barrier tape	A .001 inch thick polyester tape faced with a .002 inch thick layer of aluminum. The tape will be applied with a 50% lap, aluminum face toward the outer conductor. Diameter: .093 inch maximum.
Jacket	Cross-linked polyolefin Diameter: .110 inch ±.005. Jacket thickness: .008 inch minimum.

ENGINEERING INFORMATION:

Continuous working voltage: 1,100 V rms, maximum.

Operating frequency: 1 GHz, maximum.

Velocity of propagation: 65.9 percent, nominal.

Power rating: See figure 2.

Operating temperature range: -30°C to +85°C.

Inner conductor properties:

DC resistance (maximum at +20°C): 9.67 ohms per 100 feet.

Elongation: 1 percent, minimum.

Tensile strength: 110 $klb_f/inch^2$, minimum.

Engineering notes: This cable is useful in general purpose, medium low temperature applications. (See connector series "SMA" and "SMB" in accordance with MIL-C-39012.) These cables were redesigned to meet the vertical flame test.

REQUIREMENTS:

Dimensions, configuration, and descriptions: See figure 1 and table I.

Environmental and mechanical:

Visual and mechanical examination: Applicable.

Eccentricity: 10 percent, maximum.

Adhesion of conductors:

Inner conductor to core: 4 pounds, minimum; 12 pounds, maximum.

Aging stability: +98°C ±2°C.

Cold bend: -30°C ±2°C.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:30Z
Check the source to verify that this is the current version before use.

Dimensional stability: +85°C ±2°C.

Inner conductor from core: .062 inch, maximum.

Inner conductor from jacket: .125 inch, maximum.

Contamination: Not applicable.

Flame propagation: Applicable.

Acid gas generation: 2.0 percent, maximum.

Halogen content: 0.2 percent, maximum.

Immersion test:

Tensile strength, percent of unaged minimum: 50

Elongation, percent of unaged minimum: 50

Smoke index: 25 maximum.

Toxicity index: 5 maximum.

Durometer hardness: (Type A) 80 minimum.

Weathering: Applicable.

Abrasion resistance: 75 cycles minimum (jacket only).

Tear strength: 35 pounds per inch minimum.

Heat distortion: 30 percent maximum distortion.

Physical tests on unaged jacket:

Tensile strength: 1,300 psi, minimum.

Elongation, 160 percent, minimum.

Physical tests on aged jacket:

Air oven:

Tensile strength, percent minimum: 60

Elongation, percent minimum: 60

Hot oil immersion:

Tensile strength, percent minimum: 50

Elongation, percent minimum: 50

Tensile strength and elongation: 1,300 psi, 160 percent minimum.

Weight: 0.88 pounds per 100 feet maximum.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:30Z
Check the source to verify that this is the current version before use.




FIGURE 2. Power rating and attenuation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:30Z
Check the source to verify that this is the current version before use.




FIGURE 3. Structural return loss.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:30Z
Check the source to verify that this is the current version before use.

Electrical:

Spark test: 2,000 V rms, minimum.

Voltage withstanding: 4,500 V rms, minimum.

Corona extinction voltage: 1,500 V rms, minimum.

Characteristic impedance: 50 ±2 ohms.

Attenuation: See figure 2.

Structural return loss: See figure 3.

Capacitance 32.2 pF per foot, maximum.

Part or Identifying Number (PIN): M17/196-00001.

NOTE: Revision letters are not used to denote changes due to the extensiveness of the changes.

CONCLUDING MATERIAL

Custodians:
Army - CR
Navy - EC
Air Force - 85

Review activities:
Army - AR, MI
Navy - SH
Air Force - 11, 80, 99
DLA - ES, IS

User activities:
Army - AT, ME
Navy - AS, MC, OS
Air Force - 19

Preparing activity:
Navy - EC

Agent:
DLA - ES

(Project 6145-1176-17)

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:30Z
Check the source to verify that this is the current version before use.