JJ-N-180F
June 27, 1972
SUPERSEDING
Fed. Spec. JJ-N-180E
June 27, 1967

FEDERAL SPECIFICATION

NET, LAUNDRY (NYLON)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope.- This specification covers the requirements for a laundry net in the form of a bag.

1.1.1 Federal specification coverage.- Federal specifications do not include all varieties of the commodity as indicated by the title of the specification, or which are commercially available, but are intended to cover only those generally used by the Federal Government.

1.2 Classification.-

1.2.1 Types, styles, and sizes.- The laundry nets shall be of the following types, styles, and sizes, as specified (see 6.2):

Type I - With grommets.
Type II - Without grommets.
Style A - Leno weave.
Style B - Warp knit.
Size 2 - 12 by 22 inches.
Size 4 - 24 by 36 inches.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

V-T-285 - Thread, polyester.
V-T-295 - Thread, Nylon.

FSC 3510

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:56Z
Check the source to verify that this is the current version before use.

UU-P-268 - Paper, Kraft, Untreated, Wrapping.
PPP-B-636 - Boxes, Shipping, Fiberboard.

Federal Standards:

FED-STD-123 - Marking for Domestic Shipment (Civil Agencies).
FED-STD-191 - Textile Test Methods.
FED-STD-751 - Stitch, Seams, and Stitchings.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, Washington.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specification:

MIL-G-16491 - Grommet, Metallic.

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:56Z
Check the source to verify that this is the current version before use.

National Motor Freight Traffic Association, Inc., Agent

National Motor Freight Classification

(Application for copies should be addressed to the American Trucking Associations, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, D.C. 20036.)

Uniform Classification Committee, Agent

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Comittee, Room 1106, 222 South Riverside Plaza, Chicago, Illinois 60606.)

3. REQUIREMENTS

3.1 Materials.-

3.1.1 Fabric.-

3.1.1.1 Yarn, nylon.- The nylon yarn used for the fabric shall be bright, high tenacity, 260 denier, 17 filament nylon having sufficient twist to meet the requirements of this specification.

3.1.1.2 Construction, fabric.- The construction of the fabric shall be either style A (leno weave) or style B (warp knit), as specified (see 6.2), and conform to the requirements contained in 3.1.1.2.1 or 3.1.1.2.2.

3.1.1.2.1 Style A, leno weave.- The fabric shall be woven with a 1 and 1 leno weave and shall conform to the requirements shown in table I. The selvage to be used as the bottom of the net for size 4 bags shall be reeded alternately 4 ends and 2 ends per dent to a minimum width of 3/4 inch. The selvage for the top pin edge of all sizes shall be reeded 2 ends per dent, skip 1 dent, 2 ends per dent for 2 to 2-1/2 inches, then alternate 4 ends and 2 ends per dent to a minimum width of 3/4 inch.

3.1.1.2.2 Style B, warp knit.- The fabric shall be of the mesh type knitted on a warp-type knitting machine and shall conform to the physical requirements shown in table I.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:56Z
Check the source to verify that this is the current version before use.

TABLE I.- Physical requirements

Weave	Yarns (body) per inch				Weight per square yard		Meshes per square inch		Bursting strength minimum
	Warp		Filling		Ounces				
	Minimum	Maximum	Minimum	Maximum	Minimum	Maximum	Minimum	Maximum	Pounds
Style A (Leno)	46	48	26	28	3.0	3.6	598	675	175
Style B (Warp knit)	--	--	--	--	4.6	5.5	38	50	175

3.1.1.3 Color.- The color of the fabric shall be white (natural).

3.1.1.4 Finish.- The nylon fabric shall be scoured and heat set.

3.1.2 Thread.- The thread shall be nylon thread conforming to type I, II or III, class 1 or 2, subclass A, size E, natural of V-T-295; or polyester thread conforming to type I or II, class 1, subclass A, size E, natural of V-T-285.

3.1.3 Grommets.- Grommets for type I nets shall conform to type I, class 1, size 4 of MIL-G-16491.

3.2 Construction, net.- The fabric shall be made into a rectangular-shaped bag, formed by cutting the material so that the finished net shall conform to the size specified. Leno-weave fabric shall have the finish running lengthwise of the net. The warp-knit fabric shall have the wales running lengthwise of the net. The fabric shall be folded lengthwise and stitched along the bottom and side, with the stitching continued along the folded-side edge for 4 $\pm$ 1/2 inch, or along the two sides and bottom if two pieces are used.

3.2.1 Top.- The top of the net shall be folded to the inside with raw edge turned in and overedged with one row of stitch type 504 and stitching type EFab-1 of FED-STD-751 with 10 to 12 stitches per inch. A second row of stitch type 504 shall be stitched over the first row. The amount of fabric inclosed by the stitching measured from the needle line of stitching to the raw edge of the material shall be not less than 1/2 and not more than 1 inch.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:56Z
Check the source to verify that this is the currentversion before use.

3.2.2 Bottom and sides.- The bottom and sides of the net shall be folded and overedge stitched with one row of stitch type 504 similar to seam type SSp-1 of FED-STD-751 with 10 to 12 stitches per inch. The amount of fabric inclosed by the stitching when measured from the needle line of stitching to the raw edge of the material shall be not less than 5/8 and not more than 1 inch.

3.2.3 Type I net.- Type I net shall have two brass grommets as specified in 3.1.3, positioned as follows: One grommet shall be placed 1 $\pm$ 1/4 inch from the side seam and the top folded edge. The other grommet shall be placed on the opposite side, similarly positioned from the folded edge. The cloth shall not break, tear, or become loosened from the grommets when manual pressure is applied after laundering, as specified in 4.2.4.

3.2.4 Tolerances.- A minus tolerance of 1/2 inch and any plus tolerance in width or length of nets will be permitted (see 1.2.1).

3.3 Workmanship.- The finished nets shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection.- Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance.- Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Inspection.- Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

4.2.1 Inspection of components and materials.- In accordance with 4.1, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document. In addition, the contractor shall submit certificates of compliance for the following:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:56Z
Check the source to verify that this is the current version before use.

Material	Characteristic	Requirement reference
Nylon yarn	Material, identification, luster, tenacity, denier filament, and twist	3.1.1.1
Fabric	Scoured and heat set	3.1.1.4

4.2.2 Examination of the end item.- Defects found during this examination shall be classified in accordance with 4.2.2.1 and 4.2.2.2. The sample unit shall be one net. The lot size shall be expressed in units of one net each. The inspection levels and acceptable quality levels (AQL's) for these examinations shall be in accordance with 4.2.2.3.

4.2.2.1 Visual examination.- The nets shall be visually examined for defects listed in table II.

TABLE II.- Classification of defects

Defects	Classification Major	Minor
Material defects (leno and knit fabrics as applicable):		
Broken or missing yarns or snagged yarn (knit):		
Two or more continuous	X	
Single		X
Thin places		X
Hole, smash, mend, run or dropped stitch	X	
Sleazy or uneven fabric, loose yarns - resulting in loops or slippage of mesh or knit, clearly visible 1/		X
Color - other than white (natural)		X
Workmanship:		
Grease, oil or other foreign matter, spots or stains, except ink stains:		
More than 2 inches in combined directions	X	
More than 1/2 inch but not more than 2 inches in combined directions		X
Ink stains, more than 2 inches in combined directions		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:56Z
Check the source to verify that this is the current version before use.

TABLE II.- Classification of defects (cont'd)

Defects	Classification Major	Minor
Workmanship: (cont'd)		
Cut, tear, or needle chews:		
Resulting in a weak place	X	
Not resulting in a weak place		X
Open seams	X	
NOTE: A seam shall be classified as open when one or more stitches joining a seam are broken or when two or more continuous skipped stitches or run-offs occur.		
Raw edge - more than 2 inches in length		X
NOTE: Raw edges not securely caught in stitching shall be classified as open seams.		
Wrong seam or stitch type		X
Stitches per inch:		
Less than 8	X	
Eight or 9 or more than 12		X
Stitch tension - loose - resulting in loosely secured seam or tight - resulting in puckering, clearly visible 1/	X	
Construction:		
Top:		
Not turned under	X	
Fabric inclosed by stitching less than 1/2 or more than 1 inch		X
Not overedged with one row of stitching		X
Bottom and sides:		
Not folded under	X	
Fabric inclosed by stitching less than 5/8 or more than 1 inch		X
Stitching continued along folded edge for less than 3-1/2 or more than 4-1/2 inches		X
Grommets (type I nets only):		
One or both missing or not securely attached	X	
Located more than 1-1/4 or less than 3/4 inch from the side seam and the top folded edge		X

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:56Z
Check the source to verify that this is the current version before use.

TABLE II.- Classification of defects (cont'd)

Defects	Classification Major	Minor
Net:		
Net formed with filling running other than lengthwise direction of net (leno)	X	
Net formed with wales running other than lengthwise direction of net (knit)	X	
Net not specified type, style and size	X	

1/ At normal inspection distance (approximately 3 feet).

4.2.2.2 Examination for dimensions.- Examination for dimensions shall be in accordance with the classification of defects listed in table III.

TABLE III.- Classification of dimension defects

Defects	Classification Major	Minor
Any measurement less than the specified dimension and twice the minus tolerance	X	
Any measurement less than the specified dimension and minus tolerance, but not less than twice the minus tolerance		X
Any measurement more than the specified dimension including the plus tolerance		X

4.2.2.3 Inspection level and acceptable quality levels.- The inspection levels and AQL's expressed in defects per 100 units shall be as follows:

Examination	Inspection level	AQL	
		Major	Total (major and minor combined)
4.2.2.1	I	2.5	6.5
4.2.2.2	S-3	1.5	4.0

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:56Z
Check the source to verify that this is the current version before use.

4.2.3 Examination of preparation for delivery.- An examination shall be made to determine that the packaging, packing and marking comply with the section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery with the exception that it need not be closed. Defects of closure listed shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the AQL shall be 2.5 defects per hundred units.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.
Materials	Any component missing. Any component damaged.
Workmanship	Inadequate application of components, such as incomplete closure of container flaps, improper taping, loose strapping or inadequate stapling. Bulged or distorted containers.
Content	Number of bundles per shipping container more or less than required. Nets of different type or size in same bundle. 1/ Number of nets per bundle not as required. 1/

1/ Two bundles from each shipping container in the sample shall be examined.

4.2.4 Testing of the end item.- The test methods listed in table IV shall be in accordance with FED-STD-191, except as otherwise noted herein. The values specified in section 3 apply to the average of the number of test specimens selected for a sample unit for test purposes as specified in the applicable test methods. The sample unit shall be two finished nets. The lot size shall be expressed in units of one net each. The sample size shall be as follows and the lot shall be unacceptable if one or more sample units fail to meet any requirement specified:

Lot size (nets)	Sample size (No. of sample units)
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:56Z
Check the source to verify that this is the current version before use.

TABLE IV.- End item testing

Characteristic	Requirement reference	Test method
Fabric weave and type of knit	3.1.1.2.1 and 3.1.1.2.2	Visual 1/
Top selvage weave (style A)	3.1.1.2.1	Visual 1/
Bottom selvage weave (style A)	3.1.1.2.1	Visual 1/
Yarns per inch:		
Warp	3.1.1.2.1	5050 3/
Filling	3.1.1.2.1	5050 3/
Weight, ounces per square yard	3.1.1.2.1 and 3.1.1.2.2	5041 3/
Meshes per square inch	3.1.1.2.2	Visual 2/
Bursting strength, pounds	3.1.1.2.1 and 3.1.1.2.2	5120 3/
Grommet attachment (type I net)	3.2.3	Visual 1/

1/ One determination per sample unit and the results reported as pass or fail.

2/ Five determinations per sample unit and the average reported to the nearest whole number.

3/ Unless otherwise specified, a certificate of compliance shall be submitted and will be accepted as evidence of compliance with stated requirements.

5. PREPARATION FOR DELIVERY

5.1 Packaging.- Packaging shall be level A, B or C, as specified (see 6.2).

5.1.1 Level A.- Twelve nets of one type, style and size only shall be neatly folded and alternately stacked in a bundle and securely tied with cotton tape or twine.

5.1.2 Level B (Civil agencies).- Nets shall be packaged in accordance with 5.1.1 (see 6.2).

5.1.3 Level C.- Nets shall be packaged to afford adequate protection against physical damage during shipment from the supply source to the

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:56Z
Check the source to verify that this is the currentversion before use.

first receiving activity. The supplier may use his standard practice when it meets this requirement.

5.2 Packing.- Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 Level A.- One hundred and forty-four size 2 nets, or 72 size 4 nets of one type and style only, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, grade V2s of PPP-B-636. The inside of each shipping container shall be fitted with a taped box liner conforming to type CF, class weather-resistant, variety DW, grade V15c of PPP-B-636. Each container shall have the contents completely covered on the top and bottom with a sheet of 30-pound minimum basis weight kraft paper conforming to grade B of UU-P-268. Shipping containers shall be closed, waterproofed and reinforced in accordance with the appendix of the container specification.

5.2.2 Level B.- One hundred and forty-four size 2 nets, or 72 size 4 nets of one type and style only, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, class domestic, type CF (variety SW or SF), grade 275 of PPP-B-636. The inside of each shipping container shall be fitted with a taped box liner conforming to type CF, class domestic, variety DW, grade 200 of PPP-B-636. Each container shall have the contents completely covered on the top and bottom with a sheet of 30-pound minimum basis weight kraft paper conforming to grade B of UU-P-268. Shipping containers shall be closed in accordance with method II as specified in the appendix of the container specification.

5.2.2.1 When specified (see 6.2), the shipping container shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with the appendix of the box specification.

5.2.3 Level C.- Nets, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with Uniform Freight Classification Rules or National Motor Freight Classification Rules, as applicable.

5.3 Marking.-

5.3.1 Civil agencies.- In addition to any special marking required by the contract or order, interior packages and shipping container shall be marked in accordance with FED-STD-123.

5.3.2 Military requirements.- In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:56Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use.- The nets are intended for use in laundries when washing items of clothing.

6.2 Ordering data.- Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification
(b) Type, style and size required (see 1.2.1 and 3.1.1.2).
(c) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
(d) When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).
(e) When level B packaging is required for Civil agencies (see 5.1.2).

6.3 Standard pack for Civil agencies.- The standard pack requirements specified in 5.2.2 are intended for use in procurements of stores stock replenishments. Procuring officers should use the standard pack requirements when it is known that the material will be shipped from a supplier to a domestic warehouse, or intermediate storage point for temporary storage.

6.4 Deletions.- Size 1 (10 x 15 inches) and size 3 (18 x 30 inches) of JJ-N-180E were deleted in this revision.

Custodians:

Army - GL
Navy - YD
Air Force - 84

Review activity:

Navy - MC

Preparing activity:

Army - GL

Civil Agency Interest:

GSA-FSS
HEW
VA

Project No. 3510-0145

☆ U. S. GOVERNMENT PRINTING OFFICE : 1972 O - 514-169 (29)

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 15 cents each.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:56Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

Net, Laundry (Nylon) JJ-N-180F

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426

REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:56Z
Check the source to verify that this is the current version before use.