JJ-S-746a
DECEMBER 13, 1956

SUPERSEDING
Int. Fed. Spec. JJ-S-00746a (GSA-FSS)
March 13, 1956, and
Fed. Spec. JJ-S-746
November 29, 1945

FEDERAL SPECIFICATION

STOCKINET, SURGICAL

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope.—This specification covers surgical stockinet for uses in treatment of fractures and wounds.

1.2 Classification

1.2.1 *Types and widths.*—This specification covers the following types and widths of surgical stockinet, as specified in the invitation for bids.

Type I.—Rib knit unbleached (natural color) or bleached.
- 3 inches wide.
- 4 inches wide.
- 6 inches wide.
- 8 inches wide.
- 9 inches wide.
- 10 inches wide.
- 12 inches wide.
- 20 inches wide.

Type II.—Plain or flat knit olive drab.
- 13–14 inches wide.
- 50–54 inches wide.

2. APPLICABLE SPECIFICATIONS AND STANDARDS

2.1 The following specifications and standard of the issues in effect on date of invitation for bids, forms a part of this specification.

Federal Specifications:

CCC-T-191—Textiles, Test Methods.
PPP-B-585—Boxes; Wood, Wirebound.
PPP-B-601—Boxes, Wood, Cleated-Plywood.
PPP-B-621—Boxes, Wood, Nailed and Lock-Corner.

(Activities outside the Federal Government may obtain copies of Federal Specifications and Standards as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications and Standards and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specifications:

MIL-B-10377 — Box, Wood, Cleated, Veneer, Paper Overlaid.
MIL-L-10547 — Liners, Case Waterproof.

Military Standard:

MIL-STD-129 — Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by the contractor in connection with specific procurement functions, should be obtained from the procuring activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:56Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Material.

3.1.1 *Type I.*—Material for type I stockinet shall be carded yarn, thoroughly cleaned and properly knitted. The yarn count shall be as specified in table I.

3.1.2 *Type II.*—The material for type II stockinet shall be carded and combed, thoroughly cleaned, and properly knitted. The yarn count shall be as specified in table I.

3.2 Knitting.

3.2.1 *Type I.*—The type I stockinet shall be rib knit seamless, or circular in a continuous tube of fabric.

3.2.2 *Type II.*—The type II stockinet shall be knit with a plain stitch on a circular or flat machine.

3.3 Color.

3.3.1 *Type I.*—The type I stockinet shall be unbleached (natural color), or bleached.

3.3.2 *Type II.*—The type II stockinet shall be olive drab, stock, yarn, or piece dyed. Sulfur colors shall not be used. The color shall show "good fastness" when tested in accordance with paragraphs 4.3.3 and 4.3.4.

3.4 Length.—Unless otherwise specified, each width shall be supplied in 25-yard rolls containing not more than two pieces, neither of which shall be less than 3 yards in length.

3.4.1 *Elongation.*—A plus or minus tolerance of 15 percent of the requirement in table I will be permitted.

3.5 Physical requirements.—The physical requirements for type I and type II stockinets shall be as specified in table I.

3.6 Cutting.—Type II stockinet shall be slit parallel to the ribs, and put up in rolls the full width of the stockinet.

3.7 Workmanship.—All workmanship shall be first class throughout. The finished knitted fabric shall be clean, free from loose ends, stains, holes and other imperfections and defects.

TABLE I.

Type	Width	Yarn counts	Weight per linear yard	Weight per square yard	Ribs per inch	Loops per inch	Bursting str.	Elongation	
								Parallel ribs	Parallel to loops
	Inches		*Minimum, ounces*	*Minimum, ounces*	*Minimum*	*Minimum*	*Minimum, points*	*Percent*	*Percent*
I	3	12/1 or 14/1 or 16/1.	1.25	.....	16	24	115	75	300
	4	12/1 or 14/1 or 16/1.	1.50	.....	16	24	115	75	300
	6	12/1 or 14/1 or 16/1.	2.50	.....	16	24	115	75	300
	8	12/1 or 14/1 or 16/1.	3.00	.....	16	24	115	75	300
	9	12/1 or 14/1 or 16/1.	3.50	.....	16	24	115	75	300
	10	12/1 or 14/1 or 16/1.	4.00	.....	16	24	115	75	300
	12	12/1 or 14/1 or 16/1.	4.50	.....	16	24	115	75	300
	20	12/1 or 14/1 or 16/1.	8.00	.....	16	24	115	75	300
II	13–14	24/1 or 26/1 or 28/1.	.....	4.4	24	36	75	.....	.....
	50–54	24/1 or 26/1 or 28/1.	.....	4.4	24	36	75	.....	.....

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:56Z
Check the source to verify that this is the current version before use.

4. SAMPLING, INSPECTION AND TEST PROCEDURES

4.1 Sampling.—Unless otherwise specified, 1 roll of each type and width shall be taken at random from each 200 rolls or fraction thereof for inspection and tests to determine compliance with specification requirements.

4.2 Inspection.—Samples shall be carefully inspected for defects in material and workmanship, dimensions, and other applicable requirements.

4.3 Tests.—Tests shall be conducted in accordance with the applicable requirements of Federal Specification CCC–T–191. Before testing for elongation, bursting strength, and weight stockinets shall be unrolled and placed on a flat surface for at least 2 hours to relieve any tension on the material caused from rolling.

4.3.1 *Weight.*—The weight per yard shall be calculated from the average weight of not less than three 1-yard lengths.

4.3.2 *Elongation.*—The elongation shall be determined with an inclination balance, or pendulum type testing machine. The jaws through which the load is applied shall move at a uniform rate of 12, plus or minus 2 inches per minute. The distance between the two pairs of jaws at the start of the test shall be 1 inch. The amount of elongation shall be obtained just before failure of the textile.

4.3.3 *Fastness to weather.*—Test for type II shall be conducted as outlined in method 5672 of Federal Specification CCC–T–191, except that samples shall be exposed for 10, 20, and 30 days.

4.3.4 *Fastness to laundering.*—Test for type II shall be conducted by washing procedure as outlined in method 5550 of Federal Specification CCC–T–191.

4.3.5 *Bursting strength.*—Test for determining the bursting strength shall be either an approved type of pendulum machine equipped with a burst attachment or an approved type of diaphragm bursting tester.

4.3.5.1 *Pendulum type machine.*—The sample shall be securely held by a ring mechanism not less than 1¾ inches in internal diameter and be drawn down against a 1-inch polished steel ball until a burst is produced. The maximum capacity of the machine shall be such that the position of the pendulum shall be not greater than 45 degrees from the vertical when the break occurs. The minimum capacity shall be not less than 20 percent of the above maximum capacity. Method 5120 of Federal Specification CCC–T–191 may be used.

4.3.5.2 *Diaphragm bursting tester.*—The strength shall be determined on an approved type of diaphragm bursting tester. The sample shall be securely held by a top and bottom ring mechanism with openings not less than 1.2 inches in diameter. Method 5122 of Federal Specification CCC–T–191 may be used.

5. PREPARATION FOR DELIVERY

(For definitions and levels, see 6.1.)

5.1 Packaging.

5.1.1 *Unit of issue.*—One (1) roll, as specified in 3.4, constitutes one unit.

5.1.2 *Quantities.*—Packaging and packing quantities shall be as specified in table II.

TABLE II.—*Packaging and packing quantities*

Federal Stock No.	Unit Pack	Intermediate Pack	Shipping Container
	Units		*Units*
6510–203–9000	1	Not required	48
6510–204–0000	1	Not required	24
6510–204–1000	1	Not required	12

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:56Z
Check the source to verify that this is the current version before use.

5.1.2.1 *Packing variation permitted.*—If the required number of units to be shipped is less than the number of units specified to be overpacked in an exterior container, such units shall be packed in an exterior container of suitable size and design, acceptable to a common carrier, which will insure safe delivery to destination.

5.1.3 *Level A.*—Each unit shall be packaged in a bag fabricated from polyethylene tubing of 0.004 inch average thickness, with no wall thickness at any point below 0.00325 inch. Excess air shall be expelled or evacuated, and closure effected by heat sealing.

5.1.4 *Level C.*—Unless otherwise specified, each roll shall be securely wrapped in strong paper and sealed.

5.2 **Packing.**

5.2.1 *Level A.*

5.2.1.1 *Exterior container.*—Exterior container shall be designed for type 2 load and constructed in accordance with Federal Specification PPP–B–585, style 3, for class 3 use; Federal Specification PPP–B–601, table II, using type III, class 1 plywood; Federal Specification PPP–B–621, table III; or Military Specification MIL–B–10377, table II.

5.2.1.2 *Case liner.*—Each box shall be lined with a waterproof case liner conforming to Military Specification MIL–L–10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto.

5.2.1.3 *Strapping.*—Strapping (when required) shall be in accordance with applicable box specification.

NOTE.—Strapping will not be required for shipment forwarded to a receiving activity within the continental limits of the United States for storage redistribution.

5.2.2 *Level B.*

5.2.2.1 *Exterior container.*—Exterior container shall conform to Federal Specification PPP–B–601, table I, using class 1 plywood; or shall be designed for type 2 load and constructed in accordance with Federal Specification PPP–B–621, table I; Federal Specification PPP–B–585, style 3, for class 2 use; or Military MIL–B–10377, table I.

5.2.3 *Level C.*—The subject commodity shall be packed in substantial commercial containers of the type, size and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate to point of delivery called for in the contract or purchase order.

5.3 **Marking.**

5.3.1 *Interior packages.*—Each unit package shall be marked in accordance with section 5 of Military Standard MIL–STD–129.

5.3.2 *Shipping container.*—Shipping container shall be marked in accordance with Military Standard MIL–STD–129. Service color marking and symbol are not required on containers for level A packs when addressed to domestic establishments for the Medical Services of the Armed Forces.

6. NOTES

6.1 Federal Standard 102 should be referred to for definitions and applications of the various levels of packaging protection for supplies and equipment.

6.2 **Ordering data.** — Purchasers should specify type and size required, and should exercise any desired options offered herein. (See 1.2.1, 3.4, 4.1, 5.1, 5.2.)

6.3 It is believed that this specification adequately describes the characteristics necessary to secure the desired material, and that normally no samples will be necessary prior to award to determine compliance with this specification. If, for any particular purpose, samples with bids are necessary, they should be specifically asked for in the invitation for

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:56Z
Check the source to verify that this is the current version before use.

bids, and the particular purpose to be served by the bid sample should be definitely stated, the specification to apply in all other respects.

6.5 **Transportation Description.** — Transportation description applicable to this item is:

Fabrics, cotton, knit, in tubular form, in the original piece (surgical stockinet).

Carload minimum weight—any quantity

Truckload minimum weight — any quantity

6.6 This specification covers the following items appearing in the Armed Services Medical Stock List:

6510–203–9000 STOCKINET, SURGICAL, 3 inches by 25 yards

6510–204–0000 STOCKINET, SURGICAL, 6 inches by 25 yards

6510–204–1000 STOCKINET, SURGICAL, 10 inches by 25 yards

Patent notice.—When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

MILITARY INTERESTS:

Army—M
Navy—Md
Air Force.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:56Z
Check the source to verify that this is the currentversion before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:56Z
Check the source to verify that this is the current version before use.