UU-P-547J
July 17, 1972
SUPERSEDING
Int. Fed. Spec. UU-P-00547H(SA)
July 21, 1965 and
Fed. Spec. UU-P-547G
April 12, 1960

FEDERAL SPECIFICATION

PAPER, TELETYPEWRITER, ROLL

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers single and multi-copy teletypewriter papers in roll form.

1.2 Classification.

1.2.1 Types, classes, grades, and styles. Teletypewriter papers in roll form shall be of the following types, classes, grades, and styles, as specified (see 6.2).

Type I - Friction feed.
  Class 1 - Single copy.
    Grade A - 100 percent bleached chemical wood fibers.
    Grade B - Processed wood fibers.
  Class 2 - Multi-copy, regular weight (carbon interleaved).
    Grade A - 100 percent bleached chemical wood fibers.
    Grade B - Processed wood fibers.
  Class 3 - Auto-copy.
  Class 4 - Multi-copy, special weight (carbon interleaved).
  Class 5 - Multi-copy, carbonless, surface coated.
    Grade A - 100 percent bleached chemical wood fibers.
    Grade B - Processed wood fibers.
  Class 6 - Multi-copy, carbonless, self imaging.
      Style A - For ribbon-equipped teleprinters.
      Style B - For ribbonless teleprinters.
Type II - Sprocket feed.
  Class 1 - Single copy.
    Grade A - 100 percent bleached chemical wood fibers.
    Grade B - Processed wood fibers.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

UU-P-121 - Paper, Bond and Writing, White and Colored.
UU-P-328 - Paper, Manifold.
PPP-B-636 - Box, Fiberboard.
PPP-P-001660 - Pallet, Expendable.

Federal Standards:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civil Agencies).

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards.

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

National Motor Freight Traffic Association, Inc., Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Associations, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza., Chicago, IL 60606.)

Technical Association of the Pulp and Paper Industry (TAPPI) Standards:

T401 - Fiber Analysis of Paper and Paperboard.
T402 - Standard Conditioning and Testing Atmospheres for Paper, Board, Pulp Handsheets and Related Products.
T404 - Tensile Breaking Strength of Paper and Paperboard.
T410 - Weight per Unit Area (Basis Weight or Substance) of Paper and Paperboard.
T411 - Thickness (Caliper) of Paper and Paperboard.
T414 - Internal Tearing Resistance of Paper.

(Application for copies should be addressed to the Technical Association of the Pulp and Paper Industry, One Dunwoody Park, Atlanta, GA 30341.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and among Federal agencies.)

3. REQUIREMENTS

3.1 Material. Materials used shall conform to the requirements specified herein. Materials not definitely specified shall be of a quality used for the purpose in commercial practice. The teletypewriter rolls shall be free from poly-chlorinated biphenyls (PCB's) when tested as specified in 4.1.2.2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

3.1.1 Paper.

3.1.1.1 Stock. The stock for papers used in type I, classes 1 and 2, grade A; type II, class 1, grade A; and type I, classes 4, 5, and 6, grade A, shall be 100 percent bleached chemical wood fibers. Stock used for type I, classes 1, 2, and 5, grade B; and type II, class 1, grade B, shall be made from processed wood fibers which may include reclaimed fibers. Manifold paper used in type I, class 4 papers shall conform to the requirements for type V manifold paper specified in UU-P-328.

3.1.1.2 Physical characteristics. Teletypewriter papers shall, when tested in accordance with 4.2.1, conform to the requirements of table I for basis weight, thickness, and tearing resistance for the applicable type, class, grade, and style.

TABLE I. Physical requirements

Types	Classes	Grades, Styles and Plies	Basis weight, (pounds, 17x22-1000, ± 5 percent)	Caliper or thickness, (inches)	Tear strength, (grams) Machine direction	Tear strength, (grams) Cross direction
I and II	1	Grade A, all plies	36	0.0030-0.0044	28	34
I and II	1	Grade B, all plies	36	.0030- .0044	26	36
I	2	Grade A	32	.0030- .0038	24	30
I	2	Grade B	32	.0030- .0038	24	32
I	3	Top sheet	32	.0030- .0038	20	22
I	3	Auto-copy sheets	26	.0015- .0025	18	18
I	4	First sheet	32	.0030- .0038	20	20
I	4	Inner plies	18	----------	--	--
I	5	Grade A, first sheet	30	.0026- .0042	20	25
I	5	Grade A, inner plies	28-36 1/	.0025- .0042	20	25
I	5	Grade A, bottom sheet	30	.0023- .0034	20	25
I	5	Grade B, first sheet	28	.0031- .0038	18	22
I	5	Grade B, inner plies	32	.0031- .0038	18	22
I	5	Grade B, bottom sheet	30	.0022- .0035	18	22
I	6	Style A, first sheet white	30	.0027- .0035	20	25
I	6	Style A, first sheet colored	30	.0027- .0035	20	20
I	6	Style A, inner plies	22-30 1/	.0023- .0041	16	18
I	6	Style B, all plies	24	.0023- .0041	16	18

1/ Tolerance does not apply.

3.1.1.3 Finish and printing quality. The finish of teletypewriter papers shall be smooth but not glazed. The surfaces shall be free of lint and shall not pick in the teleprinter machines. The surface shall absorb teletype ribbon ink quickly without smearing or blurring of the printed characters when tested for performance in accordance with 4.4.2.

3.1.2 Carbon paper. Carbon paper used for type I, classes 2 and 4 multi-copy teletypewriter rolls shall be black and shall have a decoated basis weight of not more than 21.0 pounds (20 x 30 - 1000), and shall be coated to produce clear, legible copies on each ply of the multi-copy set specified. The carbon paper shall not bleed, offset or transfer when tested in accordance with 4.4.1.

3.2 Construction. Teletypewriter papers shall be furnished in rolls. Multi-copy rolls shall be assembled as indicated below with the number of plies necessary to furnish the number of copies specified (see 6.2). Type I rolls shall be constructed for use in friction feed teletypewriters and type II rolls shall be perforated for use in sprocket feed teletypewriters. Materials used shall conform to the requirements in 3.1.

3.2.1 Type I. Friction feed rolls shall be of the following classes.

3.2.1.1 Class 1. Class 1 rolls shall be single ply, and shall be furnished in a grade A or B paper, as specified (see 6.2).

3.2.1.2 Class 2. Class 2 rolls shall consist of two to four plies of either a grade A or B paper, as specified (see 6.2), interleaved with carbon papers.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

3.2.1.3 Class 3. Class 3 rolls shall be a multi-copy roll consisting of a top ply of paper conforming to table I, followed by from two to eight plies of auto-copy papers. The auto-copy papers shall have a wax coating which will produce legible copy of the teletyped characters.

3.2.1.4 Class 4. Class 4 multi-copy rolls shall consist of a first ply conforming to table I, and from one to four plies of manifold papers, interleaved with carbon papers.

3.2.1.5 Class 5. Class 5 multi-copy rolls shall consist of two to nine plies of surface-coated papers. The papers shall be coated with chemically reactive materials to effect transfer of messages to underlying plies. The first ply shall be coated on the back and the bottom ply shall be coated on the front. Middle plies shall be coated front and back.

3.2.1.6 Class 6. Class 6 multi-copy rolls shall consist of two to nine plies of a pressure activated self-imaging paper. The self-imaging paper shall be so fabricated that impact of the teletypewriter type or stylus pressure on the top ply of the multi-copy form shall develop images of the imprinted characters on subsequent underlying plies. Class 6 rolls shall be furnished in style A or B, as specified (see 6.2). Style A shall consist of a top ply of grade A, white or grade B, colored nonactivated paper specified in table I and subsequent plies of self-imaging paper. Style B rolls shall have all plies of self-imaging paper.

3.2.2 Type II. Sprocket feed rolls shall be of one class only.

3.2.2.1 Class 1. Class 1 rolls shall be single copy and shall be furnished in a grade A or B paper, as specified (see 6.2).

3.2.2.2 Sprocket holes. Type II rolls shall have sprocket feed holes in the left and right aligning margins. The holes shall have the following dimensions and positions:

(a) Hole diameter - 5/32 inch ± 1/64 inch.
(b) Distance between hole centers lengthwise with the paper - 1/2 inch ± 1/64 inch.
(c) Edge of paper to center of holes - 1/4 inch ± 1/64 inch.
(d) Center to center distance of holes across the width - 8 inches ± 1/64 inch for the 8-1/2 inch nominal width rolls; 12 inches ± 1/64 inch for the 12-1/2 inch nominal width rolls.

In addition the centers of the aligning left and right margin sprocket holes shall be on a line perpendicular to the edge of the paper with a tolerance of ± 1/64 inch.

3.3 Width.

3.3.1 Type I. Type I rolls shall be not less than 8-25/64 inches nor more than 8-31/64 inches in width.

3.3.2 Type II. Type II rolls shall be not less than 8-25/64 inches nor more than 8-31/64 inches in width or 12-1/2 inches ± 3/64 inches in width, as specified (see 6.2).

3.4 Colors. Teletypewriter rolls shall be furnished in the colors below, as specified (see 6.2). When multi-copy plies of different colors are required, the colors shall be specified, starting with the outermost ply of the roll.

3.4.1 Class 1. Class 1 rolls shall be canary, white, or pastel green.

3.4.2 Classes 2, 4, 5, and 6. Classes 2, 4, 5, and 6 rolls shall be canary, white, goldenrod, pink or blue.

3.4.3 Class 3. The color of the first ply shall be canary, white, goldenrod, pink or blue. Subsequent plies of autocopy paper shall be blue, red, or black.

3.5 Rolls. Teletypewriter rolls shall be one continuous length. Individual plies shall not be spliced. The edges of the plies shall be shear cut. Rolls shall be wound tightly and evenly and plies of multi-copy rolls shall be of equal width. Single copy rolls shall have the outer end secured by spot gluing that will keep the roll from unraveling, yet permit separation, without the need for cutting the top layers of the roll. Multi-copy rolls shall have the outer end secured with a gummed sticker or label. All rolls shall have a contrasting color signal imprinted on the outermost ply to indicate approach to the end of the roll. The signal shall be not less than 1/4 inch wide and shall be 5 to 10 feet in length ending not less than 5 feet of the core end of the roll.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

3.5.1 Cores. Nominal 8-1/2 inch wide rolls shall be wound on a fiber core having an inside diameter of 1 inch ± 0.05 inch, and a wall thickness of 1/8 inch ± 1/32 inch. Nominal 12-1/2 inch wide rolls (type II only) shall be wound on a cardboard or fiber tube having an inside diameter of 4 inches ± 1/16 inch and a wall thickness of 3/8 inch ± 1/16 inch. Cores shall have the same width as the roll width specified, with a plus 0 or minus 1/16 inch tolerance.

3.5.2 Diameter and length. Type I rolls shall have an outside diameter of not more than 5 inches. The minimum length of paper on the rolls of each class shall be as indicated in table II.

TABLE II. Length (in feet) of paper on 5-inch diameter rolls

Copies	Class 1	Class 2	Class 3	Class 4	Class 5	Class 6	
						Style A	Style B
1	325	---	---	---	---	---	---
2	---	200	249	209	239	221	209
3	---	130	178	130	154	144	139
4	---	95	139	95	113	107	94
5	---	---	114	75	90	85	84
6	---	---	96	---	75	71	69
7	---	---	83	---	64	61	60
8	---	---	73	---	56	53	52
9	---	---	66	---	49	47	47

3.5.2.1 Type II. The 12-1/2 inch width type II roll shall have a length of not less than 3520 feet and a diameter of not less than 15 inches but not more than 15-1/8 inches. The 8-25/64 inch width type II roll shall have a length of not less than 357 feet and a diameter of not more than 5 inches.

3.6 Performance. Rolls of teletypewriter paper except types I and II, class 1 in the number of copies specified, shall, when tested in accordance with 4.4.2, develop legible teletype copy on all plies of the roll.

3.6.1 Copyability. The original and all copies, shall reproduce legible copy when imaged on a Xerox copier in accordance with 4.4.2.3.

3.7 Workmanship. Teletypewriter paper rolls shall be free of any defects that may effect serviceability. The plies shall be clean, free of fluff, paper dust, grit spots, wrinkles, folds, holes, tears, smudges, offset and carbon transfer. The edges of the roll shall not be nicked or uneven and the plies shall be clean cut.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated.

4.1.2 Inspection of components and materials. In accordance with 4.1 above, the supplier is responsible for insuring that components and materials used were manufactured, examined and tested in accordance with this specification or referenced subsidiary specifications and standards.

4.1.2.1 Component testing. Each lot of paper or, as applicable, carbon paper used in the fabrication of teletypewriter paper rolls shall be tested in accordance with the applicable test methods specified hereinafter, to determine compliance with the requirements of section 3. Each inspection lot shall consist of a component of a single type or grade manufactured by the same source, under essentially the same conditions and used in the production of the quantity of the end item submitted for inspection at one time.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

4.1.2.2 Evidence of compliance. In lieu of using his own facilities, the contractor may submit a report of analysis of component materials from a laboratory acceptable to the Government, whether an independent test facility or the laboratory of the raw material supplier, as evidence of compliance with the specification requirements. The report of analysis shall include, in addition to the actual test data, the manufacturer's name, name and address of the testing laboratory, date of test, and quantity of material represented by the test report. Where certificates of compliance or reports of analysis are submitted, the Government reserves the right to check test such items to determine the validity of the certificate or analysis.

4.2 Testing of components.

4.2.1 Paper and carbon paper. Component materials shall be tested for the applicable characteristics specified in table III. The test shall be made in accordance with the indicated TAPPI methods or as referenced in the table. The lot size for the purpose of determining the sample size shall be expressed in pounds of paper or, as applicable, carbon paper used in the manufacture of the teletypewriter paper rolls. The sample unit shall consist of not less than 2,000 square inches of base paper or carbon paper. The sample size shall be drawn in accordance with level S-1 of MIL-STD-105. Test results shall include all values upon which the results are based and there shall be no failures to meet the composite, sample unit, or lot average requirements. The composite sample shall consist of approximately equal amounts drawn from all sample units combined into a single sample. Except where otherwise specified, all samples shall be conditioned and tested under uniform atmospheric conditions as specified in TAPPI method T402.

TABLE III. Instructions for testing of components

Characteristic	Specification reference: Requirements	Specification reference: Test method	Requirements applicable to: Sample unit	Requirements applicable to: Lot avg.	Number determinations per unit	Results reported as: Pass or fail	Results reported as: Numerically to nearest
Atmospheric conditions	4.1.2	T402	All testing				
Paper							
Basis weight	Table I	T410		X	one		1 pound
Thickness	Table I	T411		X	20		.001 inch
Tear strength	Table I						
Machine direction		T414		X	5		1 gram
Cross machine direction		T414		X	5		1 gram
Fiber identification	3.1.1.1	T401			one on composite 1/		1 percent
Carbon paper							
Basis weight	3.1.2	T410		X	one		1 pound
Bleeding	3.1.2	4.4.1	X		one	X	

1/ The composite sample shall consist of approximately equal amounts drawn from all the sample units into a single sample.

4.3 Inspection of the end item.

4.3.1 Examination of the end item. The end item shall be examined for the defects set forth in the applicable subparagraphs at the inspection levels and acceptable quality levels (AQLs) in 4.3.1.4. Random samples shall be drawn from each lot for examination of visual, dimensional, and preparation for delivery defects. The lot size shall be expressed in units of rolls for examinations in 4.3.1.1 and 4.3.1.2 and in units of shipping containers in the end item inspection lot for examination in 4.3.1.3.

4.3.1.1 Examination for visual defects. The sample unit for this examination shall be one roll of teletypewriter paper. The sample size shall be selected by taking an approximately equal number of rolls from the shipping containers sampled in accordance with 4.3.1.3. Examine for the defects listed below.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

Examine	Defect
Construction (type I and II)	Not type specified. Paper not of class or style specified. Number of plies not as specified. Color or colors not as specified. Sprocket rolls not type specified (type II only).
Rolls	Colors of multi-copy rolls not collated as specified. Rolls not tightly wound. Edge of roll nicked or uneven. Outer end of roll not secured with adhesive or gummed sticker or label. Plies of multi-copy roll not of equal width. Warning signal missing. Warning signal ends less than 5 feet of end of roll. Any splice in the roll. Core width, not within tolerance. Core not made of fiber or cardboard. Core collapsed or distorted.
Workmanship	Surface of paper not free of fluff, paper dust. Any grit or soil. Paper not clean. Any spots, wrinkle, fold or tear. Smudges, offset or carbon transfer.

4.3.1.2 Examination for dimensions. The sample unit for this examination shall be one roll. The sample size shall be selected from the rolls sampled in accordance with 4.3.1.1. Examine for defects listed below.

Examine	Defect	
Roll dimensions (inches)		
Width (as applicable)	Less than 8-25/64 or 12-29/64.	
	More than 8-31/64 or 12-35/64.	
Diameter		
Type I and II (as applicable)	More than 5 inches.	
Type II (12-1/2 inch wide roll only)	Less than 15 inches.	
	More than 15-1/8 inches.	
Core dimensions (inches)		
	Inside diameter	Wall thickness
Type I and II (8-1/2 inch wide rolls)	Less than 0.95 inch	Less than 3/32
	More than 1.05 inch	More than 5/32
Type II (12-1/2 inch wide roll)	Less than 3-15/16	Less than 5/16
	More than 4-1/16	More than 7/16
Sprocket hole dimensions (type II only)		
Hole diameter	Other than 5/32 ± 1/64 inch.	
Distance between hole centers lengthwise with roll	Other than 1/2 inch ± 1/64 inch.	
Edge of paper to center of holes	Other than 1/4 inch ± 1/64 inch.	
Center to center of hole distance across roll		
8-1/2 inch roll	Other than 8 inches ± 1/64 inch.	
12-1/2 inch roll	Other than 12 inches ± 1/64 inch.	
Roll length	Less than specified.	

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:21Z
Check the source to verify that this is the currentversion before use.

4.3.1.3 Examination of preparation for delivery. An examination shall be made to determine that markings, materials, and workmanship comply with the requirements of section 5. The sample unit shall be one shipping container, fully packed. An equal number of shipping containers fully prepared for delivery shall be examined for closure defects.

Examine	Defect
Marking (exterior and interior	Incorrect; incomplete; illegible; omitted; of improper size, location, sequence, or method of application.
Material	Any nonconforming component; component missing, damaged or otherwise defective.
Workmanship	Inadequate application of components, such as: incomplete closure of container flaps; loose or inadequate sealing, strapping, or stapling.
Contents	Number of intermediate packages per shipping container is less than specified.

4.3.1.4 Inspection levels and acceptable quality levels for examination. The inspection levels, for determining the sample size, and the AQLs expressed in defects per 100 rolls or 100 shipping containers, as applicable, shall be as follows:

Examination paragraph	Inspection level	AQL
4.3.1.1	S-4	4.0
4.3.1.2	S-3	4.0
4.3.1.3	S-2	2.5

4.3.2 Testing of the end item. The end item shall be tested for the applicable characteristics in table IV. The methods of testing as listed in table IV shall be followed. The lot size shall be expressed in units of rolls and the sample unit shall be one roll. The inspection level for determining the sample size shall be S-1. The rolls shall be randomly selected from the shipping containers sampled in accordance with 4.3.1.3. Test results shall include all values upon which the results are based and there shall be no failure to meet the sample unit requirements.

TABLE IV. Instructions for testing the end item

Characteristic	Specification reference		Requirements applicable to		Number determinations per unit	Results reported as	
	Requirements	Test methods	Sample unit	Lot avg.		Pass or fail	Numerically to nearest
Types I and II							
Performance and printing quality	3.6	4.4.3	X		one	X	
Copyability	3.6.1	4.4.3.2	X		one	X	

4.4 Test methods.

4.4.1 Bleeding of carbon paper (type I, class 2 and 4). Three specimens 4 inches square, consisting of two sheets of white copy paper interleaved with carbon paper shall be assembled in a stack and subjected to a uniform pressure of 4 pounds per square inch during conditioning at 90° ± 2°F. and a relative humidity of 50 percent ± 2 percent, for seven days. A difference in shade or color on the side of the paper adjacent to the coated side of the carbon and the reverse side of the paper shall be considered evidence of bleeding.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:21Z
Check the source to verify that this is the current version before use.

4.4.2 Performance and printing quality (all types and classes, except type I, class 6, style B and types I and II, class 1). The roll of teletypewriter paper to be tested shall be set up in a Model 28 or 35 Teletype Corporation teletypewriter equipped for sending messages by means of perforated tape mechanism. The teletype machine shall be equipped with a new nylon or silk ribbon. With the teletypewriter set to cut the message on the teletype tape, print the following: on the first line, twelve alternate groups of five of the letter B and D with no spacing between groups (total of 60 character); on the second line, twelve alternate groups of five of the letters C and O with no spacing between groups; on successive lines as needed, print 250 words of randomly selected copy representing a total of at least 1000 characters. After printing, use the perforated tape to actuate the teletypewriter to reproduce the previously printed material on the roll being tested. Remove the printed message material from the teletypewriter and examine all copies of the message, top sheet and, as applicable, multi-ply copies, for clarity of reproduction. All letters and words on all of the message sheets shall be readily distinguishable for the lot to be considered acceptable. The perforated tape containing the message material may be used to test other rolls of teletypewriter paper comprising the sample size.

4.4.2.1 Printing qualities of type I, class 6, style B teletypewriter rolls. Tests on this type, class, and style of paper shall be performed in accordance with the procedures in 4.4.2 except that the teletype machine shall be operated without a ribbon, when reproducing the message material. After an interval of 15 minutes, examine the top sheet and all copies for clarity of reproduction. All letters and words on all of the message sheets shall be readily distinguishable for the lot to be considered acceptable.

4.4.2.2 Printing qualities of types I and II, class 1 teletypewriter rolls. Tests on these types and class of paper shall be performed in accordance with the procedures of 4.4.2 except that a typewriter can be used in lieu of the teletype machine.

4.4.2.3 Copyability. After examination of the message copy, in accordance with 4.4.2 and 4.4.2.1, prepare a copy of the orginial and all copies of the message on Xerox model 2400 copier, in good operating condition. All letters and words on all of the Xerox copies shall be readily distinguishable for the lot to be considered acceptable.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C, as specified (see 6.2).

5.1.1 Level A. Each roll of paper shall be packaged in a box conforming to PPP-B-636, grade W5c or W5s. The box shall be closed and waterproofed in accordance with the appendix of the box specification.

5.1.2 Level C. Each roll of paper shall be packaged to afford adequate protection against damage during shipment from the supply source to the first receiving agency.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Level A. Twelve rolls of teletypewriter paper of one type, class, grade, style and color or multi-copy combination packaged as specified shall be packed in a snug-fitting fiberboard shipping container conforming to PPP-B-636, style RSC, grade V3c or V3s. The shipping container shall be closed and waterproofed in accordance with the Appendix of the container specification.

5.2.2 Level B. Twelve rolls of teletypewriter paper of one type, class, grade, style and color or multi-copy combination packaged as specified shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, type CF or SF, grade not less than 275 of PPP-B-636. Shipping containers shall be closed in accordance with the Appendix to the container specification.

5.2.3 Level C. Rolls of teletypewriter paper in quantities as specified (see 6.2), packaged as specified in 5.1 shall be packed in containers to assure carrier acceptance and safe arrival at destination in compliance with [illegible] Classification or National Motor Freight Classification, or [illegible].

5.3 Marking. In addition to any special markings required in the procurement documents, marking of the interior packages and exterior shipping containers shall be in accordance with Fed. Std. No. 123 for civil agencies or MIL-STD-129 for military agencies, as applicable (see 6.2). The shipping container shall be marked "Store in cool place".

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

5.4 Palletization. When specified (see 6.2), shipping containers shall be assembled on a pallet conforming to PPP-P-001660. The assembled load shall be strapped to the pallet with steel or nonmetallic strapping in accordance with good industry practice. Alternatively, the load may be a glued load, using a commercial type low-tensile, high shear glue.

6. NOTES

6.1 Intended use. Roll teletypewriter paper is intended for use on teletypewriter machines No. 15-A and other teleprinters. Type I, classes 3,5, and 6 papers are intended for applications requiring up to 9 legible copies. Type I, class 6, style B paper are intended for use on ribbonless high speed teleprinters.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Type, class, grade or style required (see 1.2).
(c) Number of copies required (type I, classes 2, 3, 4, 5, 6)(see 3.2).
(d) Color or colors required (see 3.4).
(e) Width of roll (type II only)(see 3.3.2).
(f) Selection of the applicable levels of packaging and packing (see 5.1 and 5.2).
(g) Marking document required (see 5.3).
(h) Quantities required (see 5.2.3).
(i) When palletization is required (see 5.4).

MILITARY INTEREST:

Army-GL, EL
Navy-SA
Air Force-84

Preparing activity:

GSA-FSS

CIVIL AGENCIES INTEREST:

GSA-FSS
COMMERCE-NBS
NASA-JFK

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 15 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.