INCLUDES:
Amendment 1 Pgs 47-54
Amendment 2 Pgs 55-62
Amendment 3 Pgs 107-150
Amendment 4 Pgs 151-194
Amendment 5 Pgs 63-106
Amendment 6 Pgs 195-238

CAGE CODE
19200

MIL-C-70478C (AR)
04 OCTOBER 1994
SUPERSEDING
MIL-C-70478B (AR)
19 APRIL 1994

MILITARY SPECIFICATION

CONTAINER, AMMUNITION, METAL, FOR CARTRIDGE, 120 mm, TANK AMMUNITION

This specification is approved for use within the U.S. Army Armament, Munitions and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the requirements, quality assurance provisions and packaging for one type of metal container used for 120 mm tank ammunition.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. The following specifications and standards form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS

FEDERAL

TT-C-490	Cleaning and Preparation of Ferrous and Zinc Coated Surfaces for Organic Protective Coatings

Beneficial comments (recommendations additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, U.S. Army Armament Research, Development and Engineering Center, Attn: SMCAR-EAC-S, Picatinny Arsenal, New Jersey 07806-5000 by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8140

Distribution Statement B: Distribution authorized to U.S. Government agencies and 120 mm system contractors only in accordance with Arms Export Control (22.USC.2778). Other requests for this document shall be referred to ARDEC, SMCAR-ESM-I, Rock Island, IL.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

MILITARY

CAGE CODE 19200

MIL-W-12332	Welding, Resistance, Spot, Seam and Production, for Fabricating Assemblies of Low-Carbon Steel
MIL-A-48078	Ammunition, Standard Quality Assurance Provisions, General Specification for

STANDARDS

MILITARY

MIL-STD-171	Finishing of Metal and Wood Surfaces
MIL-STD-1169	Packaging, Packing and Marking for Shipment of Inert Ammunition Components
MIL-STD-1261	Welding Procedures for Constructional Steel

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein. Unless otherwise specified, the issues shall be those in effect on the date of the solicitation.

DRAWINGS (See 6.4)

U.S. ARMY ARMAMENT RESEARCH, DEVELOPMENT AND ENGINEERING CENTER (ARDEC)

9386831	Container, Ammunition, Metal
12912366	Container, Ammunition, Metal
12938062	Container, Ammunition, Metal, PA116A1

(Copies of specifications, standards, and other Government documents required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issue of the nongovernment documents which is current on the date of the solicitation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D2240	Indentation Hardness of Rubber and Plastics by means of a Durometer, Standard Method of Test for
ASTM D3951	Commercial Packaging, Standard Practice for
ASTM E8	Tension Testing of Metallic Materials, Standard Method of
ASTM E18	Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials, Test for

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein (except for associated detail specifications, specification sheets or MS standards), the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Materials. Materials and parts shall be in accordance with applicable drawings and specifications.

3.2 Components and assemblies. The components and assemblies shall comply with all requirements per drawing 9386831, 12912366, or 12938062 and the drawings and specifications referenced thereon.

3.3 Welding. The welding shall comply with the requirements of MIL-W-12332 or MIL-STD-1261.

3.3.1 Tensile strength (if applicable). The tensile strength of the longitudinal body weld shall be not less than 65 percent of the tensile strength of body material when tested as specified in 4.5.1.

* 3.3.1.1 Tensile strength of body material. The tensile strength of the body material shall be not less than 60,000 pounds per square inch (psi) as specified in 4.5.1.

3.4 Painted surface. The painted surfaces of the container shall comply with the requirements of TT-C-490. However, the film thickness and salt spray requirements of TT-C-490 will not apply to the interior surfaces, welded spots and sharp corners of the exterior surface of the container. Bare spots permissible on all bearing surfaces as per drawing 9386831, 12912366, or 12938062.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

3.5 Cover assembly. Upon assembly of the cover assembly to the body weldment, the cover assembly shall freely engage and rotate within the body weldment. As the cover assembly is rotated with the square handle in the open position, the handle shaft ends shall freely engage into the respective bayonet slots of the rim. When the square handle is in the closed position (rotated 180°), the hairpin spring clip shall be inserted into the upper holes in the shaft support and handle and lock the handle in place. When the hairpin spring clip is removed and the handle rotated to the open position, the cover assembly shall disengage from the body weldment.

3.6 First article inspection. This specification contains technical provisions for first article inspection. Requirements for the submission of first article samples by the contractor shall be as specified in the contract.

3.7 Workmanship.

3.7.1 Components and assemblies. The components and assemblies shall be regular, smooth and free from wrinkles, pin holes, cracks, dirt, rough spots, burrs, sharp edges and any other defect that might affect the serviceability, durability, safety and appearance of the container.

3.7.2 Paint coating. The paint coating shall be in accordance with applicable drawings and comply with instructions in MIL-STD-171. The finish coat shall cover all required surfaces and be continuous with the possible exception of a few light scratches not exposing the base metal or the primer coat.

3.7.3 Parts. All parts shall be free of chips, dirt, grease, rust and foreign material. The cleaning method used shall not be injurious to any of the parts nor shall any of the parts be contaminated by the cleaning agents used.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements. Unless otherwise specified herein or in the contract, the provisions of MIL-A-48078 shall apply and are hereby made a part of this detail specification.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.2 Classification of inspections. The following types of inspection shall be conducted on this item:

a. First article inspection

b. Quality conformance inspection

4.3 First article inspection.

4.3.1 Submission. The contractor shall submit a first article sample as designated by the Contracting Officer for evaluation in accordance with provisions of 4.3.2. The first article sample shall consist of five painted metal containers, five painted cover assemblies, five unpainted cover assemblies, and ten each of every subassembly and component (unpainted).

4.3.2 Inspections to be performed. See MIL-A-48078 and Table I specified herein.

4.3.3 Rejection. See MIL-A-48078.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Table I. First Article Inspection.

CAGE CODE 19200

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE Assemblies and Components	SHEET 1 OF 2		DRAWING NUMBER See Below
				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
	Metal Containers, painted - (Drawing 9386831, 12912366, or 12938062)			
	a. Examination for defects	5	3.2	4.4.2.18
	b. Air pressure	5	3.2	4.5.6.2
	Body Weldment, unpainted - (Drawing 9386830 or 12938059)			
	a. Examination for defects	10	3.2	4.4.2.16
	b. Air pressure	5	3.2	4.5.6.1
	c. Weld rim to body (see note)	5	3.2	4.5.2
	Cover Assembly, unpainted - (Drawing 12934838)			
	a. Examination for defects	5	3.2	4.4.2.9
	b. Air pressure	5	3.2	4.5.6.1
	Cover assembly, painted - (Drawing 12934838)			
	Examination for defects	5	3.2	4.4.2.10

NOTES: The weld security inspections, body tensile strength, spring tests and gasket tensile stress test shall be performed after the other inspections have been performed on the applicable samples.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Table I. First Article Inspection.

CAGE CODE 19200

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE Assemblies and Components	SHEET 2 OF 2		DRAWING NUMBER See Below
				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
	Body - (Drawing 9386828)			
	a. Examination for defects	10	3.2	4.4.2.14
	b. Tensile strength (see note)	5	3.2	4.5.1
	Gasket - (Drawing 12910349)			
	a. Examination for defects	10	3.2	4.4.2.7
	b. Hardness	3	3.2	4.5.5
	Remaining subassemblies and components			
	Examination for defects	10	3.2	Applicable sub-paragraph of 4.4.2
	Yoke assembly, painted - (Drawing 12561227 or 12912337)	10	3.2	4.4.2.20

NOTES: The weld security inspections, body tensile strength, spring tests and gasket tensile stress test shall be performed after the other inspections have been performed on the applicable samples.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

4.4 Quality conformance inspection.

4.4.1 Inspection lot formation. Inspection lots shall comply with the lot formation provisions of MIL-A-48078. In addition, inspection lots of containers shall contain material from lots with the same interfix number from one manufacturer.

4.4.2 Examination. Examinations listed in the Classification of Characteristics shall be performed on inspection lots as defined in 4.4.1 of this specification.

a. Sampling plans.

1. Quality conformance examinations and tests are specified in the following Classification of Characteristics paragraphs. The contractor's quality program or detailed inspection plan shall provide assurance of compliance of all characteristics with the applicable drawing and specification requirements utilizing as a minimum the conformance criteria specified herein. Unless otherwise specified herein, attributes sampling inspection shall be conducted in accordance with Table II below. Samples shall be selected at random.

TABLE II. Sampling plan for quality conformance.

Accept on Zero Defects

Lot Size	Sample size (characteristic)	
	Major	Minor
2 to 8	#	#
9 to 150	32	13
151 to 500	32	30
501 to 1200	74	35
1201 to 3200	74	43
3201 to 10000	87	50
10001 to 35000	109	61
35001 to 150000	124	74
150001 to 500000	156	91
500001 and over	187	102

100% inspection
NOTE: If sample size equals or exceeds lot or batch size, do 100% inspection.

2. Normal inspection will be used at the start of inspection unless otherwise directed by the responsible authority. When normal inspection is in effect, tightened inspection (Table III) shall be instituted when two out of five consecutive lots or batches have not been accepted on original inspection (i.e., ignoring resubmitted lots or batches for this

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

procedure). When tightened inspection is in effect, normal inspection shall be instituted when five consecutive lots or batches have been considered acceptable on original inspection. When normal inspection is in effect, reduced inspection (Table III) shall be instituted when ten consecutive lots or batches have been considered acceptable on original inspection and production is at a steady rate. When reduced inspection is in effect, normal inspection shall be instituted if a lot or batch is not accepted or production becomes irregular or delayed.

TABLE III. Sampling plan for quality conformance.

Tightened/Reduced

Lot Size	Sample Size (Characteristic)			
	Tightened		Reduced	
	Major	Minor	Major	Minor
2 to 8	#	#	#	5
9 to 150	50	20	13	5
151 to 500	50	48	13	12
501 to 1200	119	48	30	14
1201 to 3200	119	54	30	17
3201 to 10000	119	69	35	23
10001 to 35000	136	78	43	31
35001 to 150000	172	88	58	39
150001 to 500000	196	103	78	51
500001 and over	221	116	98	64

100% inspection

NOTE: If sample size equals or exceeds lot or batch size, do 100% inspection

b. Alternative quality conformance provisions. Unless otherwise specified herein or provided for in the contract, alternative quality conformance procedures, methods or equipment (see 6.3), such as statistical process control, tool control, other types of sampling plans, etc., may be used by the contractor when they provide, as a minimum, the level of quality assurance required by the provisions herein. Prior to applying such alternative procedures, methods or equipment, the contractor shall describe them in a written proposal submitted to the Government for evaluation. When required, the contractor shall demonstrate that the effectiveness of each proposed alternative is equal to or better than the specified quality conformance provision(s) herein. In case of dispute as to whether the contractor's proposed alternative(s) provides equivalent assurance, the provisions of this specification shall apply. All approved alternative provisions shall be specifically incorporated into the contractor's quality program or inspection system, as applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

c. Lot disposition. Product lot samples inspected in accordance with paragraph 4.4.2 shall be accepted only if zero defects are found. One or more defects found in any sample shall require the product represented by the applicable sample to not be accepted.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CAGE CODE 19200

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.1	TITLE Support, Shaft	SHEET 1 OF 2		DRAWING NUMBER 12934841
				NEXT HIGHER ASSEMBLY 12934839
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Diameter of large hole	Table II	3.2	Gage
102	Diameter of small hole	Table II	3.2	Gage
103	True position of large hole and slot	Table II	3.2	Gage
104	Deleted			
105	True position of small holes	Table II	3.2	Gage
106	Distance between shaft support uprights	Table II	3.2	Gage
107	Deleted			
108	Deleted			
109	Wall thickness	Table II	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CAGE CODE 19200

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH *4.4.2.1	TITLE Support, Shaft	SHEET 2 OF 2		DRAWING NUMBER 12934841
				NEXT HIGHER ASSEMBLY 12934839
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Major				
110	Deleted			
Minor				
201	Deleted			
*202	Deleted			
203	Evidence of poor workmanship	Table II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE 19200

PARAGRAPH 4.4.2.2	TITLE Handle	SHEET 1 OF 2		DRAWING NUMBER 12929273
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	True position of small hole	Table II	3.2	Gage
102	True position of shaft hexhole, 2 places	Table II	3.2	Gage
103	Deleted			
104	Deleted			
Minor				
201	Diameter of small hole	Table II	3.2	Gage
202	Overall length of tabs	Table II	3.2	Gage
203	Width of tab	Table II	3.2	Gage
204	Width of shaft hex hole (three readings 60° apart), 2 places	Table II	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CAGE CODE 19200

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.2	TITLE Handle	SHEET 2 OF 2		DRAWING NUMBER 12929273
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
205	Largest width of handle	Table II	3.2	Gage
206	Wall thickness	Table II	3.2	Gage
207	Evidence of poor workmanship	Table II	3.7	Visual

NOTES:

14

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE 19200

PARAGRAPH 4.4.2.3	TITLE Shaft	SHEET 1 OF 2		DRAWING NUMBER 9344037
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Length of hexagon segment of shaft	Table II	3.2	Gage
102	Large diameter (two places)	Table II	3.2	Gage
103	Small diameter (two places)	Table II	3.2	Gage
104	Total length of large diameters and hexagon segments	Table II	3.2	Gage
105	Small diameter segment not tangent to large diameter segment and side of hexagon segment	Table II	3.2	Visual
106	Length of large diameter segment (two places)	Table II	3.2	Gage
NOTES:				

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

15

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE 19200

PARAGRAPH 4.4.2.3	TITLE Shaft	SHEET 2 OF 2		DRAWING NUMBER 9344037
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
201	Width across flats of hexagon segment (three readings, 60° apart)	Table II	3.2	Gage
202	Length of small diameter segment (two places)	Table II	3.2	Gage
203	Evidence of poor workmanship	Table II	3.7	Visual
NOTES:				

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE 19200

PARAGRAPH 4.4.2.4	TITLE Washer	SHEET 1 OF 1		DRAWING NUMBER 9344038
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Inside diameter	Table II	3.2	Gage
102	Height	Table II	3.2	Gage
Minor				
201	Outside diameter	Table II	3.2	Gage
202	Evidence of poor workmanship	Table II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE 19200

PARAGRAPH 4.4.2.5	TITLE Retainer, Washer	SHEET 1 OF 1		DRAWING NUMBER 9344041
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Material certification	Table II	3.2	Certification
Minor				
201	Diameter of hole	Table II	3.2	Gage
202	Inside diameter	Table II	3.2	Gage
203	Height of retainer	Table II	3.2	Gage
204	Evidence of poor workmanship	Table II	3.7	Visual

NOTES:

18

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE 19200

PARAGRAPH 4.4.2.6	TITLE Cover	SHEET 1 OF 2		DRAWING NUMBER 9386821
				NEXT HIGHER ASSEMBLY 12934839
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Outside diameter	Table II	3.2	Gage
102	Wall thickness	Table II	3.2	Gage
103	Depth of groove	Table II	3.2	Gage
104	Width of groove	Table II	3.2	Gage
105	Depth from rim to inside of cover base	Table II	3.2	Gage
106	Height of threads, minimum	Table II	3.2	Gage
107	Location of air test hole with center of cover	Table II	3.2	Gage
108	Flatness of bottom surface inside annular ring and surrounding air test hole	Table II	3.2	Gage
109	Height of annular ring around air test hole	Table II	3.2	Gage
NOTES:				

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CAGE CODE 19200

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.6	TITLE Cover	SHEET 2 OF 2		DRAWING NUMBER 9386821
				NEXT HIGHER ASSEMBLY 9386822
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor 201	Evidence of poor workmanship	Table II	3.7	Visual
NOTES:				

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE 19200

PARAGRAPH 4.4.2.7	TITLE Gasket	SHEET 1 OF 1		DRAWING NUMBER 12910349
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Material certification	Table II	3.2	Certification
102	Deleted			
103	Hardness	Table II 1/	3.2	4.5.5
104	Inside diameter, maximum	Table II	3.2	Gage
105	Large width	Table II	3.2	Gage
106	Middle width	Table II	3.2	Gage
107	Height of rectangular cross section	Table II	3.2	Gage
108	Deleted			
109	Deleted			
Minor				
201	Evidence of poor workmanship	Table II	3.7	Visual

NOTES:

1/ One plaque (4 specimens) at start and end of each shift.

21

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE 19200

PARAGRAPH *4.4.2.8	TITLE Cover Weldment	SHEET 1 OF 1		DRAWING NUMBER 12934839
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
* 101	True position of shaft hole and slot	Table II	3.2	Gage
* 102	True position of shaft support uprights	Table II	3.2	Gage
Minor				
201	Weld missing, incomplete or visually inadequate	Table II	3.2	Visual/Manual
202	Deleted			
203	Evidence of poor workmanship	Table II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE 19200

PARAGRAPH *4.4.2.9	TITLE Cover Assembly, Prior to Painting	SHEET 1 OF 1		DRAWING NUMBER 12934838
				NEXT HIGHER ASSEMBLY 9386831, 12938062, or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Air pressure	100%	3.2	4.5.6.1/Drawing 9386824
102	Rotating of shaft inadequate after crimping	Table II	3.2	Manual
103	Distance from inside cover rim to top of shaft	Table II	3.2	Gage
* 104	Deleted			
Minor				
201	Component missing or inadequately assembled	Table II	3.2	Visual
202	Evidence of poor workmanship	Table II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE 19200

PARAGRAPH *4.4.2.10	TITLE Cover Assembly, After Painting	SHEET 1 OF 1		DRAWING NUMBER 12934838
				NEXT HIGHER ASSEMBLY 9386831, 12938062, or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Gasket improperly bonded to cover	Table II	3.2	Visual
102	After painting, the shaft shall freely rotate	Table II	3.2	Manual
103	Primer thickness, min.	Table II	3.2	Gage
104	Top coat thickness, min.	Table II	3.2	Gage
* 105	Spring clip and wire rope assembly inadequately swaged onto handle or hairpin spring clip	Table II	3.2	Visual/Manual
Minor				
201	Evidence of poor workmanship	Table II	3.7	Visual
NOTES:				

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CAGE CODE 19200

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.11	TITLE Rim	SHEET 1 OF 2		DRAWING NUMBER 9386827
				NEXT HIGHER ASSEMBLY 9386830 or 12938059
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Length of larger slot on side of rim	Table II	3.2	Gage
102	Location of larger slot from inside flat	Table II	3.2	Gage
103	Deleted			
104	Location of bayonet slot, 4 places	Table II	3.2	Gage
105	Dimension across flats, 2 places (Dimension A)	Table II	3.2	Gage
106	Dimension across corner, 2 places (Dimension D)	Table II	3.2	Gage
107	Width of larger slot	Table II	3.2	Gage
108	Inside diameter of rim (Dimension E)	Table II	3.2	Gage
109	Bayonet locking edge radius (2 places)	Table II	3.2	Gage
NOTES:				

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CAGE CODE 19200

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.11	TITLE Rim	SHEET 2 OF 2		DRAWING NUMBER 9386827
				NEXT HIGHER ASSEMBLY 9386830 or 12938059
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
201	Depth from edge of rim to inside flat	Table II	3.2	Gage
202	Deleted			
203	Deleted			
204	Drainage hole missing	Table II	3.2	Visual
205	Evidence of poor workmanship	Table II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE 19200

PARAGRAPH 4.4.2.12	TITLE Ring	SHEET 1 OF 2		DRAWING NUMBER 9386826
				NEXT HIGHER ASSEMBLY 9386830 or 12938059
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Length of larger slot on side of ring	Table II	3.2	Gage
102	Location of larger slot from inside flat	Table II	3.2	Gage
103	Deleted			
104	Dimensions across flats, 2 places (Dimension A)	Table II	3.2	Gage
105	Width of larger slot	Table II	3.2	Gage
106	Opening of container interlocking grip	Table II	3.2	Gage
107	Depth of container interlocking grip	Table II	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE 19200

PARAGRAPH 4.4.2.12	TITLE Ring	SHEET 2 OF 2		DRAWING NUMBER 9386826
				NEXT HIGHER ASSEMBLY 9386830 or 12938059
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
201	Distance from edge of ring to outside flat	Table II	3.2	Gage
202	Deleted			
203	Deleted			
204	Location of container interlocking cutouts	Table II	3.2	Gage
205	Width of interlocking cutouts	Table II	3.2	Gage
206	Depth from interlocking cutout to inside flat	Table II	3.2	Gage
207	Drainage hole missing	Table II	3.2	Visual
208	Evidence of poor workmanship	Table II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CAGE CODE 19200

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.13	TITLE Bottom	SHEET 1 OF 1		DRAWING NUMBER 9386825 or 9378172
				NEXT HIGHER ASSEMBLY 9386830 or 12938059
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Material thickness	Table II	3.2	Gage
102	Hole location 1/	Table II	3.2	Gage
103	Hole diameter 1/	Table II	3.2	Gage
Minor				
201	Height of lip, minimum	Table II	3.2	Gage
202	Evidence of poor workmanship	Table II	3.7	Visual

NOTES:

1/ 9386825 only.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE 19200

PARAGRAPH 4.4.2.14	TITLE Body	SHEET 1 OF 1		DRAWING NUMBER 9386828
				NEXT HIGHER ASSEMBLY 9386830 or 12938059
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Tensile strength of weld	Table II 1/	3.3.1	4.5.1
102	Wall thickness	Table II	3.2	Gage
103	Deleted			
104	Deleted			
105	Deleted			
Minor				
201	Evidence of poor workmanship	Table II	3.7	Visual

NOTES:

1/ Three coupons per shift.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE 19200

PARAGRAPH 4.4.2.15	TITLE Plug, Stacking	SHEET 1 OF 1		DRAWING NUMBER 9386837
				NEXT HIGHER ASSEMBLY 9386830 or 12938059
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Length of plug	Table II	3.2	Gage
102	Width of plug	Table II	3.2	Gage
Minor				
201	Deleted			
202	Deleted			
203	Evidence of poor workmanship	Table II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE 19200

PARAGRAPH 4.4.2.16	TITLE Body Weldment, Prior to Painting	SHEET 1 OF 2		DRAWING NUMBER 9386830 or 12938059
				NEXT HIGHER ASSEMBLY 9386831, 12938062, or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Air pressure	100%	3.2	4.5.6.1
102	Weld of rim to body	Table II 1/	3.2	4.5.2
103	True position of holes of ring, rim and stacking plug	Table II	3.2	Gage
104	Location of hole in rim relative to holes in inside rings and stacking plugs	Table II	3.2	Gage
105	Location of hole in rim relative to hole in outside rings and stacking plugs	Table II	3.2	Gage
106	Perpendicularity of ring and rims with Datum-A	Table II	3.2	Gage
107	Distance from end of body to top of rim bayonet slot (four places)	Table II	3.2	Gage

NOTES:

1/ Three coupons per shift.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE 19200

PARAGRAPH 4.4.2.16	TITLE Body Weldment, Prior to Painting	SHEET 2 OF 2		DRAWING NUMBER 9386830 or 12938059
				NEXT HIGHER ASSEMBLY 9386831, 12938062, or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Major				
108	Minimum shear load between stacking plug and body	Table II	3.2	Gage
109	Flatness of body	Table II	3.2	Gage
110	Body end irregularities	Table II	3.2	4.5.9
111	Depth of body weldment	Table II	3.2	Gage
112	Inside diameter of body at dimple location 2/	Table II	3.2	Gage
113	True position of dimple location 2/	Table II	3.2	Gage
Minor				
201	Any weld of ring, rim or bottom to body missing, incomplete or visually inadequate	Table II	3.2	Visual
202	Evidence of poor workmanship	Table II	3.7	Visual

NOTES:

2/ 12938062 only.

33

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CAGE CODE 19200

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.17	TITLE Body Weldment, After Painting	SHEET 1 OF 1		DRAWING NUMBER 9386830 or 12938059
				NEXT HIGHER ASSEMBLY 9386831, 12938062, or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Primer thickness	Table II	3.2	Gage
102	Paint thickness	Table II	3.2	Gage
103	Marking	Table II	3.2	5.3
104	Inside diameter, minimum	Table II	3.2	Gage
Minor				
201	Evidence of poor workmanship	Table II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CAGE CODE 19200

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.18	TITLE Container, Ammunition, Metal	SHEET 1 OF 1		DRAWING NUMBER 9386831, 12912366, or 12938062
				NEXT HIGHER ASSEMBLY 9386832, 9386833, 12938055, 12938056, 12938057, or 12912369
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Cover assembly test	Table II	3.5	Visual/Manual/4.5.7
102	Air pressure test (with yoke assembly in place, PA116 only)	Table II	3.2	4.5.6.2
103	Screw torque test (top and bottom, PA116 and cover PA116A1 only)	Table II 1/	3.2	4.5.8
Minor				
201	Missing, loose or damaged components	Table II	3.2	Visual
202	Protective finish damaged, bare spots exposing metal, etc.	Table II	3.2	Visual
203	Evidence of poor workmanship	Table II	3.7	Visual

NOTES:

1/ The screw torque test shall be performed after the air pressure test has been performed and the screw has been reassembled.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CAGE CODE 19200

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH *4.4.2.19	TITLE Deleted	SHEET 1 OF 1		DRAWING NUMBER
				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
NOTES:				

36

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CAGE CODE 19200

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.20	TITLE Yoke Assembly, After Painting	SHEET 1 OF 1		DRAWING NUMBER 12561227 or 12912337
				NEXT HIGHER ASSEMBLY 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None Defined			
Major				
101	Location of the self clinching nut	Table II	3.2	Gage
102	Yoke stops inside the maximum base diameter	Table II	3.2	Gage
Minor				
201	Presence of spot welds on yoke stop	Table II	3.2	Visual
202	Pushout force improper	Table II	3.2	Gage
203	Presence of improper threads in self clinching nut	Table II	3.2	Gage/Visual
204	Evidence of poor workmanship	Table II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

4.4.3 Testing. Testing is described in the First Article and Quality Conformance Inspection Tables.

4.4.3.1 Tensile strength. (See 3.3.1) Major Defect. Five bodies shall be randomly selected for this test. Four specimens, approximately equally spaced along the axis, shall be taken from each body at right angles to the weld. If one specimen of a sample fails to comply with the requirement, that sample shall be classed defective. If two or more samples are classed defective, the lot shall be rejected.

* 4.4.3.2 Tensile strength of body material. (See 3.3.1.1) Major Defect. Five bodies shall be randomly selected for this test. From each body, three specimens shall be selected at random for determination of body material tensile strength. If one specimen fails to comply with 3.3.1.1, that sample body shall be classed defective. If two or more sample bodies are classed defective, the lot shall be rejected.

4.4.3.3 Weld of rim to body. (See Drawing 9386830 or 12938059) Major Defect. Five body assemblies shall be selected for this test. If any sample fails to comply with the requirement, the lot shall be rejected.

4.4.3.4 Hardness of gasket. (See drawing 12910349) Major Defect. Five gaskets shall be randomly selected from each lot for this test. If any gasket fails to meet the requirement, the lot shall be rejected.

4.4.3.5 Air pressure.

4.4.3.5.1 Air pressure of unpainted cover assembly. (See drawing 12934838) Major Defect. The cover assemblies shall be checked 100 percent. If any cover assembly fails to comply with the requirement, the cover assembly shall be rejected.

4.4.3.5.2 Air pressure of unpainted body weldment. (See Drawing 9386830 or 12938059) Major Defect. The body weldments shall be checked 100 percent. If the body weldment fails to comply with the requirement, the body weldment shall be rejected.

4.4.3.5.3 Air pressure of painted metal container. (See Drawing 9386831, 12912366, or 12938062) Major Defect. The containers shall be sampled in accordance with Table II.

4.4.3.6 Cover assembly test. (See Drawing 9386831, 12912366, or 12938062) The cover assemblies shall be sampled in accordance with Table II.

4.4.4 Inspection equipment. The inspection equipment required to perform the examinations and tests prescribed herein is described in the "Inspection Method Reference" column in the tables starting with paragraph 4.4.2.1. The contractor shall submit for approval, inspection equipment designs in accordance with the terms of the contract (see Section 6 of MIL-A-48078 and 6.5 herein).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

4.5 Methods of inspection. (See 6.5)

* 4.5.1 Tensile strength. The tensile strength shall be determined in accordance with ASTM E8.

4.5.2 Weld of rim to body. The test shall be performed in accordance with ASTM E8.

4.5.3 Spring embrittlement. The spring shall be repeatedly stretched with increasing loads until it does not return to its original free height. That point shall indicate minimum distortion. Any unit which fractures prior to extension to minimum distortion shall be classed defective.

4.5.4 Hardness of spring. The hardness of the spring shall be determined in accordance with ASTM E18.

4.5.5 Hardness of gasket. The hardness test shall be performed on the specimens. This test shall be performed in accordance with ASTM Method D2240. Shore A hardness readings shall be taken on the ends of each specimen. Any specimen failing the applicable requirements shall be cause for rejection of that lot of material.

4.5.6 Air pressure test.

4.5.6.1 Air pressure of unpainted cover assembly and unpainted body weldment. Subject the cover assembly and body weldment to the internal air pressure, specified in the applicable container assembly drawing. For the cover assembly, apply the pressure when the cover assembly (equipped with a gasket) is assembled to a master body assembly (or its equivalent). For the body weldment, apply the pressure when the body weldment is assembled to a master cover (or equivalent) and gasket. The master cover and the master body assembly shall be provided with satisfactory means for applying and maintaining the pressure during the test and for showing evidence of leakage. Observation shall be made for a pressure drop exceeding the requirement (as specified in the applicable drawing). A cover assembly or body weldment which exceeds the requirement, shall be classed defective.

4.5.6.1.1 Alternate air pressure test for unpainted cover assembly and unpainted body assembly (Water Method). Subject the cover assembly and container body, while under water, to the specified internal air pressure for the test time specified. For the cover assembly, apply the pressure, when the cover assembly is assembled, to a master body assembly (or its equivalent) equipped with a gasket. For the body assembly, apply the pressure when the body assembly is assembled to a master cover (or equivalent) and gasket. The master cover and master body assembly shall be provided with satisfactory means for applying and maintaining the pressure during the test and for showing evidence of leakage. No bubbles (other than surface bubbles) shall be permitted. A cover assembly or body assembly which does not meet the requirements shall be classed defective.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

4.5.6.2 Air pressure of painted metal container. Subject the metal container to the internal air pressure, specified in the applicable metal container drawing. Observation shall be made for a pressure drop exceeding the requirement (as specified in the applicable drawing. A metal container, which exceeds the requirement shall be classed defective.

4.5.7 Cover assembly test. Upon assembly of the body and cover, the cover shall freely engage and rotate within the body. The Square handle shall engage into the respective bayonet slots of the rim without interference when in the clamping position. The Square handle when disengaged and in the open position shall disengage the cover from the body.

4.5.8 Screw torque test. The minimum applicable torque shall be applied to the screw. Any evidence of motion of the screw before reaching the minimum acceptable torque shall be cause for rejection of the container assembly being tested.

4.5.9 Body end irregularities. Visually inspect the body end for any nicks, dents, gouges, or mismatch. If a defect is evident, place a .01 inch diameter wire on the defect and a one inch long block over the wire. With the wire nested in the irregularity, gently press down on the block and remove the wire. If there is no evidence of resistance caused by the block, the part shall be classed defective.

5. PACKAGING

5.1 Preservation. None required.

5.2 Packing.

5.2.1 Level A. The metal container shall be packed in accordance with Level A of MIL-STD-1169.

5.2.2 Level B. The metal container shall be packed in accordance with Level B of MIL-STD-1169.

5.2.3 Commercial. The metal container shall be packed in accordance with ASTM D3951.

5.3 Marking

5.3.1 Level A. The metal container shall be marked in accordance with Level A of MIL-STD-1169.

5.3.2 Level B. The metal container shall be marked in accordance with Level B of MIL-STD-1169.

5.3.3 Commercial. The metal container shall be marked in accordance with ASTM D3951 and the following additional instructions. Commercial shipping tags attached with wire shall show: Item name and

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

model number, part number and revision, contract number, lot number and data, name and address of manufacturer. If components and assemblies are bundled, boxed or palletized, the gross weight and quantity shall be included. The above information may be placed on pallets or boxes by labeling or stenciling.

5.4 Shipping. When containers from more than one lot are shipped at one time, each lot shall be kept separate and the division between lots clearly indicated to prevent mixing of lots in transit.

6. NOTES

6.1 Intended use. The metal container is intended for use as the outer shipping and storage packaging for the 120 mm Tank Cartridge.

6.2 Ordering data. See MIL-A-48078.

6.3 Definition of packaging and packing levels.

6.3.1 Level A. Full military protection, for unrestricted (OCONUS) shipment and storage.

6.3.2 Level B. Limited military protection for limited storage and (OCONUS) shipment.

6.3.3 Level C. For interplant (CONUS) shipment and very limited storage.

6.4 Drawings. Drawings listed in Section 2 of this specification under the heading U.S. Army Armament Research, Development and Engineering Center (ARDEC) may also include drawings prepared by, and identified as U.S. Army Armament Research and Development Command (ARRADCOM), U.S. Army Armament Research and Development Center (ARDC), Edgewood Arsenal, Frankford Arsenal, Rock Island Arsenal or Picatinny Arsenal drawings. Technical data originally prepared by these activities is now under the cognizance of ARDEC.

6.5 Submission of inspection equipment designs for approval. See MIL-A-48078. Submit designs as required to: Commander, U.S. Army Armament Research, Development and Engineering Center, ATTN: AMSMC-QAT-I(D), Dover, New Jersey 07801-5001.

6.6 Approval of equivalent test methods. Prior approval of the Contracting Officer is required for use of equivalent test methods. A description of the proposed method should be submitted through the Contracting Officer to: Commander, U.S. Army Armament Research, Development and Engineering Center, ATTN: AMSMC-QAT-A(D), Dover, New Jersey 07801-5001. This description should include but not be limited to the accuracy and precision of the method, test data demonstrating the accuracy and precision and drawings of any special equipment required.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

CAGE CODE
19200

6.7 Subject term (key words) listings.

Ammunition
Body
Cannon
Cartridge
Container
Cover
Metal
Tank

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

QUALITY ASSURANCE PROVISIONS FOR REFURBISHMENT

10. SCOPE

10.1 Scope. The appendix provides the Quality Assurance provisions for the refurbishment of containers, metal, for 120 mm tank ammunition. This Appendix is not a mandatory part of the Specification. The information contained herein is intended for compliance when refurbishing metal containers.

20. APPLICABLE DOCUMENTS

20.1 Government Drawings.

9386831 - Container, Ammo, Metal, PA116
12938062 - Container, Ammo, Metal, PA116A1
12912366 - Container, Ammo, Metal

30. REFURBISHMENT

30.1 Dents. Dents shall be removed as required to allow compliance with the workmanship requirement.

30.2 Cleaning. Paint and rust shall be removed.

30.3 Rims and/or rings. Rims and/or rings shall be straightened and welded by fillet welding where required.

30.4 Refinish. The parts shall be finished in accordance with the applicable drawings.

30.5 Seams. Seams shall be welded where required.

30.6 Gasket. The gaskets on the cover shall be replaced with new gaskets.

30.7 Refurbishment identification. Each container that will be refurbished shall have a 3/16 inch diameter hole punched/drilled in the rim (9386827-1). The hole shall be on the side where the identification markings are/were located. This side has the lip grip on the lower ring (second/bottom ring). The hole shall be approximately centered on the flat surface of the rim, but be no closer to an edge or curve than 3/8 inches. The hole will identify how many times this particular container has been refurbished.

40. REQUIREMENTS

40.1 Welds. Welds shall be in conformance with good commercial practices.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

40.2 Gasket. The gasket shall comply with all requirements specified on drawing 12910349.

40.3 Inside diameter of body weldment. The inside diameter of the body weldment shall be 6.75 inches minimum.

40.4 Air pressure test. The container assembly shall not exceed the leak rate of 5 cc/min when tested in accordance with 50.2.1.

40.5 Interchangeability. The cover assemblies and body weldments shall be interchangeable without affecting the function of the container.

40.6 Palletization test. All containers shall be palletized in accordance with 50.2.4.

40.7 Workmanship. All parts shall be free of cracks, burrs, chips, dirt, pin holes, rust, and bare spots unless allowed by the following workmanship standards.

a. Paint buildup. Runs, drips, sags and reinforcement overspray that are solid and exhibit no blistering are allowed. Paint drips on the sealing edge and paint buildup on gasket groove of cover assembly are not allowed.

b. Bare metal. Bare metal due to incidental chipping on edges and corners shall not to exceed 0.04 square inch.

c. Abrasions and scuffs. Abrasions and scuffs where bare metal is not exposed, due to normal handling and stacking at the rim and ring interface areas, are allowed.

d. Scratches. Scratches exposing bare metal are allowed on the cover assembly, ring and rim, provided all scratches do not accumulate a total of more than three (3) inches in length.

e. Dents. Dents are allowed provided there are no more than two per assembly and neither is larger than 2 inches in length.

f. Cracks. Cracks on edges are allowed provided they do not extend down the surface of the part or assembly when examined by the naked eye. Cracks on the edge of the pressure tab hole in the cover are acceptable.

50. INSPECTION

50.1 Examination. Unless otherwise specified examinations for major and minor characteristics shall be performed in accordance with Table II of paragraph 4.4.2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

CLASS	CHARACTERISTICS	CONFORMANCE CRITERIA	INSPECTION METHOD
50.1.1	Gasket (Drawing 12910349)		
CRITICAL	None defined		
MAJOR			
101	Material certification	Certification	
102	Hardness		50.2.3
103	Height of rectangular cross section	Table II	Gage
MINOR			
201	Poor workmanship	Table II	Visual/Gage
50.1.2	Cover Assembly (Drawing 9386824)		
CRITICAL	None defined		
MAJOR			
101	Paint thickness, minimum	Table II	Gage
MINOR			
201	Poor workmanship	Table II	Visual/Gage
50.1.3	Body Weldment, after painting (Drawing 9386830 or 12938059)		
CRITICAL	None defined		
MAJOR			
101	Paint thickness, minimum	Table II	Gage
102	Inside diameter, minimum	Table II	Gage
MINOR			
201	Poor workmanship	Table II	Visual/Gage

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

50.1.4 Container, Ammunition, Metal (Drawing 9386831, 12938062, or 12912366)

CRITICAL	None defined		
MAJOR			
101	Air pressure test	Table II	50.2.1
102	Interchangeability test	Table II	50.2.2
103	Palletization test	100%	50.2.4
MINOR			
201	Poor workmanship	Table II	Visual/Gage

50.2 Test methods and procedures.

50.2.1 Air pressure test of painted container assembly. Subject the container assembly to an internal air pressure of 3.0 + 0.5 PSIG. Observation shall be made for leakage. A container assembly where the leakage exceeds the requirement shall be classified as defective.

50.2.2 Interchangeability of painted container assemblies. Randomly interchange the cover assemblies with container body weldments and perform the air pressure test per 50.2.1. Failure to meet the applicable requirement shall be cause for rejection of the lot. The test shall be performed after the air pressure has been performed.

50.2.3 Hardness of gasket. One plaque (4 specimens) at the start and end of each shift shall be selected. The hardness test shall be performed on the specimens in accordance with ASTM D2240. Shore A hardness readings shall be taken on the end of each specimen. Any specimen failing the applicable requirements shall be cause for rejection of that lot of material. This requirement applies to the gasket manufacturer. If the gaskets are purchased, the contractor shall verify the hardness by obtaining a Certified Material Test Report (CMTR) from the gasket manufacturer.

50.2.4 Palletization test. Select thirty containers and palletize them five wide by six high. Any container that cannot be interlocked or stacked shall be rejected and replaced with an acceptable one

Custodian:
Army (AR)

Preparing activity:
Army (AR)

Project Number:
8140-0041

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

METRIC
MIL-C-70478C (AR)
AMENDMENT 1
29 March 1995

MILITARY SPECIFICATION

CONTAINER, AMMUNITION, METAL, FOR CARTRIDGE, 120 mm, TANK AMMUNITION

This amendment forms a part of MIL-C-70478C (AR), dated 04 October 1994, and is approved for use by the U.S. Army Armament Research, Development and Engineering Center, Department of the Army, and is available for use within the distribution limitations noted below.

The attached insertable replacement pages listed below are replacements for stipulated pages. When the new pages have been entered in the document, insert the amendment as the cover sheet to the specification.

Replacement page	Page replaced
*6	6
*40	40
*40a	None
*44	44
*44a	None
*46	46
*46a	None

* Indicates specific pages revised by this Amendment.

AMSC N/A

FSC-8140

DISTRIBUTION STATEMENT B: - Distribution authorized to U.S. Government agencies and 120 mm system contractors only in accordance with Arms Export Control (22.USC.2778). Other requests for this document shall be referred to ARDEC, AMSTA-AR-ESM-I, Rock Island, IL.

Custodian:
Army - AR

Preparing activity:
Army - AR

Project number:
8140-0048

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Supersedes page 6 dated 04 October 1994

Table I. First Article Inspection.

CAGE CODE 19200

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET 1 OF 2		DRAWING NUMBER
	Assemblies and Components			See Below
				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
	Metal Containers, painted - (Drawing 9386831, 12912366, or 12938062)			
	a. Examination for defects	5	3.2	4.4.2.18
	b. Air pressure	5	3.2	4.5.6.2
	c. Corrosion resistance test	5	3.4	4.5.10
	Body Weldment, unpainted - (Drawing 9386830 or 12938059)			
	a. Examination for defects	10	3.2	4.4.2.16
	b. Air pressure	5	3.2	4.5.6.1
	c. Weld rim to body (see note)	5	3.2	4.5.2
	Cover Assembly, unpainted - (Drawing 12934838)			
	a. Examination for defects	5	3.2	4.4.2.9
	b. Air pressure	5	3.2	4.5.6.1
	Cover assembly, painted - (Drawing 12934838)			
	Examination for defects	5	3.2	4.4.2.10

NOTES: The weld security inspections, body tensile strength, spring tests and gasket tensile stress test shall be performed after the other inspections have been performed on the applicable samples.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

4.5.6.2 Air pressure of painted metal container. Subject the metal container to the internal air pressure, specified in the applicable metal container drawing. Observation shall be made for a pressure drop exceeding the requirement (as specified in the applicable drawing). A metal container, which exceeds the requirement shall be classed defective.

4.5.7 Cover assembly test. Upon assembly of the body and cover, the cover shall freely engage and rotate within the body. The Square handle shall engage into the respective bayonet slots of the rim without interference when in the clamping position. The Square handle when disengaged and in the open position shall disengage the cover from the body.

4.5.8 Screw torque test. The minimum applicable torque shall be applied to the screw. Any evidence of motion of the screw before reaching the minimum acceptable torque shall be cause for rejection of the container assembly being tested.

4.5.9 Body end irregularities. Visually inspect the body end for any nicks, dents, gouges, or mismatch. If a defect is evident, place a .01 inch diameter wire on the defect and a one inch long block over the wire. With the wire nested in the irregularity, gently press down on the block and remove the wire. If there is no evidence of resistance caused by the block, the part shall be classed defective.

* 4.5.10 Corrosion resistance test. The exterior surface of the container shall meet the salt spray requirements of TT-C-490.

5. PACKAGING

5.1 Preservation. None required.

5.2 Packing.

5.2.1 Level A. The metal container shall be packed in accordance with Level A of MIL-STD-1169.

5.2.2 Level B. The metal container shall be packed in accordance with Level B of MIL-STD-1169.

5.2.3 Commercial. The metal container shall be packed in accordance with ASTM D3951.

5.3 Marking.

5.3.1 Level A. The metal container shall be marked in accordance with Level A of MIL-STD-1169.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

CAGE CODE
19200

5.3.2 Level B. The metal container shall be marked in accordance with Level B of MIL-STD-1169.

5.3.3 Commercial. The metal container shall be marked in accordance with ASTM D3951 and the following additional instructions. Commercial shipping tags attached with wire shall show: Item name and

New page.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

40.2 Gasket. The gasket shall comply with all requirements specified on drawing 12910349.

* 40.3 Inside diameter of body weldment. The inside diameter of the body weldment shall be 6.737 inches minimum after painting.

40.4 Air pressure test. The container assembly shall not exceed the leak rate of 5 cc/min when tested in accordance with 50.2.1.

40.5 Interchangeability. The cover assemblies and body weldments shall be interchangeable without affecting the function of the container.

40.6 Palletization test. All containers shall be palletized in accordance with 50.2.4.

40.7 Workmanship. All parts shall be free of cracks, burrs, chips, dirt, pin holes, rust, and bare spots unless allowed by the following workmanship standards.

a. Paint buildup. Runs, drips, sags and reinforcement overspray that are solid and exhibit no blistering are allowed. Paint drips on the sealing edge and paint buildup on gasket groove of cover assembly are not allowed.

b. Bare metal. Bare metal due to incidental chipping on edges and corners shall not to exceed 0.04 square inch.

c. Abrasions and scuffs. Abrasions and scuffs where bare metal is not exposed, due to normal handling and stacking at the rim and ring interface areas, are allowed.

d. Scratches. Scratches exposing bare metal are allowed on the cover assembly, ring and rim, provided all scratches do not accumulate a total of more than three (3) inches in length.

e. Dents. Dents are allowed provided there are no more than two per assembly and neither is larger than 2 inches in length.

f. Cracks. Cracks on edges are allowed provided they do not extend down the surface of the part or assembly when examined by the naked eye. Cracks on the edge of the pressure tab hole in the cover are acceptable.

* 40.8 Lot number. The container lot number shall comply with MIL-STD-1168A to include the suffix of an overhauled lot for refurbished containers.

51

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

CAGE CODE
19200

APPENDIX A

* 40.9 Paint thickness. The paint thickness may be increased to cover the shot blast profile and meet the salt spray requirement.

50. INSPECTION

50.1 Examination. Unless otherwise specified examinations for major and minor characteristics shall be performed in accordance with Table II of paragraph 4.4.2.

New page.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

50.1.4 Container, Ammunition, Metal (Drawing 9386831, 12938062, or 12912366)

CRITICAL	None defined			
MAJOR				
101	Air pressure test	Table II	50.2.1	
102	Interchangeability test	Table II	50.2.2	
103	Palletization test	100%	50.2.4	
* 104	Corrosion resistance test	5	50.2.5	
MINOR				
201	Poor workmanship	Table II	Visual/Gage	

50.2 Test methods and procedures.

50.2.1 Air pressure test of painted container assembly. Subject the container assembly to an internal air pressure of 3.0 + 0.5 PSIG. Observation shall be made for leakage. A container assembly where the leakage exceeds the requirement shall be classified as defective.

50.2.2 Interchangeability of painted container assemblies. Randomly interchange the cover assemblies with container body weldments and perform the air pressure test per 50.2.1. Failure to meet the applicable requirement shall be cause for rejection of the lot. The test shall be performed after the air pressure has been performed.

50.2.3 Hardness of gasket. One plaque (4 specimens) at the start and end of each shift shall be selected. The hardness test shall be performed on the specimens in accordance with ASTM D2240. Shore A hardness readings shall be taken on the end of each specimen. Any specimen failing the applicable requirements shall be cause for rejection of that lot of material. This requirement applies to the gasket manufacturer. If the gaskets are purchased, the contractor shall verify the hardness by obtaining a Certified Material Test Report (CMTR) from the gasket manufacturer.

50.2.4 Palletization test. Select thirty containers and palletize them five wide by six high. Any container that cannot be interlocked or stacked shall be rejected and replaced with an acceptable one.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

CAGE CODE
19200

* 50.2.5 Corrosion resistance test. The exterior surface of the container shall meet the salt spray requirements of TT-C-490. This test shall be performed prior to acceptance of the first production lot.

Custodian:
Army (AR)

Preparing activity:
Army (AR)

Project Number:
8140-0041

New page.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

METRIC
MIL-C-70478C (AR)
AMENDMENT 2
26 January 1998
SUPERSEDING
AMENDMENT 1
29 March 1995

MILITARY SPECIFICATION

CONTAINER, AMMUNITION, METAL, FOR CARTRIDGE, 120 mm, TANK AMMUNITION

This amendment forms a part of MIL-C-70478C (AR), dated 04 October 1994, and is approved for use by the U.S. Army Armament Research, Development and Engineering Center, Department of the Army, and is available for use within the distribution limitations noted below.

The attached insertable replacement pages listed below are replacements for stipulated pages. When the new pages have been entered in the document, insert the amendment as the cover sheet to the specification.

Replacement page	Page replaced
6	6
40	40
40a	None
*44	44
44a	None
46	46
*46a	None

* Indicates specific pages revised by this Amendment.

AMSC N/A

FSC-8140

DISTRIBUTION STATEMENT B: - Distribution authorized to U.S. Government agencies and 120 mm system contractors only in accordance with Arms Export Control (22.USC.2778). Other requests for this document shall be referred to ARDEC, AMSTA-AR-ESM-I, Rock Island, IL.

Custodian:
Army - AR

Preparing activity:
Army - AR

Project number:
8140-0195

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Table I. First Article Inspection.

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE Assemblies and Components	SHEET 1 OF 2		DRAWING NUMBER See Below NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
	Metal Containers, painted - (Drawing 9386831, 12912366, or 12938062)			
	a. Examination for defects	5	3.2	4.4.2.18
	b. Air pressure	5	3.2	4.5.6.2
	c. Corrosion resistance test	5	3.4	4.5.10
	Body Weldment, unpainted - (Drawing 9386830 or 12938059)			
	a. Examination for defects	10	3.2	4.4.2.16
	b. Air pressure	5	3.2	4.5.6.1
	c. Weld rim to body (see note)	5	3.2	4.5.2
	Cover Assembly, unpainted - (Drawing 12934838)			
	a. Examination for defects	5	3.2	4.4.2.9
	b. Air pressure	5	3.2	4.5.6.1
	Cover assembly, painted - (Drawing 12934838)			
	Examination for defects	5	3.2	4.4.2.10

NOTES: The weld security inspections, body tensile strength, spring tests and gasket tensile stress test shall be performed after the other inspections have been performed on the applicable samples.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

4.5.6.2 Air pressure of painted metal container. Subject the metal container to the internal air pressure, specified in the applicable metal container drawing. Observation shall be made for a pressure drop exceeding the requirement (as specified in the applicable drawing). A metal container, which exceeds the requirement shall be classed defective.

4.5.7 Cover assembly test. Upon assembly of the body and cover, the cover shall freely engage and rotate within the body. The Square handle shall engage into the respective bayonet slots of the rim without interference when in the clamping position. The Square handle when disengaged and in the open position shall disengage the cover from the body.

4.5.8 Screw torque test. The minimum applicable torque shall be applied to the screw. Any evidence of motion of the screw before reaching the minimum acceptable torque shall be cause for rejection of the container assembly being tested.

4.5.9 Body end irregularities. Visually inspect the body end for any nicks, dents, gouges, or mismatch. If a defect is evident, place a .01 inch diameter wire on the defect and a one inch long block over the wire. With the wire nested in the irregularity, gently press down on the block and remove the wire. If there is no evidence of resistance caused by the block, the part shall be classed defective.

4.5.10 Corrosion resistance test. The exterior surface of the container shall meet the salt spray requirements of TT-C-490.

5. PACKAGING

5.1 Preservation. None required.

5.2 Packing.

5.2.1 Level A. The metal container shall be packed in accordance with Level A of MIL-STD-1169.

5.2.2 Level B. The metal container shall be packed in accordance with Level B of MIL-STD-1169.

5.2.3 Commercial. The metal container shall be packed in accordance with ASTM D3951.

5.3 Marking.

5.3.1 Level A. The metal container shall be marked in accordance with Level A of MIL-STD-1169.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

5.3.2 Level B. The metal container shall be marked in accordance with Level B of MIL-STD-1169.

5.3.3 Commercial. The metal container shall be marked in accordance with ASTM D3951 and the following additional instructions. Commercial shipping tags attached with wire shall show: Item name and

New page.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

40.2 Gasket. The gasket shall comply with all requirements specified on drawing 12910349.

* 40.3 Inside diameter of body weldment. Acceptance criteria is defined as the ability of the refurbished container to accept the insertion of the Projectile Support/Sleeve and Strap assembly during the load assemble and pack operation.

40.4 Air pressure test. The container assembly shall not exceed the leak rate of 5 cc/min when tested in accordance with 50.2.1.

40.5 Interchangeability. The cover assemblies and body weldments shall be interchangeable without affecting the function of the container.

40.6 Palletization test. All containers shall be palletized in accordance with 50.2.4.

40.7 Workmanship. All parts shall be free of cracks, burrs, chips, dirt, pin holes, rust, and bare spots unless allowed by the following workmanship standards.

a. Paint buildup. Runs, drips, sags and reinforcement overspray that are solid and exhibit no blistering are allowed. Paint drips on the sealing edge and paint buildup on gasket groove of cover assembly are not allowed.

b. Bare metal. Bare metal due to incidental chipping on edges and corners shall not to exceed 0.04 square inch.

c. Abrasions and scuffs. Abrasions and scuffs where bare metal is not exposed, due to normal handling and stacking at the rim and ring interface areas, are allowed.

d. Scratches. Scratches exposing bare metal are allowed on the cover assembly, ring and rim, provided all scratches do not accumulate a total of more than three (3) inches in length.

e. Dents. Dents are allowed provided there are no more than two per assembly and neither is larger than 2 inches in length.

f. Cracks. Cracks on edges are allowed provided they do not extend down the surface of the part or assembly when examined by the naked eye. Cracks on the edge of the pressure tab hole in the cover are acceptable.

*g. Rust spots. When reusing the container in accordance with paragraph 60.1, container body rust spots shall be removed and refinished. Localized rust may be removed by mechanical means such as sanding and/or wire brush, etc. Any resultant bare metal on the container body shall be touched-up in accordance with paragraph 60.1.

59

Supersedes page 44 dated 04 October 1994.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

40.8 Lot number. The container lot number shall comply with MIL-STD-1168A to include the suffix of an overhauled lot for refurbished containers.

40.9 Paint thickness. The paint thickness may be increased to cover the shot blast profile and meet the salt spray requirement.

50. INSPECTION

50.1 Examination. Unless otherwise specified examinations for major and minor characteristics shall be performed in accordance with Table II of paragraph 4.4.2.

60

New page.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

50.1.4 Container, Ammunition, Metal (Drawing 9386831, 12938062, or 12912366)

CRITICAL	None defined		
MAJOR			
101	Air pressure test	Table II	50.2.1
102	Interchangeability test	Table II	50.2.2
103	Palletization test	100%	50.2.4
104	Corrosion resistance test	5	50.2.5
MINOR			
201	Poor workmanship	Table II	Visual/Gage

50.2 Test methods and procedures.

50.2.1 Air pressure test of painted container assembly. Subject the container assembly to an internal air pressure of 3.0 + 0.5 PSIG. Observation shall be made for leakage. A container assembly where the leakage exceeds the requirement shall be classified as defective.

50.2.2 Interchangeability of painted container assemblies. Randomly interchange the cover assemblies with container body weldments and perform the air pressure test per 50.2.1. Failure to meet the applicable requirement shall be cause for rejection of the lot. The test shall be performed after the air pressure has been performed.

50.2.3 Hardness of gasket. One plaque (4 specimens) at the start and end of each shift shall be selected. The hardness test shall be performed on the specimens in accordance with ASTM D2240. Shore A hardness readings shall be taken on the end of each specimen. Any specimen failing the applicable requirements shall be cause for rejection of that lot of material. This requirement applies to the gasket manufacturer. If the gaskets are purchased, the contractor shall verify the hardness by obtaining a Certified Material Test Report (CMTR) from the gasket manufacturer.

50.2.4 Palletization test. Select thirty containers and palletize them five wide by six high. Any container that cannot be interlocked or stacked shall be rejected and replaced with an acceptable one.

61

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

50.2.5 Corrosion resistance test. The exterior surface of the container shall meet the salt spray requirements of TT-C-490. This test shall be performed prior to acceptance of the first production lot.

* 60.1 Reuse with limited refurbishment. If approved by the Procuring Contract Officer (PCO) containers may be re-used without completely stripping the paint and removing the inserts if the container is received at the load center without any apparent rust on the inside. Remove dirt and dust from container exterior. The rust on the outside must not exceed grade 7 of ASTM-D610. Any rust spots must be removed and touched-up in accordance with the protective finish requirements of drawing 9386830 prior to pack-out. The gasket shall be replaced (30.6), old markings shall be obliterated. The following paragraphs of Appendix A shall be applicable, 30.6, 40.2, 40.4, 40.6, 40.7, 50.1.1, 50.1.4 and 50.2. Major 101 of 50.1.4, air pressure test, is required to pass normal inspection sampling per Table II. Paragraph 50.2.2 and Major 102 of 50.1.4, Interchangeability test, are not required.

Custodian:
Army (AR)

Preparing activity:
Army (AR)

Project Number:
8140-0195

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

METRIC
MIL-C-70478C (AR)
AMENDMENT 5
23 June 1998
SUPERSEDING
AMENDMENT 4
10 June 1998

MILITARY SPECIFICATION

CONTAINER, AMMUNITION, METAL, FOR CARTRIDGE, 120 mm, TANK AMMUNITION

This amendment forms a part of MIL-C-70478C (AR), dated 04 October 1994, and is approved for use by the U.S. Army Armament Research, Development and Engineering Center, Department of the Army, and is available for use within the distribution limitations noted below.

The attached insertable replacement pages listed below are replacements for stipulated pages. When the new pages have been entered in the document, insert the amendment as the cover sheet to the specification.

Replacement page		Page replaced	
2	37	2	37
3	38	3	38
4	40	4	40
5	40a	5	None
6	41	6	41
8	43	8	43
9	44	9	44
11	44a	11	None
12	45	12	45
*13	46	13	46
14-35	46a	14-35	None

* Indicates specific pages revised by this Amendment.

AMSC N/A FSC-8140

DISTRIBUTION STATEMENT B: - Distribution authorized to U.S. Government agencies and 120 mm system contractors only in accordance with Arms Export Control (22.USC.2778). Other requests for this document shall be referred to ARDEC, AMSTA-AR-ESM-I, Rock Island, IL.

Custodian:
Army - AR

Preparing activity:
Army - AR

Project number:
8140-0203

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

STANDARDS

MILITARY

MIL-STD-171	Finishing of Metal and Wood Surfaces
MIL-STD-1916	DoD Preferred Methods for Acceptance of Product

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein. Unless otherwise specified, the issues shall be those in effect on the date of the solicitation.

DRAWINGS (See 6.4)

U.S. ARMY ARMAMENT RESEARCH, DEVELOPMENT AND ENGINEERING CENTER (ARDEC)

9386831	Container, Ammunition, Metal
12912366	Container, Ammunition, Metal
12938062	Container, Ammunition, Metal, PA116A1

(Copies of specifications, standards, and other Government documents required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issue of the nongovernment documents which is current on the date of the solicitation.

Supersedes page 2 dated 04 October 1994.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D2240	Indentation Hardness of Rubber and Plastics by means of a Durometer, Standard Method of Test for
ASTM D3951	Commercial Packaging, Standard Practice for
ASTM E8	Tension Testing of Metallic Materials, Standard Method of
ASTM E18	Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials, Test for

AMERICAN WELDING SOCIETY

AWS A2.4	Standard Symbols for Welding, Brazing and Nondestructive Examination

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein (except for associated detail specifications, specification sheets or MS standards), the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Materials. Materials and parts shall be in accordance with applicable drawings and specifications.

3.2 Components and assemblies. The components and assemblies shall comply with all requirements per drawing 9386831 or 12912366 and the drawings and specifications referenced thereon.

3.3 Welding. The welding shall comply with the requirements of AWS A2.4.

3.3.1 Tensile strength (if applicable). The tensile strength of the longitudinal body weld shall be not less than 65 percent of the tensile strength of body material when tested as specified in 4.5.1.

3.3.1.1 Tensile strength of body material. The tensile strength of the body material shall be not less than 60,000 pounds per square inch (psi) as specified in 4.5.1.

3.4 Painted surface. The painted surfaces of the container shall comply with the requirements of TT-C-490. However, the film thickness and salt spray requirements of TT-C-490 will not apply to the interior surfaces, welded spots and sharp corners of the exterior surface of the container. Bare spots permissible on all bearing surfaces as per drawing 9386831, 12912366, or 12938062.

Supersedes page 3 dated 04 October 1994.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

3.5 Cover assembly. Upon assembly of the cover assembly to the body weldment, the cover assembly shall freely engage and rotate within the body weldment. As the cover assembly is rotated with the square handle in the open position, the handle shaft ends shall freely engage into the respective bayonet slots of the rim. When the square handle is in the closed position (rotated 180°), the hairpin spring clip shall be inserted into the upper holes in the shaft support and handle and lock the handle in place. When the hairpin spring clip is removed and the handle rotated to the open position, the cover assembly shall disengage from the body weldment.

3.6 First article inspection. This specification contains technical provisions for first article inspection. Requirements for the submission of first article samples by the contractor shall be as specified in the contract.

3.7 Workmanship.

3.7.1 Components and assemblies. The components and assemblies shall be regular, smooth and free from wrinkles, pin holes, cracks, dirt, rough spots, burrs, sharp edges and any other defect that might affect the serviceability, durability, safety and appearance of the container.

3.7.2 Paint coating. The paint coating shall be in accordance with applicable drawings and comply with instructions in MIL-STD-171. The finish coat shall cover all required surfaces and be continuous with the possible exception of a few light scratches not exposing the base metal or the primer coat.

3.7.3 Parts. All parts shall be free of chips, dirt, grease, rust and foreign material. The cleaning method used shall not be injurious to any of the parts nor shall any of the parts be contaminated by the cleaning agents used.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.1.2 General provisions. Unless otherwise specified herein, the provisions of MIL-STD-1916 apply and form a part of this specification.

4.2 Classification of inspections. The following types of inspection shall be conducted on this item:

a. First article inspection

b. Quality conformance inspection

4.3 First article inspection.

4.3.1 Submission. The contractor shall submit a first article sample as designated by the Contracting Officer for evaluation in accordance with provisions of 4.3.2. The first article sample shall consist of five painted metal containers, five painted cover assemblies, five unpainted cover assemblies, and ten each of every subassembly and component (unpainted).

4.3.2 Inspection to be performed. As determined by the Government, the first article assemblies, components and test specimens may be subjected to any or all of the examination and tests specified in this detail specification and be inspected for compliance with any or all requirements of the applicable drawings. (See table I)

4.3.3 Rejection. If any assembly, component or test specimen fails to comply with any of the applicable requirements, the first article sample shall be rejected. The Government reserves the right to terminate inspection upon any failure of an assembly, component or test specimen to comply with any of the requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Table I. First Article Inspection.

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE: Assemblies and Components	SHEET 1 OF 2		DRAWING NUMBER: See Below
				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
	Metal Containers, painted - (Drawing 9386831 or 12912366)			
	a. Examination for defects	5	3.2	4.4.2.18
	b. Air pressure	5	3.2	4.5.6.2
	c. Corrosion resistance test	5	3.4	4.5.10
	Body Weldment, unpainted - (Drawing 9386830)			
	a. Examination for defects	10	3.2	4.4.2.16
	b. Air pressure	5	3.2	4.5.6.1
	c. Weld rim to body (see note)	5	3.2	4.5.2
	Cover Assembly, unpainted - (Drawing 12934838)			
	a. Examination for defects	5	3.2	4.4.2.9
	b. Air pressure	5	3.2	4.5.6.1
	Cover assembly, painted - (Drawing 12934838)			
	Examination for defects	5	3.2	4.4.2.10

NOTES: The weld security inspections, body tensile strength, spring tests and gasket tensile stress test shall be performed after the other inspections have been performed on the applicable samples.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

4.4 Quality conformance inspection.

4.4.1 Inspection lot formation. Inspection lots shall comply with the lot formation provisions of MIL-STD-1916. In addition, inspection lots of containers shall contain material from lots with the same interfix number from one manufacturer.

4.4.2 Examination. Examinations listed in the Classification of Characteristics shall be performed on inspection lots as defined in 4.4.1 of this specification.

a. Sampling inspection. The provisions/procedures of MIL-STD-1916 are applicable to this specification. Unless otherwise specified, attributes sampling shall be utilized for the conformance characteristics listed in Part III herein. Attributes sampling shall be in accordance with MIL-STD-1916, Table II, as modified below, using the verification levels (VL) cited in the conformance criteria columns of Part III. When approved for use, variables and continuous sampling plans shall be in accordance with MIL-STD-1916, Tables III and IV respectively, as modified below. Unless otherwise specified, the procedure in MIL-STD-1916 for normal inspection shall be used at the start of production for current or previous suppliers of the item. For all new suppliers of the item, tightened inspection shall be used at the start of production and be continued until the criteria for normal inspection are met. The sampling plans for MIL-STD-1916, Tables II (Attribute), III (Variables), IV (Continuous), are modified as follows:

VL-I and VL-II – Replace the sample sizes for Codes C and D with the sample size for Code E.

VL-III – Replace the sample sizes for Codes B, C and D with the sample size for Code E.

VL-IV – Replace the sample size for Code A with the sample size for Code B and replace the sample size for Codes B, D and E with the sample size for Code C.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

b. Alternative quality conformance provision. Unless otherwise specified herein or provided for in the contract, alternative quality conformance procedures, methods or equipment (see 6.3), such as statistical process control, tool control, other types of sampling procedures, etc., may be used by the contractor when they provide, as a minimum, the level of quality assurance required by the provisions specified herein. Prior to applying such alternative procedures, methods or equipment, the contractor shall describe them in a written proposal submitted to the Government for evaluation. When required, the contractor shall demonstrate that the effectiveness of each proposed alternative is equal to or better than the specified quality conformance provision(s) herein. In case of dispute as to whether the contractor's proposed alternative(s) provides equivalent assurance, the provisions of this specification shall apply. All approved alternative provisions shall be specifically incorporated into the contractor's quality program or inspection system, as applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.1	TITLE Support, Shaft	SHEET 1 OF 2		DRAWING NUMBER 12934841
				NEXT HIGHER ASSEMBLY 12934839
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Diameter of large hole	Table III	3.2	Gage
102	Diameter of small hole	Table III	3.2	Gage
103	True position of large hole and slot	Table III	3.2	Gage
104	Deleted			
105	True position of small holes	Table III	3.2	Gage
106	Distance between shaft support uprights	Table III	3.2	Gage
107	Deleted			
108	Deleted			
109	Wall thickness	Table III	3.2	Gage
NOTES:				

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.1	TITLE Support, Shaft	SHEET 2 OF 2		DRAWING NUMBER 12934841
				NEXT HIGHER ASSEMBLY 12934839
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Major				
110	Deleted			
Minor				
201	Deleted			
202	Deleted			
203	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.2	TITLE Handle	SHEET 1 OF 2		DRAWING NUMBER 12929273
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
*101	True position of small holes	Level III	3.2	Gage
*102	Location of shaft hexhole, 2 places	Level III	3.2	Gage
103	Deleted			
104	Deleted			
Minor				
*201	Diameter of small holes	Level II	3.2	Gage
*202	Length of handle opening	Level II	3.2	Gage
*203	Width of handle opening	Level II	3.2	Gage
204	Width of shaft hex hole (three readings 60° apart), 2 places	Level II	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.2	TITLE Handle	SHEET 2 OF 2		DRAWING NUMBER 12929273
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
205	Largest width of handle	Level II	3.2	Gage
206	Wall thickness	Level II	3.2	Gage
207	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.3	TITLE Shaft	SHEET 1 OF 2		DRAWING NUMBER 9344037
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Length of hexagon segment of shaft	Level III	3.2	Gage
102	Large diameter (two places)	Level III	3.2	Gage
103	Small diameter (two places)	Level III	3.2	Gage
104	Total length of large diameters and hexagon segments	Level III	3.2	Gage
105	Small diameter segment not tangent to large diameter segment and side of hexagon segment	Level III	3.2	Visual
106	Length of large diameter segment (two places)	Level III	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET 2 OF 2	DRAWING NUMBER
4.4.2.3	Shaft		9344037
			NEXT HIGHER ASSEMBLY
			12934838

CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
201	Width across flats of hexagon segment (three readings, 60° apart)	Level II	3.2	Gage
202	Length of small diameter segment (two places)	Level II	3.2	Gage
203	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.4	TITLE Washer	SHEET 1 OF 1		DRAWING NUMBER 9344038
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Inside diameter	Level III	3.2	Gage
102	Height	Level III	3.2	Gage
Minor				
201	Outside diameter	Level II	3.2	Gage
202	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.5	TITLE Retainer, Washer	SHEET 1 OF 1		DRAWING NUMBER 9344041
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Material certification	Level III	3.2	Certification
Minor				
201	Diameter of hole	Level II	3.2	Gage
202	Inside diameter	Level II	3.2	Gage
203	Height of retainer	Level II	3.2	Gage
204	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.6	TITLE Cover	SHEET 1 OF 2		DRAWING NUMBER 9386821
				NEXT HIGHER ASSEMBLY 12934839 or 9386822
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Outside diameter	Level III	3.2	Gage
102	Wall thickness	Level III	3.2	Gage
103	Depth of groove	Level III	3.2	Gage
104	Width of groove	Level III	3.2	Gage
105	Depth from rim to inside of cover base	Level III	3.2	Gage
106	Height of threads, minimum	Level III	3.2	Gage
107	Location of air test hole with center of cover	Level III	3.2	Gage
108	Flatness of bottom surface inside annular ring and surrounding air test hole	Level III	3.2	Gage
109	Height of annular ring around air test hole	Level III	3.2	Gage
NOTES:				

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.6	TITLE Cover	SHEET 2 OF 2		DRAWING NUMBER 9386821
				NEXT HIGHER ASSEMBLY 9386822 or 12934839
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor 201	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.7	TITLE Gasket	SHEET 1 OF 1		DRAWING NUMBER 12910349
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Material certification	Level III	3.2	Certification
102	Deleted			
103	Hardness	Level III 1/	3.2	4.5.5
104	Inside diameter, maximum	Level III	3.2	Gage
105	Large width	Level III	3.2	Gage
106	Middle width	Level III	3.2	Gage
107	Height of rectangular cross section	Level III	3.2	Gage
108	Deleted			
109	Deleted			
Minor				
201	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:
1/ One plaque (4 specimens) at start and end of each shift.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.8	TITLE Cover Weldment	SHEET 1 OF 1		DRAWING NUMBER 12934839
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	True position of shaft hole and slot	Level III	3.2	Gage
102	True position of shaft support uprights	Level III	3.2	Gage
Minor				
201	Weld missing, incomplete or visually inadequate	Level II	3.2	Visual/Manual
202	Deleted			
203	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.9	TITLE Cover Assembly, Prior to Painting	SHEET 1 OF 1		DRAWING NUMBER 12934838
				NEXT HIGHER ASSEMBLY 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Air pressure	100%	3.2	4.5.6.1/Drawing 9386824
102	Rotating of shaft inadequate after crimping	Level III	3.2	Manual
103	Distance from inside cover rim to top of shaft	Level III	3.2	Gage
104	Deleted			
Minor				
201	Component missing or inadequately assembled	Level II	3.2	Visual
202	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.10	TITLE Cover Assembly, After Painting	SHEET 1 OF 1		DRAWING NUMBER 12934838
				NEXT HIGHER ASSEMBLY 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Gasket improperly bonded to cover	Level III	3.2	Visual
102	After painting, the shaft shall freely rotate	Level III	3.2	Manual
103	Primer thickness, min.	Level III	3.2	Gage
104	Top coat thickness, min.	Level III	3.2	Gage
105	Spring clip and wire rope assembly inadequately swaged onto handle or hairpin spring clip	Level III	3.2	Visual/Manual
Minor				
201	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.11	TITLE Rim	SHEET 1 OF 2		DRAWING NUMBER 9386827
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Length of larger slot on side of rim	Level III	3.2	Gage
102	Location of larger slot from inside flat	Level III	3.2	Gage
103	Deleted			
104	Location of bayonet slot, 4 places	Level III	3.2	Gage
105	Dimension across flats, 2 places (Dimension A)	Level III	3.2	Gage
106	Dimension across corner, 2 places (Dimension D)	Level III	3.2	Gage
107	Width of larger slot	Level III	3.2	Gage
108	Inside diameter of rim (Dimension E)	Level III	3.2	Gage
109	Bayonet locking edge radius (2 places)	Level III	3.2	Gage
NOTES:				

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.11	TITLE Rim	SHEET 2 OF 2		DRAWING NUMBER 9386827
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
201	Depth from edge of rim to inside flat	Level II	3.2	Gage
202	Deleted			
203	Deleted			
204	Drainage hole missing	Level II	3.2	Visual
205	Evidence of poor workmanship	Level II	3.7	Visual
NOTES:				

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.12	TITLE Ring	SHEET 1 OF 2		DRAWING NUMBER 9386826
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Length of larger slot on side of ring	Level III	3.2	Gage
102	Location of larger slot from inside flat	Level III	3.2	Gage
103	Deleted			
104	Dimensions across flats, 2 places (Dimension A)	Level III	3.2	Gage
105	Width of larger slot	Level III	3.2	Gage
106	Opening of container interlocking grip	Level III	3.2	Gage
107	Depth of container interlocking grip	Level III	3.2	Gage
NOTES:				

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.12	TITLE Ring	SHEET 2 OF 2		DRAWING NUMBER 9386826
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
201	Distance from edge of ring to outside flat	Level II	3.2	Gage
202	Deleted			
203	Deleted			
204	Location of container interlocking cutouts	Level II	3.2	Gage
205	Width of interlocking cutouts	Level II	3.2	Gage
206	Depth from interlocking cutout to inside flat	Level II	3.2	Gage
207	Drainage hole missing	Level II	3.2	Visual
208	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.13	TITLE Bottom	SHEET 1 OF 1		DRAWING NUMBER 9386825
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Material thickness	Level III	3.2	Gage
102	Hole location 1/	Level III	3.2	Gage
103	Hole diameter 1/	Level III	3.2	Gage
Minor				
201	Height of lip, minimum	Level II	3.2	Gage
202	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:
1/ 9386825 only.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.14	TITLE Body	SHEET 1 OF 1		DRAWING NUMBER 9386828
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Tensile strength of weld	Level III 1/	3.3.1	4.5.1
102	Wall thickness	Level III	3.2	Gage
103	Deleted			
104	Deleted			
105	Deleted			
Minor				
201	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:
1/ Three coupons per shift.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.15	TITLE Plug, Stacking	SHEET 1 OF 1		DRAWING NUMBER 9386837
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Length of plug	Level III	3.2	Gage
102	Width of plug	Level III	3.2	Gage
Minor				
201	Deleted			
202	Deleted			
203	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.16	TITLE Body Weldment, Prior to Painting	SHEET 1 OF 2		DRAWING NUMBER 9386830
				NEXT HIGHER ASSEMBLY 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Air pressure	100%	3.2	4.5.6.1
102	Weld of rim to body	Level III 1/	3.2	4.5.2
103	True position of holes of ring, rim and stacking plug	Level III	3.2	Gage
104	Location of hole in rim relative to holes in inside rings and stacking plugs	Level III	3.2	Gage
105	Location of hole in rim relative to hole in outside rings and stacking plugs	Level III	3.2	Gage
106	Perpendicularity of ring and rims with Datum-A	Level III	3.2	Gage
107	Distance from end of body to top of rim bayonet slot (four places)	Level III	3.2	Gage

NOTES:
1/ Three coupons per shift.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.16	TITLE Body Weldment, Prior to Painting	SHEET 2 OF 2		DRAWING NUMBER 9386830
				NEXT HIGHER ASSEMBLY 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Major				
108	Minimum shear load between stacking plug and body	Level III	3.2	Gage
109	Flatness of body	Level III	3.2	Gage
110	Body end irregularities	Level III	3.2	4.5.9
111	Depth of body weldment	Level III	3.2	Gage
112	Deleted			
113	Deleted			
Minor				
201	Any weld of ring, rim or bottom to body missing, incomplete or visually inadequate	Level II	3.2	Visual
202	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:
2/ Deleted

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.17	TITLE Body Weldment, After Painting	SHEET 1 OF 1		DRAWING NUMBER 9386830 or 12938059
				NEXT HIGHER ASSEMBLY 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Primer thickness	Level III	3.2	Gage
102	Paint thickness	Level III	3.2	Gage
103	Marking	Level III	3.2	5.3
104	Inside diameter, minimum	Level III	3.2	Gage
Minor				
201	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.18	TITLE Container, Ammunition, Metal	SHEET 1 OF 1		DRAWING NUMBER 9386831 or 12912366
				NEXT HIGHER ASSEMBLY 9386833, 12912369, or 12913178
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Cover assembly test	Level III	3.5	Visual/Manual/4.5.7
102	Air pressure test (with yoke assembly in place, PA116 only)	Level III	3.2	4.5.6.2
103	Screw torque test (top and bottom, PA116 and cover PA116A1 only)	Level III 1/	3.2	4.5.8
Minor				
201	Missing, loose or damaged components	Level II	3.2	Visual
202	Protective finish damaged, bare spots exposing metal, etc.	Level II	3.2	Visual
203	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:
1/ The screw torque test shall be performed after the air pressure test has been performed and the screw has been reassembled.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.20	TITLE Yoke Assembly, After Painting	SHEET 1 OF 1		DRAWING NUMBER 12561227 or 12912337
				NEXT HIGHER ASSEMBLY 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None Defined			
Major				
101	Location of the self clinching nut	Level III	3.2	Gage
102	Yoke stops inside the maximum base diameter	Level III	3.2	Gage
Minor				
201	Presence of spot welds on yoke stop	Level II	3.2	Visual
202	Pushout force improper	Level II	3.2	Gage
203	Presence of improper threads in self clinching nut	Level II	3.2	Gage/Visual
204	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

4.4.3 Testing. Testing is described in the First Article and Quality Conformance Inspection Tables.

4.4.3.1 Tensile strength. (See 3.3.1) Major Defect. Five bodies shall be randomly selected for this test. Four specimens, approximately equally spaced along the axis, shall be taken from each body at right angles to the weld. If one specimen of a sample fails to comply with the requirement, that sample shall be classed defective. If two or more samples are classed defective, the lot shall be rejected.

4.4.3.2 Tensile strength of body material. (See 3.3.1.1) Major Defect. Five bodies shall be randomly selected for this test. From each body, three specimens shall be selected at random for determination of body material tensile strength. If one specimen fails to comply with 3.3.1.1, that sample body shall be classed defective. If two or more sample bodies are classed defective, the lot shall be rejected.

4.4.3.3 Weld of rim to body. (See Drawing 9386830) Major Defect. Five body assemblies shall be selected for this test. If any sample fails to comply with the requirement, the lot shall be rejected.

4.4.3.4 Hardness of gasket. (See drawing 12910349) Major Defect. Five gaskets shall be randomly selected from each lot for this test. If any gasket fails to meet the requirement, the lot shall be rejected.

4.4.3.5 Deleted

4.4.3.5.1 Deleted

4.4.3.5.2 Deleted

4.4.3.5.3 Deleted

4.4.3.6 Deleted

4.4.4 Inspection equipment. The inspection equipment required to perform the examinations and tests prescribed herein is described in the "Inspection Method Reference" column in the tables starting with paragraph 4.4.2.1. The contractor shall submit for approval, inspection equipment designs in accordance with the terms of the contract (see 6.5).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

4.5.6.2 Air pressure of painted metal container. Subject the metal container to the internal air pressure, specified in the applicable metal container drawing. Observation shall be made for a pressure drop exceeding the requirement (as specified in the applicable drawing). A metal container, which exceeds the requirement shall be classed defective.

4.5.7 Cover assembly test. Upon assembly of the body and cover, the cover shall freely engage and rotate within the body. The Square handle shall engage into the respective bayonet slots of the rim without interference when in the clamping position. The Square handle when disengaged and in the open position shall disengage the cover from the body.

4.5.8 Screw torque test. The minimum applicable torque shall be applied to the screw. Any evidence of motion of the screw before reaching the minimum acceptable torque shall be cause for rejection of the container assembly being tested.

4.5.9 Body end irregularities. Visually inspect the body end for any nicks, dents, gouges, or mismatch. If a defect is evident, place a .01 inch diameter wire on the defect and a one inch long block over the wire. With the wire nested in the irregularity, gently press down on the block and remove the wire. If there is no evidence of resistance caused by the block, the part shall be classed defective.

4.5.10 Corrosion resistance test. The exterior surface of the container shall meet the salt spray requirements of TT-C-490.

5. PACKAGING

5.1 Preservation. None required.

5.2 Packing.

5.2.1 Deleted

5.2.2 Deleted

5.2.3 Commercial. The metal container shall be packed in accordance with ASTM D3951.

5.3 Marking.

5.3.1 Deleted

Supersedes page 40 dated 04 October 1994.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

5.3.2 Deleted

5.3.3 Commercial. The metal container shall be marked in accordance with ASTM D3951 and the following additional instructions. Commercial shipping tags attached with wire shall show: Item name and

New page.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

model number, part number and revision, contract number, lot number and data, name and address of manufacturer. If components and assemblies are bundled, boxed or palletized, the gross weight and quantity shall be included. The above information may be placed on pallets or boxes by labeling or stenciling.

5.4 Shipping. When containers from more than one lot are shipped at one time, each lot shall be kept separate and the division between lots clearly indicated to prevent mixing of lots in transit.

6. NOTES

6.1 Intended use. The metal container is intended for use as the outer shipping and storage packaging for the 120 mm Tank Cartridge.

6.2 Ordering data. Deleted

6.3 Definition of packaging and packing levels.

6.3.1 Level A. Full military protection, for unrestricted (OCONUS) shipment and storage.

6.3.2 Level B. Limited military protection for limited storage and (OCONUS) shipment.

6.3.3 Level C. For interplant (CONUS) shipment and very limited storage.

6.4 Drawings. Drawings listed in Section 2 of this specification under the heading U.S. Army Armament Research, Development and Engineering Center (ARDEC) may also include drawings prepared by, and identified as U.S. Army Armament Research and Development Command (ARRADCOM), U.S. Army Armament Research and Development Center (ARDC), Edgewood Arsenal, Frankford Arsenal, Rock Island Arsenal or Picatinny Arsenal drawings. Technical data originally prepared by these activities is now under the cognizance of ARDEC.

6.5 Submission of inspection equipment designs for approval. Submit designs as required to: Commander, U.S. Army Armament Research, Development and Engineering Center, ATTN: AMSTA-AR-QAC-T, Picatinny Arsenal, New Jersey 07801-5001.

6.6 Approval of equivalent test methods. Prior approval of the Contracting Officer is required for use of equivalent test methods. A description of the proposed method should be submitted through the Contracting Officer to: Commander, U.S. Army Armament Research, Development and Engineering Center, ATTN: AMSTA-AR-QAC-T, Picatinny Arsenal, New Jersey 07801-5001. This description should include but not be limited to the accuracy and precision of the method, test data demonstrating the accuracy and precision and drawings of any special equipment required.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

QUALITY ASSURANCE PROVISIONS FOR REFURBISHMENT

10. SCOPE

10.1 Scope. The appendix provides the Quality Assurance provisions for the refurbishment of containers, metal, for 120 mm tank ammunition. This Appendix is not a mandatory part of the Specification. The information contained herein is intended for compliance when refurbishing metal containers.

20. APPLICABLE DOCUMENTS

20.1 Government Drawings.

9386831 - Container, Ammo, Metal, PA116
Deleted
12912366 - Container, Ammo, Metal

30. REFURBISHMENT

30.1 Dents. Dents shall be removed as required to allow compliance with the workmanship requirement.

30.2 Cleaning. Paint and rust shall be removed.

30.3 Rims and/or rings. Rims and/or rings shall be straightened and welded by fillet welding where required.

30.4 Refinish. The parts shall be finished in accordance with the applicable drawings.

30.5 Seams. Seams shall be welded where required.

30.6 Gasket. The gaskets on the cover shall be replaced with new gaskets.

30.7 Refurbishment identification. Each container that will be refurbished shall have a 3/16 inch diameter hole punched/drilled in the rim (9386827-1). The hole shall be on the side where the identification markings are/were located. This side has the lip grip on the lower ring (second/bottom ring). The hole shall be approximately centered on the flat surface of the rim, but be no closer to an edge or curve than 3/8 inches. The hole will identify how many times this particular container has been refurbished.

40. REQUIREMENTS

40.1 Welds. Welds shall be in conformance with good commercial practices.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

40.2 Gasket. The gasket shall comply with all requirements specified on drawing 12910349.

40.3 Inside diameter of body weldment. Acceptance criteria is defined as the ability of the refurbished container to accept the insertion of the Projectile Support/Sleeve and Strap assembly during the load assemble and pack operation.

40.4 Air pressure test. The container assembly shall not exceed the leak rate of 5 cc/min when tested in accordance with 50.2.1.

40.5 Interchangeability. The cover assemblies and body weldments shall be interchangeable without affecting the function of the container.

40.6 Palletization test. All containers shall be palletized in accordance with 50.2.4.

40.7 Workmanship. All parts shall be free of cracks, burrs, chips, dirt, pin holes, rust, and bare spots unless allowed by the following workmanship standards.

a. Paint buildup. Runs, drips, sags and reinforcement overspray that are solid and exhibit no blistering are allowed. Paint drips on the sealing edge and paint buildup on gasket groove of cover assembly are not allowed.

b. Bare metal. Bare metal due to incidental chipping on edges and corners shall not to exceed 0.04 square inch.

c. Abrasions and scuffs. Abrasions and scuffs where bare metal is not exposed, due to normal handling and stacking at the rim and ring interface areas, are allowed.

d. Scratches. Scratches exposing bare metal are allowed on the cover assembly, ring and rim, provided all scratches do not accumulate a total of more than three (3) inches in length.

e. Dents. Dents are allowed provided there are no more than two per assembly and neither is larger than 2 inches in length.

f. Cracks. Cracks on edges are allowed provided they do not extend down the surface of the part or assembly when examined by the naked eye. Cracks on the edge of the pressure tab hole in the cover are acceptable.

g. Rust spots. When reusing the container in accordance with paragraph 60.1, container body rust spots shall be removed and refinished. Localized rust may be removed by mechanical means such as sanding and/or wire brush, etc. Any resultant bare metal on the container body shall be touched-up in accordance with paragraph 60.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

40.8 Lot number. The container lot number shall comply with MIL-STD-1168A to include the suffix of an overhauled lot for refurbished containers.

40.9 Paint thickness. The paint thickness may be increased to cover the shot blast profile and meet the salt spray requirement.

40.10 Reuse criteria. When limited refurbishment is performed on the containers in accordance with paragraph 60.1, the containers shall be inspected in accordance with paragraph 50.1.5. The unit load does not need to be depalletized if it meets the criteria of 50.1.5 and the visible exterior containers on the pallet do not appear damaged beyond the requirements of this appendix. Also that the old ammo lot number has previously been removed from the side of the container and is currently stenciled on the bottom.

50. INSPECTION

50.1 Examination. Unless otherwise specified examinations for major and minor characteristics shall be performed in accordance with Table II of paragraph 4.4.2.

New page.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

CLASS	CHARACTERISTICS	CONFORMANCE CRITERIA	INSPECTION METHOD
50.1.1	Gasket (Drawing 12910349)		
CRITICAL	None defined		
MAJOR			
101	Material certification	Certification	
102	Hardness		50.2.3
103	Height of rectangular cross section	Level III	Gage
MINOR			
201	Poor workmanship	Level II	Visual/Gage
50.1.2	Cover Assembly (Drawing 9386824)		
CRITICAL	None defined		
MAJOR			
101	Paint thickness, minimum	Level III	Gage
MINOR			
201	Poor workmanship	Level II	Visual/Gage
50.1.3	Body Weldment, after painting (Drawing 9386830)		
CRITICAL	None defined		
MAJOR			
101	Paint thickness, minimum	Level III	Gage
102	Inside diameter, minimum	Level III	Gage
MINOR			
201	Poor workmanship	Level II	Visual/Gage

Supersedes page 45 dated 04 October 1994.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

50.1.4	Container, Ammunition, Metal (Drawing 9386831 or 12912366)		
CRITICAL	None defined		
MAJOR			
101	Air pressure test	Level III	50.2.1
102	Interchangeability test	Level III	50.2.2
103	Palletization test	100%	50.2.4
104	Corrosion resistance test	5	50.2.5
MINOR			
201	Poor workmanship	Level II	Visual/Gage
50.1.5	Internal component test		
CRITICAL	None defined		
MAJOR			
101	Internal component test	100%	50.2.6
MINOR	None defined		

50.2 Test methods and procedures.

50.2.1 Air pressure test of painted container assembly. Subject the container assembly to an internal air pressure of 3.0 + 0.5 PSIG. Observation shall be made for leakage. A container assembly where the leakage exceeds the requirement shall be classified as defective.

50.2.2 Interchangeability of painted container assemblies. Randomly interchange the cover assemblies with container body weldments and perform the air pressure test per 50.2.1. Failure to meet the applicable requirement shall be cause for rejection of the lot. The test shall be performed after the air pressure has been performed.

50.2.3 Hardness of gasket. One plaque (4 specimens) at the start and end of each shift shall be selected. The hardness test shall be performed on the specimens in accordance with ASTM D2240. Shore A hardness readings shall be taken on the end of each specimen. Any specimen failing the applicable requirements shall be cause for rejection of that lot of material. This requirement applies to the gasket manufacturer. If the gaskets are purchased, the contractor shall verify the hardness by obtaining a Certified Material Test Report (CMTR) from the gasket manufacturer.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

50.2.4 Palletization test. Select thirty containers and palletize them five wide by six high. Any container that cannot be interlocked or stacked shall be rejected and replaced with an acceptable one.

50.2.5 Corrosion resistance test. The exterior surface of the container shall meet the salt spray requirements of TT-C-490. This test shall be performed prior to acceptance of the first production lot.

50.2.6 Internal component test. The cover of each container shall be removed and checked for freedom of movement of the sleeve and strap assembly. The sleeve and strap assembly shall move out of the container approximately 3-4 inches. Visually inspect for any foreign material, missing or damaged internal components, and that there is no standing moisture/water on the components or under the sleeve and strap. Wet components shall be dried prior to reuse.

60.1 Reuse with limited refurbishment. If approved by the Procuring Contract Officer (PCO) containers may be re-used without completely stripping the paint and removing the inserts if the container is received at the load center without any apparent rust on the inside. Remove dirt and dust from container exterior. The rust on the outside must not exceed grade 7 of ASTM-D610. Any rust spots must be removed and touched-up in accordance with the protective finish requirements of drawing 9386830 prior to pack-out. The gasket shall be replaced (30.6), old markings shall be obliterated. The following paragraphs of Appendix A shall be applicable, 30.6, 40.2, 40.4, 40.6, 40.7, 50.1.1, 50.1.4 and 50.2. Major 101 of 50.1.4, air pressure test, is required to pass normal inspection sampling per Table II. Paragraph 50.2.2 and Major 102 of 50.1.4, Interchangeability test, are not required.

Custodian:
Army (AR)

Preparing activity:
Army (AR)

Project Number:
8140

New page.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

CAGE CODE: 19200

METRIC
MIL-C-70478C (AR)
AMENDMENT 3
02 June 1998
SUPERSEDING
AMENDMENT 2
26 JANUARY 1998

MILITARY SPECIFICATION

CONTAINER, AMMUNITION, METAL, FOR CARTRIDGE, 120 mm, TANK AMMUNITION

This amendment forms a part of MIL-C-70478C (AR), dated 04 October 1994, and is approved for use by the U.S. Army Armament Research, Development and Engineering Center, Department of the Army, and is available for use within the distribution limitations noted below.

The attached insertable replacement pages listed below are replacements for stipulated pages. When the new pages have been entered in the document, insert the amendment as the cover sheet to the specification.

Replacement page		Page replaced	
*2	*40	2	40
*3	*40a	3	None
*4	*41	4	41
*5	*43	5	43
*6	44	6	44
*8	44a	8	None
*9	*45	9	45
*11-*35	*46	11-35	46
*37	46a	37	None
*38		38	

* Indicates specific pages revised by this Amendment.

AMSC N/A FSC-8140

DISTRIBUTION STATEMENT B: - Distribution authorized to U.S. Government agencies and 120 mm system contractors only in accordance with Arms Export Control (22.USC.2778). Other requests for this document shall be referred to ARDEC, AMSTA-AR-ESM-I, Rock Island, IL.

Custodian:
Army - AR

Preparing activity:
Army - AR

Project number:
8140 0197

~~1 of 1~~

107

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

*

*

STANDARDS

MILITARY

MIL-STD-171	Finishing of Metal and Wood Surfaces
* MIL-STD-1916	DoD Preferred Methods for Acceptance of Product

*

*

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein. Unless otherwise specified, the issues shall be those in effect on the date of the solicitation.

DRAWINGS (See 6.4)

U.S. ARMY ARMAMENT RESEARCH, DEVELOPMENT AND ENGINEERING CENTER (ARDEC)

9386831	Container, Ammunition, Metal
12912366	Container, Ammunition, Metal
12938062	Container, Ammunition, Metal, PA116A1

(Copies of specifications, standards, and other Government documents required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issue of the nongovernment documents which is current on the date of the solicitation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D2240	Indentation Hardness of Rubber and Plastics by means of a Durometer, Standard Method of Test for
ASTM D3951	Commercial Packaging, Standard Practice for
ASTM E8	Tension Testing of Metallic Materials, Standard Method of
ASTM E18	Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials, Test for

* AMERICAN WELDING SOCIETY

* AWS A2.4	Standard Symbols for Welding, Brazing and Nondestructive Examination

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein (except for associated detail specifications, specification sheets or MS standards), the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Materials. Materials and parts shall be in accordance with applicable drawings and specifications.

* 3.2 Components and assemblies. The components and assemblies shall comply with all requirements per drawing 9386831 or 12912366 and the drawings and specifications referenced thereon.

* 3.3 Welding. The welding shall comply with the requirements of AWS A2.4.

3.3.1 Tensile strength (if applicable). The tensile strength of the longitudinal body weld shall be not less than 65 percent of the tensile strength of body material when tested as specified in 4.5.1.

3.3.1.1 Tensile strength of body material. The tensile strength of the body material shall be not less than 60,000 pounds per square inch (psi) as specified in 4.5.1.

3.4 Painted surface. The painted surfaces of the container shall comply with the requirements of TT-C-490. However, the film thickness and salt spray requirements of TT-C-490 will not apply to the interior surfaces, welded spots and sharp corners of the exterior surface of the container. Bare spots permissible on all bearing surfaces as per drawing 9386831, 12912366, or 12938062.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

3.5 Cover assembly. Upon assembly of the cover assembly to the body weldment, the cover assembly shall freely engage and rotate within the body weldment. As the cover assembly is rotated with the square handle in the open position, the handle shaft ends shall freely engage into the respective bayonet slots of the rim. When the square handle is in the closed position (rotated 180°), the hairpin spring clip shall be inserted into the upper holes in the shaft support and handle and lock the handle in place. When the hairpin spring clip is removed and the handle rotated to the open position, the cover assembly shall disengage from the body weldment.

3.6 First article inspection. This specification contains technical provisions for first article inspection. Requirements for the submission of first article samples by the contractor shall be as specified in the contract.

3.7 Workmanship.

3.7.1 Components and assemblies. The components and assemblies shall be regular, smooth and free from wrinkles, pin holes, cracks, dirt, rough spots, burrs, sharp edges and any other defect that might affect the serviceability, durability, safety and appearance of the container.

3.7.2 Paint coating. The paint coating shall be in accordance with applicable drawings and comply with instructions in MIL-STD-171. The finish coat shall cover all required surfaces and be continuous with the possible exception of a few light scratches not exposing the base metal or the primer coat.

3.7.3 Parts. All parts shall be free of chips, dirt, grease, rust and foreign material. The cleaning method used shall not be injurious to any of the parts nor shall any of the parts be contaminated by the cleaning agents used.

4. QUALITY ASSURANCE PROVISIONS

* 4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this

A

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

* 4.1.2 General provisions. Unless otherwise specified herein, the provisions of MIL-STD-1916 apply and form a part of this specification.

4.2 Classification of inspections. The following types of inspection shall be conducted on this item:

a. First article inspection

b. Quality conformance inspection

4.3 First article inspection.

4.3.1 Submission. The contractor shall submit a first article sample as designated by the Contracting Officer for evaluation in accordance with provisions of 4.3.2. The first article sample shall consist of five painted metal containers, five painted cover assemblies, five unpainted cover assemblies, and ten each of every subassembly and component (unpainted).

* 4.3.2 Inspection to be performed. As determined by the Government, the first article assemblies, components and test specimens may be subjected to any or all of the examination and tests specified in this detail specification and be inspected for compliance with any or all requirements of the applicable drawings. (See table I)

* 4.3.3 Rejection. If any assembly, component or test specimen fails to comply with any of the applicable requirements, the first article sample shall be rejected. The Government reserves the right to terminate inspection upon any failure of an assembly, component or test specimen to comply with any of the requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Supersedes page 6 dated 04 October 1994.

Table I. First Article Inspection.

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE: Assemblies and Components	SHEET 1 OF 2		DRAWING NUMBER: See Below
				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
*	Metal Containers, painted - (Drawing 9386831 or 12912366)			
	a. Examination for defects	5	3.2	4.4.2.18
	b. Air pressure	5	3.2	4.5.6.2
	c. Corrosion resistance test	5	3.4	4.5.10
*	Body Weldment, unpainted - (Drawing 9386830)			
	a. Examination for defects	10	3.2	4.4.2.16
	b. Air pressure	5	3.2	4.5.6.1
	c. Weld rim to body (see note)	5	3.2	4.5.2
	Cover Assembly, unpainted - (Drawing 12934838)			
	a. Examination for defects	5	3.2	4.4.2.9
	b. Air pressure	5	3.2	4.5.6.1
	Cover assembly, painted - (Drawing 12934838)			
	Examination for defects	5	3.2	4.4.2.10

NOTES: The weld security inspections, body tensile strength, spring tests and gasket tensile stress test shall be performed after the other inspections have been performed on the applicable samples.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

4.4 Quality conformance inspection.

* 4.4.1 Inspection lot formation. Inspection lots shall comply with the lot formation provisions of MIL-STD-1916. In addition, inspection lots of containers shall contain material from lots with the same interfix number from one manufacturer.

* 4.4.2 Examination. Examinations listed in the Classification of Characteristics shall be performed on inspection lots as defined in 4.4.1 of this specification.

a. Sampling inspection. The provisions/procedures of MIL-STD-1916 are applicable to this specification. Unless otherwise specified, attributes sampling shall be utilized for the conformance characteristics listed in Part III herein. Attributes sampling shall be in accordance with MIL-STD-1916, Table II, as modified below, using the verification levels (VL) cited in the conformance criteria columns of Part III. When approved for use, variables and continuous sampling plans shall be in accordance with MIL-STD-1916, Tables III and IV respectively, as modified below. Unless otherwise specified, the procedure in MIL-STD-1916 for normal inspection shall be used at the start of production for current or previous suppliers of the item. For all new suppliers of the item, tightened inspection shall be used at the start of production and be continued until the criteria for normal inspection are met. The sampling plans for MIL-STD-1916, Tables II (Attribute), III (Variables), IV (Continuous), are modified as follows:

VL-I and VL-II – Replace the sample sizes for Codes C and D with the sample size for Code E.

VL-III – Replace the sample sizes for Codes B, C and D with the sample size for Code E.

VL-IV – Replace the sample size for Code A with the sample size for Code B and replace the sample size for Codes B, D and E with the sample size for Code C.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

b. Alternative quality conformance provision. Unless otherwise specified herein or provided for in the contract, alternative quality conformance procedures, methods or equipment (see 6.3), such as statistical process control, tool control, other types of sampling procedures, etc., may be used by the contractor when they provide, as a minimum, the level of quality assurance required by the provisions specified herein. Prior to applying such alternative procedures, methods or equipment, the contractor shall describe them in a written proposal submitted to the Government for evaluation. When required, the contractor shall demonstrate that the effectiveness of each proposed alternative is equal to or better than the specified quality conformance provision(s) herein. In case of dispute as to whether the contractor's proposed alternative(s) provides equivalent assurance, the provisions of this specification shall apply. All approved alternative provisions shall be specifically incorporated into the contractor's quality program or inspection system, as applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH *4.4.2.1	TITLE Support, Shaft	SHEET 1 OF 2		DRAWING NUMBER 12934841
				NEXT HIGHER ASSEMBLY 12934839
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
* 101	Diameter of large hole	Table III	3.2	Gage
* 102	Diameter of small hole	Table III	3.2	Gage
* 103	True position of large hole and slot	Table III	3.2	Gage
* 104	Deleted			
* 105	True position of small holes	Table III	3.2	Gage
* 106	Distance between shaft support uprights	Table III	3.2	Gage
107	Deleted			
108	Deleted			
*109	Wall thickness	Table III	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH	TITLE	SHEET 2 OF 2		DRAWING NUMBER
*4.4.2.1	Support, Shaft			12934841
				NEXT HIGHER ASSEMBLY 12934839
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Major				
110	Deleted			
Minor				
201	Deleted			
202	Deleted			
* 203	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Supersedes page 12 dated 04 October 1994.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH *4.4.2.2	TITLE Handle	SHEET 1 OF 2		DRAWING NUMBER 12929273
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
* 101	True position of small hole	Level III	3.2	Gage
* 102	True position of shaft hexhole, 2 places	Level III	3.2	Gage
103	Deleted			
104	Deleted			
Minor				
* 201	Diameter of small hole	Level II	3.2	Gage
* 202	Overall length of tabs	Level II	3.2	Gage
* 203	Width of tab	Level II	3.2	Gage
* 204	Width of shaft hex hole (three readings 60° apart), 2 places	Level II	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH	TITLE	SHEET 2 OF 2		DRAWING NUMBER
*4.4.2.2	Handle			12929273
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
* 205	Largest width of handle	Level II	3.2	Gage
* 206	Wall thickness	Level II	3.2	Gage
* 207	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Supersedes page 15 dated 04 October 1994.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH *4.4.2.3	TITLE Shaft	SHEET 1 OF 2		DRAWING NUMBER 9344037
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
* 101	Length of hexagon segment of shaft	Level III	3.2	Gage
* 102	Large diameter (two places)	Level III	3.2	Gage
* 103	Small diameter (two places)	Level III	3.2	Gage
* 104	Total length of large diameters and hexagon segments	Level III	3.2	Gage
* 105	Small diameter segment not tangent to large diameter segment and side of hexagon segment	Level III	3.2	Visual
* 106	Length of large diameter segment (two places)	Level III	3.2	Gage
NOTES:				

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH	TITLE	SHEET 2 OF 2		DRAWING NUMBER
*4.4.2.3	Shaft			9344037
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
* 201	Width across flats of hexagon segment (three readings, 60° apart)	Level II	3.2	Gage
* 202	Length of small diameter segment (two places)	Level II	3.2	Gage
* 203	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH	TITLE	SHEET 1 OF 1		DRAWING NUMBER
*4.4.2.4	Washer			9344038
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
* 101	Inside diameter	Level III	3.2	Gage
* 102	Height	Level III	3.2	Gage
Minor				
* 201	Outside diameter	Level II	3.2	Gage
* 202	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH *4.4.2.5	TITLE Retainer, Washer	SHEET 1 OF 1		DRAWING NUMBER 9344041
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
* 101	Material certification	Level III	3.2	Certification
Minor				
* 201	Diameter of hole	Level II	3.2	Gage
* 202	Inside diameter	Level II	3.2	Gage
* 203	Height of retainer	Level II	3.2	Gage
* 204	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH *4.4.2.6	TITLE Cover	SHEET 1 OF 2		DRAWING NUMBER 9386821
				NEXT HIGHER ASSEMBLY * 12934839 or 9386822
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
* 101	Outside diameter	Level III	3.2	Gage
* 102	Wall thickness	Level III	3.2	Gage
* 103	Depth of groove	Level III	3.2	Gage
* 104	Width of groove	Level III	3.2	Gage
* 105	Depth from rim to inside of cover base	Level III	3.2	Gage
* 106	Height of threads, minimum	Level III	3.2	Gage
* 107	Location of air test hole with center of cover	Level III	3.2	Gage
* 108	Flatness of bottom surface inside annular ring and surrounding air test hole	Level III	3.2	Gage
* 109	Height of annular ring around air test hole	Level III	3.2	Gage

NOTES:

123

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH	TITLE	SHEET 2 OF 2		DRAWING NUMBER
*4.4.2.6	Cover			9386821
				NEXT HIGHER ASSEMBLY
				* 9386822 or 12934839
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
* 201	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Supersedes page 20 dated 04 October 1994. 20

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH *4.4.2.7	TITLE Gasket	SHEET 1 OF 1		DRAWING NUMBER 12910349
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
* 101	Material certification	Level III	3.2	Certification
102	Deleted			
* 103	Hardness	Level III 1/	3.2	4.5.5
* 104	Inside diameter, maximum	Level III	3.2	Gage
* 105	Large width	Level III	3.2	Gage
* 106	Middle width	Level III	3.2	Gage
* 107	Height of rectangular cross section	Level III	3.2	Gage
108	Deleted			
109	Deleted			
Minor				
* 201	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:
1/ One plaque (4 specimens) at start and end of each shift.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH	TITLE	SHEET		DRAWING NUMBER
*4.4.2.8	Cover Weldment	1 OF 1		12934839
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
* 101	True position of shaft hole and slot	Level III	3.2	Gage
* 102	True position of shaft support uprights	Level III	3.2	Gage
Minor				
* 201	Weld missing, incomplete or visually inadequate	Level II	3.2	Visual/Manual
202	Deleted			
* 203	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

CAGE CODE: 19200

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH *4.4.2.9	TITLE Cover Assembly, Prior to Painting	SHEET 1 OF 1		DRAWING NUMBER 12934838
				NEXT HIGHER ASSEMBLY * 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Air pressure	100%	3.2	4.5.6.1/Drawing 9386824
* 102	Rotating of shaft inadequate after crimping	Level III	3.2	Manual
* 103	Distance from inside cover rim to top of shaft	Level III	3.2	Gage
104	Deleted			
Minor				
* 201	Component missing or inadequately assembled	Level II	3.2	Visual
* 202	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH	TITLE	SHEET		DRAWING NUMBER
*4.4.2.10	Cover Assembly, After Painting	1 OF 1		12934838
				NEXT HIGHER ASSEMBLY: * 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
* 101	Gasket improperly bonded to cover	Level III	3.2	Visual
* 102	After painting, the shaft shall freely rotate	Level III	3.2	Manual
* 103	Primer thickness, min.	Level III	3.2	Gage
* 104	Top coat thickness, min.	Level III	3.2	Gage
* 105	Spring clip and wire rope assembly inadequately swaged onto handle or hairpin spring clip	Level III	3.2	Visual/Manual
Minor				
* 201	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH *4.4.2.11	TITLE Rim	SHEET 1 OF 2		DRAWING NUMBER 9386827
				NEXT HIGHER ASSEMBLY * 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
* 101	Length of larger slot on side of rim	Level III	3.2	Gage
* 102	Location of larger slot from inside flat	Level III	3.2	Gage
103	Deleted			
* 104	Location of bayonet slot, 4 places	Level III	3.2	Gage
* 105	Dimension across flats, 2 places (Dimension A)	Level III	3.2	Gage
* 106	Dimension across corner, 2 places (Dimension D)	Level III	3.2	Gage
* 107	Width of larger slot	Level III	3.2	Gage
* 108	Inside diameter of rim (Dimension E)	Level III	3.2	Gage
* 109	Bayonet locking edge radius (2 places)	Level III	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH	TITLE	SHEET 2 OF 2		DRAWING NUMBER
*4.4.2.11	Rim			9386827
				NEXT HIGHER ASSEMBLY * 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
* 201	Depth from edge of rim to inside flat	Level II	3.2	Gage
202	Deleted			
203	Deleted			
* 204	Drainage hole missing	Level II	3.2	Visual
* 205	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH *4.4.2.12	TITLE Ring	SHEET 1 OF 2		DRAWING NUMBER 9386826
				NEXT HIGHER ASSEMBLY * 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
* 101	Length of larger slot on side of ring	Level III	3.2	Gage
* 102	Location of larger slot from inside flat	Level III	3.2	Gage
103	Deleted			
* 104	Dimensions across flats, 2 places (Dimension A)	Level III	3.2	Gage
* 105	Width of larger slot	Level III	3.2	Gage
* 106	Opening of container interlocking grip	Level III	3.2	Gage
* 107	Depth of container interlocking grip	Level III	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH *4.4.2.12	TITLE Ring	SHEET 2 OF 2		DRAWING NUMBER 9386826
				NEXT HIGHER ASSEMBLY * 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
* 201	Distance from edge of ring to outside flat	Level II	3.2	Gage
202	Deleted			
203	Deleted			
* 204	Location of container interlocking cutouts	Level II	3.2	Gage
* 205	Width of interlocking cutouts	Level II	3.2	Gage
* 206	Depth from interlocking cutout to inside flat	Level II	3.2	Gage
* 207	Drainage hole missing	Level II	3.2	Visual
* 208	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH	TITLE	SHEET 1 OF 1		DRAWING NUMBER
*4.4.2.13	Bottom			* 9386825
				NEXT HIGHER ASSEMBLY * 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
* 101	Material thickness	Level III	3.2	Gage
* 102	Hole location 1/	Level III	3.2	Gage
* 103	Hole diameter 1/	Level III	3.2	Gage
Minor				
* 201	Height of lip, minimum	Level II	3.2	Gage
* 202	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:
1/ 9386825 only.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH *4.4.2.14	TITLE Body	SHEET 1 OF 1		DRAWING NUMBER 9386828
				NEXT HIGHER ASSEMBLY * 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
* 101	Tensile strength of weld	Level III 1/	3.3.1	4.5.1
* 102	Wall thickness	Level III	3.2	Gage
103	Deleted			
104	Deleted			
105	Deleted			
Minor				
* 201	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:
1/ Three coupons per shift.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH *4.4.2.15	TITLE Plug, Stacking	SHEET 1 OF 1		DRAWING NUMBER 9386837
				NEXT HIGHER ASSEMBLY * 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
* 101	Length of plug	Level III	3.2	Gage
* 102	Width of plug	Level III	3.2	Gage
Minor				
201	Deleted			
202	Deleted			
* 203	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH	TITLE	SHEET 1 OF 2		DRAWING NUMBER
*4.4.2.16	Body Weldment, Prior to Painting			* 9386830
				NEXT HIGHER ASSEMBLY
				* 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Air pressure	100%	3.2	4.5.6.1
* 102	Weld of rim to body	Level III 1/	3.2	4.5.2
* 103	True position of holes of ring, rim and stacking plug	Level III	3.2	Gage
* 104	Location of hole in rim relative to holes in inside rings and stacking plugs	Level III	3.2	Gage
* 105	Location of hole in rim relative to hole in outside rings and stacking plugs	Level III	3.2	Gage
* 106	Perpendicularity of ring and rims with Datum-A	Level III	3.2	Gage
* 107	Distance from end of body to top of rim bayonet slot (four places)	Level III	3.2	Gage

NOTES:

1/ Three coupons per shift.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH	TITLE	SHEET 2 OF 2		DRAWING NUMBER
*4.4.2.16	Body Weldment, Prior to Painting			* 9386830
				NEXT HIGHER ASSEMBLY
				* 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Major				
* 108	Minimum shear load between stacking plug and body	Level III	3.2	Gage
* 109	Flatness of body	Level III	3.2	Gage
* 110	Body end irregularities	Level III	3.2	4.5.9
* 111	Depth of body weldment	Level III	3.2	Gage
* 112	Deleted			
* 113	Deleted			
Minor				
* 201	Any weld of ring, rim or bottom to body missing, incomplete or visually inadequate	Level II	3.2	Visual
* 202	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:
* 2/ Deleted

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH	TITLE	SHEET 1 OF 1		DRAWING NUMBER
*4.4.2.17	Body Weldment, After Painting			9386830 or 12938059
				NEXT HIGHER ASSEMBLY
				* 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
* 101	Primer thickness	Level III	3.2	Gage
* 102	Paint thickness	Level III	3.2	Gage
* 103	Marking	Level III	3.2	5.3
* 104	Inside diameter, minimum	Level III	3.2	Gage
Minor				
* 201	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

CAGE CODE: 19200

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH *4.4.2.18	TITLE Container, Ammunition, Metal	SHEET 1 OF 1		DRAWING NUMBER * 9386831 or 12912366
				NEXT HIGHER ASSEMBLY * 9386833, 12912369, or 12913178
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
*101	Cover assembly test	Level III	3.5	Visual/Manual/4.5.7
*102	Air pressure test (with yoke assembly in place, PA116 only)	Level III	3.2	4.5.6.2
*103	Screw torque test (top and bottom, PA116 and cover PA116A1 only)	Level III 1/	3.2	4.5.8
Minor				
*201	Missing, loose or damaged components	Level II	3.2	Visual
*202	Protective finish damaged, bare spots exposing metal, etc.	Level II	3.2	Visual
*203	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:
1/ The screw torque test shall be performed after the air pressure test has been performed and the screw has been reassembled.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

CAGE CODE: 19200

PARAGRAPH *4.4.2.20	TITLE Yoke Assembly, After Painting	SHEET 1 OF 1		DRAWING NUMBER 12561227 or 12912337
				NEXT HIGHER ASSEMBLY 9386831 or 12912366.
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None Defined			
Major				
* 101	Location of the self clinching nut	Level III	3.2	Gage
* 102	Yoke stops inside the maximum base diameter	Level III	3.2	Gage
Minor				
* 201	Presence of spot welds on yoke stop	Level II	3.2	Visual
* 202	Pushout force improper	Level II	3.2	Gage
* 203	Presence of improper threads in self clinching nut	Level II	3.2	Gage/Visual
* 204	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

4.4.3 Testing. Testing is described in the First Article and Quality Conformance Inspection Tables.

4.4.3.1 Tensile strength. (See 3.3.1) Major Defect. Five bodies shall be randomly selected for this test. Four specimens, approximately equally spaced along the axis, shall be taken from each body at right angles to the weld. If one specimen of a sample fails to comply with the requirement, that sample shall be classed defective. If two or more samples are classed defective, the lot shall be rejected.

4.4.3.2 Tensile strength of body material. (See 3.3.1.1) Major Defect. Five bodies shall be randomly selected for this test. From each body, three specimens shall be selected at random for determination of body material tensile strength. If one specimen fails to comply with 3.3.1.1, that sample body shall be classed defective. If two or more sample bodies are classed defective, the lot shall be rejected.

* 4.4.3.3 Weld of rim to body. (See Drawing 9386830) Major Defect. Five body assemblies shall be selected for this test. If any sample fails to comply with the requirement, the lot shall be rejected.

4.4.3.4 Hardness of gasket. (See drawing 12910349) Major Defect. Five gaskets shall be randomly selected from each lot for this test. If any gasket fails to meet the requirement, the lot shall be rejected.

* 4.4.3.5 Deleted

* 4.4.3.5.1 Deleted

* 4.4.3.5.2 Deleted

* 4.4.3.5.3 Deleted

* 4.4.3.6 Deleted

4.4.4 Inspection equipment. The inspection equipment required to perform the examinations and tests prescribed herein is described in the "Inspection Method Reference" column in the tables starting with paragraph 4.4.2.1. The contractor shall submit for approval, inspection equipment designs in accordance with the terms of the contract (see 6.5).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

4.5.6.2 Air pressure of painted metal container. Subject the metal container to the internal air pressure, specified in the applicable metal container drawing. Observation shall be made for a pressure drop exceeding the requirement (as specified in the applicable drawing). A metal container, which exceeds the requirement shall be classed defective.

4.5.7 Cover assembly test. Upon assembly of the body and cover, the cover shall freely engage and rotate within the body. The Square handle shall engage into the respective bayonet slots of the rim without interference when in the clamping position. The Square handle when disengaged and in the open position shall disengage the cover from the body.

4.5.8 Screw torque test. The minimum applicable torque shall be applied to the screw. Any evidence of motion of the screw before reaching the minimum acceptable torque shall be cause for rejection of the container assembly being tested.

4.5.9 Body end irregularities. Visually inspect the body end for any nicks, dents, gouges, or mismatch. If a defect is evident, place a .01 inch diameter wire on the defect and a one inch long block over the wire. With the wire nested in the irregularity, gently press down on the block and remove the wire. If there is no evidence of resistance caused by the block, the part shall be classed defective.

4.5.10 Corrosion resistance test. The exterior surface of the container shall meet the salt spray requirements of TT-C-490.

5. PACKAGING

5.1 Preservation. None required.

5.2 Packing.

* 5.2.1 Deleted

* 5.2.2 Deleted

5.2.3 Commercial. The metal container shall be packed in accordance with ASTM D3951.

5.3 Marking.

* 5.3.1 Deleted

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

* 5.3.2 Deleted

5.3.3 Commercial. The metal container shall be marked in accordance with ASTM D3951 and the following additional instructions. Commercial shipping tags attached with wire shall show: Item name and

New page. 40a

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

model number, part number and revision, contract number, lot number and data, name and address of manufacturer. If components and assemblies are bundled, boxed or palletized, the gross weight and quantity shall be included. The above information may be placed on pallets or boxes by labeling or stenciling.

5.4 Shipping. When containers from more than one lot are shipped at one time, each lot shall be kept separate and the division between lots clearly indicated to prevent mixing of lots in transit.

6. NOTES

6.1 Intended use. The metal container is intended for use as the outer shipping and storage packaging for the 120 mm Tank Cartridge.

* 6.2 Ordering data. Deleted

6.3 Definition of packaging and packing levels.

6.3.1 Level A. Full military protection, for unrestricted (OCONUS) shipment and storage.

6.3.2 Level B. Limited military protection for limited storage and (OCONUS) shipment.

6.3.3 Level C. For interplant (CONUS) shipment and very limited storage.

6.4 Drawings. Drawings listed in Section 2 of this specification under the heading U.S. Army Armament Research, Development and Engineering Center (ARDEC) may also include drawings prepared by, and identified as U.S. Army Armament Research and Development Command (ARRADCOM), U.S. Army Armament Research and Development Center (ARDC), Edgewood Arsenal, Frankford Arsenal, Rock Island Arsenal or Picatinny Arsenal drawings. Technical data originally prepared by these activities is now under the cognizance of ARDEC.

* 6.5 Submission of inspection equipment designs for approval. Submit designs as required to: Commander, U.S. Army Armament Research, Development and Engineering Center, ATTN: AMSTA-AR-QAC-T, Picatinny Arsenal, New Jersey 07801-5001.

6.6 Approval of equivalent test methods. Prior approval of the Contracting Officer is required for use of equivalent test methods. A description of the proposed method should be submitted through the Contracting Officer to: Commander, U.S. Army Armament Research, Development and Engineering Center, ATTN: AMSTA-AR-QAC-T, Picatinny Arsenal, New Jersey 07801-5001. This description should include but not be limited to the accuracy and precision of the method, test data demonstrating the accuracy and precision and drawings of any special equipment required.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

QUALITY ASSURANCE PROVISIONS FOR REFURBISHMENT

10. SCOPE

10.1 Scope. The appendix provides the Quality Assurance provisions for the refurbishment of containers, metal, for 120 mm tank ammunition. This Appendix is not a mandatory part of the Specification. The information contained herein is intended for compliance when refurbishing metal containers.

20. APPLICABLE DOCUMENTS

20.1 Government Drawings.

9386831 - Container, Ammo, Metal, PA116
* Deleted
12912366 - Container, Ammo, Metal

30. REFURBISHMENT

30.1 Dents. Dents shall be removed as required to allow compliance with the workmanship requirement.

30.2 Cleaning. Paint and rust shall be removed.

30.3 Rims and/or rings. Rims and/or rings shall be straightened and welded by fillet welding where required.

30.4 Refinish. The parts shall be finished in accordance with the applicable drawings.

30.5 Seams. Seams shall be welded where required.

30.6 Gasket. The gaskets on the cover shall be replaced with new gaskets.

30.7 Refurbishment identification. Each container that will be refurbished shall have a 3/16 inch diameter hole punched/drilled in the rim (9386827-1). The hole shall be on the side where the identification markings are/were located. This side has the lip grip on the lower ring (second/bottom ring). The hole shall be approximately centered on the flat surface of the rim, but be no closer to an edge or curve than 3/8 inches. The hole will identify how many times this particular container has been refurbished.

40. REQUIREMENTS

40.1 Welds. Welds shall be in conformance with good commercial practices.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

40.2 Gasket. The gasket shall comply with all requirements specified on drawing 12910349.

* 40.3 Inside diameter of body weldment. Acceptance criteria is defined as the ability of the refurbished container to accept the insertion of the Projectile Support/Sleeve and Strap assembly during the load assemble and pack operation.

40.4 Air pressure test. The container assembly shall not exceed the leak rate of 5 cc/min when tested in accordance with 50.2.1.

40.5 Interchangeability. The cover assemblies and body weldments shall be interchangeable without affecting the function of the container.

40.6 Palletization test. All containers shall be palletized in accordance with 50.2.4.

40.7 Workmanship. All parts shall be free of cracks, burrs, chips, dirt, pin holes, rust, and bare spots unless allowed by the following workmanship standards.

a. Paint buildup. Runs, drips, sags and reinforcement overspray that are solid and exhibit no blistering are allowed. Paint drips on the sealing edge and paint buildup on gasket groove of cover assembly are not allowed.

b. Bare metal. Bare metal due to incidental chipping on edges and corners shall not to exceed 0.04 square inch.

c. Abrasions and scuffs. Abrasions and scuffs where bare metal is not exposed, due to normal handling and stacking at the rim and ring interface areas, are allowed.

d. Scratches. Scratches exposing bare metal are allowed on the cover assembly, ring and rim, provided all scratches do not accumulate a total of more than three (3) inches in length.

e. Dents. Dents are allowed provided there are no more than two per assembly and neither is larger than 2 inches in length.

f. Cracks. Cracks on edges are allowed provided they do not extend down the surface of the part or assembly when examined by the naked eye. Cracks on the edge of the pressure tab hole in the cover are acceptable.

*g. Rust spots. When reusing the container in accordance with paragraph 60.1, container body rust spots shall be removed and refinished. Localized rust may be removed by mechanical means such as sanding and/or wire brush, etc. Any resultant bare metal on the container body shall be touched-up in accordance with paragraph 60.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

40.8 Lot number. The container lot number shall comply with MIL-STD-1168A to include the suffix of an overhauled lot for refurbished containers.

40.9 Paint thickness. The paint thickness may be increased to cover the shot blast profile and meet the salt spray requirement.

50. INSPECTION

50.1 Examination. Unless otherwise specified examinations for major and minor characteristics shall be performed in accordance with Table II of paragraph 4.4.2.

New page.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

	CLASS	CHARACTERISTICS	CONFORMANCE CRITERIA	INSPECTION METHOD
	50.1.1	Gasket (Drawing 12910349)		
	CRITICAL	None defined		
	MAJOR			
	101	Material certification	Certification	
	102	Hardness		50.2.3
*	103	Height of rectangular cross section	Level III	Gage
	MINOR			
*	201	Poor workmanship	Level II	Visual/Gage
	50.1.2	Cover Assembly (Drawing 9386824)		
	CRITICAL	None defined		
	MAJOR			
*	101	Paint thickness, minimum	Level III	Gage
	MINOR			
*	201	Poor workmanship	Level II	Visual/Gage
*	50.1.3	Body Weldment, after painting (Drawing 9386830)		
	CRITICAL	None defined		
	MAJOR			
*	101	Paint thickness, minimum	Level III	Gage
*	102	Inside diameter, minimum	Level III	Gage
	MINOR			
*	201	Poor workmanship	Level II	Visual/Gage

Supersedes page 45 dated 04 October 1994.

148

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

* 50.1.4 Container, Ammunition, Metal (Drawing 9386831 or 12912366)

CRITICAL	None defined			
MAJOR				
*	101	Air pressure test	Level III	50.2.1
*	102	Interchangeability test	Level III	50.2.2
	103	Palletization test	100%	50.2.4
	104	Corrosion resistance test	5	50.2.5
MINOR				
*	201	Poor workmanship	Level II	Visual/Gage

50.2 Test methods and procedures.

50.2.1 Air pressure test of painted container assembly. Subject the container assembly to an internal air pressure of 3.0 + 0.5 PSIG. Observation shall be made for leakage. A container assembly where the leakage exceeds the requirement shall be classified as defective.

50.2.2 Interchangeability of painted container assemblies. Randomly interchange the cover assemblies with container body weldments and perform the air pressure test per 50.2.1. Failure to meet the applicable requirement shall be cause for rejection of the lot. The test shall be performed after the air pressure has been performed.

50.2.3 Hardness of gasket. One plaque (4 specimens) at the start and end of each shift shall be selected. The hardness test shall be performed on the specimens in accordance with ASTM D2240. Shore A hardness readings shall be taken on the end of each specimen. Any specimen failing the applicable requirements shall be cause for rejection of that lot of material. This requirement applies to the gasket manufacturer. If the gaskets are purchased, the contractor shall verify the hardness by obtaining a Certified Material Test Report (CMTR) from the gasket manufacturer.

50.2.4 Palletization test. Select thirty containers and palletize them five wide by six high. Any container that cannot be interlocked or stacked shall be rejected and replaced with an acceptable one.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

50.2.5 Corrosion resistance test. The exterior surface of the container shall meet the salt spray requirements of TT-C-490. This test shall be performed prior to acceptance of the first production lot.

60.1 Reuse with limited refurbishment. If approved by the Procuring Contract Officer (PCO) containers may be re-used without completely stripping the paint and removing the inserts if the container is received at the load center without any apparent rust on the inside. Remove dirt and dust from container exterior. The rust on the outside must not exceed grade 7 of ASTM-D610. Any rust spots must be removed and touched-up in accordance with the protective finish requirements of drawing 9386830 prior to pack-out. The gasket shall be replaced (30.6), old markings shall be obliterated. The following paragraphs of Appendix A shall be applicable, 30.6, 40.2, 40.4, 40.6, 40.7, 50.1.1, 50.1.4 and 50.2. Major 101 of 50.1.4, air pressure test, is required to pass normal inspection sampling per Table II. Paragraph 50.2.2 and Major 102 of 50.1.4, Interchangeability test, are not required.

Custodian:
Army (AR)

Preparing activity:
Army (AR)

Project Number:
8140

New page.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

METRIC
MIL-C-70478C (AR)
AMENDMENT 4
10 June 1998
SUPERSEDING
AMENDMENT 3
02 June 1998

MILITARY SPECIFICATION

CONTAINER, AMMUNITION, METAL, FOR CARTRIDGE, 120 mm, TANK AMMUNITION

This amendment forms a part of MIL-C-70478C (AR), dated 04 October 1994, and is approved for use by the U.S. Army Armament Research, Development and Engineering Center, Department of the Army, and is available for use within the distribution limitations noted below.

The attached insertable replacement pages listed below are replacements for stipulated pages. When the new pages have been entered in the document, insert the amendment as the cover sheet to the specification.

Replacement page		Page replaced	
2	40	2	40
3	40a	3	None
4	41	4	41
5	43	5	43
6	44	6	44
8	*44a	8	None
9	45	9	45
11-35	*46	11-35	46
37	*46a	37	None
38		38	

* Indicates specific pages revised by this Amendment.

AMSC N/A FSC-8140

DISTRIBUTION STATEMENT B: - Distribution authorized to U.S. Government agencies and 120 mm system contractors only in accordance with Arms Export Control (22.USC.2778). Other requests for this document shall be referred to ARDEC, AMSTA-AR-ESM-I, Rock Island, IL.

Custodian:
Army - AR

Preparing activity:
Army - AR

Project number:
8140-0202

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

STANDARDS

MILITARY

MIL-STD-171	Finishing of Metal and Wood Surfaces
MIL-STD-1916	DoD Preferred Methods for Acceptance of Product

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein. Unless otherwise specified, the issues shall be those in effect on the date of the solicitation.

DRAWINGS (See 6.4)

U.S. ARMY ARMAMENT RESEARCH, DEVELOPMENT AND ENGINEERING CENTER (ARDEC)

9386831	Container, Ammunition, Metal
12912366	Container, Ammunition, Metal
12938062	Container, Ammunition, Metal, PA116A1

(Copies of specifications, standards, and other Government documents required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issue of the nongovernment documents which is current on the date of the solicitation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D2240	Indentation Hardness of Rubber and Plastics by means of a Durometer, Standard Method of Test for
ASTM D3951	Commercial Packaging, Standard Practice for
ASTM E8	Tension Testing of Metallic Materials, Standard Method of
ASTM E18	Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials, Test for

AMERICAN WELDING SOCIETY

AWS A2.4	Standard Symbols for Welding, Brazing and Nondestructive Examination

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein (except for associated detail specifications, specification sheets or MS standards), the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Materials. Materials and parts shall be in accordance with applicable drawings and specifications.

3.2 Components and assemblies. The components and assemblies shall comply with all requirements per drawing 9386831 or 12912366 and the drawings and specifications referenced thereon.

3.3 Welding. The welding shall comply with the requirements of AWS A2.4.

3.3.1 Tensile strength (if applicable). The tensile strength of the longitudinal body weld shall be not less than 65 percent of the tensile strength of body material when tested as specified in 4.5.1.

3.3.1.1 Tensile strength of body material. The tensile strength of the body material shall be not less than 60,000 pounds per square inch (psi) as specified in 4.5.1.

3.4 Painted surface. The painted surfaces of the container shall comply with the requirements of TT-C-490. However, the film thickness and salt spray requirements of TT-C-490 will not apply to the interior surfaces, welded spots and sharp corners of the exterior surface of the container. Bare spots permissible on all bearing surfaces as per drawing 9386831, 12912366, or 12938062.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

3.5 Cover assembly. Upon assembly of the cover assembly to the body weldment, the cover assembly shall freely engage and rotate within the body weldment. As the cover assembly is rotated with the square handle in the open position, the handle shaft ends shall freely engage into the respective bayonet slots of the rim. When the square handle is in the closed position (rotated 180°), the hairpin spring clip shall be inserted into the upper holes in the shaft support and handle and lock the handle in place. When the hairpin spring clip is removed and the handle rotated to the open position, the cover assembly shall disengage from the body weldment.

3.6 First article inspection. This specification contains technical provisions for first article inspection. Requirements for the submission of first article samples by the contractor shall be as specified in the contract.

3.7 Workmanship.

3.7.1 Components and assemblies. The components and assemblies shall be regular, smooth and free from wrinkles, pin holes, cracks, dirt, rough spots, burrs, sharp edges and any other defect that might affect the serviceability, durability, safety and appearance of the container.

3.7.2 Paint coating. The paint coating shall be in accordance with applicable drawings and comply with instructions in MIL-STD-171. The finish coat shall cover all required surfaces and be continuous with the possible exception of a few light scratches not exposing the base metal or the primer coat.

3.7.3 Parts. All parts shall be free of chips, dirt, grease, rust and foreign material. The cleaning method used shall not be injurious to any of the parts nor shall any of the parts be contaminated by the cleaning agents used.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.1.2 General provisions. Unless otherwise specified herein, the provisions of MIL-STD-1916 apply and form a part of this specification.

4.2 Classification of inspections. The following types of inspection shall be conducted on this item:

a. First article inspection

b. Quality conformance inspection

4.3 First article inspection.

4.3.1 Submission. The contractor shall submit a first article sample as designated by the Contracting Officer for evaluation in accordance with provisions of 4.3.2. The first article sample shall consist of five painted metal containers, five painted cover assemblies, five unpainted cover assemblies, and ten each of every subassembly and component (unpainted).

4.3.2 Inspection to be performed. As determined by the Government, the first article assemblies, components and test specimens may be subjected to any or all of the examination and tests specified in this detail specification and be inspected for compliance with any or all requirements of the applicable drawings. (See table I)

4.3.3 Rejection. If any assembly, component or test specimen fails to comply with any of the applicable requirements, the first article sample shall be rejected. The Government reserves the right to terminate inspection upon any failure of an assembly, component or test specimen to comply with any of the requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Table I. First Article Inspection.

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE Assemblies and Components	SHEET 1 OF 2		DRAWING NUMBER See Below NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
	Metal Containers, painted - (Drawing 9386831 or 12912366)			
	a. Examination for defects	5	3.2	4.4.2.18
	b. Air pressure	5	3.2	4.5.6.2
	c. Corrosion resistance test	5	3.4	4.5.10
	Body Weldment, unpainted - (Drawing 9386830)			
	a. Examination for defects	10	3.2	4.4.2.16
	b. Air pressure	5	3.2	4.5.6.1
	c. Weld rim to body (see note)	5	3.2	4.5.2
	Cover Assembly, unpainted - (Drawing 12934838)			
	a. Examination for defects	5	3.2	4.4.2.9
	b. Air pressure	5	3.2	4.5.6.1
	Cover assembly, painted - (Drawing 12934838)			
	Examination for defects	5	3.2	4.4.2.10

NOTES: The weld security inspections, body tensile strength, spring tests and gasket tensile stress test shall be performed after the other inspections have been performed on the applicable samples.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

4.4 Quality conformance inspection.

4.4.1 Inspection lot formation. Inspection lots shall comply with the lot formation provisions of MIL-STD-1916. In addition, inspection lots of containers shall contain material from lots with the same interfix number from one manufacturer.

4.4.2 Examination. Examinations listed in the Classification of Characteristics shall be performed on inspection lots as defined in 4.4.1 of this specification.

a. Sampling inspection. The provisions/procedures of MIL-STD-1916 are applicable to this specification. Unless otherwise specified, attributes sampling shall be utilized for the conformance characteristics listed in Part III herein. Attributes sampling shall be in accordance with MIL-STD-1916, Table II, as modified below, using the verification levels (VL) cited in the conformance criteria columns of Part III. When approved for use, variables and continuous sampling plans shall be in accordance with MIL-STD-1916, Tables III and IV respectively, as modified below. Unless otherwise specified, the procedure in MIL-STD-1916 for normal inspection shall be used at the start of production for current or previous suppliers of the item. For all new suppliers of the item, tightened inspection shall be used at the start of production and be continued until the criteria for normal inspection are met. The sampling plans for MIL-STD-1916, Tables II (Attribute), III (Variables), IV (Continuous), are modified as follows:

VL-I and VL-II – Replace the sample sizes for Codes C and D with the sample size for Code E.

VL-III – Replace the sample sizes for Codes B, C and D with the sample size for Code E.

VL-IV – Replace the sample size for Code A with the sample size for Code B and replace the sample size for Codes B, D and E with the sample size for Code C.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

b. Alternative quality conformance provision. Unless otherwise specified herein or provided for in the contract, alternative quality conformance procedures, methods or equipment (see 6.3), such as statistical process control, tool control, other types of sampling procedures, etc., may be used by the contractor when they provide, as a minimum, the level of quality assurance required by the provisions specified herein. Prior to applying such alternative procedures, methods or equipment, the contractor shall describe them in a written proposal submitted to the Government for evaluation. When required, the contractor shall demonstrate that the effectiveness of each proposed alternative is equal to or better than the specified quality conformance provision(s) herein. In case of dispute as to whether the contractor's proposed alternative(s) provides equivalent assurance, the provisions of this specification shall apply. All approved alternative provisions shall be specifically incorporated into the contractor's quality program or inspection system, as applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.1	TITLE Support, Shaft	SHEET 1 OF 2		DRAWING NUMBER 12934841
				NEXT HIGHER ASSEMBLY 12934839
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Diameter of large hole	Table III	3.2	Gage
102	Diameter of small hole	Table III	3.2	Gage
103	True position of large hole and slot	Table III	3.2	Gage
104	Deleted			
105	True position of small holes	Table III	3.2	Gage
106	Distance between shaft support uprights	Table III	3.2	Gage
107	Deleted			
108	Deleted			
109	Wall thickness	Table III	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.1	TITLE Support, Shaft	SHEET 2 OF 2		DRAWING NUMBER 12934841
				NEXT HIGHER ASSEMBLY 12934839
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Major				
110	Deleted			
Minor				
201	Deleted			
202	Deleted			
203	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

160

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.2	TITLE Handle	SHEET 1 OF 2		DRAWING NUMBER 12929273
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	True position of small hole	Level III	3.2	Gage
102	True position of shaft hexhole, 2 places	Level III	3.2	Gage
103	Deleted			
104	Deleted			
Minor				
201	Diameter of small hole	Level II	3.2	Gage
202	Overall length of tabs	Level II	3.2	Gage
203	Width of tab	Level II	3.2	Gage
204	Width of shaft hex hole (three readings 60° apart), 2 places	Level II	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.2	TITLE Handle	SHEET 2 OF 2		DRAWING NUMBER 12929273
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
205	Largest width of handle	Level II	3.2	Gage
206	Wall thickness	Level II	3.2	Gage
207	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.3	TITLE Shaft	SHEET 1 OF 2		DRAWING NUMBER 9344037
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Length of hexagon segment of shaft	Level III	3.2	Gage
102	Large diameter (two places)	Level III	3.2	Gage
103	Small diameter (two places)	Level III	3.2	Gage
104	Total length of large diameters and hexagon segments	Level III	3.2	Gage
105	Small diameter segment not tangent to large diameter segment and side of hexagon segment	Level III	3.2	Visual
106	Length of large diameter segment (two places)	Level III	3.2	Gage
NOTES:				

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.3	TITLE Shaft	SHEET 2 OF 2		DRAWING NUMBER 9344037
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
201	Width across flats of hexagon segment (three readings, 60° apart)	Level II	3.2	Gage
202	Length of small diameter segment (two places)	Level II	3.2	Gage
203	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.4	TITLE Washer	SHEET 1 OF 1		DRAWING NUMBER 9344038
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Inside diameter	Level III	3.2	Gage
102	Height	Level III	3.2	Gage
Minor				
201	Outside diameter	Level II	3.2	Gage
202	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.5	TITLE Retainer, Washer	SHEET 1 OF 1		DRAWING NUMBER 9344041
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Material certification	Level III	3.2	Certification
Minor				
201	Diameter of hole	Level II	3.2	Gage
202	Inside diameter	Level II	3.2	Gage
203	Height of retainer	Level II	3.2	Gage
204	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Supersedes page 19 dated 04 October 1994.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.6	TITLE Cover	SHEET 1 OF 2		DRAWING NUMBER 9386821
				NEXT HIGHER ASSEMBLY 12934839 or 9386822
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Outside diameter	Level III	3.2	Gage
102	Wall thickness	Level III	3.2	Gage
103	Depth of groove	Level III	3.2	Gage
104	Width of groove	Level III	3.2	Gage
105	Depth from rim to inside of cover base	Level III	3.2	Gage
106	Height of threads, minimum	Level III	3.2	Gage
107	Location of air test hole with center of cover	Level III	3.2	Gage
108	Flatness of bottom surface inside annular ring and surrounding air test hole	Level III	3.2	Gage
109	Height of annular ring around air test hole	Level III	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET 2 OF 2		DRAWING NUMBER
4.4.2.6	Cover			9386821
				NEXT HIGHER ASSEMBLY
				9386822 or 12934839
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
201	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assistdla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.7	TITLE Gasket	SHEET 1 OF 1		DRAWING NUMBER 12910349
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Material certification	Level III	3.2	Certification
102	Deleted			
103	Hardness	Level III 1/	3.2	4.5.5
104	Inside diameter, maximum	Level III	3.2	Gage
105	Large width	Level III	3.2	Gage
106	Middle width	Level III	3.2	Gage
107	Height of rectangular cross section	Level III	3.2	Gage
108	Deleted			
109	Deleted			
Minor				
201	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

1/ One plaque (4 specimens) at start and end of each shift.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.8	TITLE Cover Weldment	SHEET 1 OF 1		DRAWING NUMBER 12934839
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	True position of shaft hole and slot	Level III	3.2	Gage
102	True position of shaft support uprights	Level III	3.2	Gage
Minor				
201	Weld missing, incomplete or visually inadequate	Level II	3.2	Visual/Manual
202	Deleted			
203	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

170

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:20Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.9	TITLE Cover Assembly, Prior to Painting	SHEET 1 OF 1		DRAWING NUMBER 12934838
				NEXT HIGHER ASSEMBLY 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Air pressure	100%	3.2	4.5.6.1/Drawing 9386824
102	Rotating of shaft inadequate after crimping	Level III	3.2	Manual
103	Distance from inside cover rim to top of shaft	Level III	3.2	Gage
104	Deleted			
Minor				
201	Component missing or inadequately assembled	Level II	3.2	Visual
202	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assistdla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.10	TITLE Cover Assembly, After Painting	SHEET 1 OF 1		DRAWING NUMBER 12934838
				NEXT HIGHER ASSEMBLY 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Gasket improperly bonded to cover	Level III	3.2	Visual
102	After painting, the shaft shall freely rotate	Level III	3.2	Manual
103	Primer thickness, min.	Level III	3.2	Gage
104	Top coat thickness, min.	Level III	3.2	Gage
105	Spring clip and wire rope assembly inadequately swaged onto handle or hairpin spring clip	Level III	3.2	Visual/Manual
Minor				
201	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Supersedes page 25 dated 04 October 1994.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.11	TITLE Rim	SHEET 1 OF 2		DRAWING NUMBER 9386827
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Length of larger slot on side of rim	Level III	3.2	Gage
102	Location of larger slot from inside flat	Level III	3.2	Gage
103	Deleted			
104	Location of bayonet slot, 4 places	Level III	3.2	Gage
105	Dimension across flats, 2 places (Dimension A)	Level III	3.2	Gage
106	Dimension across corner, 2 places (Dimension D)	Level III	3.2	Gage
107	Width of larger slot	Level III	3.2	Gage
108	Inside diameter of rim (Dimension E)	Level III	3.2	Gage
109	Bayonet locking edge radius (2 places)	Level III	3.2	Gage
NOTES:				

173

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.11	TITLE Rim	SHEET 2 OF 2		DRAWING NUMBER 9386827
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
201	Depth from edge of rim to inside flat	Level II	3.2	Gage
202	Deleted			
203	Deleted			
204	Drainage hole missing	Level II	3.2	Visual
205	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.12	TITLE Ring	SHEET 1 OF 2		DRAWING NUMBER 9386826
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Length of larger slot on side of ring	Level III	3.2	Gage
102	Location of larger slot from inside flat	Level III	3.2	Gage
103	Deleted			
104	Dimensions across flats, 2 places (Dimension A)	Level III	3.2	Gage
105	Width of larger slot	Level III	3.2	Gage
106	Opening of container interlocking grip	Level III	3.2	Gage
107	Depth of container interlocking grip	Level III	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.12	TITLE Ring	SHEET 2 OF 2		DRAWING NUMBER 9386826
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
201	Distance from edge of ring to outside flat	Level II	3.2	Gage
202	Deleted			
203	Deleted			
204	Location of container interlocking cutouts	Level II	3.2	Gage
205	Width of interlocking cutouts	Level II	3.2	Gage
206	Depth from interlocking cutout to inside flat	Level II	3.2	Gage
207	Drainage hole missing	Level II	3.2	Visual
208	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-28T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.13	TITLE Bottom	SHEET 1 OF 1		DRAWING NUMBER 9386825
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Material thickness	Level III	3.2	Gage
102	Hole location 1/	Level III	3.2	Gage
103	Hole diameter 1/	Level III	3.2	Gage
Minor				
201	Height of lip, minimum	Level II	3.2	Gage
202	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:
1/ 9386825 only.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.14	TITLE Body	SHEET 1 OF 1		DRAWING NUMBER 9386828
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Tensile strength of weld	Level III 1/	3.3.1	4.5.1
102	Wall thickness	Level III	3.2	Gage
103	Deleted			
104	Deleted			
105	Deleted			
Minor				
201	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:
1/ Three coupons per shift.

178

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.15	TITLE Plug, Stacking	SHEET 1 OF 1		DRAWING NUMBER 9386837
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Length of plug	Level III	3.2	Gage
102	Width of plug	Level III	3.2	Gage
Minor				
201	Deleted			
202	Deleted			
203	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Supersedes page 32 dated 04 October 1994.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.16	TITLE Body Weldment, Prior to Painting	SHEET 1 OF 2		DRAWING NUMBER 9386830
				NEXT HIGHER ASSEMBLY 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Air pressure	100%	3.2	4.5.6.1
102	Weld of rim to body	Level III 1/	3.2	4.5.2
103	True position of holes of ring, rim and stacking plug	Level III	3.2	Gage
104	Location of hole in rim relative to holes in inside rings and stacking plugs	Level III	3.2	Gage
105	Location of hole in rim relative to hole in outside rings and stacking plugs	Level III	3.2	Gage
106	Perpendicularity of ring and rims with Datum-A	Level III	3.2	Gage
107	Distance from end of body to top of rim bayonet slot (four places)	Level III	3.2	Gage

NOTES:

1/ Three coupons per shift.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.16	TITLE Body Weldment, Prior to Painting	SHEET 2 OF 2		DRAWING NUMBER 9386830
				NEXT HIGHER ASSEMBLY 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Major				
108	Minimum shear load between stacking plug and body	Level III	3.2	Gage
109	Flatness of body	Level III	3.2	Gage
110	Body end irregularities	Level III	3.2	4.5.9
111	Depth of body weldment	Level III	3.2	Gage
112	Deleted			
113	Deleted			
Minor				
201	Any weld of ring, rim or bottom to body missing, incomplete or visually inadequate	Level II	3.2	Visual
202	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:
2/ Deleted

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET		DRAWING NUMBER
4.4.2.17	Body Weldment, After Painting	1 OF 1		9386830 or 12938059
				NEXT HIGHER ASSEMBLY 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Primer thickness	Level III	3.2	Gage
102	Paint thickness	Level III	3.2	Gage
103	Marking	Level III	3.2	5.3
104	Inside diameter, minimum	Level III	3.2	Gage
Minor				
201	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-01-29T04:20Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.18	TITLE Container, Ammunition, Metal	SHEET 1 OF 1		DRAWING NUMBER 9386831 or 12912366
				NEXT HIGHER ASSEMBLY 9386833, 12912369, or 12913178
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Cover assembly test	Level III	3.5	Visual/Manual/4.5.7
102	Air pressure test (with yoke assembly in place, PA116 only)	Level III	3.2	4.5.6.2
103	Screw torque test (top and bottom, PA116 and cover PA116A1 only)	Level III 1/	3.2	4.5.8
Minor				
201	Missing, loose or damaged components	Level II	3.2	Visual
202	Protective finish damaged, bare spots exposing metal, etc.	Level II	3.2	Visual
203	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:
1/ The screw torque test shall be performed after the air pressure test has been performed and the screw has been reassembled.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.20	TITLE Yoke Assembly, After Painting	SHEET 1 OF 1		DRAWING NUMBER 12561227 or 12912337
				NEXT HIGHER ASSEMBLY 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None Defined			
Major				
101	Location of the self clinching nut	Level III	3.2	Gage
102	Yoke stops inside the maximum base diameter	Level III	3.2	Gage
Minor				
201	Presence of spot welds on yoke stop	Level II	3.2	Visual
202	Pushout force improper	Level II	3.2	Gage
203	Presence of improper threads in self clinching nut	Level II	3.2	Gage/Visual
204	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

4.4.3 Testing. Testing is described in the First Article and Quality Conformance Inspection Tables.

4.4.3.1 Tensile strength. (See 3.3.1) Major Defect. Five bodies shall be randomly selected for this test. Four specimens, approximately equally spaced along the axis, shall be taken from each body at right angles to the weld. If one specimen of a sample fails to comply with the requirement, that sample shall be classed defective. If two or more samples are classed defective, the lot shall be rejected.

4.4.3.2 Tensile strength of body material. (See 3.3.1.1) Major Defect. Five bodies shall be randomly selected for this test. From each body, three specimens shall be selected at random for determination of body material tensile strength. If one specimen fails to comply with 3.3.1.1, that sample body shall be classed defective. If two or more sample bodies are classed defective, the lot shall be rejected.

4.4.3.3 Weld of rim to body. (See Drawing 9386830) Major Defect. Five body assemblies shall be selected for this test. If any sample fails to comply with the requirement, the lot shall be rejected.

4.4.3.4 Hardness of gasket. (See drawing 12910349) Major Defect. Five gaskets shall be randomly selected from each lot for this test. If any gasket fails to meet the requirement, the lot shall be rejected.

4.4.3.5 Deleted

4.4.3.5.1 Deleted

4.4.3.5.2 Deleted

4.4.3.5.3 Deleted

4.4.3.6 Deleted

4.4.4 Inspection equipment. The inspection equipment required to perform the examinations and tests prescribed herein is described in the "Inspection Method Reference" column in the tables starting with paragraph 4.4.2.1. The contractor shall submit for approval, inspection equipment designs in accordance with the terms of the contract (see 6.5).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

4.5.6.2 Air pressure of painted metal container. Subject the metal container to the internal air pressure, specified in the applicable metal container drawing. Observation shall be made for a pressure drop exceeding the requirement (as specified in the applicable drawing). A metal container, which exceeds the requirement shall be classed defective.

4.5.7 Cover assembly test. Upon assembly of the body and cover, the cover shall freely engage and rotate within the body. The Square handle shall engage into the respective bayonet slots of the rim without interference when in the clamping position. The Square handle when disengaged and in the open position shall disengage the cover from the body.

4.5.8 Screw torque test. The minimum applicable torque shall be applied to the screw. Any evidence of motion of the screw before reaching the minimum acceptable torque shall be cause for rejection of the container assembly being tested.

4.5.9 Body end irregularities. Visually inspect the body end for any nicks, dents, gouges, or mismatch. If a defect is evident, place a .01 inch diameter wire on the defect and a one inch long block over the wire. With the wire nested in the irregularity, gently press down on the block and remove the wire. If there is no evidence of resistance caused by the block, the part shall be classed defective.

4.5.10 Corrosion resistance test. The exterior surface of the container shall meet the salt spray requirements of TT-C-490.

5. PACKAGING

5.1 Preservation. None required.

5.2 Packing.

5.2.1 Deleted

5.2.2 Deleted

5.2.3 Commercial. The metal container shall be packed in accordance with ASTM D3951.

5.3 Marking.

5.3.1 Deleted

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

5.3.2 Deleted

5.3.3 Commercial. The metal container shall be marked in accordance with ASTM D3951 and the following additional instructions. Commercial shipping tags attached with wire shall show: Item name and

New page.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

model number, part number and revision, contract number, lot number and data, name and address of manufacturer. If components and assemblies are bundled, boxed or palletized, the gross weight and quantity shall be included. The above information may be placed on pallets or boxes by labeling or stenciling.

5.4 Shipping. When containers from more than one lot are shipped at one time, each lot shall be kept separate and the division between lots clearly indicated to prevent mixing of lots in transit.

6. NOTES

6.1 Intended use. The metal container is intended for use as the outer shipping and storage packaging for the 120 mm Tank Cartridge.

6.2 Ordering data. Deleted

6.3 Definition of packaging and packing levels.

6.3.1 Level A. Full military protection, for unrestricted (OCONUS) shipment and storage.

6.3.2 Level B. Limited military protection for limited storage and (OCONUS) shipment.

6.3.3 Level C. For interplant (CONUS) shipment and very limited storage.

6.4 Drawings. Drawings listed in Section 2 of this specification under the heading U.S. Army Armament Research, Development and Engineering Center (ARDEC) may also include drawings prepared by, and identified as U.S. Army Armament Research and Development Command (ARRADCOM), U.S. Army Armament Research and Development Center (ARDC), Edgewood Arsenal, Frankford Arsenal, Rock Island Arsenal or Picatinny Arsenal drawings. Technical data originally prepared by these activities is now under the cognizance of ARDEC.

6.5 Submission of inspection equipment designs for approval. Submit designs as required to: Commander, U.S. Army Armament Research, Development and Engineering Center, ATTN: AMSTA-AR-QAC-T, Picatinny Arsenal, New Jersey 07801-5001.

6.6 Approval of equivalent test methods. Prior approval of the Contracting Officer is required for use of equivalent test methods. A description of the proposed method should be submitted through the Contracting Officer to: Commander, U.S. Army Armament Research, Development and Engineering Center, ATTN: AMSTA-AR-QAC-T, Picatinny Arsenal, New Jersey 07801-5001. This description should include but not be limited to the accuracy and precision of the method, test data demonstrating the accuracy and precision and drawings of any special equipment required.

Supersedes page 41 dated 04 October 1994.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

QUALITY ASSURANCE PROVISIONS FOR REFURBISHMENT

10. SCOPE

10.1 Scope. The appendix provides the Quality Assurance provisions for the refurbishment of containers, metal, for 120 mm tank ammunition. This Appendix is not a mandatory part of the Specification. The information contained herein is intended for compliance when refurbishing metal containers.

20. APPLICABLE DOCUMENTS

20.1 Government Drawings.

9386831 - Container, Ammo, Metal, PA116
Deleted
12912366 - Container, Ammo, Metal

30. REFURBISHMENT

30.1 Dents. Dents shall be removed as required to allow compliance with the workmanship requirement.

30.2 Cleaning. Paint and rust shall be removed.

30.3 Rims and/or rings. Rims and/or rings shall be straightened and welded by fillet welding where required.

30.4 Refinish. The parts shall be finished in accordance with the applicable drawings.

30.5 Seams. Seams shall be welded where required.

30.6 Gasket. The gaskets on the cover shall be replaced with new gaskets.

30.7 Refurbishment identification. Each container that will be refurbished shall have a 3/16 inch diameter hole punched/drilled in the rim (9386827-1). The hole shall be on the side where the identification markings are/were located. This side has the lip grip on the lower ring (second/bottom ring). The hole shall be approximately centered on the flat surface of the rim, but be no closer to an edge or curve than 3/8 inches. The hole will identify how many times this particular container has been refurbished.

40. REQUIREMENTS

40.1 Welds. Welds shall be in conformance with good commercial practices.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

40.2 Gasket. The gasket shall comply with all requirements specified on drawing 12910349.

40.3 Inside diameter of body weldment. Acceptance criteria is defined as the ability of the refurbished container to accept the insertion of the Projectile Support/Sleeve and Strap assembly during the load assemble and pack operation.

40.4 Air pressure test. The container assembly shall not exceed the leak rate of 5 cc/min when tested in accordance with 50.2.1.

40.5 Interchangeability. The cover assemblies and body weldments shall be interchangeable without affecting the function of the container.

40.6 Palletization test. All containers shall be palletized in accordance with 50.2.4.

40.7 Workmanship. All parts shall be free of cracks, burrs, chips, dirt, pin holes, rust, and bare spots unless allowed by the following workmanship standards.

a. Paint buildup. Runs, drips, sags and reinforcement overspray that are solid and exhibit no blistering are allowed. Paint drips on the sealing edge and paint buildup on gasket groove of cover assembly are not allowed.

b. Bare metal. Bare metal due to incidental chipping on edges and corners shall not to exceed 0.04 square inch.

c. Abrasions and scuffs. Abrasions and scuffs where bare metal is not exposed, due to normal handling and stacking at the rim and ring interface areas, are allowed.

d. Scratches. Scratches exposing bare metal are allowed on the cover assembly, ring and rim, provided all scratches do not accumulate a total of more than three (3) inches in length.

e. Dents. Dents are allowed provided there are no more than two per assembly and neither is larger than 2 inches in length.

f. Cracks. Cracks on edges are allowed provided they do not extend down the surface of the part or assembly when examined by the naked eye. Cracks on the edge of the pressure tab hole in the cover are acceptable.

g. Rust spots. When reusing the container in accordance with paragraph 60.1, container body rust spots shall be removed and refinished. Localized rust may be removed by mechanical means such as sanding and/or wire brush, etc. Any resultant bare metal on the container body shall be touched-up in accordance with paragraph 60.1.

190

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

40.8 Lot number. The container lot number shall comply with MIL-STD-1168A to include the suffix of an overhauled lot for refurbished containers.

40.9 Paint thickness. The paint thickness may be increased to cover the shot blast profile and meet the salt spray requirement.

* 40.10 Reuse criteria. When limited refurbishment is performed on the containers in accordance with paragraph 60.1, the containers shall be inspected in accordance with paragraph 50.1.5. The unit load does not need to be depalletized if it meets the criteria of 50.1.5 and the visible exterior containers on the pallet do not appear damaged beyond the requirements of this appendix. Also that the old ammo lot number has previously been removed from the side of the container and is currently stenciled on the bottom.

50. INSPECTION

50.1 Examination. Unless otherwise specified examinations for major and minor characteristics shall be performed in accordance with Table II of paragraph 4.4.2.

New page.

191

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

CLASS	CHARACTERISTICS	CONFORMANCE CRITERIA	INSPECTION METHOD
50.1.1	Gasket (Drawing 12910349)		
CRITICAL	None defined		
MAJOR			
101	Material certification	Certification	
102	Hardness		50.2.3
103	Height of rectangular cross section	Level III	Gage
MINOR			
201	Poor workmanship	Level II	Visual/Gage
50.1.2	Cover Assembly (Drawing 9386824)		
CRITICAL	None defined		
MAJOR			
101	Paint thickness, minimum	Level III	Gage
MINOR			
201	Poor workmanship	Level II	Visual/Gage
50.1.3	Body Weldment, after painting (Drawing 9386830)		
CRITICAL	None defined		
MAJOR			
101	Paint thickness, minimum	Level III	Gage
102	Inside diameter, minimum	Level III	Gage
MINOR			
201	Poor workmanship	Level II	Visual/Gage

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

50.1.4 Container, Ammunition, Metal (Drawing 9386831 or 12912366)

CRITICAL	None defined		
MAJOR			
101	Air pressure test	Level III	50.2.1
102	Interchangeability test	Level III	50.2.2
103	Palletization test	100%	50.2.4
104	Corrosion resistance test	5	50.2.5
MINOR			
201	Poor workmanship	Level II	Visual/Gage

* 50.1.5 Internal component test

CRITICAL	None defined		
MAJOR			
101	Internal component test	100%	50.2.6
MINOR	None defined		

50.2 Test methods and procedures.

50.2.1 Air pressure test of painted container assembly. Subject the container assembly to an internal air pressure of 3.0 + 0.5 PSIG. Observation shall be made for leakage. A container assembly where the leakage exceeds the requirement shall be classified as defective.

50.2.2 Interchangeability of painted container assemblies. Randomly interchange the cover assemblies with container body weldments and perform the air pressure test per 50.2.1. Failure to meet the applicable requirement shall be cause for rejection of the lot. The test shall be performed after the air pressure has been performed.

50.2.3 Hardness of gasket. One plaque (4 specimens) at the start and end of each shift shall be selected. The hardness test shall be performed on the specimens in accordance with ASTM D2240. Shore A hardness readings shall be taken on the end of each specimen. Any specimen failing the applicable requirements shall be cause for rejection of that lot of material. This requirement applies to the gasket manufacturer. If the gaskets are purchased, the contractor shall verify the hardness by obtaining a Certified Material Test Report (CMTR) from the gasket manufacturer.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

50.2.4 Palletization test. Select thirty containers and palletize them five wide by six high. Any container that cannot be interlocked or stacked shall be rejected and replaced with an acceptable one.

50.2.5 Corrosion resistance test. The exterior surface of the container shall meet the salt spray requirements of TT-C-490. This test shall be performed prior to acceptance of the first production lot.

* 50.2.6 Internal component test. The cover of each container shall be removed and checked for freedom of movement of the sleeve and strap assembly. The sleeve and strap assembly shall move out of the container approximately 3-4 inches. Visually inspect for any foreign material, missing or damaged internal components, and that there is no standing moisture/water on the components or under the sleeve and strap. Wet components shall be dried prior to reuse.

60.1 Reuse with limited refurbishment. If approved by the Procuring Contract Officer (PCO) containers may be re-used without completely stripping the paint and removing the inserts if the container is received at the load center without any apparent rust on the inside. Remove dirt and dust from container exterior. The rust on the outside must not exceed grade 7 of ASTM-D610. Any rust spots must be removed and touched-up in accordance with the protective finish requirements of drawing 9386830 prior to pack-out. The gasket shall be replaced (30.6), old markings shall be obliterated. The following paragraphs of Appendix A shall be applicable, 30.6, 40.2, 40.4, 40.6, 40.7, 50.1.1, 50.1.4 and 50.2. Major 101 of 50.1.4, air pressure test, is required to pass normal inspection sampling per Table II. Paragraph 50.2.2 and Major 102 of 50.1.4, Interchangeability test, are not required.

Custodian:
Army (AR)

Preparing activity:
Army (AR)

Project Number:
8140

New page.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

METRIC
MIL-C-70478C (AR)
AMENDMENT 6
26 October 1998
SUPERSEDING
AMENDMENT 5
23 June 1998

MILITARY SPECIFICATION

CONTAINER, AMMUNITION, METAL, FOR CARTRIDGE, 120 mm, TANK AMMUNITION

This amendment forms a part of MIL-C-70478C (AR), dated 04 October 1994, and is approved for use by the U.S. Army Armament Research, Development and Engineering Center, Department of the Army, and is available for use within the distribution limitations noted below.

The attached insertable replacement pages listed below are replacements for stipulated pages. When the new pages have been entered in the document, insert the amendment as the cover sheet to the specification.

Replacement page		Page replaced	
2	37	2	37
*3	38	3	38
4	40	4	40
5	40a	5	None
6	41	6	41
8	43	8	43
9	44	9	44
11	44a	11	None
12	45	12	45
13	46	13	46
14-35	46a	14-35	None

* Indicates specific pages revised by this Amendment.

AMSC N/A

FSC-8140

DISTRIBUTION STATEMENT B: - Distribution authorized to U.S. Government agencies and 120 mm system contractors only in accordance with Arms Export Control (22.USC.2778). Other requests for this document shall be referred to ARDEC, AMSTA-AR-ESM-I, Rock Island, IL.

Custodian:
Army - AR

Preparing activity:
Army - AR

Project number:
8140-0212

195

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

STANDARDS

MILITARY

MIL-STD-171	Finishing of Metal and Wood Surfaces
MIL-STD-1916	DoD Preferred Methods for Acceptance of Product

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein. Unless otherwise specified, the issues shall be those in effect on the date of the solicitation.

DRAWINGS (See 6.4)

U.S. ARMY ARMAMENT RESEARCH, DEVELOPMENT AND ENGINEERING CENTER (ARDEC)

9386831	Container, Ammunition, Metal
12912366	Container, Ammunition, Metal
12938062	Container, Ammunition, Metal, PA116A1

(Copies of specifications, standards, and other Government documents required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issue of the nongovernment documents which is current on the date of the solicitation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D2240	Indentation Hardness of Rubber and Plastics by means of a Durometer, Standard Method of Test for
ASTM D3951	Commercial Packaging, Standard Practice for
ASTM E8	Tension Testing of Metallic Materials, Standard Method of
ASTM E18	Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials, Test for

AMERICAN WELDING SOCIETY

AWS A2.4	Standard Symbols for Welding, Brazing and Nondestructive Examination

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein (except for associated detail specifications, specification sheets or MS standards), the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Materials. Materials and parts shall be in accordance with applicable drawings and specifications.

3.2 Components and assemblies. The components and assemblies shall comply with all requirements per drawing 9386831 or 12912366 and the drawings and specifications referenced thereon.

3.3 Welding. The welding shall comply with the requirements of AWS A2.4.

3.3.1 Tensile strength (if applicable). The tensile strength of the longitudinal body weld shall be not less than 65 percent of the tensile strength of body material when tested as specified in 4.5.1.

3.3.1.1 Tensile strength of body material. The tensile strength of the body material shall be not less than 60,000 pounds per square inch (psi) as specified in 4.5.1.

* 3.4 Painted surface. The painted surfaces of the container shall comply with the requirements of TT-C-490. The painted surface shall meet 96 hours of salt spray resistance per TT-C-490. However, the film thickness and salt spray requirements of TT-C-490 will not apply to the interior surfaces, welded spots and sharp corners of the exterior surface of the container. Bare spots permissible on all bearing surfaces as per drawing 9386831, 12912366, or 12938062.

Supersedes page 3 dated 04 October 1994.

197

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

3.5 Cover assembly. Upon assembly of the cover assembly to the body weldment, the cover assembly shall freely engage and rotate within the body weldment. As the cover assembly is rotated with the square handle in the open position, the handle shaft ends shall freely engage into the respective bayonet slots of the rim. When the square handle is in the closed position (rotated 180°), the hairpin spring clip shall be inserted into the upper holes in the shaft support and handle and lock the handle in place. When the hairpin spring clip is removed and the handle rotated to the open position, the cover assembly shall disengage from the body weldment.

3.6 First article inspection. This specification contains technical provisions for first article inspection. Requirements for the submission of first article samples by the contractor shall be as specified in the contract.

3.7 Workmanship.

3.7.1 Components and assemblies. The components and assemblies shall be regular, smooth and free from wrinkles, pin holes, cracks, dirt, rough spots, burrs, sharp edges and any other defect that might affect the serviceability, durability, safety and appearance of the container.

3.7.2 Paint coating. The paint coating shall be in accordance with applicable drawings and comply with instructions in MIL-STD-171. The finish coat shall cover all required surfaces and be continuous with the possible exception of a few light scratches not exposing the base metal or the primer coat.

3.7.3 Parts. All parts shall be free of chips, dirt, grease, rust and foreign material. The cleaning method used shall not be injurious to any of the parts nor shall any of the parts be contaminated by the cleaning agents used.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.1.2 General provisions. Unless otherwise specified herein, the provisions of MIL-STD-1916 apply and form a part of this specification.

4.2 Classification of inspections. The following types of inspection shall be conducted on this item:

a. First article inspection

b. Quality conformance inspection

4.3 First article inspection.

4.3.1 Submission. The contractor shall submit a first article sample as designated by the Contracting Officer for evaluation in accordance with provisions of 4.3.2. The first article sample shall consist of five painted metal containers, five painted cover assemblies, five unpainted cover assemblies, and ten each of every subassembly and component (unpainted).

4.3.2 Inspection to be performed. As determined by the Government, the first article assemblies, components and test specimens may be subjected to any or all of the examination and tests specified in this detail specification and be inspected for compliance with any or all requirements of the applicable drawings. (See table I)

4.3.3 Rejection. If any assembly, component or test specimen fails to comply with any of the applicable requirements, the first article sample shall be rejected. The Government reserves the right to terminate inspection upon any failure of an assembly, component or test specimen to comply with any of the requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Table I. First Article Inspection.

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE: Assemblies and Components	SHEET 1 OF 2		DRAWING NUMBER: See Below
				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
	Metal Containers, painted - (Drawing 9386831 or 12912366)			
	a. Examination for defects	5	3.2	4.4.2.18
	b. Air pressure	5	3.2	4.5.6.2
	c. Corrosion resistance test	5	3.4	4.5.10
	Body Weldment, unpainted - (Drawing 9386830)			
	a. Examination for defects	10	3.2	4.4.2.16
	b. Air pressure	5	3.2	4.5.6.1
	c. Weld rim to body (see note)	5	3.2	4.5.2
	Cover Assembly, unpainted - (Drawing 12934838)			
	a. Examination for defects	5	3.2	4.4.2.9
	b. Air pressure	5	3.2	4.5.6.1
	Cover assembly, painted - (Drawing 12934838)			
	Examination for defects	5	3.2	4.4.2.10

NOTES: The weld security inspections, body tensile strength, spring tests and gasket tensile stress test shall be performed after the other inspections have been performed on the applicable samples.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

4.4 Quality conformance inspection.

4.4.1 Inspection lot formation. Inspection lots shall comply with the lot formation provisions of MIL-STD-1916. In addition, inspection lots of containers shall contain material from lots with the same interfix number from one manufacturer.

4.4.2 Examination. Examinations listed in the Classification of Characteristics shall be performed on inspection lots as defined in 4.4.1 of this specification.

a. Sampling inspection. The provisions/procedures of MIL-STD-1916 are applicable to this specification. Unless otherwise specified, attributes sampling shall be utilized for the conformance characteristics listed in Part III herein. Attributes sampling shall be in accordance with MIL-STD-1916, Table II, as modified below, using the verification levels (VL) cited in the conformance criteria columns of Part III. When approved for use, variables and continuous sampling plans shall be in accordance with MIL-STD-1916, Tables III and IV respectively, as modified below. Unless otherwise specified, the procedure in MIL-STD-1916 for normal inspection shall be used at the start of production for current or previous suppliers of the item. For all new suppliers of the item, tightened inspection shall be used at the start of production and be continued until the criteria for normal inspection are met. The sampling plans for MIL-STD-1916, Tables II (Attribute), III (Variables), IV (Continuous), are modified as follows:

VL-I and VL-II – Replace the sample sizes for Codes C and D with the sample size for Code E.

VL-III – Replace the sample sizes for Codes B, C and D with the sample size for Code E.

VL-IV – Replace the sample size for Code A with the sample size for Code B and replace the sample size for Codes B, D and E with the sample size for Code C.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

b. Alternative quality conformance provision. Unless otherwise specified herein or provided for in the contract, alternative quality conformance procedures, methods or equipment (see 6.3), such as statistical process control, tool control, other types of sampling procedures, etc., may be used by the contractor when they provide, as a minimum, the level of quality assurance required by the provisions specified herein. Prior to applying such alternative procedures, methods or equipment, the contractor shall describe them in a written proposal submitted to the Government for evaluation. When required, the contractor shall demonstrate that the effectiveness of each proposed alternative is equal to or better than the specified quality conformance provision(s) herein. In case of dispute as to whether the contractor's proposed alternative(s) provides equivalent assurance, the provisions of this specification shall apply. All approved alternative provisions shall be specifically incorporated into the contractor's quality program or inspection system, as applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Supersedes page 11 dated 04 October 1994.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.1	TITLE Support, Shaft	SHEET 1 OF 2		DRAWING NUMBER 12934841
				NEXT HIGHER ASSEMBLY 12934839
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Diameter of large hole	Table III	3.2	Gage
102	Diameter of small hole	Table III	3.2	Gage
103	True position of large hole and slot	Table III	3.2	Gage
104	Deleted			
105	True position of small holes	Table III	3.2	Gage
106	Distance between shaft support uprights	Table III	3.2	Gage
107	Deleted			
108	Deleted			
109	Wall thickness	Table III	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.1	TITLE Support, Shaft	SHEET 2 OF 2		DRAWING NUMBER 12934841
				NEXT HIGHER ASSEMBLY 12934839
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Major				
110	Deleted			
Minor				
201	Deleted			
202	Deleted			
203	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

204

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.2	TITLE Handle	SHEET 1 OF 2		DRAWING NUMBER 12929273
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	True position of small holes	Level III	3.2	Gage
102	Location of shaft hexhole, 2 places	Level III	3.2	Gage
103	Deleted			
104	Deleted			
Minor				
201	Diameter of small holes	Level II	3.2	Gage
202	Length of handle opening	Level II	3.2	Gage
203	Width of handle opening	Level II	3.2	Gage
204	Width of shaft hex hole (three readings 60° apart), 2 places	Level II	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.2	TITLE Handle	SHEET 2 OF 2		DRAWING NUMBER 12929273
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
205	Largest width of handle	Level II	3.2	Gage
206	Wall thickness	Level II	3.2	Gage
207	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

206

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.3	TITLE Shaft	SHEET 1 OF 2		DRAWING NUMBER 9344037
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Length of hexagon segment of shaft	Level III	3.2	Gage
102	Large diameter (two places)	Level III	3.2	Gage
103	Small diameter (two places)	Level III	3.2	Gage
104	Total length of large diameters and hexagon segments	Level III	3.2	Gage
105	Small diameter segment not tangent to large diameter segment and side of hexagon segment	Level III	3.2	Visual
106	Length of large diameter segment (two places)	Level III	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Supersedes page 16 dated 04 October 1994.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.3	TITLE Shaft	SHEET 2 OF 2		DRAWING NUMBER 9344037
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
201	Width across flats of hexagon segment (three readings, 60° apart)	Level II	3.2	Gage
202	Length of small diameter segment (two places)	Level II	3.2	Gage
203	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.4	TITLE Washer	SHEET 1 OF 1		DRAWING NUMBER 9344038
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Inside diameter	Level III	3.2	Gage
102	Height	Level III	3.2	Gage
Minor				
201	Outside diameter	Level II	3.2	Gage
202	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Supersedes page 18 dated 04 October 1994.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.5	TITLE Retainer, Washer	SHEET 1 OF 1		DRAWING NUMBER 9344041
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Material certification	Level III	3.2	Certification
Minor				
201	Diameter of hole	Level II	3.2	Gage
202	Inside diameter	Level II	3.2	Gage
203	Height of retainer	Level II	3.2	Gage
204	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.6	TITLE Cover	SHEET 1 OF 2		DRAWING NUMBER 9386821
				NEXT HIGHER ASSEMBLY 12934839 or 9386822
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Outside diameter	Level III	3.2	Gage
102	Wall thickness	Level III	3.2	Gage
103	Depth of groove	Level III	3.2	Gage
104	Width of groove	Level III	3.2	Gage
105	Depth from rim to inside of cover base	Level III	3.2	Gage
106	Height of threads, minimum	Level III	3.2	Gage
107	Location of air test hole with center of cover	Level III	3.2	Gage
108	Flatness of bottom surface inside annular ring and surrounding air test hole	Level III	3.2	Gage
109	Height of annular ring around air test hole	Level III	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.6	TITLE Cover	SHEET 2 OF 2		DRAWING NUMBER 9386821
				NEXT HIGHER ASSEMBLY 9386822 or 12934839
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor 201	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.7	TITLE Gasket	SHEET 1 OF 1		DRAWING NUMBER 12910349
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Material certification	Level III	3.2	Certification
102	Deleted			
103	Hardness	Level III 1/	3.2	4.5.5
104	Inside diameter, maximum	Level III	3.2	Gage
105	Large width	Level III	3.2	Gage
106	Middle width	Level III	3.2	Gage
107	Height of rectangular cross section	Level III	3.2	Gage
108	Deleted			
109	Deleted			
Minor				
201	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:
1/ One plaque (4 specimens) at start and end of each shift.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.8	TITLE Cover Weldment	SHEET 1 OF 1		DRAWING NUMBER 12934839
				NEXT HIGHER ASSEMBLY 12934838
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	True position of shaft hole and slot	Level III	3.2	Gage
102	True position of shaft support uprights	Level III	3.2	Gage
Minor				
201	Weld missing, incomplete or visually inadequate	Level II	3.2	Visual/Manual
202	Deleted			
203	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.9	TITLE Cover Assembly, Prior to Painting	SHEET 1 OF 1		DRAWING NUMBER 12934838
				NEXT HIGHER ASSEMBLY 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Air pressure	100%	3.2	4.5.6.1/Drawing 9386824
102	Rotating of shaft inadequate after crimping	Level III	3.2	Manual
103	Distance from inside cover rim to top of shaft	Level III	3.2	Gage
104	Deleted			
Minor				
201	Component missing or inadequately assembled	Level II	3.2	Visual
202	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.10	TITLE Cover Assembly, After Painting	SHEET 1 OF 1		DRAWING NUMBER 12934838
				NEXT HIGHER ASSEMBLY 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Gasket improperly bonded to cover	Level III	3.2	Visual
102	After painting, the shaft shall freely rotate	Level III	3.2	Manual
103	Primer thickness, min.	Level III	3.2	Gage
104	Top coat thickness, min.	Level III	3.2	Gage
105	Spring clip and wire rope assembly inadequately swaged onto handle or hairpin spring clip	Level III	3.2	Visual/Manual
Minor				
201	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Supersedes page 25 dated 04 October 1994.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.11	TITLE Rim	SHEET 1 OF 2		DRAWING NUMBER 9386827
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Length of larger slot on side of rim	Level III	3.2	Gage
102	Location of larger slot from inside flat	Level III	3.2	Gage
103	Deleted			
104	Location of bayonet slot, 4 places	Level III	3.2	Gage
105	Dimension across flats, 2 places (Dimension A)	Level III	3.2	Gage
106	Dimension across corner, 2 places (Dimension D)	Level III	3.2	Gage
107	Width of larger slot	Level III	3.2	Gage
108	Inside diameter of rim (Dimension E)	Level III	3.2	Gage
109	Bayonet locking edge radius (2 places)	Level III	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Supersedes page 26 dated 04 October 1994.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.11	TITLE Rim	SHEET 2 OF 2		DRAWING NUMBER 9386827
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
201	Depth from edge of rim to inside flat	Level II	3.2	Gage
202	Deleted			
203	Deleted			
204	Drainage hole missing	Level II	3.2	Visual
205	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.12	TITLE Ring	SHEET 1 OF 2		DRAWING NUMBER 9386826
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Length of larger slot on side of ring	Level III	3.2	Gage
102	Location of larger slot from inside flat	Level III	3.2	Gage
103	Deleted			
104	Dimensions across flats, 2 places (Dimension A)	Level III	3.2	Gage
105	Width of larger slot	Level III	3.2	Gage
106	Opening of container interlocking grip	Level III	3.2	Gage
107	Depth of container interlocking grip	Level III	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Supersedes page 28 dated 04 October 1994.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.12	TITLE Ring	SHEET 2 OF 2		DRAWING NUMBER 9386826
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
201	Distance from edge of ring to outside flat	Level II	3.2	Gage
202	Deleted			
203	Deleted			
204	Location of container interlocking cutouts	Level II	3.2	Gage
205	Width of interlocking cutouts	Level II	3.2	Gage
206	Depth from interlocking cutout to inside flat	Level II	3.2	Gage
207	Drainage hole missing	Level II	3.2	Visual
208	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

320

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Supersedes page 29 dated 04 October 1994.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.13	TITLE Bottom	SHEET 1 OF 1		DRAWING NUMBER 9386825
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Material thickness	Level III	3.2	Gage
102	Hole location 1/	Level III	3.2	Gage
103	Hole diameter 1/	Level III	3.2	Gage
Minor				
201	Height of lip, minimum	Level II	3.2	Gage
202	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:
1/ 9386825 only.

22/

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Supersedes page 30 dated 04 October 1994.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.14	TITLE Body	SHEET 1 OF 1		DRAWING NUMBER 9386828
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Tensile strength of weld	Level III 1/	3.3.1	4.5.1
102	Wall thickness	Level III	3.2	Gage
103	Deleted			
104	Deleted			
105	Deleted			
Minor				
201	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:
1/ Three coupons per shift.

2.22

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Supersedes page 31 dated 04 October 1994.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.15	TITLE Plug, Stacking	SHEET 1 OF 1		DRAWING NUMBER 9386837
				NEXT HIGHER ASSEMBLY 9386830
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Length of plug	Level III	3.2	Gage
102	Width of plug	Level III	3.2	Gage
Minor				
201	Deleted			
202	Deleted			
203	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

22.3

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.16	TITLE Body Weldment, Prior to Painting	SHEET 1 OF 2		DRAWING NUMBER 9386830
				NEXT HIGHER ASSEMBLY 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Air pressure	100%	3.2	4.5.6.1
102	Weld of rim to body	Level III 1/	3.2	4.5.2
103	True position of holes of ring, rim and stacking plug	Level III	3.2	Gage
104	Location of hole in rim relative to holes in inside rings and stacking plugs	Level III	3.2	Gage
105	Location of hole in rim relative to hole in outside rings and stacking plugs	Level III	3.2	Gage
106	Perpendicularity of ring and rims with Datum-A	Level III	3.2	Gage
107	Distance from end of body to top of rim bayonet slot (four places)	Level III	3.2	Gage

NOTES:
1/ Three coupons per shift.

224

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Supersedes page 33 dated 04 October 1994.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.16	TITLE Body Weldment, Prior to Painting	SHEET 2 OF 2		DRAWING NUMBER 9386830
				NEXT HIGHER ASSEMBLY 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Major				
108	Minimum shear load between stacking plug and body	Level III	3.2	Gage
109	Flatness of body	Level III	3.2	Gage
110	Body end irregularities	Level III	3.2	4.5.9
111	Depth of body weldment	Level III	3.2	Gage
112	Deleted			
113	Deleted			
Minor				
201	Any weld of ring, rim or bottom to body missing, incomplete or visually inadequate	Level II	3.2	Visual
202	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:
2/ Deleted

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

Supersedes page 34 dated 04 October 1994.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.17	TITLE Body Weldment, After Painting	SHEET 1 OF 1		DRAWING NUMBER 9386830 or 12938059
				NEXT HIGHER ASSEMBLY 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Primer thickness	Level III	3.2	Gage
102	Paint thickness	Level III	3.2	Gage
103	Marking	Level III	3.2	5.3
104	Inside diameter, minimum	Level III	3.2	Gage
Minor				
201	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

2.26

Supersedes page 35 dated 04 October 1994.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.18	TITLE Container, Ammunition, Metal	SHEET 1 OF 1		DRAWING NUMBER 9386831 or 12912366
				NEXT HIGHER ASSEMBLY 9386833, 12912369, or 12913178
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Cover assembly test	Level III	3.5	Visual/Manual/4.5.7
102	Air pressure test (with yoke assembly in place, PA116 only)	Level III	3.2	4.5.6.2
103	Screw torque test (top and bottom, PA116 and cover PA116A1 only)	Level III 1/	3.2	4.5.8
Minor				
201	Missing, loose or damaged components	Level II	3.2	Visual
202	Protective finish damaged, bare spots exposing metal, etc.	Level II	3.2	Visual
203	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:
1/ The screw torque test shall be performed after the air pressure test has been performed and the screw has been reassembled.

227

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH 4.4.2.20	TITLE Yoke Assembly, After Painting	SHEET 1 OF 1		DRAWING NUMBER 12561227 or 12912337
				NEXT HIGHER ASSEMBLY 9386831 or 12912366
CATEGORY	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None Defined			
Major				
101	Location of the self clinching nut	Level III	3.2	Gage
102	Yoke stops inside the maximum base diameter	Level III	3.2	Gage
Minor				
201	Presence of spot welds on yoke stop	Level II	3.2	Visual
202	Pushout force improper	Level II	3.2	Gage
203	Presence of improper threads in self clinching nut	Level II	3.2	Gage/Visual
204	Evidence of poor workmanship	Level II	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

4.4.3 Testing. Testing is described in the First Article and Quality Conformance Inspection Tables.

4.4.3.1 Tensile strength. (See 3.3.1) Major Defect. Five bodies shall be randomly selected for this test. Four specimens, approximately equally spaced along the axis, shall be taken from each body at right angles to the weld. If one specimen of a sample fails to comply with the requirement, that sample shall be classed defective. If two or more samples are classed defective, the lot shall be rejected.

4.4.3.2 Tensile strength of body material. (See 3.3.1.1) Major Defect. Five bodies shall be randomly selected for this test. From each body, three specimens shall be selected at random for determination of body material tensile strength. If one specimen fails to comply with 3.3.1.1, that sample body shall be classed defective. If two or more sample bodies are classed defective, the lot shall be rejected.

4.4.3.3 Weld of rim to body. (See Drawing 9386830) Major Defect. Five body assemblies shall be selected for this test. If any sample fails to comply with the requirement, the lot shall be rejected.

4.4.3.4 Hardness of gasket. (See drawing 12910349) Major Defect. Five gaskets shall be randomly selected from each lot for this test. If any gasket fails to meet the requirement, the lot shall be rejected.

4.4.3.5 Deleted

4.4.3.5.1 Deleted

4.4.3.5.2 Deleted

4.4.3.5.3 Deleted

4.4.3.6 Deleted

4.4.4 Inspection equipment. The inspection equipment required to perform the examinations and tests prescribed herein is described in the "Inspection Method Reference" column in the tables starting with paragraph 4.4.2.1. The contractor shall submit for approval, inspection equipment designs in accordance with the terms of the contract (see 6.5).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

4.5.6.2 Air pressure of painted metal container. Subject the metal container to the internal air pressure, specified in the applicable metal container drawing. Observation shall be made for a pressure drop exceeding the requirement (as specified in the applicable drawing). A metal container, which exceeds the requirement shall be classed defective.

4.5.7 Cover assembly test. Upon assembly of the body and cover, the cover shall freely engage and rotate within the body. The Square handle shall engage into the respective bayonet slots of the rim without interference when in the clamping position. The Square handle when disengaged and in the open position shall disengage the cover from the body.

4.5.8 Screw torque test. The minimum applicable torque shall be applied to the screw. Any evidence of motion of the screw before reaching the minimum acceptable torque shall be cause for rejection of the container assembly being tested.

4.5.9 Body end irregularities. Visually inspect the body end for any nicks, dents, gouges, or mismatch. If a defect is evident, place a .01 inch diameter wire on the defect and a one inch long block over the wire. With the wire nested in the irregularity, gently press down on the block and remove the wire. If there is no evidence of resistance caused by the block, the part shall be classed defective.

4.5.10 Corrosion resistance test. The exterior surface of the container shall meet the salt spray requirements of TT-C-490.

5. PACKAGING

5.1 Preservation. None required.

5.2 Packing.

5.2.1 Deleted

5.2.2 Deleted

5.2.3 Commercial. The metal container shall be packed in accordance with ASTM D3951.

5.3 Marking.

5.3.1 Deleted

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

5.3.2 Deleted

5.3.3 Commercial. The metal container shall be marked in accordance with ASTM D3951 and the following additional instructions. Commercial shipping tags attached with wire shall show: Item name and

New page.

231

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

model number, part number and revision, contract number, lot number and data, name and address of manufacturer. If components and assemblies are bundled, boxed or palletized, the gross weight and quantity shall be included. The above information may be placed on pallets or boxes by labeling or stenciling.

5.4 Shipping. When containers from more than one lot are shipped at one time, each lot shall be kept separate and the division between lots clearly indicated to prevent mixing of lots in transit.

6. NOTES

6.1 Intended use. The metal container is intended for use as the outer shipping and storage packaging for the 120 mm Tank Cartridge.

6.2 Ordering data. Deleted

6.3 Definition of packaging and packing levels.

6.3.1 Level A. Full military protection, for unrestricted (OCONUS) shipment and storage.

6.3.2 Level B. Limited military protection for limited storage and (OCONUS) shipment.

6.3.3 Level C. For interplant (CONUS) shipment and very limited storage.

6.4 Drawings. Drawings listed in Section 2 of this specification under the heading U.S. Army Armament Research, Development and Engineering Center (ARDEC) may also include drawings prepared by, and identified as U.S. Army Armament Research and Development Command (ARRADCOM), U.S. Army Armament Research and Development Center (ARDC), Edgewood Arsenal, Frankford Arsenal, Rock Island Arsenal or Picatinny Arsenal drawings. Technical data originally prepared by these activities is now under the cognizance of ARDEC.

6.5 Submission of inspection equipment designs for approval. Submit designs as required to: Commander, U.S. Army Armament Research, Development and Engineering Center, ATTN: AMSTA-AR-QAC-T, Picatinny Arsenal, New Jersey 07801-5001.

6.6 Approval of equivalent test methods. Prior approval of the Contracting Officer is required for use of equivalent test methods. A description of the proposed method should be submitted through the Contracting Officer to: Commander, U.S. Army Armament Research, Development and Engineering Center, ATTN: AMSTA-AR-QAC-T, Picatinny Arsenal, New Jersey 07801-5001. This description should include but not be limited to the accuracy and precision of the method, test data demonstrating the accuracy and precision and drawings of any special equipment required.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

QUALITY ASSURANCE PROVISIONS FOR REFURBISHMENT

10. SCOPE

10.1 Scope. The appendix provides the Quality Assurance provisions for the refurbishment of containers, metal, for 120 mm tank ammunition. This Appendix is not a mandatory part of the Specification. The information contained herein is intended for compliance when refurbishing metal containers.

20. APPLICABLE DOCUMENTS

20.1 Government Drawings.

9386831 - Container, Ammo, Metal, PA116
Deleted
12912366 - Container, Ammo, Metal

30. REFURBISHMENT

30.1 Dents. Dents shall be removed as required to allow compliance with the workmanship requirement.

30.2 Cleaning. Paint and rust shall be removed.

30.3 Rims and/or rings. Rims and/or rings shall be straightened and welded by fillet welding where required.

30.4 Refinish. The parts shall be finished in accordance with the applicable drawings.

30.5 Seams. Seams shall be welded where required.

30.6 Gasket. The gaskets on the cover shall be replaced with new gaskets.

30.7 Refurbishment identification. Each container that will be refurbished shall have a 3/16 inch diameter hole punched/drilled in the rim (9386827-1). The hole shall be on the side where the identification markings are/were located. This side has the lip grip on the lower ring (second/bottom ring). The hole shall be approximately centered on the flat surface of the rim, but be no closer to an edge or curve than 3/8 inches. The hole will identify how many times this particular container has been refurbished.

40. REQUIREMENTS

40.1 Welds. Welds shall be in conformance with good commercial practices.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

40.2 Gasket. The gasket shall comply with all requirements specified on drawing 12910349.

40.3 Inside diameter of body weldment. Acceptance criteria is defined as the ability of the refurbished container to accept the insertion of the Projectile Support/Sleeve and Strap assembly during the load assemble and pack operation.

40.4 Air pressure test. The container assembly shall not exceed the leak rate of 5 cc/min when tested in accordance with 50.2.1.

40.5 Interchangeability. The cover assemblies and body weldments shall be interchangeable without affecting the function of the container.

40.6 Palletization test. All containers shall be palletized in accordance with 50.2.4.

40.7 Workmanship. All parts shall be free of cracks, burrs, chips, dirt, pin holes, rust, and bare spots unless allowed by the following workmanship standards.

a. Paint buildup. Runs, drips, sags and reinforcement overspray that are solid and exhibit no blistering are allowed. Paint drips on the sealing edge and paint buildup on gasket groove of cover assembly are not allowed.

b. Bare metal. Bare metal due to incidental chipping on edges and corners shall not to exceed 0.04 square inch.

c. Abrasions and scuffs. Abrasions and scuffs where bare metal is not exposed, due to normal handling and stacking at the rim and ring interface areas, are allowed.

d. Scratches. Scratches exposing bare metal are allowed on the cover assembly, ring and rim, provided all scratches do not accumulate a total of more than three (3) inches in length.

e. Dents. Dents are allowed provided there are no more than two per assembly and neither is larger than 2 inches in length.

f. Cracks. Cracks on edges are allowed provided they do not extend down the surface of the part or assembly when examined by the naked eye. Cracks on the edge of the pressure tab hole in the cover are acceptable.

g. Rust spots. When reusing the container in accordance with paragraph 60.1, container body rust spots shall be removed and refinished. Localized rust may be removed by mechanical means such as sanding and/or wire brush, etc. Any resultant bare metal on the container body shall be touched-up in accordance with paragraph 60.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

40.8 Lot number. The container lot number shall comply with MIL-STD-1168A to include the suffix of an overhauled lot for refurbished containers.

40.9 Paint thickness. The paint thickness may be increased to cover the shot blast profile and meet the salt spray requirement.

40.10 Reuse criteria. When limited refurbishment is performed on the containers in accordance with paragraph 60.1, the containers shall be inspected in accordance with paragraph 50.1.5. The unit load does not need to be depalletized if it meets the criteria of 50.1.5 and the visible exterior containers on the pallet do not appear damaged beyond the requirements of this appendix. Also that the old ammo lot number has previously been removed from the side of the container and is currently stenciled on the bottom.

50. INSPECTION

50.1 Examination. Unless otherwise specified examinations for major and minor characteristics shall be performed in accordance with Table II of paragraph 4.4.2.

235

New page.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

CLASS	CHARACTERISTICS	CONFORMANCE CRITERIA	INSPECTION METHOD
50.1.1	Gasket (Drawing 12910349)		
CRITICAL	None defined		
MAJOR			
101	Material certification	Certification	
102	Hardness		50.2.3
103	Height of rectangular cross section	Level III	Gage
MINOR			
201	Poor workmanship	Level II	Visual/Gage
50.1.2	Cover Assembly (Drawing 9386824)		
CRITICAL	None defined		
MAJOR			
101	Paint thickness, minimum	Level III	Gage
MINOR			
201	Poor workmanship	Level II	Visual/Gage
50.1.3	Body Weldment, after painting (Drawing 9386830)		
CRITICAL	None defined		
MAJOR			
101	Paint thickness, minimum	Level III	Gage
102	Inside diameter, minimum	Level III	Gage
MINOR			
201	Poor workmanship	Level II	Visual/Gage

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

50.1.4 Container, Ammunition, Metal (Drawing 9386831 or 12912366)

CRITICAL	None defined		
MAJOR			
101	Air pressure test	Level III	50.2.1
102	Interchangeability test	Level III	50.2.2
103	Palletization test	100%	50.2.4
104	Corrosion resistance test	5	50.2.5
MINOR			
201	Poor workmanship	Level II	Visual/Gage

50.1.5 Internal component test

CRITICAL	None defined		
MAJOR			
101	Internal component test	100%	50.2.6
MINOR	None defined		

50.2 Test methods and procedures.

50.2.1 Air pressure test of painted container assembly. Subject the container assembly to an internal air pressure of 3.0 + 0.5 PSIG. Observation shall be made for leakage. A container assembly where the leakage exceeds the requirement shall be classified as defective.

50.2.2 Interchangeability of painted container assemblies. Randomly interchange the cover assemblies with container body weldments and perform the air pressure test per 50.2.1. Failure to meet the applicable requirement shall be cause for rejection of the lot. The test shall be performed after the air pressure has been performed.

50.2.3 Hardness of gasket. One plaque (4 specimens) at the start and end of each shift shall be selected. The hardness test shall be performed on the specimens in accordance with ASTM D2240. Shore A hardness readings shall be taken on the end of each specimen. Any specimen failing the applicable requirements shall be cause for rejection of that lot of material. This requirement applies to the gasket manufacturer. If the gaskets are purchased, the contractor shall verify the hardness by obtaining a Certified Material Test Report (CMTR) from the gasket manufacturer.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.

APPENDIX A

50.2.4 Palletization test. Select thirty containers and palletize them five wide by six high. Any container that cannot be interlocked or stacked shall be rejected and replaced with an acceptable one.

50.2.5 Corrosion resistance test. The exterior surface of the container shall meet the salt spray requirements of TT-C-490. This test shall be performed prior to acceptance of the first production lot.

50.2.6 Internal component test. The cover of each container shall be removed and checked for freedom of movement of the sleeve and strap assembly. The sleeve and strap assembly shall move out of the container approximately 3-4 inches. Visually inspect for any foreign material, missing or damaged internal components, and that there is no standing moisture/water on the components or under the sleeve and strap. Wet components shall be dried prior to reuse.

60.1 Reuse with limited refurbishment. If approved by the Procuring Contract Officer (PCO) containers may be re-used without completely stripping the paint and removing the inserts if the container is received at the load center without any apparent rust on the inside. Remove dirt and dust from container exterior. The rust on the outside must not exceed grade 7 of ASTM-D610. Any rust spots must be removed and touched-up in accordance with the protective finish requirements of drawing 9386830 prior to pack-out. The gasket shall be replaced (30.6), old markings shall be obliterated. The following paragraphs of Appendix A shall be applicable, 30.6, 40.2, 40.4, 40.6, 40.7, 50.1.1, 50.1.4 and 50.2. Major 101 of 50.1.4, air pressure test, is required to pass normal inspection sampling per Table II. Paragraph 50.2.2 and Major 102 of 50.1.4, Interchangeability test, are not required.

~~Custodian: Army (AR)~~

~~Preparing activity: Army (AR)~~

~~Project Number: 8140~~

New page.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:29Z
Check the source to verify that this is the current version before use.