INCH-POUND

MIL-I-82799(OS)
29 December 1989
SUPERSEDING
WS 23737
6 January 1986

MILITARY SPECIFICATION

INSULATION SLEEVING, ELECTRICAL, HEAT-SHRINKABLE

his specification is approved for use by the Naval Sea Systems Command, Depart-ent of the Navy and is available for use by all Departments and Agencies of the epartment of Defense.

1. SCOPE

1.1 **Scope.** This specification covers the requirements for six types of eat-shrinkable, electrical insulation sleeving, referred to herein as sleeving.

1.2 **Classification.** The sleeving, prior to unrestricted shrinkage, shall e classified as follows:

Type I	0.187-inch inside diameter (ID)
Type II	0.238-inch ID
Type III	0.355-inch ID
Type IV	0.475-inch ID
Type V	0.712-inch ID
Type VI	0.950-inch ID

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 **Specifications, standards and handbooks.** The following specifica-ions, standards and handbooks form a part of this document to the extent pecified herein. Unless otherwise specified, the issues of these documents are hose listed in the issue of the Department of Defense Index of Specifications nd Standards (DODISS) and supplement thereto, cited in the solicitation see 6.2).

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commanding Officer, Naval Ordnance Station, Standardization Branch (3730), Indian Head, MD 20640-5000, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

MSC N/A FSC 5970

DISTRIBUTION STATEMENT A. Approved for public release; distribution is nlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:41Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

MILITARY

MIL-H-5606 Hydraulic Fluid, Petroleum Base, Aircraft, Missile and Ordnance

MIL-T-5624 Turbine Fuel, Aviation, Grades JP-4, JP-5 and JP-5/JP-8 ST

STANDARDS

FEDERAL

FED-STD-313 Material Safety Data, Transportation Data and Disposal Data for Hazardous Materials Furnished to Government Activities

MILITARY

MIL-STD-104 Limits for Electrical Insulation Color

MIL-STD-129 Marking for Shipment and Storage

(Unless otherwise indicated, copies of federal and military specifications standards, and handbooks are available from: Military Specifications and Standards, Bldg. 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094).

2.1.2 **Other Government documents, drawings, and publications.** The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

CODE OF FEDERAL REGULATIONS (CFR)

49 CFR 100-199 Transportation

(Application for copies of CFRs should be addressed to the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402-0001.)

2.2 **Non-Government publications.** The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN TRUCKING ASSOCIATION, INC.

National Motor Freight Classification

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:41Z
Check the source to verify that this is the current version before use.

(Application for copies should be addressed to the American Trucking Association, Inc., Attn: Traffic Dept., 2200 Mill Road, Alexandria, VA 22314-4677.)

NATIONAL RAILROAD FREIGHT COMMITTEE

Uniform Freight Classification (UFC) 6000

(Application for copies should be addressed to the National Railroad Freight Committee, 222 South Riverside Plaza, Suite 1120, Chicago, IL 60606-5945.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D 876	Testing Nonrigid Vinyl Chloride Polymer Tubing Used for Electrical Insulation
ASTM D 910	Aviation Gasolines
ASTM D 2671	Heat-Shrinkable Tubing for Electrical Use
ASTM G 21	Determining Resistance of Synthetic Polymeric Materials to Fungi (DoD adopted)

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample of the sleeving shall be subjected to first article inspection (see 6.5) in accordance with 4.3.

3.2 Material. The sleeving shall be fabricated from thermally stabilized, radiation crosslinked, modified polyolefin with an interior coating of thermoplastic adhesive.

3.3 Dimensions. The sleeving dimensions shall be as specified in table I.

3.4 Physical, electrical, and chemical properties. The properties of the six types of sleeving shall be as specified in table II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:41Z
Check the source to verify that this is the current version before use.

TABLE I. Sleeving dimensions.

As supplied		After unrestricted shrinkage (200 ± 2°C for 10 minutes)	
Type	Inside diameter, inches, minimum	Inside diameter, inches, maximum	Total wall thickness
I	0.187	0.093	0.022 +0.010 -0.005
II	0.238	0.125	0.029 +0.010 -0.005
III	0.355	0.187	0.029 +0.010 -0.005
IV	0.475	0.250	0.030 +0.010 -0.005
V	0.712	0.375	0.035 +0.010 -0.005
VI	0.950	0.500	0.042 +0.010 -0.007

TABLE II. Physical, electrical, and chemical properties.

Property	Minimum	Maximum
Physical		
Longitudinal change, percent	- 10	+ 1
Tensile strength, psi	1500	---
Ultimate elongation, percent	200	---
Secant modulus, psi	---	2.5×10^4
Specific gravity	---	1.35
Low temperature flexibility, 4 hours at -55°C	No cracking	
Heat shock, 4 hours at 250°C	No dripping, flowing, or cracking	
Heat resistance, percent, 336 hours at 175°C followed by test for ultimate elongation	150	---
Copper stability, percent, 168 hours at 160°C followed by test for ultimate elongation	200	---
Color stability, 48 hours at 175°C	MIL-STD-104	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:41Z
Check the source to verify that this is the current version before use.

TABLE II. Physical, electrical, and chemical properties (continued).

Property	Minimum	Maximum
Electrical		
Dielectric strength, volts/mil	400	---
Volume resistivity, ohm-cm	10^{14}	---
Chemical		
Corrosive effect	Noncorrosive	
Flame retardancy	Self-extinguishing within 1 minute, 25 percent maximum flag burn	
Fungus resistance	Rating of one or less	
Water absorption, percent, 24 hours at 25°C (77°F)	---	[illegible]
Fluid resistance, 24 hours at 25°C (77°F) in: MIL-T-5624 JP-4 Fuel; SKYDROL 500; MIL-H-5606 Hydraulic Fluid; ASTM D 910 Aviation Gas; Water	run tests listed below after immersion	
Followed by tests for:		
Tensile strength, psi	1000	---
Dielectric strength, volts/mil	500	---

3.5 **Color.** The sleeving shall be black in accordance with the requirements of MIL-STD-104.

3.6 **Safety.**

3.6.1 **Toxic products and formulations.** The material shall have no adverse effect on the health of personnel when used for its intended purpose. Questions pertinent to this effect shall be referred by the contracting activity to the appropriate departmental medical service who will act as an advisor to the contracting agency (see 4.1.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:41Z
Check the source to verify that this is the current version before use.

3.6.2 **Material Safety Data Sheets (MSDS).** The contractor shall prepare and submit an MSDS in accordance with FED-STD-313 as specified in the contract (see 6.2).

3.7 **Shelf life.** The sleeving specified herein shall have an unlimited shelf life when stored at ambient conditions (see 6.3.1).

3.8 **Workmanship.** The sleeving, both before and after shrinkage, shall be free from internal voids, blisters, lumps, dents, tears, pinholes, seams, cracks, foreign matter, or other defect that would be detrimental to fabrication, acceptance, or performance.

4. QUALITY ASSURANCE PROVISIONS

4.1 **Responsibility for inspection.** Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 **Responsibility for compliance.** All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.1.2 **Toxicological product formulations.** The contractor shall have the toxicological product formulations and associated information available for review by the contracting activity to evaluate the safety of the material for the proposed use.

4.2 **Classification of inspections.** The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 **First article inspection.** First article inspection shall consist of the examinations and tests specified in table III. The test samples shall consist of 50 feet of sleeving of the size specified prior to shrinkage. Samples shall be grouped into two size ranges: 3/16 to 1/4 inch and 3/8 to 3/4

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:41Z
Check the source to verify that this is the current version before use.

inch. Failure to meet all of the requirements specified herein shall be cause for rejection of the first article sample.

Table III. First article inspection.

Examinations and Tests	Requirement	Test Method
Dimension and longitudinal change	3.3	4.5.2
Tensile strength and ultimate elongation	3.4	4.5.3
Secant modulus	3.4	4.5.4
Specific gravity	3.4	4.5.5
Low temperature flexibility	3.4	4.5.6
Heat shock	3.4	4.5.7
Heat resistancy	3.4	4.5.8
Copper stability	3.4	4.5.9
Dielectric strength	3.4	4.5.10
Volume resistivity	3.4	4.5.11
Color stability	3.4	4.5.12
Corrosive effect	3.4	4.5.13
Flame retardancy	3.4	4.5.14
Fungus resistance	3.4	4.5.15
Fluid resistance	3.4	4.5.16
Water absorption	3.4	4.5.17
Color	3.4	4.5.1.1

4.4 **Quality conformance inspection.** Quality conformance inspection shall consist of the tests specified in table IV

4.4.1 **Lot.** A lot shall consist of all sleeving of the same size and submitted for inspection at one time from the same production run.

TABLE IV. Quality conformance inspection.

Examinations and Tests	Requirement	Test Method
Visual examination	3.8 and Section 5	4.5.1.1
Dimension, as supplied	3.3	4.5.2
Longitudinal change	3.4	4.5.2
Tensile strength and ultimate elongation	3.4	4.5.3
Secant modulus	3.4	4.5.4
Heat shock	3.4	4.5.7

4.4.2 Sampling. Samples shall consist of not less than 16 feet of sleeving selected from each lot. Sample size shall be as specified in table V

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:41Z
Check the source to verify that this is the current version before use.

TABLE V. Sampling.

Number of containers in lot	Number of containers to be selected
1 - 3	all
4 - 15	3
16 - 25	4
26 - 40	5
41 - 65	7
66 - 110	10
111 - 180	15

4.5 **Inspection methods.** The following inspection methods shall be used. Unless otherwise specified in the applicable test method, all weights, volumes, temperatures, and times shall be measured to the nearest specified unit or decimal.

NOTE: Reagent grade chemicals shall be used for chemical reactions in the conduct of all tests defined herein. Solvents and indicators may be commercial nonreagent grade materials.

4.5.1 **Visual examination.** Visual examination shall be made to verify conformance to the requirements of 3.8 and section 5.

4.5.1.1 **Color.** The color shall be determined in accordance with MIL-STD-104.

4.5.2 **Dimensions and longitudinal change.** Three 6-inch specimens of tubing shall be measured for length, within 1/32 inch, and inside diameter in accordance with ASTM D 2671; conditioned for 3 minutes in a 200 ± 5°C (392 ± 10°F) oven, cooled to 23 ± 3°C (73 ± 5°F), and then remeasured. Prior to and after conditioning, the dimensions of the tubing shall be in accordance with table I and the longitudinal change shall be in accordance with table II. The longitudinal change shall be calculated as follows:

$$C = \frac{L_1 - L_0}{L_0} \times 100$$

Where:
C = longitudinal change (percent)
L_0 = length before conditioning, inches
L_1 = length after conditioning, inches

4.5.3 **Tensile strength and ultimate elongation.** The tensile strength and ultimate elongation of the tubing shall be determined in accordance with ASTM D 2671 using 1-inch benchmarks and a 1-inch initial jaw separation. The speed of jaw separation shall be 20 ± 2 inches per minute.

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:41Z
Check the source to verify that this is the currentversion before use.

4.5.4 **Secant modulus.** The secant modulus of the tubing shall be determined in accordance with ASTM D 2671.

4.5.5 **Specific gravity.** The specific gravity shall be determined in accordance with ASTM D 2671.

4.5.6 **Low temperature flexibility.** Three 12-1/4 inch strips cut from size 0.750 and a mandrel selected in accordance with table VI shall be conditioned for a minimum of 4 hours at 55 ± 2°C. While at this same temperature, the specimens shall then be wrapped around the mandrel for not less than 360 degrees in 2.0 ± 0.4 seconds. The specimens shall then be visually examined for evidence of cracking.

TABLE VI. Mandrel dimensions for bend testing.

Tubing size, inch (as supplied)	Diameter of mandrel, inch (nominal)
0.125 to 0.250	7/16
0.251 to 0.750	1/2
over 0.750	9/16

4.5.7 **Heat shock.** Three 6.0 ± 1.2-inch specimens of tubing shall be conditioned for 4 hours in a 250 ± 5°C (482 ± 10°F) oven. After this conditioning, the specimens shall be removed from the oven, cooled to 23 ± 3°C (73 ± 5°F), wrapped 180 degrees around a mandrel selected in accordance with table VI, and then visually examined for evidence of dripping, flowing, or cracking. Any side cracking caused by flattening of the specimen on the mandrel shall not constitute failure.

4.5.8 **Heat resistance.** Three 6.0 ± 1.2-inch specimens of tubing shall be conditioned for a minimum of 336 hours in a 175 ± 3°C (347 ± 10°F) oven. After this conditioning, the specimens shall be removed from the oven, cooled to 23 ± 3°C (73 ± 5°F) and tested for elongation in accordance with 4.5.3.

4.5.9 **Copper stability.** A 6-inch specimen of tubing shall be slid over a snug fitting, straight, clean, bare copper conductor. For tubing sizes 0.250 inch and smaller, a solid conductor shall be used; for tubing sizes 0.375 inch and larger, a solid or tubular conductor shall be used. The specimens on the conductors shall be conditioned for a minimum of 24 hours in a desiccator or similar humidity chamber at 90 to 95 percent relative humidity and 25 ± 3°C (77 ± 5°F). The specimens on the conductors shall then be conditioned for a minimum of 168 hours in a 160 ± 3°C (320 ± 10°F) oven. The copper conductor shall then be removed from the tubing, and the tubing and conductor examined. Darkening of the copper due to normal air oxidation shall not be cause for rejection. The tubing shall be tested for elongation in accordance with 4.5.3.

4.5.10 **Dielectric strength.** The dielectric strength shall be determined by following the procedure of ASTM D 876 for dielectric breakdown. When

Source: https://assist.dla.mil -- Downloaded: 2026l0-26T04:41Z
Check the source to verify that this is the current version before use.

dielectric breakdown occurs, the thickness measurements for calculating dielectric strength shall be made adjacent to the point of breakdown and the dielectric strength shall be calculated in volts per mil.

4.5.11 **Volume resistivity.** Volume resistivity shall be determined in accordance with ASTM D 2671.

4.5.12 **Color stability.** The color stability of the tubing shall be tested in accordance with ASTM D 2671 for 48 ± 4 hours at 175 ± 3°C (347 ± 10°F). After conditioning, the specimens shall be examined for conformance with MIL-STD-104.

4.5.13 **Corrosive effect.**

4.5.13.1 **Copper mirror corrosion.** The tubing shall be tested for copper mirror corrosion in accordance with ASTM D 2671, Procedure A, for a minimum of 16 hours at 175 ± 3°C (347 ± 10°F). For tubing sizes 0.125 inches and larger, specimens shall consist of 1/4- x 1-inch strips cut longitudinally. Evidence of corrosion shall be the removal of copper from a mirror, leaving an area of transparency greater than 5 percent of its total area.

4.5.13.2 **Corrosion in contact with copper.** The tubing shall be tested for corrosion in contact with copper in accordance with ASTM D 2671, Procedure B, for a minimum of 16 hours at 175 ± 3°C (347 ± 10°F).

4.5.14 **Flame retardance.** An approximate 18-inch specimen of tubing shall be recovered over a 21-inch metal rod with a diameter equivalent to the maximum recovered diameter specified in table I. The specimen shall then be subjected to the vertical test in accordance with ASTM D 2671. The tubing shall be considered self-extinguishing only if it extinguishes within 1 minute after the final removal of the gas flame, and if not more than 25 percent of the indicator flag is burned or charred. Brown scorching or soot on the indicator flag shall not be cause for rejection.

4.5.15 **Fungus resistance.** Fungus resistance shall be determined in accordance with ASTM G 21.

4.5.16 **Fluid resistance.** Six 6-inch specimens of tubing, prepared and measured in accordance with ASTM D 2671, shall be completely immersed in each listed fluid for 24 ± 2 hours at 25 ± 3°C (77 ± 5°F). The volume of the fluid shall be not less than 20 times that of the specimens. After immersion, the specimens shall be lightly wiped and air dried for 30 to 60 minutes at room temperature. Three specimens shall then be tested for dielectric strength and the other three tested for tensile strength.

4.5.17 **Water absorption.** Water absorption shall be determined in accordance with ASTM D 2671.

4.6 **Inspection of packaging.** The sleeving containers and container markings shall be visually examined to verify compliance with section 5

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:41Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 **Packaging.** Unless otherwise specified in the contract or order (see 6.2), packaging shall be level C as specified herein.

5.1.1 **Level C.** The sleeving shall be packaged to afford adequate protection against loss, contamination, deterioration, and damage during shipment from the supply source to the first receiving activity and during storage under the shelf life period and conditions specified in 3.7. Containers in the same shipment shall be of the same size. The packaging shall conform to UFC 6000, National Motor Freight Classification, 49 CFR 171-178, or to other carrier rules and regulations as applicable to the mode of transportation.

5.2 **Marking.**

5.2.1 **Standard marking.** In addition to any special marking required by the contract or order (see 6.2), interior and exterior containers shall be marked in accordance with MIL-STD-129.

5.2.2 **Special marking.** In addition to the marking requirements of 5.2.1, each container marking shall include the following:

a. Title, number, and date of this specification.

b. Manufacturer's name and address.

c. Date of manufacture.

d. Net weight of contents.

e. Shelf life expiration date.

f. Storage conditions.

g. Toxicity warning (if applicable).

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 **Intended use.** The sleeving is intended for use in the manufacture of Standard Missile Mk 104 Dual Thrust Rocket Motors.

6.2 **Acquisition requirements.** Acquisition documents must specify the following:

a. Title, number and date of this specification.

b. Issue of DODISS to be cited in the solicitation, and if required

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:41Z
Check the source to verify that this is the current version before use.

the specific issue of individual documents referenced (see 2.1.1 and 2.1.2).

c. Material Safety Data Sheets Required (see 3.6.2 and 6.6)

d. Whether first article inspection is required (see 3.1 and 6.5)

e. Special marking, if other than as specified in 5.2.

6.3 **Definitions.**

6.3.1 **Ambient conditions.** Ambient conditions are those conditions of temperature and relative humidity experienced by the material when stored in an enclosed warehouse.

6.4 **Possible material.** The following material has been found to meet the requirements of this specification. This is only given for information and is not restrictive. TAT-125 Thermofit Adhesive Tubing manufactured by Raychem Corporation, 300 Constitution Drive, Menlo Park, California 94025, has been found to meet the requirements of this specification.

6.5 **First article.** When first article inspection is required, the contracting officer should provide specific guidance to offerors whether the item(s) should be a preproduction sample, a first article sample, a first production item, a sample selected from the first production items, or a standard production item from the contractor's current inventory (see 3.1), and the number of items to be tested as specified in 4.3. The contracting officer should also include specific instructions in acquisition documents regarding arrangements for examinations, approval of first article test results, and disposition of first articles. Invitations for bids should provide that the Government reserves the right to waive the requirement for samples for first article inspection to those bidders offering a product which has been previously acquired or tested by the Government, and that bidders offering such products, who wish to rely on such production or test, must furnish evidence with the bid that prior Government approval is presently appropriate for the pending contract. Bidders should not submit alternate bids unless specifically requested to do so in the solicitation.

6.6 **Material Safety Data Sheets.** MSDS requirements are applicable to this specification and should be specified in the contract as required by the Federal Acquisition Regulation (FAR) Part 23, subpart 23.3. Contracting officers will identify those activities requiring copies of completed Material Safety Data Sheets prepared in accordance with FED-STD-313. The pertinent Government mailing addresses for submission of data are listed in FED-STD-313.

6.7 **Subject term (key word) listing.**

Rocket Motor, Dual Thrust, Mk 104
Standard Missile

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:41Z
Check the source to verify that this is the current version before use.

Preparing Activity:
Navy - OS
(Project 5970-N673)

★U.S. GOVERNMENT PRINTING OFFICE: 1990--704-034/30,260

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:41Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:41Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER MIL-I-82799	2. DOCUMENT DATE (YYMMDD) 29 December 1989

3. DOCUMENT TITLE
INSULATION SLEEVING, ELECTRICAL, HEAT-SHRINKABLE

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY NAVAL ORDNANCE STATION (CODE 3730) INDIAN HEAD, MD 20640-5000

a. NAME	b. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON
c. ADDRESS (Include Zip Code)	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:41Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:41Z
Check the source to verify that this is the current version before use.