INCH-POUND

MIL-PRF-32828
30 September 2026

PERFORMANCE SPECIFICATION

AUSTENITIC CHROMIUM-NICKEL-MOLYBDENUM STAINLESS STEEL, CORROSION-RESISTANT, WIRE ARC, DIRECTED ENERGY DEPOSITION, ADDITIVELY MANUFACTURED

This specification is approved for use by the Naval Sea Systems Command and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers additively manufactured (AM) corrosion-resistant austenitic chromium-nickel-molybdenum stainless steel (316L and 316LSi) material using the wire arc directed energy deposition (DED) process.

1.2 Classification. Material is of the following grades and classes, as specified (see 6.2).

1.2.1 Grades. (see 4.8)

a. Grade A – Material manufactured in compliance with S9074-A4-GIB-010/AM-WIRE DED.

b. Grade B – Material manufactured in compliance with manufacturer specifications or industry standards (see 6.3).

1.2.2 Classes.

a. Class 1 – Material manufactured using wire feedstock that is in compliance with MIL-E-19933, type MIL-316L, or with a modified version of type MIL-316L that aligns with UNS S31688 by increasing silicon content to a value not less than 0.65 and not greater than 1.00 weight-percent.

b. Class 2 – Material manufactured using wire feedstock that is in compliance with AWS A5.9/A5.9M, class 316L (UNS S31683) or class 316LSi (UNS S31688).

Comments, suggestions, or questions on this document should be addressed to Commander, Naval Sea Systems Command, ATTN: SEA 05T, 1333 Isaac Hull Avenue, SE, Stop 5160, Washington Navy Yard, DC 20376-5160 or emailed to commandstandards@navy.mil, with the subject line “Document Comment”. Since contact information can change, you may want to verify the currency of this address information using ASSIST at https://assist.dla.mil.

AMSC N/A AREA AMPR

Distribution Statement A. Approved for public release: distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T07:48Z
Check the source to verify that this is the current version before use.

1.3 Part or identifying number (PIN). PINs to be used for material acquired to this specification are created as follows (see 6.2):

M	**32828**	-	**X**	**X**
Prefix for Military Specification	Specification Number	-	Grade (see code below)	Class (see code below)

PIN Codes

Grade	Code
A	A
B	B

Class	Code
1	1
2	2

Example: M32828-A2

2. APPLICABLE PUBLICATIONS

2.1 General. The publications listed in this section are specified in sections 3 and 4 of this specification. This section does not include publications cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, users of this document are cautioned that they must meet all specified requirements of publications cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government publications.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these publications are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-E-19933 - Electrodes and Rods - Welding, Bare, Chromium and Chromium-Nickel Steels

DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-792 - Manufacturing Process Standard Identification Marking Requirements for Special Purpose Components

MIL-STD-1684 - Control of Heat Treatment

(Copies of these publications are available online at https://quicksearch.dla.mil.)

2.2.2 Other Government publications. The following other Government publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these publications are those cited in the solicitation or contract.

NAVAL SEA SYSTEMS COMMAND (NAVSEA) PUBLICATIONS

S9074-A4-GIB-010/AM-WIRE DED - Requirements for Metal Wire-Fed Directed Energy Deposition Additive Manufacturing

(Copies of this publication are available online via Model Based Product Support (MBPS) at https://mbps.navsea.cloud.navy.mil/Windchill. To request an MBPS account, submit a ticket to the ServiceNow Assistance Portal (SNAP), https://snap.navair.navy.mil/mbps (DoD PKI Certificate required). This publication is available for ordering (hard copy) via the Naval Logistics Library (NLL) at https://nll.navsup.navy.mil. For questions regarding the NLL, contact the NLL Customer Service at nllhelpdesk@navy.mil, (866) 817-3130, or (215) 697-2626/DSN 442-2626.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T07:48Z
Check the source to verify that this is the current version before use.

2.3 Non-Government publications. The following publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these publications are those cited in the solicitation or contract.

AMERICAN WELDING SOCIETY

AWS A5.9/A5.9M - Specification for Bare Stainless Steel Welding Electrodes and Rods

(Copies of this publication are available online at www.aws.org.)

ASTM INTERNATIONAL

ASTM A751 - Standard Test Methods and Practices for Chemical Analysis of Steel Products

ASTM E8/E8M - Standard Test Methods for Tension Testing of Metallic Materials

ASTM E353 - Standard Test Methods for Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

ASTM E1019 - Standard Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel, Iron, Nickel, and Cobalt Alloys by Combustion and Inert Gas Fusion Techniques

ASTM E1086 - Standard Test Method for Analysis of Austenitic Stainless Steel by Spark Atomic Emission Spectrometry

ASTM E3515 - Standard Test Method for Analysis of Low Alloy Steel by Inductively Coupled Plasma Atomic Emission Spectrometry (Performance Based)

(Copies of these publications are available online at www.astm.org.)

SAE INTERNATIONAL

SAE AMS2750 - Pyrometry

(Copies of this publication are available online at www.sae.org.)

2.4 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Feedstock. Unless otherwise specified (see 6.2), wire feedstock shall be in accordance with the standard (MIL-E-19933 or AWS A5.9/A5.9M) of the appropriate class (see 1.2). Each manufacturing lot (see 4.3) shall be produced from the minimum practicable number of lots of feedstock (see 6.6.2).

3.2 Build platform. Unless otherwise specified (see 6.2), the build platform shall not be integrated into the printed material. If material other than S-8 material, as defined by S9074-A4-GIB-010/AM-WIRE DED, is used for a non-integrated build platform, a minimum of 0.5 inch of discardable AM build material shall separate the build platform from the deposited material's attached dimensional surface. Methods used for removal of the build platform (e.g., band saw, water jet, or electro-discharge machining with recast layer removed) shall not affect the mechanical properties of the AM material.

3.3 Chemical composition. All DED material shall conform to the compositions specified in table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T07:48Z
Check the source to verify that this is the current version before use.

TABLE I. Chemical composition, weight-percent. 1/, 2/

Element	Composition
Carbon	0.03
Manganese	1.0 to 2.5
Phosphorus	0.03
Sulfur	0.03
Silicon	0.30 to 1.00
Chromium	18.0 to 20.0
Nickel	11.0 to 14.0
Molybdenum	2.0 to 3.0
Copper	0.75
Cobalt	3/
Other Elements, total	0.50
Iron	Remainder

NOTES:

1/ Analysis shall be made for the elements with specific values shown in this table. However, if the presence of other elements is indicated during routine analysis, further analysis shall be made to determine their content. The total of these other elements shall not exceed the limits specified for the "Other Elements, total" row of the table.

2/ Single values are maximum.

3/ When specified (see 6.2), cobalt content shall be limited to the maximum quantity specified in the contract or order.

3.4 Heat treatment. Material shall be heat treated in a furnace that is in accordance with the pyrometry requirements of SAE AMS2750, class 5 or better. Material shall be heated to 1950 °F and held for a minimum of 1 hour per inch of thickness or fraction thereof, then rapidly quenched to below 700 °F. When specified (see 6.2), heat treatment shall be in accordance with MIL-STD-1684.

3.5 Tensile properties. The tensile properties of all material shall meet or exceed the values specified in table II. Reduction of area shall be measured and reported for information.

TABLE II. Tensile properties.

Property	Minimum value
Ultimate tensile strength (ksi)	70
Yield strength, 0.2% offset (ksi)	30
Elongation in 2 inches (%)	30
Reduction of area (%)	Information only

3.6 Additional mechanical properties. Additional mechanical properties shall be as specified (see 6.2).

3.7 Surface condition. Unless otherwise specified (see 6.2), material shall be ground, machined, or otherwise finished to produce smooth surfaces.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T07:48Z
Check the source to verify that this is the current version before use.

3.8 Detrimental material controls. During the manufacturing processes, examinations, and tests, the material shall not come into direct contact with mercury or any of its compounds, nor with any mercury-containing device employing a single boundary of containment. The presence of mercury in a product or contact material may be determined by reviewing product labeling, material safety data sheets, or safety data sheets for declarations that mercury is a constituent of the product. The absence of a declaration of mercury on product labeling, material safety data sheets, or safety data sheets shall be considered as evidence of no mercury or mercury containing compounds in the product or contact material. If a product is reported to contain mercury, the content shall contain no more than 10 parts per million (ppm) mercury. Additional detrimental material controls shall be as specified (see 6.2).

3.9 Identification marking. Material other than specimens used for conformance inspections shall be marked with the number and revision of this specification, manufacturer name or CAGE code, and manufacturing lot number. Markings shall be permanently applied in accordance with MIL-STD-792; an alternate marking method is permissible provided it is an available option in the contractually invoked drawing or specification. Markings shall be located so as not to affect the form, fit, or function of the material and must be legible after all required surface finishing and post-processing operations.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Conformance inspection (see 4.2).

4.2 Conformance inspection. Conformance inspection shall include the examinations and tests of table III.

TABLE III. Conformance inspections.

Examinations and tests	Requirement	Conformance inspection	Sampling requirements
Feedstock	3.1	4.8	---
Build platform	3.2	4.8	---
Chemical composition	3.3	4.5 and 4.8	4.4.1 and 4.4.3
Heat treatment	3.4	4.8	---
Tensile properties	3.5	4.6 and 4.8	4.4.2 and 4.4.3
Additional mechanical properties	3.6	4.7 and 4.8	---
Surface condition	3.7	4.8	---
Detrimental material controls	3.8	4.8	---
Identification marking	3.9	4.8	---

4.3 Lot size. For the purposes of inspections and tests, material produced in one build cycle, as defined in S9074-A4-GIB-010/AM-WIRE DED, and heat treated in the same furnace load shall constitute a manufacturing lot.

4.4 Sampling.

4.4.1 Chemical composition. A minimum of one sample shall be tested from each lot in its final heat treated condition.

4.4.2 Tensile properties. A minimum of two tensile specimens shall be tested from each lot in its final heat treated condition. Tensile specimens shall be machined from bulk deposition or near-net shape blanks. Tensile specimens shall conform to ASTM E8/E8M standard round specimen size 1 geometry with a gauge length four times the diameter. At least one specimen shall be oriented with its length in the Z-axis and at least one specimen shall be oriented with its length in the XY plane (see 6.6.1 for clarification on DED build orientations).

4.4.3 Resampling and retesting. Unless otherwise specified (see 6.2), non-conforming test results may be addressed by testing two additional samples taken from the same manufacturing lot as the original non-conforming sample. The average of all test results shall meet specified requirements for lot acceptance. If any two samples of

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T07:48Z
Check the source to verify that this is the current version before use.

any type of test fail to meet the acceptance criteria, then the manufacturing lot shall be rejected. When specified (see 6.2), any manufacturing lot may be rejected based on a single tensile test.

4.5 Chemical composition analysis. Chemical analysis shall be performed in accordance with ASTM A751, ASTM E353, ASTM E1086, ASTM E1479, or ASTM E1019, or other methods, as specified (see 6.2). Phosphorus content shall be determined in accordance with ASTM E3515. Carbon and sulfur content shall be determined in accordance with ASTM E1019. The chemical composition of each lot shall conform to the compositions shown in table I.

4.6 Tensile testing. Tensile specimens shall be tested in accordance with ASTM E8/E8M and shall meet the requirements of table II (see 3.5).

4.7 Additional mechanical properties. Test methods and sampling requirements for additional mechanical testing shall be as specified (see 6.2).

4.8 Certificate of conformance. Unless otherwise specified (see 6.2), a certificate of conformance (COC) shall be provided for each lot of material offered for acceptance in accordance with the lot definition specified in 4.3. The COC shall include the following:

a. Statement that each lot has been sampled, tested, and inspected in accordance with the requirements specified herein.
b. For grade A material (see 1.2.1), record of approval from the Technical Authority (see 6.6.3) or authorized representative thereof that indicates the manufacturer is in compliance with S9074-A4-GIB-010/AM-WIRE DED.
c. For grade B material (see 1.2.1), statement specifying the manufacturer specification or industry standard(s) used to determine material compliance and a record of approval from the Technical Authority (see 6.6.3) or authorized representative thereof.
d. Record of the feedstock, including COC from manufacturer (see 3.1).
e. Record of the build platform, including thickness and COC from manufacturer (see 3.2).
f. Complete record of all heat treatments, including time, temperatures, atmosphere, and heating and cooling rates (see 3.4).
g. Measurement result for reduction of area (see 3.5).
h. Statement describing surface finishing method(s) used (see 3.7).
i. Statement certifying that detrimental material controls have been met (see 3.8).
j. Statement certifying that all material markings comply with the requirements of this specification (see 3.9).
k. Complete record of testing with measurement results (see table III) used to demonstrate compliance with this specification, including any failed tests.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the military service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful but is not mandatory.)

6.1 Intended use. Wire arc DED 316L and 316LSi AM material is intended for maritime applications that would otherwise incorporate materials such as Gr. CF3M and CF8M (ASTM A351/A351M, ASTM A743/A743M, and ASTM A744/A744M) and Gr. CF8M (MIL-C-24707/3). It is noted that specifications for castings often incorporate requirements that are out of scope for this material specification, including but not limited to surface roughness minimums or additional evaluation techniques (e.g., hydrostatic tests). This specification only purports to

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T07:48Z
Check the source to verify that this is the current version before use.

address material properties and no other product characteristics. This material is intended for use in applications with a maximum operating temperature of 600 °F where general corrosion or pitting may be a problem. This material is acceptable for use in welded applications.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.

b. Grade and class required (see 1.2).

c. Applicable part or identifying number (PIN) (see 1.3).

d. Wire feedstock requirements if other than specified (see 3.1).

e. Permissible material specification and grade for integrated build platform and any additional test requirements associated with its use (see 3.2).

f. When a cobalt maximum is required and what the maximum value is (see table I).

g. When heat treatment in accordance with MIL-STD-1684 is required (see 3.4).

h. Additional mechanical properties and corresponding acceptance criteria (see 3.6).

i. When surface finishing is not required or is other than specified (see 3.7 and 6.4).

j. When needed, additional detrimental material control requirements (see 3.8).

k. Requirements for resampling and retesting (see 4.4.3).

l. Acceptable chemical analysis methods that are different than those already specified (see 4.5).

m. Test specimen number, geometry, orientation, and test method requirements for additional mechanical testing (see 4.7).

n. When a certificate of conformance is not required (see 4.8).

o. Packaging requirements (see 5.1 and 6.5).

6.3 DED qualification. Grade B material requires the disclosure of a process qualification standard. Examples of appropriate commercial standards include SAE AMS7005, “Wire Fed Plasma Arc Directed Energy Deposition Additive Manufacturing Process,” and AWS D20.1/D20.1M, “Specification for Fabrication of Metal Components Using Additive Manufacturing.” These documents provide a framework to prove that the DED process is capable of producing material of consistent quality. Use of grade A material is recommended for critical applications.

6.4 Surface finish. Material produced using DED may have a rough surface finish associated with a reduction in corrosion resistance or fatigue life, or both. A rough surface finish may also reduce inspectability by restricting the use of NDT methods such as ultrasonic testing and dye penetrant testing, particularly when average roughness exceeds 250 microinch. Material is often post-processed via machining, grinding, electrical discharge machining, or polishing, to achieve desired surface finish. To ensure good performance, prescriptive surface finishing requirements should be incorporated into acquisition requirements, as specified (see 6.2).

6.5 Packaging marking. In addition to other packaging and labeling requirements required by the contract (see 6.2), each unit, intermediate, and exterior shipping container should be marked with the material specification number, manufacturer’s name or CAGE code, and manufacturing lot number. This marking should be placed on each MIL-STD-129, “Military Marking for Shipment and Storage,” label required by the contract and should be placed either below the identification test marking or in a conspicuous location on the identification marked side of the container.

6.6 Definitions.

6.6.1 DED build orientations. The Z orientation is parallel to the layer-by-layer build direction (i.e., perpendicular to the surface of the build platform if no reorientation has occurred). The X-axis is parallel to the weld axis, and the Y-axis is perpendicular to the weld axis and parallel to the layer plane.

6.6.2 Feedstock lots. Feedstock lots are defined in accordance with AWS A5.01M/A5.01, “Welding and Brazing Consumables – Procurement of Filler Metals and Fluxes.”

6.6.3 Technical authority. The Technical Authority has the authority, responsibility, and accountability to establish, monitor, and approve technical standards, tools, and processes in conformance to higher authority policy,

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T07:48Z
Check the source to verify that this is the current version before use.

requirements, architectures, and standards. NAVSEA 05T may be contacted to determine the appropriate Technical Authority for any given requirement related to equipment and systems of U.S. Navy ships and submarines.

6.7 Subject term (key word) listing.

316L
316LSi
3-D Printing
Casting Substitute
CF3M
CF8M
CRES
Metal Printing

CONCLUDING MATERIAL

Custodians:
Army – MR
Navy – SH

Preparing activity:
Navy – SH
(Project AMPR-2026-010)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using ASSIST at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T07:48Z
Check the source to verify that this is the current version before use.