MIL-T-13020C(EL)
20 May 1971
SUPERSEDING
MIL-T-13020B(EL)
9 March 1966

MILITARY SPECIFICATION

TAPE, RUBBER UNVULCANIZED, SPLICING AND MOLDING

(TAPES TL-317/U AND TL-318/U)

1. SCOPE

1.1 Scope. This specification covers two types of unvulcanized rubber tape, for use in splicing and molding joints in communication cables insulated and jacketed with rubber or rubber substitute.

1.2 Classification. Tapes shall be of the following types, as specified (see 6.1).

Type I - TL-317/U. Gray, used for restoring the interior electrical insulation of communication cables.
Type II - TL-318/U. Black, used for restoring the outside or jacket of communication cables.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

QQ-S-781 - Strapping, Steel, Flat and Seals.
PPP-B-566 - Boxes, Folding, Paperboard.
PPP-B-585 - Boxes, Wood, Wirebound.
PPP-B-601 - Boxes, Wood, Cleated-Plywood.
PPP-B-621 - Boxes, Wood, Nailed and Locked Corner.
PPP-B-636 - Box, Fiberboard.
PPP-B-676 - Boxes, Set-up.

MILITARY

MIL-P-116 - Preservation, Methods of.
MIL-B-43014 - Boxes, Water Resistant Paperboard, Folding, Set-up and Metal-Stayed.
MIL-C-45662 - Calibration System Requirements.

STANDARDS

FEDERAL

FED-STD-601 - Rubber: Sampling and Testing.

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-109 - Quality Assurance Terms and Definitions.
MIL-STD-129 - Marking for Shipment and Storage.
MIL-STD-147 - Palletized and Containerized Unit Loads 40" x 48" Pallets, Skids Runners, or Pallet-Type Base.
MIL-STD-202 - Test Methods for Electronic and Electrical Component Parts.

Source: https://assist.dla.mil -- Downloaded: 202610-17T23:58Z
Check the source to verify that this is the currentversion before use.

(Copies of specifications and standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal, shall apply.

American Society for Testing And Materials (ASTM)

D-15	-	Methods of Sample Preparation for Physical Testing of Rubber Products.
D-119	-	Specification for Rubber Insulating Tape.
D-295	-	Methods of Testing Varnished Cotton Fabrics and Varnished Cotton Fabric Tapes Used For Electrical Insulation.
D-297	-	Methods for Chemical Analysis of Rubber Products.
D-573	-	Methods of Test for Accelerated Aging of Vulcanized Rubber by the Oven Method.
D-746	-	Methods of Test for Brittleness Temperature of Plastics and Elastomers by Impact.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.)

Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.

3. REQUIREMENTS

3.1 Definitions. Terms and definitions specified herein shall be in accordance with MIL-STD-109.

3.2 Design. Tape shall be of the design and construction such as to enable it to meet the requirements specified herein.

3.2.1 Construction. Tape shall be manufactured from unvulcanized rubber compounds so compounded as to give a flat curing characteristic. The compound shall be well, evenly, and smoothly calendered, cut to widths specified, tightly wound in rolls and having a linen or glazed sheeting separator between the layers.

3.3 Material. The material shall be as specified herein. Acceptance or approval of any constituent material shall not be construed as a guaranty of the acceptance of the finished product.

3.3.1 Rubber compounds.

3.3.1.1 Type I. The rubber compound shall contain not less than 38 percent by weight, nor more than 70 percent by volume, of crude rubber to which may be added small amounts of curing agents, antioxidants, and waxy hydrocarbons. The remainder shall consist of inorganic mineral fillers.

3.3.1.1.1 Sulfur. Fifteen-minute cured material shall contain not more than 0.2 percent free elemental sulfur nor more than 1.25 percent total sulfur when tested in accordance with 4.6.2.

3.3.1.2 Type II. The rubber compound shall contain not less than 40 percent by weight, nor more than 70 percent by volume, of crude rubber to which may be added small amounts of curing agents, antioxidants, waxy hydrocarbons, and carbon black. The mainder shall consist of inorganic mineral fillers.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:58Z
Check the source to verify that this is the current version before use.

3.3.1.2.1 Sulfur. Fifteen-minute cured material shall contain not more than 0.75 percent free elemental sulfur nor more than 1.25 percent total sulfur when tested in accordance with 4.6.2.

3.4 Dimensions. When tested as specified in 4.6.3, the dimensions shall be as follows:

(a) Width - 1 ± 1/32 inch.
(b) Thickness - 0.031 ± 0.003 inch.
(c) Length - Each roll shall contain not less than 55 feet of tape.

3.5 Separator stripping. When tested as specified in 4.6.4, the separator shall strip readily from the tape in a continuous web without transference of residue to the tape.

3.6 Fusion. When tape is tested as specified in 4.6.5, it shall sustain the specified weight or shall break at the point of unwinding.

3.7 Tackiness. When tape is tested as specified in 4.6.6, it shall show no tendency to unwind from the mandrel.

3.8 Tensile strength and elongation. When tested as specified in 4.6.7, the tensile strength and elongation at rupture shall be not less than the following:

TENSILE STRENGTH

Before vulcanization	Pounds, per square inch
TL-317/U	125
TL-318/U	200
After vulcanization (15-minute cure)	
TL-317/U	1,200
TL-318/U	1,500

ELONGATION

Before vulcanization	Percent	Inches
TL-317/U	400	10
TL-318/U	300	8
After vulcanization (15-minute cure)		
TL-317/U	300	8
TL-318/U	300	8

3.9 Flat cure. When calculated as specified in 4.6.8, the change in elongation at rupture between 15-minute cured specimens and 30-minute cured specimens shall not be greater than 15 percent.

3.10 Accelerated aging. When tested as specified in 4.6.9, fifteen-minute cured specimens, accelerated aged as specified, shall not change in elongation at rupture by more than 20 percent for both types of tape.

3.11 Dielectric strength. When tested as specified in 4.6.10, the tape shall withstand a 60-hertz alternating current potential of not less than the following:

Before vulcanization	Volts (rms) per mil thickness
TL-317/U	350
TL-318/U	100
After vulcanization and cooling	
TL-317/U	350
TL-318/U	150

Source: https://assist.dla.mil -- Downloaded: 202610-17T23:58Z
Check the source to verify that this is the current version before use.

3.12 Brittleness temperature. When tested as specified in 4.6.11, the specimens shall not be brittle at -40° C.

3.13 Workmanship. Tape shall be processed in such a manner as to be uniform in quality and shall be free from any defects that will affect life, serviceability, and appearance.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Test equipment and inspection facilities. Test and measuring equipment and inspection facilities of sufficient accuracy, quality and quantity to permit performance of the required inspection shall be established and maintained by the supplier. The establishment and maintenance of a calibration system to control the accuracy of the measuring and test equipment shall be in accordance with MIL-C-45662.

4.2 Classification of inspections. The inspections specified herein are classified as follows:

(a) Materials inspection (see 4.3)
(b) Quality conformance inspection (see 4.5)

4.3 Materials inspection. Materials inspection shall consist of certification supported by verifying data that the materials listed in table I, used in fabricating the rubber tape, are in accordance with the applicable referenced specifications or requirements prior to such fabrication.

TABLE I. Materials inspection.

Material	Requirement paragraph	Applicable specification
Rubber compounds	3.3 1.1 and 3.3.1.2	---

4.4 Inspection conditions. Unless otherwise specified herein, all inspections shall be performed in accordance with the test conditions specified in the "GENERAL REQUIREMENTS" of MIL-STD-202.

4.5 Quality conformance inspection.

4.5.1 Inspection of product for delivery. Inspection of product for delivery shall consist of groups A and B inspections.

4.5.1.1 Inspection lot. An inspection lot shall consist of all the tape of the same type, produced under essentially the same conditions, and offered for inspection at one time.

4.5.1.2 Group A inspection. Group A inspection shall consist of the examinations and tests specified in table II, in the order shown.

4.5.1.2.1 Sampling plan. Statistical sampling and inspection shall be in accordance with MIL-STD-105 for general inspection level II. The acceptable quality level (AQL) shall be as specified in table II. Major and minor defects shall be as defined in MIL-STD-105.

4.5.1.2.2 Rejected lots. If an inspection lot is rejected, the supplier may rework it to correct the defects, or screen out the defective units, and resubmit for reinspection. Resubmitted lots shall be inspected using tightened inspection. Such lots shall be separate from new lots, and shall be clearly identified as reinspected lots.

Source: https://assist.dla.mil -- Downloaded: 202610-17T23:58Z
Check the source to verify that this is the current version before use.

TABLE II. Group A inspection.

Examination or test	Requirement paragraph	Test method paragraph	AQL (percent defective) Major	AQL (percent defective) Minor
Visual and mechanical examination	3.2, 3.2.1, 3.3, and 3.13	4.6.1		
Dimensional	3.4	4.6.3		
Separator stripping	3.5	4.6.4		
Fusion	3.6	4.6.5		
Tackiness	3.7	4.6.6		
Tensile strength:				
Unvulcanized	3.8	4.6.7.1	1.0	1.0
Vulcanized	3.8	4.6.7.2		
Elongation:				
Unvulcanized	3.8	4.6.7.1		
Vulcanized	3.8	4.6.7.2		
Flat cure	3.9	4.6.8		
Accelerated aging	3.10	4.6.9		

4.5.1.3 Group B inspection. Group B inspection shall consist of the examinations and tests specified in table III, in the order shown. Group B inspection shall be made on specimens selected from inspection lots which have passed the group A inspection.

TABLE III. Group B inspection.

Test	Requirement paragraph	Method paragraph
Sulfur:		
Free	3.3.1.1.1 and 3.3.1.2.1	4.6.2
Total	3.3.1.1.1 and 3.3.1.2.1	4.6.2
Dielectric strength:		
Unvulcanized	3.11	4.6.10.1
Vulcanized	3.11	4.6.10.2
Brittleness temperature	3.12	4.6.11

4.5.1.3.1 Sampling plan. Five specimens should be selected from each lot consisting of the same type, manufactured under essentially the same conditions.

4.5.1.3.2 Failures. If one or more specimens fail to pass group B inspection, the lot shall be considered to have failed.

4.5.1.3.3 Disposition of specimens. Specimens which have been subjected to group B inspection shall not be delivered on the contract or purchase order.

4.5.1.3.4 Noncompliance. If a specimen fails to pass group B inspection, the supplier shall take corrective action on the materials or processes, or both, as warranted, and on all lots of product which can be corrected and which were manufactured under essentially the same conditions, with essentially the same materials, processes, etc, and which are considered subject to the same failure. Acceptance of the product shall be discontinued until corrective action, acceptable to the Government, has been taken. After the corrective action has been taken, group B inspection shall be repeated on additional specimens (all inspection, or the inspection which the original sample failed, at the option of the Government). Group A inspection may be reinstituted; however, final acceptance shall be withheld until the group B reinspection has shown that the corrective action was successful. In the event of failure after reinspection, information concerning the failure and corrective action taken shall be furnished to the cognizant inspection activity and the qualifying activity

Source: https://assist.dla.mil -- Downloaded: 202610-17T23:58Z
Check the source to verify that this is the currentversion before use.

4.5.2 Inspection of preparation for delivery. Sample packages and packs and the inspection of the preservation and packaging, packing and marking for shipment and storage shall be in accordance with the requirements of section 5 and the documents specified therein.

4.6 Methods of examinations and tests.

4.6.1 Visual and mechanical examination (see 3.2, 3.2.1, 3.3, and 3.13). Tape shall be examined to verify that the materials, design, construction, physical dimensions, and workmanship are in accordance with the applicable requirements.

4.6.2 Sulfur (see 3.3.1.1.1 and 3.3.1.2.1). The sulfur analysis for free (elemental) sulfur and total sulfur shall be made in accordance with ASTM D-297. If greater sensitivity is required, the testing laboratory may use a 0.01 N iodine solution instead of the 0.05 to 0.1 N iodine solution indicated for free sulfur. The blue endpoint is the one wherein the color lasts for several seconds. Specimens shall be taken from the same vulcanized sheets which were used for tensile test specimens.

4.6.3 Dimensional test (see 3.4). Thickness and width of tapes shall be determined by using the methods outlined in FED-STD-601. Length shall be determined by using a standard steel rule or scale.

4.6.4 Separator stripping (see 3.5). A specimen of tape approximately 1 foot long shall be removed from the roll. One end of the specimen shall be pulled so that the separator cracks and parts from the tape. The cracked end of the separator shall be grasped and stripped from the tape.

4.6.5 Fusion (see 3.6) Three specimens from each sample roll of the tape shall be subjected to the fusions test set forth in ASTM D-119 except that a 2-pound weight shall be substituted for the 4-pound weight specified.

4.6.6 Tackiness (see 3.7). Three specimens from each sample roll of tape shall be subjected to the tackiness test set forth in ASTM D-119.

4.6.7 Tensile strength and elongation (see 3.8). Tensile strength and elongation tests on unvulcanized specimens shall be made in accordance with methods 13021 and 13031, respectively, of FED-STD-601, using die I, and a separation speed of 20 inches per minute. Calculate individual specimen values of tensile strength or elongation at rupture.

4.6.7.1 Unvulcanized specimens. Three specimens shall be die-cut from each sample roll.

4.6.7.2 Vulcanized specimens. Five specimens shall be die-cut from each of three vulcanized sheets.

4.6.7.3 Preparation of vulcanized (cured) specimens. Lengths of unvulcanized tape shall be cut from each roll and laid up or folded into 1-inch wide 3-ply strips. The strips are then placed parallel and adjacent to each other in a tensile specimen sheet mold, in accordance with ASTM D-15, which has been preheated to 149° ±2.8° C. Strips should be so laid out in advance to minimize the time consumed in loading the mold cavities. (For a 6-inch by 6-inch cavity, six each 3-ply strips 6-inches long by 1 inch wide are required.) Vulcanize at 149° ±2.8° C, using a minimum of 500 pounds-force per square inch (lb_f/in^2) pressure, based on total mold area, for a period of 15 or 30 (±1) minutes, as required. When not specified for any particular test on vulcanized samples, the cure time shall be 15 minutes. The molded sheets shall be allowed to cool and rest at room temperature for a minimum of 16 hours prior to the preparation of specimens. Unless otherwise indicated in the particular test, the specimens shall be cut parallel to the length and within the 1-inch width of the strips as prepared prior to molding.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:58Z
Check the source to verify that this is the current version before use.

4.6.8 Flat cure (see 3.9). The arithmetic mean values of elongation for 15-minute and 30-minute cured specimens shall be used. The cure characteristic shall be expressed as the percent difference in elongations calculated as follows:

$$\frac{\% \text{ elongation for 15-min cure} - \% \text{ elongation for 30-min cure}}{\% \text{ elongation for 15-min cure}} \times 100$$

4.6.9 Accelerated aging (see 3.10). Specimens shall be aged in a circulating-air oven in accordance with ASTM D-573 at a temperature of 70° C for a period of 118 ± 1/4 hours. Upon removal from the oven the specimens shall be allowed to cool and rest at room temperature for a minimum of 16 hours.

4.6.10 Dielectric strength (see 3.11).

4.6.10.1 Unvulcanized tape. The dielectric strength of unvulcanized tapes shall be determined at a temperature between 20°C and 28°C by placing specimens of tape approximately 6 inches in length between two flat electrodes 1/4-inch in width by 4-1/4 inches in length. The edges of the electrodes shall be square and the ends rounded to 1/8-inch radius thus giving an area of contact with the surface of the tape of exactly 1/4-inch in width by 4 inches in length. The electrode pressure shall be adjusted to an average value of 1 lb_f/in^2. Then a 60-Hz alternating current (ac) voltage, having an approximate sine-wave form and an initial value of less than 1,000 volts root mean square (rms), shall be applied to the electrodes. This voltage shall be increased at the rate of 1,000 volts rms per second until puncture occurs. In order to prevent flashover, increased widths may be effected by attaching to each side of the test specimen an added piece of tape making a 1/8-inch, carefully rolled down, lap seam. At least five specimens, one from each roll, shall be tested.

4.6.10.2 Vulcanized tapes. Dielectric strength test of vulcanized tapes shall be in accordance with ASTM D-295. Specimens shall be vulcanized for 15 minutes at a temperature of 149° ± 2.8° C.

4.6.11 Brittleness temperature (see 3.12). The brittleness temperature test shall be in accordance with procedure B of ASTM D-746.

5. PREPARATION FOR DELIVERY

5.1 Preservation and packaging. Preservation and packaging shall be level A or C, as specified (see 6.1).

5.1.1 Level A.

5.1.1.1 Cleaning. Rolls of tape shall be cleaned in accordance with MIL-P-116, process C-1.

5.1.1.2 Drying. Rolls of tape shall be dried in accordance with MIL-P-116.

5.1.1.3 Preservative application. None required.

5.1.1.4 Unit packaging. Rolls of tape shall be individually packaged in accordance with MIL-P-116, submethod IC-2 insuring compliance with the general requirements paragraph under methods of preservation (unit protection) and the physical protection requirements paragraph thereto.

5.1.1.5 Intermediate packaging. Unless otherwise specified (see 6.1), rolls of tape, packaged as described in 5.1.1.4, shall be placed in intermediate containers conforming to PPP-B-566, PPP-B-676 or MIL-B-43014. Containers conforming to PPP-B-566 or PPP-B-676 shall be overwrapped with waterproof barrier materials. Intermediate containers shall be uniform in size, shape and quantities shall be of minimum tare and cube and shall contain multiples of five unit packages, not to exceed 50 unit packages. No intermediate packaging is required when the quantity shipped to a single destination is less than 50 unit packages.

Source: https://assist.dla.mil -- Downloaded: 202640-17T23:58Z
Check the source to verify that this is the currentversion before use.

5.1.2 Level C. Cleaned and dried rolls of tape shall be individually packaged in a manner that will afford adequate protection against corrosion, deterioration and physical damage during shipment from supply source to the first receiving activity.

5.2 Packing. Packing shall be level A, B or C, as specified (see 6.1).

5.2.1 Level A. The packaged rolls of tape shall be packed in fiberboard containers conforming to PPP-B-636, class weather resistant, style optional, special requirements. Closure shall be in accordance with the appendix thereto. For unitized loads (see 5.2.4), banding (reinforcement requirements) shall be applied in accordance with the appendix of PPP-B-636 using nonmetallic or tape banding only. When quantities per destination are less than a unitized load, the fiberboard containers shall not be banded but shall be placed in a close fitting box conforming to PPP-B-601, overseas type; PPP-B-621, class 2, style 4 or PPP-B-585, class 3, style 2 or 3. Closure and strapping shall be in accordance with the applicable container specification except that metal strapping shall conform to QQ-S-781, type I, class A.

5.2.2 Level B. The packaged rolls of tape shall be packed in fiberboard containers conforming to PPP-B-636, class weather resistant, style optional, special requirements. Closures shall be in accordance with the appendix thereto. Banding (reinforcement requirements) shall be applied in accordance with the appendix of PPP-B-636 using nonmetallic or tape banding only.

5.2.3 Level C. The packaged rolls of tape shall be packed in shipping containers in a manner that will afford adequate protection against damage during direct shipment from the supply source to the first receiving activity. These packs shall conform to the applicable carrier rules and regulations.

5.2.4 Unitized loads. Unitized loads, commensurate with the level of packing specified in the contract or order, shall be used whenever total quantities for shipment to one destination equal 40 cubic feet or more. Quantities less than 40 cubic feet need not be unitized. Unitized loads shall be uniform in size and quantities to the greatest extent practicable.

5.2.4.1 Level A. Tapes, packed as specified in 5.2.1, shall be placed on pallets in conformance with MIL-STD-147, load type I, with a fiberboard cap (storage aid 4) positioned over the load.

5.2.4.2 Level B. Tapes, packed as specified in 5.2.2, shall be palletized as specified in 5.2.4.1.

5.2.4.3 Level C. Tapes, packed as specified in 5.2.3, shall be unitized with pallets and caps of the type, size and kind commonly used for the purpose and shall conform to the applicable carrier rules and regulations.

5.3 Marking. In addition to any special marking required by the contract or order, each unit package, intermediate and exterior container and unitized load shall be marked in accordance with MIL-STD-129.

5.4 General.

5.4.1 Exterior containers. Exterior containers (see 5.2.1, 5.2.2 and 5.2.3) shall be of a minimum tare and cube consistent with the protection required and shall contain equal quantities of identical stock numbered items to the greatest extent practicable.

6. NOTES

6.1 Ordering data. Purchasers should exercise any desired options offered herein, and procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Type of tape required. (See 1.2.)
(c) Selection of applicable levels of packaging and packing required. (See 5.1 and 5.2.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:58Z
Check the source to verify that this is the current version before use.

Custodians:
Army - EL

Review activities:
Army - EL, ME, WC, AT, AV

User activity:
Army - MI

Preparing activity:
Army - EL

Agent:
DSA - ES

(Project 5970-A366)

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:58Z
Check the source to verify that this is the current version before use.

To detach this form, cut along this line

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

MIL-T-13020C (EL) Tape, Rubber Unvulcanized, Splicing & Molding

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426

REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

ESC-FM 1068-68

Source: https://assist.dla.mil -- Downloaded: 20261O-17T23:58Z
Check the source to verify that this is the current version before use.

FOLD

Department of the Army
Headquarters
U.S.Army Electronics Command
Fort Monmouth, New Jersey 07703

POSTAGE AND FEES PAID

OFFICIAL BUSINESS

Commanding General
U.S.Army Electronics Command
ATTN: AMSEL- PP-ED
Fort Monmouth, New Jersey 07703

FOLD

To detach this form, cut along this line

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:58Z
Check the source to verify that this is the current version before use.