[INCH-POUND]
A-A-3100
March 5, 1997
SUPERSEDES
MIL-C-83957A
July 23, 1975

COMMERCIAL ITEM DESCRIPTION

CLEANING AND POLISHING PAD, NONMETALLIC (FOR AIRCRAFT)

The General Services Administration has authorized the use of this commercial item description by all Federal agencies.

1. SCOPE. This commercial item description (CID) covers nonwoven, nonmetallic, nonabrasive, polyester cleaning and polishing pads for use on aluminum aircraft surfaces.

2. CLASSIFICATION. The pads shall be of the two following types:

Type I - 3/8 inch thick
Type II - 1 inch thick

3. SALIENT CHARACTERISTICS

3.1 Material. The fiber of the pad shall be a crimped, cut filament, 100% polyester fiber meeting the requirements of table I. When testing is neccessary, the appropriate method cited by ASTM D 1117 shall be used.

Table I, Polyester fiber requirements

Characteristic	Type I	Type II
Denier	9.6 average, ±1	15 average, ±1
Staple length	1-1/2 inch (3.8 cm) min.	1-1/2 inch (3.8 cm) min.
Tenacity, grams/denier	2.7 - 4.5	4.0 - 5.0
% Elongation	30 - 70	30 - 70

3.2 Construction. The fibers shall be adhered together into a uniform sheet that is then cut into the specified size and thickness. The pad shall not contain any abrasive or hard particles. The finished pad shall have the tensile strength specified when tested in accordance with table II and 3.2.1.

Table II, Water and chemical resistance

Test Solution	Tensile Strength minimum, lbs/in (N/cm) Type I Machine dir.	Type I Across web dir.	Type II Machine dir.	Type II Across web dir.	Solution Temp. °F±5 (°C±2.7)	Time of Immersion (min.)
Water	24 (42)	24 (42)	14 (24)	21 (36)	150 (65)	10
5% NaOH	8 (14)	8 (14)	10 (17)	15 (26)	73 (22)	5
Mineral spirits (165°F BP)	24 (42)	24 (42)	16 (28)	24 (42)	73 (22)	5
MIL-C-87937 1/	20 (35)	20 (35)	16 (28)	24 (42)	73 (22)	10
MIL-C-38334	23 (40)	23 (40)	13 (22)	20 (35)	73 (22)	15
MIL-R-25134	15 (26)	15 (26)	2 (4)	3 (5)	73 (22)	15

1/ Mixture of 1 part MIL-C-87937 Cleaning compound alkaline water base and 3 parts water.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to: General Services Administration, Engineering Branch (7FXEE), 819 Taylor Street, Fort Worth, TX 76102

FSC 7920

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:29Z
Check the source to verify that this is the current version before use.

3.2.1 Tensile strength. Test samples shall be immersed in the test solution at the specified temperature for the specified time. Tensile strength shall be determined in accordance with the appropriate test cited by ASTM D 1117 for breaking force. The reported value for each characteristic shall be the average of three test samples per chemical and direction.

3.3 Size. Both types of the pads shall be 6 x 12 ±1/8 inches (15.2 x 30.4 ±0.3 cm). The thickness of the type I pads shall be 3/8 ±1/16 inch (9.5 ±1.5 mm), the thickness of the type II pads shall be 1 ±1/8 inch (25.4 ±3.2 mm).

3.4 Total weight. The type I pads shall be 21 grams minimum. The type II pads shall be 40 grams minimum.

3.5 Workmanship. The finished pads shall be uniform in size and weight, with squared edges and parallel sides. The pads shall have no wrinkles in the material, hard particles, torn edges, thin areas, or heavy areas.

3.6 Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch-pound units, providing they fall within tolerances specified and all other requirements of this document are met.

4. REGULATORY REQUIREMENTS

4.1 Regulatory requirements. The offeror/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

5. QUALITY ASSURANCE PROVISIONS

5.1 Product conformance. The products provided shall meet the salient characteristics of this CID, shall conform to the producer's own drawings, specifications, standards, and quality assurance practices, and shall be the same product offered for sale in the commercial market. The government reserves the right to require proof of such conformance.

6. PACKAGING, PACKING AND MARKING

6.1 Packaging, packing and marking. The packaging, packing, and marking shall be as specified in the contract or order.

7. NOTES

7.1 Ordering data. Purchases should select the preferred options permitted herein and include the following information in procurement documents:

a. Title, number, and date of this CID.
b. Type.
c. The packaging, packing and marking desired

7.2 Referenced documents.
ASTM D 1117 Standard Methods of Testing Nonwoven Fabrics

Copies of ASTM standards are available from ASTM, 100 Bar Harbor Dr., West Conshohocken, PA 19428-2959 (610-832-9500).

7.3 National Stock Numbers. The following NSNs are known to use this document:

7920-00-151-6120	Type I
7920-00-171-1534	Type II

Preparing Activity:
GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:29Z
Check the source to verify that this is the current version before use.