[METRIC]

A-A-3124
August 13, 1997

COMMERCIAL ITEM DESCRIPTION

BAG, COTTON DUCK (SOIL AND GRAIN)

The General Services Administration has authorized the use of this commercial item description in preference to Federal Specification PPP-B-1087, which is cancelled.

1. SCOPE. This description covers the requirements for a plain selvage top bag, made of cotton duck, designed without hem, grommets, or draw string, with a capacity of 35.2 liters (1 bushel).

2. SALIENT CHARACTERISTICS.

2.1. Materials.

2.1.1. Cloth, cotton duck. The cloth shall be hard textured, with a minimum weight of 378.4 gm/m^2 (11.16 oz/$yard^2$), with a minimum breaking point of 27 Newtons (195 lbs) in the warp direction, and a minimum of 16.6 Newtons (120 lbs) in the filling direction. The warp yarns shall be plied and the filling yarns shall be singles or plied (see 4.3).

2.1.2. Thread. The thread shall be 4-ply cotton glazed, with a minimum of 1,937 m/kg (2,880 ft/lb), and a maximum of 2,610 m/kg (3,880 ft/lb), with a minimum breaking strength of 1 Newton (7.5 lbs).

2.2. Dimensions. The dimensions of the bag shall be 43 ± 2.5 cm (17 ± 1") in width, and 81 ± 5cm (32 ± 2") in length.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document, should be sent to: General Services Administration, Federal Supply Service, 26 Federal Plaza, New York N.Y. 10278 ATTN: Engineering Branch (2FYEE).

FSC 8105

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:30Z
Check the source to verify that this is the current version before use.

2.3. Stitching. All stitching shall conform to types 301 and 401 of Fed.Std.No.751, four to six stitches per 2.5cm (1"). Thread breaks in stitching shall be overstitched not less than 2.5 cm (1") at each break for Type 301 stitching, or 3.8 cm (1-1/2") for Type 401 stitching. The ends of each continuous row of stitches may be anchored by backstitches for a length of not less than 2.5 cm (1"), except where anchorage is provided by another seam or stitching. Alternatively, a 1.9cm (3/4") bartack may be used instead of backstitches.

2.4. Construction. The bag shall be constructed of a single width of material folded in half, with one double row of stitches, not less than 1.3 cm (1/2") from the edge of the material, forming the side opposite the fold. Two rows of stitches across one open end not less than 1.3 cm (1/2") from the edge of the material, shall form the bottom of the bag. The thread tension shall be maintained to prevent loose stitching. All outside thread ends shall be trimmed.

2.5. Workmanship. The bags shall be free from defects which affect their serviceability.

3. REGULATORY REQUIREMENTS. The offeror/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

4. QUALITY ASSURANCE.

4.1. Product conformance. The product provided shall meet the salient characteristics of this commercial item description, conform to producer's own drawings, specifications, standards, and quality assurance practices and be the same product offered for sale in the commercial market. The Government reserves the right to require proof of such conformance.

4.2. Test methods. The following test shall be conducted for breaking strength of cloth used in the fabrication of the bags. Failure of the test shall be cause for rejection.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:30Z
Check the source to verify that this is the current version before use.

4.3. Breaking strength. Ten specimens per lot of woven cloth 10.2cm x 15.2cm (4"x6") with long dimension parallel to the direction being evaluated shall be tested as follows: Each specimen shall be placed in a machine which is equipped with a constant rate of extension straining mechanism. The distance between the clamps at the start of each test shall be 7.6 cm (3"), and the clamps shall travel at a uniform rate of 30.5 ± 1.3 cm (12 ± 0.5") per minute. The force required to break the specimen shall be read from the recording mechanism. The reading strength shall be the average of the results and reported to the nearest pound.

5. PACKAGING, PACKING AND MARKING. Packing, packing and marking shall be as specified in the contract or purchase order.

6. REFERENCED DOCUMENTS. The issue of the referenced documents in effect on the date of the solicitation for offers or request for proposals shall be used to determine conformance with the requirements of this Commercial Item Description.

6.1 Federal Regulations: Federal Acquisition Regulation. Paragraph 23.403. Copies of the U.S. Code may be obtained through the Congressional Sales Office, U.S. Government Printing Office, Washington, D.C. 20402.

6.2. Federal Standards And Test Methods: Federal Standards, Specifications and Commercial Item Descriptions, may be obtained from the General Services Administration Specifications Section (3FBO-W) in Suite 8100 at 490 L'Enfant Plaza, SW Washington D.C.20407. phone numbers(202) 708-9205, or FTS-458-9205.

7. NOTES.

7.1. Ordering data. Purchasers shall specify the following in the contract or purchase order:

7.1.1. Title, number and date of this description.
7.1.2. Packaging, packing and marking required.

7.2. List of NSNs: 8105-00-597-4757

MILITARY INTERESTS:

No official DOD interest in this Commercial Item Description has been registered.

PREPARING ACTIVITY:

GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:30Z
Check the source to verify that this is the current version before use.