FED. SUP CLASS
6640

PART NUMBER	SIZE ± 5mm	CLASS	PART NUMBER	SIZE ± 5mm	CLASS	PART NUMBER	SIZE ± 5mm	CLASS
MS36508-1	76x127	1	MS36508-16	178x279	2	MS36508-31	108x127	4
MS36508-2	76x178	1	MS36508-17	191x279	2	MS36508-32	127x146	4
MS36508-3	102x152	1	MS36508-18	508x762	2	MS36508-33	127x171	4
MS36508-4	108x127	1	MS36508-19	76x127	3	MS36508-34	178x279	4
MS36508-5	127x146	1	MS36508-20	76x178	3	MS36508-35	191x279	4
MS36508-6	127x171	1	MS36508-21	102x152	3	MS36508-36	508x762	4
MS36508-7	178x279	1	MS36508-22	108x127	3	MS36508-37	76x127	5
MS36508-8	191x279	1	MS36508-23	127x146	3	MS36508-38	76x178	5
MS36508-9	508x762	1	MS36508-24	127x171	3	MS36508-39	102x152	5
MS36508-10	76x127	2	MS36508-25	176x279	3	MS36508-40	108x127	5
MS36508-11	76x178	2	MS36508-26	191x279	3	MS36508-41	127x146	5
MS36508-12	102x152	2	MS36508-27	508x762	3	MS36508-42	127x171	5
MS36508-13	108x127	2	MS36508-28	76x127	4	MS36508-43	178x279	5
MS36508-14	127x146	2	MS36508-29	76x178	4	MS36508-44	191x279	5
MS36508-15	127x171	2	MS36508-30	102x152	4	MS36508-45	508x762	5
						MS36508-46	*	6

*As specified at invitations for bid.

MATERIAL AND CLASSES: Class 1 - Lightweight and Class 4 - Heavyweight, wet-strength paper shall be made from bleached chemical wood pulp, cotton or linen fibers or mixtures of these, and shall not contain any unbleached or mechanical wood pulp.

Class 2 - Heavyweight, wet-strength paper shall be made from 100 percent cotton or linen fibers.

Class 3 paper shall be made from 100 percent [illegible] made from 1.5 denier or cellulose derivative fiber.

Classes 4, 5, and 6 paper shall be either white or unbleached [illegible].

COLOR: Classes 1, 2, and 4 paper shall be white, Class 3 paper shall be white or of natural unbleached pulp.

DESIGN: [illegible] be furnished in individual sheets or book form. If furnished in book form, the sheets shall be securely [illegible] together along one edge and perforated in such manner that [illegible] be easily and cleanly torn from the book.

INTENDED USE: Classes 1, 2, and 3 lens paper are used for wrapping and dry cleaning applications of lenses and other glass and highly polished surfaces; Classes 4 and 5, for wet cleaning. Class 6 lens paper is used for wrapping or covering of all coated optics.

NOTES:
1. Items differing from this Military Standard by minor variations in design or dimensions are considered Standard under this document, provided such variations do not affect performance and are not in conflict with the material requirements specified herein.
2. For design feature purposes, this standard takes precedence over procurement document referenced herein.
3. Referenced documents shall be of the issue in effect on date of invitation for bid.

(A) CANCELLATION

CANCELLED
CANCELLED AFTER 29 AUG 1990
NO SUPERSEDING STANDARD

REVISED (A) 29 AUG 1990
SUPERSEDES

P.A.	EA	INTERNATIONAL INTEREST	TITLE	MILITARY STANDARD
Other Cust	MS 99		PAPER, LENS	MS36508
Procurement Specifications: NNN-P-40		SUPERSEDES:		SHEET 1 OF 1

DD FORM 672 (COORDINATED) PREVIOUS EDITIONS OF THIS FORM ARE OBSOLETE. Project Number 8040-1838-11

CANCELLATION

AMSC N/A
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

This military standard is approved for use by all Departments and Agencies of the Department of Defense. Selection for all new engineering and design applications and for repetitive use shall be made from this document.

REVIEWER ACTIVITIES: ARMY - ME, NAVY - OS, AIR FORCE - 03

USER ACTIVITIES: ARMY - MD, DM, NAVY - MS

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T17:42Z
Check the source to verify that this is the current version before use.