INCH-POUND

A-A-50057C
21 April 2017
SUPERSEDING
A-A-50057B
23 August 1991

COMMERCIAL ITEM DESCRIPTION

ROPE, FIBROUS, TENT-LAY

The General Services Administration has authorized the use of this Commercial Item Description in preference to MIL-R-1670.

1. ABSTRACT

1.1 Abstract. This commercial item description (CID) covers rope intended for use in the fabrication of tent lines.

1.2 Classification. The rope shall be in the following sizes as specified (see 5.1).

Diameter, inch (approx.)	Circumference, inches Min	Max	Breaking strength, pounds (min)	Length per pound, feet (min)
.187	.562	.687	220	70.0
.250	.625	.875	400	50.0
.312	.875	1.125	630	34.5
.375	1.000	1.250	850	24.4
.500	1.375	1.625	1400	13.3
.625	1.812	2.187	2300	7.4
.750	2.062	2.437	3000	6.1
1.000	2.750	3.250	8100	3.7
1.250	3.500	4.000	12150	2.4

Comments, suggestions, or questions on this document should be addressed to DLA Troop Support – Industrial Hardware Division (ATTN: Code FHTE), 700 Robbins Avenue, Philadelphia, PA 19111-5096 or email trpsptspecspa@dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil .

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:38Z
Check the source to verify that this is the current version before use.

2. SALIENT CHARACTERISTICS

2.1 General description. The rope shall be of either a three or a four strand construction and shall be fabricated from musa textilis fiber, sisal, jute, or cotton fiber. The rope shall be furnished with either a natural finish or with a mildew resistance treatment conforming to the requirements specified in T-T-616 (see 5.1). No material shall be added for the purpose of weighting the rope. The percentage extractable matter by weight shall not exceed 25 percent. The maximum allowable water absorption by weight for juke and cotton rope shall be 25 and 35 percent respectively.

3. QUALITY ASSURANCE.

3.1 Certification. The contractor shall certify, and maintain substantiating evidence, that the product offered meets the salient characteristics and requirements of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first and thereafter as may be otherwise provided for under the provisions of the contract

3.2 Regulatory requirements. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580 to the maximum extent practicable.

4. PACKAGING

4.1 Put-up. The rope shall be furnished in coils or on tubes. No piece of rope shall be less than 100 feet. The minimum length shall be 3500 feet for .187 (3/16) inch (diameter) rope, 2200 feet for .250 (1/4) inch rope, 1400 feet for

4.2 Packing.

4.2.1 Packing for coils or tubes weighing under 100 pounds. Each coil or tube of rope shall be packed in a fiberboard container conforming to RSC-L, grade V13c of ASTM-D1974/ D1974M or ASTM-D5118/ D5118M. The container shall be closed by method V as specified in the appendix of ASTM-D1974/ D1974M or ASTM-D5118/ D5118M.

4.2.2 Packing for coils or tubes weighing over 100 pounds . Each coil or tube of rope shall be packed in a cleated plywood container conforming to overseas type, style A or I, type II load of ASTM-D6251/D6251M. The container shall be closed in accordance with ASTM-D6251/D6251M.

4.3 Palletization. When specified, rope packed as specified in 4.2.1 or 4.2.2, shall be palletized on a 4-y entry pallet in accordance with load type 1a of MIL-STD-147. Pallet types shall be type I (4-y entry), type IV, or type V fabricated from wood groups I, II, III, or IV of ASTM-D6199. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means C and D or film bonding meant F or G.

4.4 Marking. In addition to any special marking required by the contract or purchase order, chipping containers and palletized unit loads shall be marked in accordance with MIL-STD-129.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:38Z
Check the source to verify that this is the current version before use.

5. NOTES

5.1 Acquisition requirements. Acquisition documents must specify the following:

a. Title , number, and date of this document.
b. Size required (see 1.1).
c. Whether a natural finish or mildew resistant treatment is required (see 2.1)
d. When palletization is required (see 4.3).

5.2 Source for Government documents. Copies of this CID or Military and Federal documents are available online at: ASSIST Online (https://assist.dla.mil) or ASSIST Quick Search (http://quicksearch.dla.mil).

5.3 Changes from previous issues. Marginal notations are used in this revision to identify changes with respect to the previous issue.

MILITARY ACTIVITIES:

Custodians:
Army – GL
Air Force – 71

Preparing activity:
DLA - IS

(Project 4020-2014-011)

Reviewer:
Army – CR, MD

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:38Z
Check the source to verify that this is the current version before use.