A-A-50063A
July 31, 1987
SUPERSEDING
A-A-50063
September 27, 1983

COMMERCIAL ITEM DESCRIPTION

BOOTS, KNEE AND HIP (RUBBER)

The General Services Administration has authorized the use of this commercial item description in preference to Federal Specification ZZ-B-530.

1. CLASSIFICATION

1.1. Classification. This commercial item description covers rubber boots in whole sizes 5 through 15 in the following types:

Type I - Knee length
Type II - Hip length

2. SALIENT CHARACTERISTICS.

2.1 Description. The boots shall be heavy duty vulcanized rubber boots made over the manufacturer's regular boot lasts using rubber and rubber/cotton cloth parts in accordance with the manufacturer's standard practice. Type II boots shall contain an adjustable top strap and knee patch.

2.2 Dimensions. For type I boots, the height (inside) at the back and front shall be not less than 14-1/2 inches. For type II boots, the extreme height (inside) shall be not less than 34 inches and the crotch height (inside) shall be not less than 29 inches. The girth measured around the inside of the boot at the crotch shall be not less than 23 inches. The circumference at the calf of the boot last shall be not less than 16 inches for sizes 5, 6, and 7; 16-1/2 inches for sizes 8 and 9; 17 inches for sizes 10 and 11; and 18 inches for sizes 12 through 15.

2.3 Rubber/cotton parts. The cotton cloth shall be either woven or knitted and shall be frictioned, calendar coated, or spread and calendar coated with rubber compound as necessary to prepare the parts such as leg linings, toe linings, vamp forms, and reinforcement strips necessary to build a boot.

2.4 Rubber parts. The rubber parts shall be made from upper compound or outsole and heel compound. The leg cover rubber shall be calendared from upper compound and shall be a minimum of 0.025 inch thick. Other gum rubber upper parts such as vamp, counter, and reinforcement strips shall be of appropriate thickness for the intended use. The outsole shall be cleated or heavily knurled and shall be a minimum of 0.285 inch at the ball. The heel shall be a minimum of 9/16 inch at the thinnest part and shall carry the manufacturer's standard tread design. The rubber parts shall conform to the following requirements:

FSC 8430

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:38Z
Check the source to verify that this is the current version before use.

Compound	Characteristics	Requirement	Test method (ASTM)
Upper compound	Tensile strength:		
	- initial	1000 p.s.i. (min.)	D 412
	- after aging (7 days at 158°F)	At least 75 percent of original tensile strength	D 573 and D 412
	Elongation:		
	- initial	375 percent (min.)	D 412
	- after aging (7 days at 158°F)	At least 75 percent of original elongation	D 573 and D 412
	Ozone resistance (bent loop - 3 days - 50 pphm at 104°F)	No cracks visible to the unaided eye	D 518 Procedure B D 1149
Outsole and heel compound	Abrasive index (before and after aging - 7 days at 158°F)	35	D 1630
	Hardness (before and after aging)	60 ± 10	D 2240

2.5 Top strap assembly (type II). The strap shall be either a double cotton cloth frictioned on both sides and coated with upper compound or a rubber strap not less than 0.090 inch thick. The strap shall be not less than 9-1/2 inches long and 5/8 inch wide. The loop at the top of the strap shall be large enough to permit easy passage and secure holding over a 2-inch belt. The strap buckle shall be made of brass, aluminum, or steel, and shall be of the slide type suitable for the intended purpose. Brass buckles shall be nickel plated; aluminum buckles shall be anodized with a coat of black enamel; and steel buckles shall be either nickel plated or have baked enamel finish. The strap slot shall be not less than 5/8 inch wide and the stay slot shall be not less than 7/16 inch wide.

2.6 Knee patch (type II). The boot upper shall have a knee patch not less than 60 square inches and placed to prevent chafing.

2.7 Color and finish. The boots should be black in color, although other colors are acceptable, and have a natural heater or dull lacquer finish.

2.8 Vulcanization. The boots shall be vulcanized under pressure to insure a watertight compact unit.

2.9 Leakage. The boots shall show no evidence of leakage when subjected to compressed air at 1 pound per square inch pressure while immersed in a tank of water to within 3 inches of the top of the boot.

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:38Z
Check the source to verify that this is the current version before use.

2.10 Marking. The manufacturer's name or trademark shall be embossed on the outsole in the shank or a manufacturer's label shall be used. The size shall be legibly incised on the outsole in the shank, or the size may be incised on a label and the label permanently vulcanized to the boot.

3. QUALITY ASSURANCE

3.1 Certification. The contractor shall certify that the product offered meets the salient characteristics of the description and conforms to the producers' own drawings, specifications, standards, and quality assurance practices, and is the same as the product offered for sale in the commercial marketplace. When specific quality assurance provisions are specified for any commercial characteristic the contractor shall furnish data resulting from inspection conducted in accordance with the specific quality assurance provisions. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

4. PACKAGING

4.1 Packaging. Each mated pair of boots of one type only, shall be secured together with cotton tape or twine to prevent separation.

4.2 Packing. Seven pairs of type I, or six pairs of type II boots of one size only, shall be packed in a fiberboard shipping container conforming to style RSC-L, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each fiberboard container shall be fitted with a box liner conforming to type CF class domestic variety DW, grade 275 of PPP-B-636. Prior to placing each pair of hip boots in the container, the tops shall be folded over so that the packing can be accomplished as specified. The boots shall be packed within a shipping container so that the first pair of boots has the sole of one boot against one end panel and the side of the sole of the second boot resting on the ankle of the first boot. The remaining pairs of boots shall then be placed in the container in the same manner with every other pair reversed. Inside dimensions of each container shall approximate 23-1/2 inches in length, 15 inches in width, and 15 inches in depth. Approximate dimensions are furnished as a guide only. A sheet of 30 pound minimum basis weight kraft paper conforming to A-A-203 shall be used to completely separate each pair of boots from the others. Each container shall be closed in accordance with method II as specified in the appendix of PPP-B-636.

4.3 Palletization. When specified (see 5.2), boots, packed as specified in 4.2, shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallet type shall be type I (4-way entry), type IV, or type V in accordance with MIL-STD-147. Pallets shall be fabricated from wood groups I, II, III, or IV of MIL-STD-731. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L or film bonding means O or P. Pallet pattern shall be number 3 in accordance with the appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:38Z
Check the source to verify that this is the current version before use.

4.4 Marking. In addition to any special marking required by the contract or purchase order, shipping containers and palletized unit loads shall be marked in accordance with MIL-STD-129.

5. NOTES

5.1 Intended use. The boots are intended for use as water-resistant boots.

5.2 Ordering data.

a. Title, number, and date of this document.
b. Type and size of boots required (see 1.1).
c. When palletization is required (see 4.3).

5.3 Sources for nongovernment documents.

ASTM D 412	Standard Test Methods for Rubber Properties in Tension
ASTM D 573	Test Method for Rubber - Deterioration in an Air Oven
ASTM D 518	Test Methods for Rubber Deterioration - Surface Cracking
ASTM D 1149	Test Method for Rubber Deterioration - Surface Ozone Cracking in a Chamber (Flat Specimens)
ASTM D 1630	Test Method for Rubber Property - Abrasion Resistance (NBS abrader)
ASTM D 2240	Test Method for Rubber Property - Durometer Hardness

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

MILITARY INTERESTS:

Custodians

Army - GL
Navy - NU
Air Force - 99

Review Activities

Army - MD
Air Force - 11, 82
DLA - CT

User Activities

Navy - CG, MC, YD
Air Force - 45

CIVIL AGENCY COORDINATING ACTIVITY:

GSA - FSS

PREPARING ACTIVITY:

Army - GL

Project No. 8430-0359

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:38Z
Check the source to verify that this is the current version before use.