(INCH-POUND)

A-A-148B
February 4, 1991
SUPERSEDING
A-A-148A
September 25, 1979

COMMERCIAL ITEM DESCRIPTION

BAG, PLASTIC (SANDWICH)

The General Services Administration has authorized the use of this commercial item description in preference to Federal Specification PPP-B-28 which is cancelled.

This description covers sandwich bags used for protection of sandwiches and various foods.

1. SALIENT CHARACTERISTICS:

A. Physical Properties. Bags furnished under this description shall be made from transparent, flexible, plastic film which has a Water Vapor Transmission Rate (WVTR) of not more than 31 g / m^2 * d @ 100 ± 5°F & 90 ± 5 percent RH, when tested in accordance with ASTM E 96 or ASTM F 1249. Bags shall pass the Strength test (see paragraph 2C).

B. Construction. Closure shall be of the manufacturer's normal commercial flap, fold, or tuck type. Bags shall have a face width of 6-1/2 ± 1/4 inches and a height of 5-1/2 ± 1/4 inches, exclusive of gussets, tucks, folds, or flaps. A bottom gusset is optional.

C. Workmanship. The bags shall be free of any imperfections or foreign matter that may affect their appearance or serviceability. Bag surfaces shall not adhere to each other during normal storage conditions.

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

FSC 8105

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:05Z
Check the source to verify that this is the current version before use.

3. QUALITY ASSURANCE:

A. Responsibility for Inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the government. The government reserves the right to perform inspections set forth in the commercial item description where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

B. Sampling. Samples shall be selected for inspection in accordance with MIL-STD-105, using the plans described in Table I. For water vapor transmission rate, (WVTR), samples shall be selected from lots of plastic film, not to exceed 5,000,000 square feet per lot, which are traceable directly to specific lots of bags.

TABLE I

Inspection or test	AQL (percent) defective)	Inspection Level	Sample Unit	See Paragraph
WVTR	2.5	S-1	1 square foot of film	1A
Strength	2.5	S-1	1 bag	1A
Construction	2.5	S-2	1 bag	1B
Workmanship	2.5	S-2	1 bag	1C
Packaging, packing, and marking	4.0	S-2	1 fully prepared shipping container	4

C. Strength test. Freshly formed seams shall be permitted to cool at normal room temperature not less than 1 hour before cutting the test strip. From each bag selected for the test, cut a 1 ± 1/16 inch wide strip perpendicular to the seams. A seam shall be located at each end of the strip. Open the strip to form a loop with the seams in the middle of the loop. Support one end of the loop in such a manner that the rest of the loop hangs free. Carefully and without impact loading, clamp a weight of not less than 1.5 pounds to the bottom of the loop. Allow the weight to hang, supported only by the strip, for not less than 5 minutes. If the strip breaks or the seams separate, the bag fails the test.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:05Z
Check the source to verify that this is the current version before use.

3. REGULATORY REQUIREMENTS:

A. Conformance to the Federal Food, Drug, and Cosmetic Act. The materials used in the sandwich bags shall conform to the Federal Food, Drug, and Cosmetic Act and regulations promulgated thereunder.

B. Use of Recovered Materials. The offeror/contractor is encouraged to use recovered materials in accordance with Public Law 94-580, as amended, to the maximum extent practicable.

4. PACKAGING, PACKING, AND MARKING:

Packaging, packing, and marking shall be as specified in the contract or order.

5. REFERENCED DOCUMENTS:

The issue of the referenced documents in effect on the date of the solicitation for offers or request for proposals shall be used to determine conformance with the requirements of this Commercial Item Description.

A. Public Law

Public Law 94-580 - Resource Conservation and Recovery Act,
(Part of U.S. Code, Title 42)

Available from:

Congressional Sales Office
U.S. Government Printing Office
Washington, DC 20402

B. Federal Regulations

21 CFR 121 - Federal Food, Drug, and Cosmetic Act and Regulations Promulgated Thereunder

Available from:

Superintendent of Documents
U.S Government Printing Office
Washington, DC 20402

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:05Z
Check the source to verify that this is the current version before use.

3. Military Standard

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

Available from:

Standardization Documents Order Desk
Building 4D
700 Robbins Avenue
Philadelphia, PA 19111-5094

C. Other References

ASTM E 96 - Standard Test Methods for Water Vapor Transmission of Materials.

ASTM F 1249 - Standard Test Method for Water Vapor Transmission Rate Through Plastic Film and Sheeting Using a Modulated Infrared Sensor.

Available from:

ASTM
1916 Race Street,
Philadelphia, PA 19103

6. NOTES:

Purchasers shall specify packaging, packing, and marking required.

MILITARY INTERESTS:

Review Activity

Army - SM

PREPARING ACTIVITY:

GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:05Z
Check the source to verify that this is the current version before use.