[METRIC]

A-A-206A
February 16, 1994
SUPERSEDING
A-A-206
January 8, 1981

COMMERCIAL ITEM DESCRIPTION

INK, DUPLICATING MACHINE STENCIL, PASTE, BLACK

The General Services Administration has authorized the use of this Commercial Item Description, for all Federal agencies.

Scope. The description covers the requirements for one type and two compositions of paste ink for use with stencil-process duplicating machines.

Classification: The stencil ink covered by this Commercial Item Descriptions is to be formulated for use on hard-sized and mimeograph papers. The paste stencil ink shall be of the water-in-oil or oil-in-water emulsion type and of the following compositions.

Composition A - For use on single-cylinder (drum-type), internally inked machines.
Composition B - for use on dual-cylinder externally inked machines.

1. SALIENT CHARACTERISTICS:

A- The ink shall not contain oil soluble dyes or toners. It shall be free from caking, skinning, lumps or coarse particles, separated materials, and any materials that would tend to dry on the cylinder rollers, in the cylinder drum, or on the ink pad or tend to close or obstruct the openings in applicable style cylinders.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document, should be sent to: General Services Administration, Federal Supply Service, 26 Federal Plaza, New York, NY 10278 ATTN: Engineering Branch (2FYEE).

Distribution Statement A:
Approved for public release;
distribution is unlimited.

FSC 7510

Source: https://assist.dla.mil -- Downloaded: 202640-26T08:05Z
Check the source to verify that this is the current version before use.

B- The consistency of composition A ink shall be 1200 to 1400 Saybolt Furol seconds at 38.7°C (100°F).

C- The ink shall not cause deterioration of the coating or base tissue of the stencil sheet and shall produce acceptable reproduction on both sides of the mimeograph paper.

D- When run with 18.1kg (40)-pound chemical-wood mimeograph paper the ink shall produce clean and clear, black-image duplicated copies without strike-through or set off sufficient to interfere with the legibility of the finished work on either side of the mimeograph paper.

E- The ink shall not show an oily halo around character outlines when mimeographed on the 18.1kg (40)-pound chemical-wood mimeograph paper.

F- When the printed copies are stacked, there shall be no objectionable transfer of ink from one sheet to the next.

G- The ink shall not run or drip off cylinders or drums, shall not leak, and shall not clog the stencil carrier, ink distributor, and other components of the machine, as applicable.

H- Color of ink copies shall be uniformly black and clearly legible.

I-.Odor. The ink shall at no time during a duplicating operation have or develop an objectionable odor.

J-. Shelf Life. The ink in original unopened containers (tubes) and not subjected to extremes of temperature and humidity, shall retain its utility and serviceability as defined by this description for not less than 12 months from the date of receipt to the Government.

K- (Usage instructions composition B only). Comprehensive instructions for fitting the tube to the ink pump shall be provided by the manufacturer, and shall be enclosed with each tube of ink, or may be printed on the tube.

2. APPLICABLE DOCUMENTS AND DOCUMENT SOURCES: The following document's form a part of this Commercial Item Description to the extent specified herein. Unless otherwise indicated, the issue in effect on the date of invitation for bids or request for proposal shall apply:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:05Z
Check the source to verify that this is the current version before use.

Military Standards

MIL-Std.-105 Sampling Procedures and Tables for Inspection by Attribution

Available from: Standarization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philladelphia, Pa 19111-5094

Federal Standards:

Fed. Std. No. 191- (5660) Colorfastness to Light of Textile Materials

(Single copies of this Commercial Item Description, or other Commercial Item Descriptions required by activities outside the Federal Government for bidding purposes are available without charge from General Services Administration Business Service Centers in Boston; New York,; Philadelphia; Washington, D.C.; Atlanta; Chicago; Kansas City, MO; Fort Worth; Houston; Denver; Los Angeles; San Francisco; and Auburn, WA.)

ASTM Standards:

ASTM D 891- Standard Test Measure for Specific Gravity

(ASTM Standards are available from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

3. QUALITY ASSURANCE:

A. Responsibility for Inspection: Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all the inspection requirements in this CID. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the Commercial Item Description, where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements (See Section 5, Ordering Data).

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:05Z
Check the source to verify that this is the current version before use.

B. Contracting Certification. The contracting shall certify and maintain substantiating evidence that the product offered meet the salient characteristics of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications standards, and quality assurance practices.

C. Sampling: All sampling shall be in accordance with MIL-STD-105.

(1) Sampling for Visual Inspection. A random sampling of Ink shall be taken from each lot. The inspection level shall be S-4 with an Acceptable Quality Level (AQL) of 4.0 percent defective. The sample unit shall be one pound of ink.

(2) Sampling for tests. A random sample of ink shall be taken from each lot. The inspection level shall be S-1 with an AQL of 4.0 percent defective. The sample unit shall be one pound of ink.

D. Inspections.

(1) Visual Examination. Samples taken in accordance with paragraph 3.C.1. shall be examined to verify that the superficial product requirements are in compliance with Section 1.

(2) Tests. Samples taken in accordance with paragraph 3.C.2. shall be subjected to the following tests to demonstrate consistency in product functionality, durability, and performance expectations.

A- Specific Gravity. Composition A ink shall be not greater than 1.060 at 25°C. Composition B ink shall be no greater than 1.100 at 25°C. The specific gravity of the ink shall be determined with a pycnometer bottle at 25°C, in accordance with test method ASTM D 891.

B- Fading. Ink impressions shall remain uniformly black with negligible loss in color value upon completion of the fading test shall be taken from the first 100 copies from the typical run of stencil on the mimeograph machine. The specimen shall be exposed for a period of 48 hours to the radiation from a glass-enclosed carbon-arc such as the fading apparatus described in method No.5660 of Fed Test Method Std. No. 191.

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:05Z
Check the source to verify that this is the current version before use.

4. **PREPARATION FOR DELIVERY.**

Packaging and Packing Provisions. As specified in contract or order.

5. **ORDERING DATA:** Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(1) Title, number, and date of this Commercial Item Description.

(2) Packaging, packing, and marking.

MILITARY INTEREST:		PREPARING ACTIVITY:
NONE:	DoD has no registered interest in revisions and amendments to this Commercial Item Description until further notice.	GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:05Z
Check the source to verify that this is the current version before use.