A-A-54350
8 March 1991

COMMERCIAL ITEM DESCRIPTION

BOLT, TIBIAL

The General Services Administration has authorized the use of this Commercial Item Description as a replacement for Military Specification MIL-T-36772 which is cancelled.

This Commercial Item Description covers a tibial bolt used in orthopedic surgery for repair of fractures of the tibia.

Salient characteristics:

General. The tibial bolt shall be suitable for orthopedic surgery involving fractures of the human tibia.

Material. The tibial bolt shall be fabricated from cold drawn bar or wire conforming to the composition specified in ASTM F138 for Grade 2.

Grain size and microcleanliness of the material shall be in accordance with ASTM F138.

Hardness. The Rockwell hardness of all components of the bolt shall be C30 to C35 when tested in accordance with ASTM E18 or E92 whichever is applicable. Conversion of hardness values shall be in accordance with ASTM E140.

Style, design and dimensions. The tibial bolt shall be furnished with two mating nuts and two mating washers. The bolt proper shall be of one piece construction. As an alternate, the head of the bolt shall be heliarc welded to the thread member; swaging or other cold working operations shall not be acceptable. The bolt head shall possess a slot, and the distal end of the bolt shall possess a sharp point. The threads of the bolt shall be in accordance with American National Standards Institute (ANSI) Standard B1.1 for 3-48 UNC-2A (Unified Screw Thread System of Dimensions).

AMSC N/A FSC 6515

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

The threaded portion of the bolt shall extend to and approximate the head of the screw. As an alternate, a shoulder of the same diameter of the bolt shall extend to the head of the screw. The external threads of the bolt shall allow the "GO" thread ring gages to pass over their full length and turn freely and shall not allow passage of the "LO" and "NOT GO" thread ring gages.

The following dimensional notations shall be inscribed on the ring gages:

THREAD SIZE	3-48 UNC-2A
"GO" PITCH DIAMETER:	0.0848
"LO" PITCH DIAMETER:	0.0825
"GO" MAJOR DIAMETER:	0.0983
"NOT GO" MAJOR DIAMETER:	0.0938

Internal threads of the nuts shall allow the "GO" thread plug gages to be inserted and turned freely, and shall not allow entry of the "HI" and "NOT GO" thread plug gages.

The following dimensional notations shall be inscribed on the plug gages:

THREAD SIZE	3-48 UNC-2A
"GO" PITCH DIAMETER:	0.0855
"LO" PITCH DIAMETER:	0.0885
"GO" MINOR DIAMETER:	0.0764
"NOT GO" MINOR DIAMETER:	0.0845

The gaging procedure to be used for internal and external thread, dimensions, tolerances and gage identifications shall be in accordance with ANSI Standard B1.2. Fits of gages onto the bolt threads shall be noted.

Tibial bolt shall be in accordance with Defense Personnel Support Center (DPSC) Drawing No. 10130.

Finish. The washers, nuts and heads of the bolt shall have a mirror finish. The bolt proper (excluding washers and nuts) shall not be electropolished. Definitions of acceptable surface characteristics shall be as described in ASTM F86.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

Passivation. All components of the tibial bolt shall be properly passivated after completion of all finishing operations. Passivation shall be accomplished by methods described in ASTM F86.

Resistance to Corrosion. The tibial bolt shall not show evidence of corrosion when tested in accordance with ASTM F1089. As an alternate, the following saline test may be used: Scrub the tibial bolt with soap and warm water and rinse in hot water followed by immersion into ethyl alcohol (95%) and then dry. The tibal bolt shall be completely immersed into Normal Saline Solution (USP) and while immersed, placed into an oven at a temperature of 37 ± 1 degrees centigrade for a period of 7 days, removed from the oven and examined for corrosion while still immersed.

Identification marking. The tibial bolt shall be permanently and legibly marked with the contractor's name or registered trademark, and an indication that the material is stainless steel. Tibial bolts of foreign manufacture shall, in addition to the above, indicate the country of origin. All methods of marking shall be in accordance with ASTM F86.

Workmanship. Screw threads and bolt head slot shall be free from burrs, pits and tool marks. Tibial bolts shall be free from defects which detract from their appearance or impair their serviceability.

Unit. Each (EA). One bolt along with 2 nuts and 2 washers, as specified, constitutes one unit.

QUALITY ASSURANCE PROVISIONS.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory applicants or procedures) and testing (determination by technical means and chemical properties) of the item.

Sampling for examination. Sampling for examination shall be conducted in accordance with MIL-STD-105 and as specified herein. Unit of product for examination purposes shall be one tibial bolt. Sampling shall be Inspection level II with an acceptable quality level (AQL) of 1.0.

Examination. Examination shall be conducted to determine compliance with specification requirements.

Sampling for tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and as specified herein. Unit of product for test purposes shall be one tibial bolt. Sampling shall be Inspection level S-2 with an AQL of 1.0.

Tests. Tests shall be conducted to determine compliance with specification requirements. Where feasible, the same sample shall be used for the determination of two or more test characteristics.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producers' own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch-pound units, providing they fall within the tolerance specified using conversion tables contained in the latest revision of Federal Standard No. 376, and all other requirements of this document are met.

If a product is manufactured to metric dimensions and those dimensions exceed the tolerances specified in the inch/pound units, a request should be made to the contracting officer to determine if the product is acceptable.

The contracting officer has the option of accepting or rejecting the product.

Regulatory requirements.

Federal Food, Drug, and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction , the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal State, and local statutes, ordinances, and regulations.

Recovered material. The offeror/contractor is encouraged to use recovered material in accordance with Federal Acquisition Regulation Subpart 23.4 to the maximum extent practical.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging, and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

Source: https://assist.dla.mil -- Downloaded: 202610-26T09:33Z
Check the source to verify that this is the current version before use.

NOTE: The following National Stock Number is covered by this document:

NSN	Item Identification
6515-00-310-5000	BOLT, TIBIAL.

Ordering data. (Intermediate/exterior package quantities and labeling and marking must be specified in the contract and/or order).

MILITARY INTERESTS:

Custodians:

Army-MD
Navy-MS
Air Force-03

PREPARING ACTIVITY:

DoD-MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITIES:

VA-OSS
PHS
FDA-MPQAS

Project No. 6515-4983

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	A-A-54350	8 March 1991

3. DOCUMENT TITLE: BOLT, TIBIAL

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable) / 7. DATE SUBMITTED (YYMMDD)

8. PREPARING activity

a. NAME	b. TELEPHONE (Include Area Code) (1) Commercial	(2) AUTOVON
Defense Personnel Support Center	(215)737-2870	444-2870
c. ADDRESS (Include Zip Code) ATTN: DPSC-MSTE 2800 S. 20th Street Philadelphia, PA 19101	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

DD Form 1426, OCT 89 — Previous editions are obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.