MIL-T-13867C
10 October 1983
SUPERSEDING
MIL-T-13867B(MR)
10 December 1971

MILITARY SPECIFICATION

# TREATMENT, MOISTURE AND FUNGUS RESISTANT FOR FIRE CONTROL ELECTRICAL AND ELECTRONIC INSTRUMENTS AND EQUIPMENT

This specification is approved for use by the Army Materials and Mechanics Research Center, Department of the Army, and is available for use by all Departments and Agencies of the Department of Defense.

## 1. SCOPE

1.1 Scope. This specification covers five types of treatments for increasing the moisture and fungus resistance of fire control electrical and electronic instruments and equipment.

1.2 Classification. The treatments covered by this specification shall be of the following types as specified.

Type I - Wax treatment
Type II - Varnish treatment
Type III - Bonding treatment
Type IV - Vacuum impregnation treatment
Type V - Wax impregnation treatment

Procedure 1 - Bake drying
Procedure 2 - Centrifugal drying

## 2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. Unless otherwise specified, the following specifications, standards, and handbooks of the issue listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation form a part of this specification to the extent specified herein.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Director, US Army Materials and Mechanics Research Center, ATTN: DRXMR-SMS, Watertown, MA 02172 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

/ FSC 8030 /

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:30Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

MILITARY

MIL-V-173 - Varnish, Moisture- and Fungus-Resistant (for the Treatment of Communications, Electronic and Associated Electrical Equipment
MIL-W-12465 - Wax, Microcrystalline, Electrical Insulating
MIL-V-13497 - Varnish, Impregnating, Electrical Insulating (for Fire Control Instruments)
MIL-I-24092 - Insulating Varnish, Electrical Impregnating

(Copies of specifications, standards, handbooks, drawings, and publications required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Type I, wax treatment.

3.1.1 Coverage. This process covers an overall wax treatment for assembled electrical units containing non-moving parts.

3.1.2 Material. The wax shall conform to MIL-W-12465.

3.1.3 Description of treatment.

3.1.3.1 The application of the moisture and fungus resistant wax treatment covered by this specification shall be performed on equipment which meets the electrical performance requirements of the applicable specifications.

3.1.3.2 Cleaning. All parts to be coated shall be thoroughly clean before treatment. All dirt and other foreign matter that will interfere with the adhesion of the wax shall be removed. Components that cannot be satisfactorily cleaned and parts that show evidence of corrosion shall be replaced by acceptable components.

3.1.3.3 Masking. To prevent molten wax from running into conduits when wax-treating the components to which they are connected, the conduit openings shall be sealed by a compound approved by the contracting officer (see 6.6).

3.1.3.4 Drying of equipment. The component shall be preheated in a ventilated oven to a temperature of 221° - 230°F (105° - 110°C) for one half hour.

3.1.3.5 Wax application. A sufficient quantity of molten wax shall be heated to a temperature of 230°F (110°C) and shall be poured immediately into the hot component to a level prescribed by the drawings or contracting officer.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:30Z
Check the source to verify that this is the current version before use.

3.1.3.5.1 The wax shall be drained off within 30 to 60 seconds after pouring has been completed.

3.1.3.5.2 The coating shall not contain any bubbles or blisters, nor any thick areas or large masses.

3.1.3.6 Thickness of coating. The maximum thickness of the coating permissible on vertical surfaces shall be 0.005 inch.

3.2 Type II, varnish treatment.

3.2.1 Coverage. This process covers the application of varnish to electrical equipment and components. It shall not be used for electrical components whose operating temperatures exceed 200°F (93.3°C).

3.2.1.1 Wire harnesses and laced cable forms. Wire harnesses for wire type equipment need not be covered with coating material providing such harnesses and the individual wires of which they are composed have been coated in accordance with this specification or with other approved fungicidal coatings before their installation into the equipment; where possible, coatings on polyamide jacketed wire and harnesses composed of this wire should be avoided. After installation of the laced forms and soldering of the wires to their terminals, the wire ends (bare wire and adjacent textiles, servings and tie cords) and soldered terminals shall be covered with the coating material. In congested locations, the coating treatment shall be applied as the wires are connected.

3.2.2 Material. The varnish shall conform to the requirements of MIL-V-173.

3.2.3 Description of treatment.

3.2.3.1 The application of the varnish treatment covered by this specification shall be performed on equipment or components which meet the electrical performance requirements of the applicable specifications.

3.2.3.2 Preparation for treatment. The parts, circuit elements, etc. shall be exposed so that the coating may be applied effectively and completely over all surfaces to be treated. On assemblies, the case, cans, covers, shields, etc. shall be removed in order to expose the parts; however, this is unnecessary if the subassemblies have been previously treated in accordance with this specification or by other approved methods prior to their assembly. Where practicable, untreated cables shall be bent back and untreated terminal boards shall be loosened to expose the underside.

3.2.3.2.1 When judged necesssary by the contracting officer, disassembly of units shall be made to insure proper treatment of the individual components.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:30Z
Check the source to verify that this is the current version before use.

3.2.3.3 Cleaning. All surfaces of parts to be coated, shall be sufficiently clean so that they are free from dirt, grease or other foreign matter which would interfere with the adhesion or proper functioning of the coating material. Components that cannot be satisfactorily cleaned and parts that show evidence of corrosion shall be replaced by acceptable components.

3.2.3.4 Drying of equipment. The coating material shall be applied only on dry surfaces. In no case shall the coating material be applied on wet or damp surfaces. If required by paragraph 3.2.3.4.1, the equipment shall be dried by preheating. The preheating temperatures shall be 160° - 180°F (71° - 82°C). Preheating shall be accomplished at a slow enough rate to avoid shrinking, cracking, warping or other deterioration of the parts or materials. After preheating, the treatment shall be applied while the temperature of the dry equipment is not more than 100°F (38°C).

3.2.3.4.1 When any of the following conditions exist, the equipment parts and materials shall be preheated at approximately 160° - 180°F (71° - 82°C) for a length of time sufficient to dehydrate substantially the unit prior to treatment, but no longer than 3 hours.

a. Specification required by the contract or order.

b. The manufacturer or contractor so desires.

c. The equipment or its parts are obviously wet or damp.

d. The humidity conditions are so severe that the treated equipment cannot meet the electrical performance requirements given in the applicable specification.

e. The appearance of the film indicates that moisture has been entrapped, i.e., there is blushing, darkening of the materials, poor adhesion, etc.

3.2.3.5 Masking. The coating material shall not be applied to any surface or parts where such application will interfere with the operation or performance of the equipment. Care shall be exercised to insure that the coating when completely dry shall not prevent field replacement of components. Surfaces or parts to be masked shall include the following:

a. Contact portion of: binding posts, connectors, fuses, jacks, keys, plugs, relays, sockets, switches, test points, variable capacitors.

b. Surfaces which rub together for electrical or magnetic contact such as those in bearings, contact fingers, potentiometers, shafts, shields, variable autotransformers and relays.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:30Z
Check the source to verify that this is the current version before use.

c. Mechanical parts such as bearing surfaces (including bearing surfaces of gaskets and sliding surfaces). Gear teeth and gear trains or assemblies. Pivots and pivot portion of hinges, locks, etc. Screw threads and screw adjustments (normally moved in the process of operation of adjustments). Springs except at base of pile up. Surfaces, whose operating temperatures exceed 200°F (93.3°C) or will cause carbonization or smoking. Transparent plastic parts. Windows, lenses, etc.

d. Components, parts and materials such as cable with plastic insulation where application of the coating materials reduces the insulation resistance below acceptable values. Capacitors, variable, air-ceramic or mica-dielectric types. Ceramic insulators subject to over 600 volts operating where danger of flashover exists. Materials when used for their specific arc and moisture resistant properties and classified as "arc-resistant" in applicable materials specifications. Painted, lacquered or varnished exterior surfaces. Plugs, plug-connectors, tube sockets, etc. (pins, mating surfaces and threads). Resistors (high temperature ratings where wattage dissipation material may become carbonized).

e. The exterior or visible portion of those indicating instruments, control boxes or equipment which mount in the cockpit of aircraft.

3.2.3.5.1 All masking materials shall be removed after they have served their purpose in connection with this process. The masking materials used shall leave no residue on the surfaces of the equipment.

3.2.3.6 Application methods. The coating material shall be applied by a choice of, or any combination of, spraying, brushing, and dipping, in such manner that the dried film shall have a clear smooth finish free from defects, such as bubbles, wrinkles, filaments, or spray dust. Running, lumping, or gathering of the coating material into drops shall be avoided.

3.2.3.6.1 Temperature conditions. The varnish shall not be applied to components which have been preheated until temperature of the component is below 100°F (38°C). The temperature of the coating material shall not be less than room temperature.

3.2.3.6.2 Coating material as applied. If thinning of the coating material is required for application, it shall be performed in accordance with the varnish manufacturer's recommendation.

3.2.3.6.3 Thickness of coating. Where practicable, the thickness of the dry film shall be at least 0.001 inch.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:30Z
Check the source to verify that this is the current version before use.

3.2.3.6.4 Spraying. Where spraying is used as the method of application of the varnish coating material, a pressure-point spray gun with a tip regulated to give a wet spray is recommended; for small compact equipment a pencil spray tip regulated to give a narrow wet spray is recommended. The coating material shall be applied in a wet coat over all parts. (This prevents the formation of fuzz or filaments on fabric insulation.) A dry spray which forms spray dust shall not be used. The equipment or individual assembly shall be sprayed from as many directions and angles as is necesssary to insure complete coverage with a wet coat. Where more than one coat of varnish is applied, sufficient drying time between each coat should be allowed. Unless otherwise specified in the contract or order or option given to the manufacturer, coated assemblies and components shall be force dried between coats at a temperature between 160° - 180°F (71° - 82°C) for 30 minutes in a well ventilated oven.

3.2.3.6.5 Brushing. All parts which cannot be reached by spray shall be coated as completely as practicable by use of a brush. A brush shall also be used to cover small areas that have not been covered during the spraying process. On components requiring extensive masking, brush applicaton of the coating material may prove more efficient than spray application through elimination of the masking, and may be used.

3.2.3.6.6 Dipping. Subassemblies or components may be coated by dipping provided that the requirements of 3.2.3.5 are met.

3.2.3.7 Final drying of coating materials. On metal surfaces, the coatings shall be "dry hard" before packaging. On other surfaces the coatings shall not be "tacky". Care shall be taken to insure sufficient drying to prevent the presence of solvent vapors in any enclosure. Unless otherwise specified in the contract or order, or option given to the equipment manufacturer, coated assemblies shall be force dried at a temperature between 160° - 180°F (71° - 82°C) for one to two hours in a well ventilated oven.

3.2.3.8 Adjusting and final testing. After the treatment, the equipment or individual assembly shall be adjusted and aligned for optimum operating characteristics and, wherever the film is broken during such alignment, such breaks shall be recoated. The equipment shall then meet the requirements of the applicable equipment specification.

3.2.3.9 Connections to other apparatus. When subassemblies and components are treated separately, their permanent electrical connections to other apparatus should be coated after assembly.

3.3 Type III - bonding treatment.

3.3.1 Coverage. This process covers the bonding with varnish of wire wound cards for potentiometers, rheostats, and for components and equipment which operate above 200°F (93.3°C). The bonding is designed to prevent the loosening and slipping of the wire turns.

3.3.2 Materials. The varnish shall conform to the requirements of MIL-I-24092, class 220 type M.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:30Z
Check the source to verify that this is the current version before use.

3.3.3 Description of treatment.

3.3.3.1 The application of the bonding treatment covered by this specification shall be performed on equipment or components which meet the electrical performance requirements of the applicable specifications.

3.3.3.2 Preparation for treatment. All wire wound cards shall be performed into final shape before being subjected to the bonding treatment.

3.3.3.3 Cleaning. All surfaces of parts to be coated, shall be sufficiently clean so that they are free from dirt, oil, grease or other foreign matter which would interfere with the adhesion or proper function of the coating material. Components that cannot be satisfactorily cleaned and parts that show evidence of corrosion shall be replaced by acceptable components.

3.3.3.4 Masking. The bonding material shall not be applied to any surface which would have its normal mechanical or electrical function impaired or adversely affected by the treatment. All threaded and other holes in the assembly designed for mounting or other mechanical or electrical purposes shall be kept free from bonding varnish by the insertion of suitable machine plugs or screws during the bonding treatment.

3.3.3.4.1 All masking materials shall be removed after they have served their purpose in connection with this process.

3.3.3.4.2 The masking materials used shall leave no residue on the surfaces of the equipment.

3.3.3.5 Application methods.

3.3.3.5.1 The cleaned component shall be preheated in a ventilated oven at a temperature of 275°F (135°C) for one half hour.

3.3.3.5.2 While still hot, the component shall be immersed in varnish. Complete coverage shall be maintained for at least five minutes after all bubbling has ceased.

3.3.3.5.3 The component shall then be drained and air dried for twenty minutes at room temperature. During this period, the excess varnish will drain from the surface.

3.3.3.5.4 The component shall then be baked in accordance with the recommendation of the varnish manufacturer.

3.3.3.5.5 Steps 3.3.3.5.1, 3.3.3.5.2, 3.3.3.5.3 and 3.3.3.5.4 shall then be repeated once again in the order given.

3.4 Type IV - vacuum impregnation treatment.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:30Z
Check the source to verify that this is the current version before use.

3.4.1 Coverage. This process covers the vacuum impregnation with varnish of windings of rotor and stator assemblies of rotating electrical machinery and the subsequent coating with insulating enamels wherever indicated. This procedure is also applicable to coil windings or relays, solenoids, contactors, reactors and transformers (see 6.5).

3.4.2 The varnish shall conform to the requirements of MIL-V-13497 or MIL-I-24092 as specified by the contracting officer. The finish protective coating (enamels or varnish) shall be specified by the contracting officer.

3.4.3 Description of treatment.

3.4.3.1 The vacuum impregnation treatment covered by this specification shall be performed on equipment which meets the electrical performance requirements of the applicable specifications.

3.4.3.2 Preparation for treatment. Coils shall be in their assembled condition, with leads firmly connected to assure a minimum of movement.

3.4.3.2.1 All parts to be coated shall be thoroughly clean before treatment. All dirt and other foreign matter that will interfere with the adhesion of the varnish shall be removed. Components that cannot be satisfactorily cleaned and parts that show evidence of corrosion shall be replaced by acceptable components.

3.4.3.2.2 All threaded and other holes in the assembly designed for mounting or other mechanical or electrical purposes shall be kept free from impregnating varnish by the insertion of suitable machine screws or plugs during the treatment.

3.4.3.3 Application methods.

3.4.3.3.1 All periods of time referred to in this specification shall begin from the time the tank and assembly are up to the specified temperature and under the specified vacuum.

3.4.3.3.2 The cleaned component shall be preheated in a tank under a vacuum of 28 inches of mercury and at a temperature of 212°F (100°C) for one hour or in air at 230°F (110°C) for two hours.

3.4.3.3.3 The component shall be immediately transferred while hot to a second and unheated impregnation tank. The impregnating tank shall be evacuated to a vacuum of 28 inches of mercury, and then a sufficient amount of varnish at room temperature shall be drawn into the tank to permit complete immersion to a depth of at least six inches over the component. The vacuum shall be broken as soon as all components are covered. The component shall remain immersed in the varnish for one half hour.

3.4.3.3.4 The component shall then be drained and air dried for one hour at room temperature. During this period, the excess varnish will drain from the surface.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:30Z
Check the source to verify that this is the current version before use.

3.4.3.3.5 The component shall then be baked at 275°F (135°C) for four hours.

3.4.3.3.6 While still hot, the component shall be impregnated a second time with the varnish under a vacuum of 28 inches of mercury. Complete immersion to a depth of at least six inches over the component shall be maintained for ten minutes.

3.4.3.3.7 The component shall then be drained and air dried for one half hour at room temperature. During this period the excess varnish will drain from the surfaces.

3.4.3.3.8 The component shall then be baked at 275°F (135°C) for twenty hours.

3.4.3.3.9 Surfaces to be covered with enamel as indicated in the drawing or by the contracting officer shall be ground and cleaned thoroughly with a material approved by the contracting officer.

3.4.3.3.10 The component shall then be baked at 275°F (135°C) for ten hours.

3.4.3.3.11 Coating with enamel. The ground surfaces and any other surfaces indicated in the drawings or by the contracting officer shall be sprayed with an insulating enamel.

3.4.3.3.12 The component shall then be baked at 248°F (120°C) for two hours.

3.4.3.3.13 Thickness of coating. The same surfaces shall be sprayed again with insulating enamel to a total coating thickness of 0.0008 to 0.0015 inch (dried film).

3.4.3.3.14 The components shall be air dried at room temperature for one half hour.

3.4.3.3.15 The components shall then be baked at 248°F (120°C) for eight hours.

3.5 Type V - wax vacuum impregnation treatment.

3.5.1 Coverage. This process covers two vacuum impregnation procedures with wax of ceramic and phenolic fiber parts or small coils.

3.5.2 Material. The wax shall conform to MIL-W-12465.

3.5.3 Description of treatment.

3.5.3.1 Procedure 1 (bake drying).



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:30Z
Check the source to verify that this is the current version before use.

3.5.3.1.1 Cleaning. All parts to be coated shall be thoroughly clean before treatment. All dirt and other foreign matter that will interfere with the adhesion of the wax shall be removed. Components that cannot be satisfactorily cleaned and parts that show evidence of corrosion shall be replaced by acceptable components.

3.5.3.1.2 Drying. The cleaned parts shall be placed in a heated (impregnating) tank at 230° ± 10°F (110° ± 6°C) and the pressure in the tank reduced until a vacuum of 28 inches of mercury is obtained. The parts shall be dried under this vacuum for one hour.

3.5.3.1.3 Wax impregnation. The wax shall be drawn from an auxiliary tank into the impregnating tank at 230° ± 10°F (110° ± 6°C) in such a manner that the previously established vacuum shall not be broken. After a sufficient amount of wax has been drawn into the tank to completely cover the parts, the vacuum shall be broken and the parts shall remain in the tank for five minutes. The wax shall then be drained from the tank.

3.5.3.1.4 Bake drying of wax impregnated parts. The part shall be baked dry at 230° ± 10°F (110° ± 6°C) for 15 minutes to allow the excess wax to drop off.

3.5.3.2 Procedure 2 (centrifugal drying).

3.5.3.2.1 Cleaning. The parts shall be cleaned in accordance with 3.5.3.1.1.

3.5.3.2.2 Drying. The cleaned parts shall be dried in accordance with 3.5.3.1.2.

3.5.3.2.3 Wax impregnation. The clean dry parts shall be impregnated with wax in accordance with 3.5.3.1.3.

3.5.3.2.4 Centrifugal drying of wax impregnated parts. Immediately after removing the parts from the hot wax, the parts shall be treated in a centrifugal dryer until all excess wax is removed. Care should be taken that a thin uniform coating of wax remains on the part.

3.6 Workmanship. Treatment of equipment as specified herein shall be effected in a careful and workmanlike manner. Quality of workmanship shall be such that the treatment will meet the requirements for quality as specified in 3.1 through 3.5.3.2.4. The individual procedures and the completed treatment shall meet the inspection requirements for quality as specified in 4.3.

## 4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:30Z
Check the source to verify that this is the current version before use.

any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Size of lot. A lot shall be as designated in applicable specifications for the component being treated.

4.3 Inspection. One hundred percent inspection tests for acceptance of individual lots shall consist of requirements of paragraphs 4.3.1 to 4.3.5 inclusive.

4.3.1 Wax treatment - type I. Inspection shall be limited to determining compliance with the requirements of paragraphs 3.1.3.2, 3.1.3.3, 3.1.3.5.2 and 3.1.3.6. Changes in appearance of components caused by application of the coating material shall not be used as a basis for rejection during inspection.

4.3.2 Varnish treatment - type II. Inspection shall be limited to determining compliance with the requirements of paragraphs 3.2.3.3, 3.2.3.5, 3.2.3.6, 3.2.3.6.3, 3.2.3.7 and 3.2.3.8. Changes in appearance of components caused by application of the coating material shall not be used as a basis for rejection during inspection.

4.3.3 Bonding treatment - type III. Inspection shall be limited to determining compliance with the requirements of paragraphs 3.3.3.2, 3.3.3.3 and 3.3.3.4. The appearance of bubbles or blister formations in the varnish coating shall be cause for rejection. Changes in appearance of components caused by this bonding procedure shall not be used as a basis for rejection during inspection.

4.3.4 Vacuum impregnation - type IV. Inspection shall be limited to determining compliance with the requirements of paragraphs 3.4.3.2, 3.4.3.2.1, 3.4.3.2.2, 3.4.3.3.11 and 3.4.3.3.13. The appearance of bubbles, streaks, or thick areas, or wrinkles on the finished surface shall be cause for rejection. Changes in appearance of components caused by this impregnation procedure shall not be used as a basis for rejection during inspection.

4.3.5 Wax vacuum impregnation - type V. Inspection shall be limited to determining compliance with the requirements of paragraphs 3.5.3.1.1 and 3.5.3.2.1. The appearance of bubbles, streaks, or thick areas and foreign inclusions on the finished surface shall be cause for rejection. Changes in appearance of components caused by this impregnation procedure shall not be used as a basis for rejection during inspection.

## 5. PREPARATION FOR DELIVERY

5.1 Packaging. Not applicable.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:30Z
Check the source to verify that this is the current version before use.

5.2 Marking. Each unit of equipment which has been treated to be resistant to moisture and fungus and each treated plug-in assembly, as well as all cases and containers in which they are packed for shipment, shall bear a marking reading MFP and date (month and year of treatment), i.e., MFP June 45. The date shall be acurate to within a month; thus, equipment treated in June 1945 may be marked as having been treated in either May, June or July 1945. The month and year may be abbreviated as indicated. The marking shall appear on the exterior of the case and the chassis of the part (not on control panel). The letters MFP may be applied by means of a rubber stamp or a decalcomania, but the complete tie-type tag shall be secured to the equipment in such a manner that it will not become detached during handling, shipment or installation. Marking data shall refer only to date of application of overall treatment of completed equipment. Where an equipment is comprised of major components or assemblies, each of these may be individually marked.

6. NOTES

6.1 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Type of treating required.
(c) Whether spray coated assemblies and components shall be force dried.
(d) Whether final drying of coating material shall be force dried.
(e) Type of varnish required.

6.2 Purpose of treatment. The purpose of the specified treatment of electrical and electronic instruments and equipment is to protect said equipment items when subjected to moisture and fungus conditions and internal mechanical and electrical stresses normally encountered in service. These treatments were promulgated for use on fire control materiel. This treatment is intended to accomplish the following:

(a) To render the surfaces moisture-resistant.
(b) To envelop terminals and connections with a low moisture-absorbing film and thereby minimize surface electrical leakage and arc-covers.
(c) To retard the absorption of moisture.
(d) To aid in retarding corrosion.
(e) To inhibit the growth of fungi.
(f) To provide medium for retention of coil winding wires.
(g) To eliminate air spaces in the electric field winding and provide adequate dielectric medium.

6.3 Technique of treatment. All questions regarding technique of application or other technical data or questions arising from inspection of the coating treatment shall be referred to the contracting officer.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:30Z
Check the source to verify that this is the current version before use.

6.4 Substitution of method of treatment. If the contractor desires to substitute for a specified or previously approved method of treatment, he shall submit to the bureau or agency concerned, with his bid or sample, a statement to that effect describing the proposed substitution, together with evidence to substantiate his claim that such substitution is suitable. Similar notification and substantiating evidence shall be submitted at any later time that substitution becomes necesssary or desirable. At the discretion of the bureau or agency concerned, test samples may be required to prove the suitability of the proposed substitution.

6.5 At the discretion of the contracting officer, the following other methods of impregnation may be used depending on the size of the wire and space between wires:

(a) Immersion method consisting of simple single or multiple immersion of the part in varnish followed by baking after each immersion.

(b) Centrifugal method consisting of diffusing of varnish into the part by the use of centrifugal force.

(c) Pulsating pressure method consisting of repeated applications of pressure for suitable periods of time alternating with zero gage pressure.

(d) Buildup method consisting of impregnation and curing of the insulation at each step in the building up of the winding.

(e) Brush or spraying method consisting of brushing or spraying of the varnish. The use of this method should be limited to the final coat of varnish applied to windings previously impregnated by one of the other methods outlined in the foregoing paragraphs.

6.6 Masking. Masking may be accomplished by the use of any suitable method or device for preventing the coating material from being applied to any part of the equipment which is not to be coated. Application of the coating material may be prevented by the use of a masking tape, jigs, fixture of metal or cardboard. Tube sockets may be masked by using dummy tubes, but they must not be removed until the coating material has dried hard to prevent tube prongs from drawing coating material through the sockets.

6.7 Materials that are inherently moisture and fungus-resistant or interior surfaces of metal parts that have been surface treated or passivated, such as anodized aluminum or chromated cadmium, do not require moisture fungus proof treatment.

6.8 Inspection. To facilitate inspection of equipment processed in accordance with type II and type IV, observation of items under near ultra-violet light (black light) and noting the presence or absence of fluorescent indications will reveal untreated items.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:30Z
Check the source to verify that this is the current version before use.

Custodian:

Army - MR

Review Activities:

Army - AR, MI,

User activities:

Army - AT
Navy - SH, YD

Preparing activity:

Army - MR

Project No. 8030-0504

(KBWP# ID-0380A/DISK 0109A. FOR AMMRC USE ONLY)



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:30Z
Check the source to verify that this is the current version before use.

**INSTRUCTIONS:** In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

*NOTE:* This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

*(Fold along this line)*

*(Fold along this line)*

DEPARTMENT OF THE ARMY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Director
US Army Materials and Mechanics Research Center
ATTN: DRXMR-SSS
Watertown, MA 02172

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:30Z
Check the source to verify that this is the current version before use.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

*(See Instructions – Reverse Side)*

| 1. DOCUMENT NUMBER | 2. DOCUMENT TITLE |
|---|---|
| | |

| 3a. NAME OF SUBMITTING ORGANIZATION | 4. TYPE OF ORGANIZATION *(Mark one)* |
|---|---|
| | ☐ VENDOR |
| b. ADDRESS *(Street, City, State, ZIP Code)* | ☐ USER |
| | ☐ MANUFACTURER |
| | ☐ OTHER *(Specify)*: _____ |

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

| 7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional | b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional |
|---|---|
| c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional | 8. DATE OF SUBMISSION *(YYMMDD)* |
| | |

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:30Z
Check the source to verify that this is the current version before use.