MILITARY SPECIFICATION

ARMOR, PLATE, STEEL, WROUGHT, HIGH-HARDNESS

PAGE 4

Paragraph 3.2.2 change last sentence to read, "It is recommended that the delay after quenching be no greater than 24 hours, see 6.15."

PAGE 9

Change the following paragraphs 3.2.9.2, 3.2.9.3, 3.2.9.4, 3.2.9.4.1, 3.2.9.4.1.1, 3.2.9.4.1.2, 3.2.9.4.1.3, and 3.2.9.4.1.4.

To: 3.2.9.3, 3.2.9.4, 3.2.9.5, 3.2.9.5.1, 3.2.9.5.1.1, 3.2.9.5.1.2, 3.2.9.5.1.3, and 3.2.9.5.1.4 respectively.

Paragraph 3.2.9.3, Add to end of 2nd sentence, "Unless otherwise specified."

Add the following paragraph:

"3.2.9.2 Internal soundness. All plates 1/2-inch and greater in thickness shall be ultrasonically examined for internal soundness in accordance with 4.6.6."

PAGE 10

Paragraph 4.3, change second sentence to read, "When specified by the procuring activity (see 4.3.1 and 6.2.), production and ballistic test plates may be allowed to be heat-treated separately."

PAGE 11

Paragraph 4.3.1, delete contents and substitute, "When the procuring activity allows a ballistic test plate to be heat-treated separately from the production plates it represents, it will be so stated in the data to be supplied in accordance with MIL-STD-367 (see 6.15)."

PAGE 12

Paragraph 4.4.2.7, Delete this entire paragraph.

DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:51Z
Check the source to verify that this is the current version before use.

PAGE 13

Paragraph 4.6.6.2, section (c) and (d), delete "2-1/4 megahertz" and substitute "2 megahertz".

PAGE 14

Below "NOTES" insert "(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)"

PAGE 18

Paragraph 6.15, delete paragraph in its entirety and substitute, "6.15 Production plates. Material made to this specification has tendency to develop stress cracks if not tempered as soon as possible after austenizing treatment. To avoid this situation, all plates should be left in the hot rolled or tempered condition while waiting for the ballistic test results."

PAGE 22

Delete this entire page and substitute the following page:

TABLE VII. Minimum required ballistic limits - Caliber .30 AP M2 Projectile at 30 degrees Obliquity.

Thickness inches	Required BL(P) FPS	Thickness inches	Required BL(P) FPS	Thickness inches	Required BL(P) FPS
0.100	994	0.185	1799	0.265	2328
0.105	1057	0.190	1836	0.270	2357
0.110	1116	0.195	1872	0.275	2386
0.115	1172	0.200	1908	0.280	2415
0.120	1226	0.205	1943	0.285	2443
1/ 0.125	1279	0.210	1978	0.290	2471
0.130	1329	0.215	2012	0.295	2499
0.135	1378	0.220	2046	2/ 0.300	2526
0.140	1425	0.225	2079	0.305	2554
0.145	1471	0.230	2111	0.310	2581
0.150	1515	0.235	2144	0.315	2607
0.155	1558	0.240	2175	0.320	2634
0.160	1601	0.245	2207	0.325	2660
0.165	1642	0.250	2237	0.330	2686
0.170	1682	0.255	2268	0.335	2711
0.175	1722	0.260	2298	0.340	2737
0.180	1761				

1/ Specification requirements begin for this ordered thickness.
2/ Specification requirements end for this ordered thickness.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:51Z
Check the source to verify that this is the current version before use.

Delete this entire page and substitute the following page:

TABLE VIII. Minimum required ballistic limits - Caliber .50 AP M2 Projectile at 30 degrees Obliquity.

Thickness inches	Required BL(P) FPS	Thickness inches	Required BL(P) FPS	Thickness inches	Required BL(P) FPS
0.290	1783	0.400	2151	0.515	2481
0.295	1801	0.405	2166	0.520	2494
0.300	1820	0.410	2182	0.525	2508
1/ 0.301	1823	0.415	2197	0.530	2521
0.305	1837	0.420	2212	0.535	2534
0.310	1855	0.425	2227	0.540	2547
0.315	1873	0.430	2242	0.545	2560
0.320	1890	0.435	2256	0.550	2573
0.325	1907	0.440	2271	0.555	2586
0.330	1925	0.445	2286	0.560	2599
0.335	1942	0.450	2300	0.565	2612
0.340	1958	0.455	2314	0.570	2625
0.345	1975	0.460	2329	0.575	2638
0.350	1992	0.465	2343	0.580	2650
0.355	2008	0.470	2357	0.585	2663
0.360	2025	0.475	2371	2/ 0.590	2675
0.365	2041	0.480	2385	0.595	2688
0.370	2057	0.485	2399	0.600	2700
0.375	2073	0.490	2413	0.605	2713
0.380	2089	0.495	2427	0.610	2725
0.385	2104	0.500	2440	0.615	2737
0.390	2120	0.505	2454	0.620	2750
0.395	2136	0.510	2468	0.625	2762

1/ Specification requirements begin for this ordered thickness.
2/ Specification requirements end for this ordered thickness.

Custodian:
Army - MR

Preparing activity:
Army - MR

Review activities:
Army - AT, EA, AR, TE
DLA - IS

Project 9515-A059

(WP# ID 2901A/DISC 0393A. FOR MTL USE ONLY)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T04:51Z
Check the source to verify that this is the current version before use.