A-A-50015A
June 30, 1989
SUPERSEDING
A-A-50015
23 December 1981

COMMERCIAL ITEM DESCRIPTION

SOCKS, MEN'S, RIBBED KNIT, STRETCH TYPE

The General Services Administration has authorized the use of this commercial item description in preference to MIL-S-12549; Sock's, Men's, Nylon and Cotton, Ribbed, Stretch Type.

1. CLASSIFICATION

1.1 Classification. This commercial item description covers socks in the following sizes:

Small - Sizes 9-11
Medium - Sizes 10-13
Large - Sizes 13-15

2. SALIENT CHARACTERISTICS

2.1 Description. The socks shall be seamless, circular true rib knit, stretch type with a ribbed elastic top, fabricated on a 132-240 needle machine, and suitable for dress wear.

2.2 Material. The socks shall be made of cotton plied yarn or plated with stretch nylon yarn. The plating will result in the cotton yarn dominating the inside of the sock.

2.3 Elastic top. The elastic top shall be a true 1 by 1 ribbed knit made with an elastic yarn consisting of a spandex core with a stretch type inner and outer cover, and finished with a turn-over, non-raveling welt, and free from loose ends.

2.4 Color. The color of the socks shall be black or white, as specified (see 5.2).

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to: Commander, U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014.

AMSC/NA FSC 8440

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:37Z
Check the source to verify that this is the current version before use.

2.5 Stretch. The finished socks shall conform to the stretch requirements listed in table I.

TABLE I. Physical requirements

Size	Min. wt. per dozen 1/	Min. relaxed leg length in inches 2/	Max. relaxed foot length in inches 3/	Min. stretched foot length in inches 4/
Small	10.5 oz.	10-1/2	8 2	12
Medium	11.5 oz.	10-1/2	10-1/2	14
Large	12.5 oz.	10-1/2	12-1/2	16

1/ Unpackaged socks only.

2/ The length is the measured distance from the bottom of the heel to the top of the sock.

3/ The measurement of the relaxed foot length shall be taken in a straight line from the tip of the toe to the back of the heel along a straight line through the tip of the toe and the bottom of heel gore.

4/ The measurement of the stretched foot length shall be taken from the tip of the toe to the lower end of the heel gore, holding the sock firmly between the thumb and the finger at the toe tip and at the heel gore, and stretching the fabric to its limit.

2.6 Labeling. Each sock shall have a size marking applied to it just below the instep and centered between the ankle and toe. The color of the marking shall be black on white socks, and white marking on black socks.

2.7 Workmanship. The socks shall not contain any holes, runs, dropped stitches, thin areas or mends.

3. QUALITY ASSURANCE

3.1 Certification. The contractor shall certify, and maintain substantiating evidence, that the product offered meets the salient characteristics and requirements of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:37Z
Check the source to verify that this is the current version before use.

3.2 Component testing. The leg material of the finished socks shall have a ball bursting strength of not less than 85 pounds when tested in accordance with ASTM D3787.

3.3 End item examination. The contractor is responsible for assuring that the product offered conforms to the stated requirements. Sampling inspection shall be in accordance with MIL-STD-105. The inspection level shall be I and the AQL shall be 4.0. The lot size shall be expressed in units of one individual sock. The sample unit shall be one sock and the selection done in pairs. All socks shall be examined for commercial type defects affecting form, fit, function or appearance. The defects are as follows:

Any holes, runs or dropped stitches, including holes looping or seaming
Thin areas, mends
Welt omitted, cut, frayed, raveled
Noticeable variation in shade between two socks of a pair
Variation in size in a pair

4. PACKAGING

4.1 Packaging. Each pair of socks shall be folded at the heels in accordance with commercial practice. Twelve pairs of the same size socks shall be neatly stacked in a bundle and securely tied with cotton tape or twine.

4.2 Packing. One-hundred and twenty pairs of socks (10 bundles) of the same size shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC-L, type CF, (variety SW), or SF, class domestic, grade 275 of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class domestic, variety DW, grade 200 of PPP-B-636. Inside dimensions of each shipping container shall be approximately 16-1/2 inches long, 11-1/2 inches wide, and 8-1/2 inches deep. Each shipping container shall be closed in accordance with the appendix of PPP-B-636.

4.3 Palletization. When required (see 5.2), socks, packed as specified, shall be palletized on a 4-way entry pallet in accordance with MIL-STD-147. Load type shall be Ia; bonding means shall be K and L, or P; and pallet pattern shall be number 9 of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course.

4.4 Marking. In addition, to any special markings required by the contract or purchase order, shipping containers and palletized unit loads shall be in accordance with MIL-STD-129.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:37Z
Check the source to verify that this is the current version before use.

5. NOTES

5.1 Intended use. The socks are intended for use as dress wear by Military Personnel.

5.2 Ordering data. Acquisition documents must specify the following:

a. Title, number, and date of this document.
b. Size and color required (see 1.1 and 2.4).
c. When palletization is required (see 4.3).

5.3 Sources of documents.

5.3.1 Source of government documents. Copies of Military and federal documents are available from:

Naval Publications and Forms Center
ATTN: NPODS
5801 Tabor Avenue
Philadelphia, PA 19120

5.3.1 Sources for nongovernment association.

ASTM D3787 - Bursting Strength of Knitted Goods - Constant-rate-of-Traverse (CRT) Ball Burst Test, is available from:

American Society for Testing and Materials (ASTM)
1916 Race Street
Philadelphia, PA 19103-1187

MILITARY INTERESTS:

Custodians:

Army - GL
Navy - NU
Air Force - 11

Review Activities:

Army - MD
Navy - MC
Air Force - 82, 99
DLA - CT

User Activity:

Air Force - 45

CIVIL AGENCY COORDINATING ACTIVITY:

GSA - FSS

PREPARING ACTIVITY:

Army - GL

(Project 8440-0174)

Source: https://assist.dla.mil -- Downloaded: 202640-26T08:37Z
Check the source to verify that this is the currentversion before use.