INCH-POUND

MIL-B-48553 (AR)
AMENDMENT 3
28 October 1992
SUPERSEDING
AMENDMENT 2
25 March 1991

MILITARY SPECIFICATION

BANDOLEER, XM8

This amendment forms a part of MIL-B-48553 (AR), dated 18 December 1974, and is approved for use by the US Army Armament, Munitions, and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 1

Title: Delete "Bandoleer, XM8" and substitute "Bandoleer, M8".

2.1:

Under Drawings: Delete "Bandoleer, XM8" and substitute "Bandoleer, M8".

* Under Standards: Add the following:

"FEDERAL

FED-STD-191 - Textile Test Methods"

PAGE 2

3.3, line 1: Delete "7035 grains plus or minus 20 grains" and substitute "1 pound plus or minus 0.05 pounds".

Add new paragraphs 3.5 and 3.6 as follows:

"3.5 Slip stitch. The slip stitch shall be easily removable."

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:31Z
Check the source to verify that this is the current version before use.

* "3.6 Preproduction evaluation of ultrasonic weld. The finished seam shall offer a neat, even appearance. Also, there shall be no holes evident when the seam is held up to a light source and the seam shall possess a minimum of 12 pounds (5.46kg) bond strength when tested in accordance with prescribed bond strength procedure."

4.2.1, subparagraph a: Delete in its entirety and substitute the following:

"a 50ea -Bandoleer for dimensional and visual examination, drop test (see 6.2), and slip stitch test"

PAGE 4

4.3.3: Add the following characteristics:

"111	Pocket overlap	Measure"
* "112	Ultrasonic bonded seam width not between 5/32 to 5/16 inch	Measure"

Add new paragraphs 4.3.4.2 and 4.3.4.3:

"4.3.4.2 Slip stitch test. A sample of 50 bandoleers shall be subjected to a slip stitch test. The slip stitch will be removed by pulling the slip stitch thread overhang until the slip stitch is completely removed. No locking of the slip stitch shall occur. If three or more bandoleers fail to comply with the above requirement the lot shall be rejected. If one or two bandoleers fail to comply with the requirements, a second sample consisting of the same number of units as specified in the first sample shall be tested. If in the accumulated sample four or more units fail to comply with the requirements, the lot shall be rejected."

* "4.3.4.3 Bond strength test. Three specimens shall be prepared and subjected to the bond strength test. The ultrasonic machine shall be considered set properly when three specimens with the same machine setting have a minimum average peak bond strength of 12 pounds. The test shall be run at the start of each production shift."

4.4.1, line 2: Delete "7035 grains plus or minus 20 grains" and substitute "1 pound plus or minus 0.05 pounds".

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:31Z
Check the source to verify that this is the current version before use.

PAGE 5

* Add new paragraph 4.4.2 as follows:

"4.4.2 Bond strength test. Three specimens shall be prepared at a particular machine setting as follows:

a. Using the 65 percent (minimum) synthetic based outer shell material, cut two 12 inch long swatches in the warp (machine) direction, one 2 inches wide and one 8 inches wide each in the filling (cross-machine) direction.

b. If using a plunge type ultrasonic machine, then use appropriate manufacturer's leveling procedures to assure that the horn is level with the anvil.

c. Use a 5/32 inch (min) wide light knurled faced horn or roller as appropriate.

d. Set the ultrasonic machine with the proper weld time, pressure, and roller speed (if appropriate) to longitudinally bond the 2 inch wide strip in the middle to the middle of the 8 inch wide strip.

e. Test the bond strength of previously prepared sample per FED-STD-191, TM 5100 except place the top jaw of the tensile tester on one side of the wider base material and place the lower jaw such that it grabs both sides of the narrow strip in an even manner.

f. As an alternate test method, a calibrated spring scale with the capability to detect a minimum of 15 pounds may be used. However, the one side of the wider base material shall be firmly affixed while both sides of the narrow strip may be fixed to the spring scale. The specimen shall be pulled down in a smooth, even manner as not to jerk the spring scale."

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:31Z
Check the source to verify that this is the current version before use.

The margins of this amendment are marked with an asterisk or vertical lines to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in this notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 1305-AE41)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:31Z
Check the source to verify that this is the current version before use.