MIL-P-60812(MU)
AMENDMENT 2
16 June 1969
SUPERSEDING
Amendment 1
7 February 1969

MILITARY SPECIFICATION

PROJECTILE, 4.2 INCH, WP, SMOKE, M328A1
METAL PARTS ASSEMBLY

This amendment forms a part of Military Specification MIL-P-60812(MU) dated 5 February 1968.

Paragraph 4.3.2.3 For MINOR characteristic 201. add "(if applicable)"

Paragraph 4.3.2.7 For MINOR characteristic 215. change "Depty" to "Depth"

Paragraph 4.3.2.8 For CRITICAL characteristic 4. add "NOTE: To be inspected only after all manufacturing and gaging operations have been completed"

For MINOR characteristic 209. change "VCI paper missing" to "VCI crystals missing".

Add new paragraph 4.4.1.1.1.1

"4.4.1.1.1.1 One piece body.-In addition to the specimens removed and tested in accordance with 4.4.1.1.1 above, when the one piece body is used one tension test specimen conforming to the largest obtainable standard "R" type specimen as prescribed by Federal Test Method Standard No. 151 shall be taken in a transverse direction one inch from the centerline of the base of each sample. The specimens shall be tested in accordance with the criteria for determining yield strength and elongation as prescribed by Federal Standard No. 151. Yield strength shall be determined by the offset method. The limiting set shall be 0.1 percent (0.001) inch per inch of gage length."

The margins of this amendment are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodian
Army - MU

Preparing activity
Army - MU
Project No. 1315 -A710

FSC 1315

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:58Z
Check the source to verify that this is the current version before use.