MIL-W-63388 (AR)
AMENDMENT 6
17 SEPTEMBER 1984
SUPERSEDING
AMENDMENT 5
23 June 1983

MILITARY SPECIFICATION

WARHEAD, GUIDED MISSILE, HE, M207E1
BODY AND BOATTAIL BUSHING FOR

This Amendment forms a part of Military Specification MIL-W-63388 (AR) dated 7 January 1980 and is approved for use by the US Army Armament, Munitions and Chemical Command and is available for use by all Departments and Agencies of the Department of Defense.

Page 1

2.1 Under "SPECIFICATIONS," Federal: Delete in its entirety.

Page 2

3.3: Delete in its entirety.

Page 4

Table 1, under "Body (Dwg. 9332486):" Delete the following:

"Adhesive and Mar Resistance of Paint, 20, 3.3, 4.5.2"

Pages 6 & 7

4.4.2.1 Delete Pages 6 and 7 and substitute Pages 6, 7 and 7A attached.

Page 6

* 4.4.2.1 Major 110: Delete "AQL 0.40%" and substitute "100%"

Page 7

* 4.4.2.1 Add major defect 124 as follows:

"124 Minor diameter of small aft threads, max., 100%, 3.2, Gage"

Page 7A

* Minor 205: Delete in its entirety.

FSC 1336

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:46Z
Check the source to verify that this is the current version before use.

Page 8

4.4.2.2 Add major defect 107 as follows:

"107 Smallest outside diameter, 0.40%, 3.2, Gage"

Page 9

4.5.2, 4.5.2.1 and 4.5.2.2, delete in their entirety.

Add 4.5.2 as follows:

"4.5.2 - Molded components. At the start of production from a new mold or repair to a mold or cavity, consecutively produced units from each mold or cavity shall be dimensionally examined until 4 consecutive units meet all applicable drawing requirements. After adjustment or repair, those dimensions affected by the adjustment or repair shall similarly be examined. During production, the molding procedures shall be monitored randomly every two hundred units for uniformity of molding practices. Suspected deviations in mold product shall be examined to determine if corrective action or mold repair is required.

NOTE: The margins of this amendment are marked with an asterick to indicate where changes (additions, modifications, corrections deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document in relationship to the last previous amendment.

Custodian:
Army-AR

Preparing Activity:
Army-AR

(Project 1336-A486)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:46Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 3		DRAWING NUMBER 9332486
4.4.2.1	Body				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined.				
Major					
101	Large inside diameter		0.25%	3.2	Gage
102	True position of small holes		100%	3.2	Gage
103	Diameter of small holes		0.25%	3.2	Gage
104	Perpendicularity of aft shoulder with outside diameter		0.40%	3.2	Gage
105	Large aft diameter		100%	3.2	Gage
106	Runout of large aft diameter with datum		0.40%	3.2	Gage
107	Pitch diameter of large aft thread		0.40%	3.2	Gage
108	Length of ring retaining full thread		0.40%	3.2	Gage
109	True position of small aft holes		100%	3.2	Gage
110	Pitch diameter of small internal threads		100%	3.2	Gage
111	Location of wireway slot		0.25%	3.2	Gage
112	Location of boattail positioning slot		0.40%	3.2	Gage
113	Wall thickness, aft end		0.25%	3.2	Gage
114	Small inside diameter at aft end		0.40%	3.2	Gage
115	Runout of small inside diameter at aft end with datums		0.40%	3.2	Gage
116	Inside corner radius, large aft mounting shoulder		0.40%	3.2	Gage
117	Length next to large basic dimension aft end		0.40%	3.2	Gage

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-23T02:46Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 2 OF 3		DRAWING NUMBER 9332486
4.4.2.1	Body				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Major	(continued)				
118	Length to large basic dimension aft end		0.40%	3.2	Gage
119	Length to small basic dimension aft end		0.40%	3.2	Gage
120	Runout between two basic dimensions with datum		0.40%	3.2	Gage
121	Perpendicularity of front face with datum		0.40%	3.2	Gage
122	Runout of O.D. with datums		0.40%	3.2	Gage
123	Evidence of raised hanging burrs on exit hole surface of 6 threaded holes		100%	3.2	10X Magnifier
124	Minor diameter of small aft threads, max.		100%	3.2	Gage
Minor					
201	Distance from front face to missile mounting diameter face		0.65%	3.2	Gage
202	Distance from front face to shoulder		0.65%	3.2	Gage
203	Distance from front face to inside shoulder		0.65%	3.2	Gage
204	Overall length		0.65%	3.2	Gage
206	Major diameter of large aft threads, min.		0.65%	3.2	Gage
207	Protective finish missing, damaged or incomplete		0.65%	3.2	Visual
208	Identification missing or illegible		0.65%	3.2	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:46Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 3 OF 3		DRAWING NUMBER 9332486
4.4.2.1	Body				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Minor	(continued)				
209	Radius on conduit slot		0.65%	3.2	Gage
210	Depth of conduit slot		0.65%	3.2	Gage
211	Angle of conduit slot		0.65%	3.2	Gage
212	Evidence of poor workmanship		1.00%	3.2	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:46Z
Check the source to verify that this is the current version before use.