INCH-POUND

MIL-T-43182D
9 January 1989
SUPERSEDING
MIL-T-43182C
16 August 1974

MILITARY SPECIFICATION

TENTS, MISSILE SYSTEM EQUIPMENT CONSOLE (HAWK)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers four different frame-supported tents for sheltering console, maintenance test shop, aft radar and front radar assemblies of the Hawk Missile System.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATIONS

FEDERAL

V-F-106	- Fasteners, Slide, Interlocking
V-T-285	- Thread, Polyester
QQ-A-225/8	- Aluminum Alloy 6061, Bar, Rod, Wire, and Special Shapes; Rolled, Drawn or Cold Finished

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A

FSC 8340

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

U.S. Coats, Overcoats, and Jackets: Department of Defense Men's and Wome

QQ-B-613 - Brass, Leaded and Non Leaded: Flat Products (Plate, Bar, Sheet and Strip)
QQ-S-763 - Steel Bars, Wire Shapes and Forgings, Corrosion-Resisting

TT-E-529 - Enamel, Alkyd, Semi-Gloss
TT-P-595 - Preservative Coating, Canvas
TT-P-1757 - Primer Coating, Zinc Chromate, Low-Moisture Sensitivity
DDD-L-20 - Label: For Clothing, Equipage, and Tentage, (General Use)
PPP-B-601 - Boxes, Wood, Cleated-Plywood

MILITARY

MIL-P-501 - Pins, Tent, Metal
MIL-R-1670 - Rope, Tent-Lay
MIL-L-1709 - Lines, Tent
MIL-S-1734 - Slips, Tent Line
MIL-P-2383 - Pins, Tent, Wood
MIL-C-2399 - Cement, Liquid, Tent Patching
MIL-C-10578 - Corrosion Removing and Metal Conditioning Compound (Phosphoric Acid Base)
MIL-F-10884 - Fasteners, Snap
MIL-C-12095 - Cloth, Wind-Resistant Sateen, Cotton; Fire and Water Resistant
MIL-G-16491 - Grommet, Metallic
MIL-T-43566 - Tape, Textile, Cotton or Polyester, General Purpose, Natural or in Colors

STANDARDS

FEDERAL

FED-STD-191 - Textile Test Methods
FED-STD-751 - Stitches, Seams, and Stitchings

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage
MIL-STD-147 - Palletized Unit Loads
MIL-STD-731 - Quality of Wood Members for Containers and Pallets

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Naval Publications and Forms Center, (ATTN: NPODS), 5801 Tabor Avenue, Philadelphia, PA 19120-5099.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

Department of the Army Field Manual FM 10-16
General Repair of Tents, Canvas and Webbing

(Copies are available from the Superintendent of Documents, U.S. Printing Office, Washington, D.C. 20402)

DRAWINGS

U.S. ARMY NATICK RESEARCH, DEVELOPMENT & ENGINEERING CENTER

TENT, CONSOLE, RANGE ONLY RADAR; CW ACQUISITION RADAR AND CW ILLUMINATOR RADAR (HAWK SYSTEM)

5-4-712	- Assembly and Illustration
5-4-713	- Details
5-4-714	- Details and Views
5-4-715	- Details & Sections
5-4-716	- Erection Instructions
5-4-717	- Frame, Assembly Complete
5-4-718	- Details
5-4-790	- Guy Line Lug and Blackout Curtain Details

TENT, MAINTENANCE, MISSILE TEST SHOP

5-4-654	- Assembly and Illustration
5-4-655	- Details
5-4-656	- Details and Views
5-4-657	- Sections
5-4-658	- Erection Instructions
5-4-663	- Frame, Assembly Complete
5-4-664	- Details
5-4-789	- Guy Line Lug and Blackout Curtain Details

TENT, PULSE ACQUISITION RADAR, AFT

5-4-644	- Assembly and Illustration
5-4-645	- Details
5-4-646	- Details & Views
5-4-647	- Details & Sections
5-4-648	- Erection Instructions
5-4-659	- Frame, Front & Aft; Assembly Complete
5-4-660	- Details
5-4-793	- Guy Line Lug and Blackout Curtain Details

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

TENT, PULSE ACQUISITION RADAR, FRONT

5-4-639	- View Assembly and Illustration
5-4-640	- Details
5-4-641	- Details and Views
5-4-642	- Details & Sections
5-4-643	- Erection Instructions
5-4-659	- Frame, Front & Aft; Assembly Complete
5-4-660	- Details
5-4-792	- Blackout Curtain Details

(Copies of drawings are available from the U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014.)

2.2 Non-Government publications. The following document(s) form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN SOCIETY FOR TESTING AND MATERIALS

A 108	- Steel Bars, Carbon, Cold-Finished, Standard Quality
B 241	- Aluminum and Aluminum-Alloy Seamless Pipe and Seamless Extruded Tube
D 3951	- Standard Practice for Commercial Packaging

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 6.3) in accordance with 4.3.

3.2 Materials and components. Materials and components shall be as specified herein.

3.2.1 Cloth, cotton, sateen. The wind-resistant cloth shall conform to MIL-C-12095 and shall match shade OG 107.

Source: https://assist.dla.mil -- Downloaded: 202640-21T20:52Z
Check the source to verify that this is the currentversion before use.

3.2.2 Cloth, polyester. The natural color, water repellent treated polyester cloth used for light ports shall conform to the following requirements (see 4.4.1.1):

Physical Properties:

Fiber - Polyester
Weave - Plain, 1 x 1
Texture- Threads per inch (minimum):
Warp 80 ends
Filling 64 picks
Breaking strength-lbs (grab), (minimum):
Warp 290
Filling 265
Weight, oz/sq.yd - 5.5 (plus or minus 0.5).
Spray rating - 90, 90, 80 (three determinations).

Finishing Properties:

A water repellent of the silicone type shall be used; however, other water-repellent compounds may be used if approved by the contracting officer, (see 6.4).

The fabric shall be scoured, calendered, and heat set. The color shall be natural and the fabric shall have a maximum air permeability of 1.5 cu. ft./min/sq. ft. and a minimum of 40 percent luminous transmission.

3.2.3 Tape textile, cotton. The tape shall be 3/4, 1-1/2, and 2 inch widths, shade Olive Drab No. 7, conforming to type I, class 4 of MIL-T-43566.

3.2.4 Thread, polyester. The thread shall conform to type I, class 1, subclass B, shade S-1 (Cable No. 66022) of V-T-285. The dyed thread shall show fastness to weathering equal to or better than the standard shade sample (see 6.4). When no standard shade sample is available, the dyed thread shall show good fastness to weathering.

Thread sizes shall be as follows:

For all stitching on tent, except stitching indicated by "Z" on drawings and bartacking	- Size F for needle and E for bobbin
For stitching on tent indicated by "Z" on drawings	- Size F for needle and E for looper
For bartacking	- Size E for needle and bobbin

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

3.2.5 Grommet, metallic. The grommets with washers shall conform to type III, class 3, sizes 3 and 4 of MIL-G-16491.

3.2.6 Fasteners, slide, interlocking. The slide fasteners shall conform to size H, wire stirrup pulls of V-F-106. The fastener for the front wall section shall be type V, style 1 or 3 and for the light port and personnel door shall be type III, style 1. The slide fastener chain shall be fabricated of brass or polyester coil. The slider for the brass chain shall be brass and the slider for the polyester coil shall be die cast zinc alloy. The slide fastener tape shall be dyed to match Olive Drab shade S (CA 66519) and be water repellent and mildew-resistant. (Tapes made of 100 percent polyester need not be tested for mildew-resistance.) The color of the tape after treatment will be considered acceptable. The tape shall show good fastness to weathering. Alternatively, the slide fastener chain shall be polyester continuous monofilament in a ladder or coil type configuration. Color of the chain shall be olive drab or natural finish brass and the sliders shall be brass.

3.2.7 Rope, manila. The manila rope shall conform to type 1, class 2, 1/4 inch diameter of MIL-R-1670.

3.2.8 Lines, tent. The tent lines shall conform to MIL-L-1709. Types shall be as follows:

Type I (footstop)
Type XXIII, except that the end finish shall be in accordance with figure 19 of MIL-L-1709 (guy line)

3.2.9 Fastener, snap. The snap fastener shall conform to style 2, finish 2, button 24 line, size 1 and eyelet, size 1 of MIL-F-10884.

3.2.10 Eyelet and washer. The eyelet and washer (quarter-turn stud fastener) shall be brass, black finish, conforming to the United Carr Company components, eyelet BS 78403 and washer BS 78505, or equal.

3.2.11 Socket and clinch plate. The long-pronged socket and clinch plate (large curtain type) shall conform to style 1, finish 2 of MIL-F-10884.

3.2.12 Grommet, oblong and washer.

3.2.12.1 Eyelet. The oblong eyelet shall be brass, black finish, conforming to No. A867 of Edwin B. Stimpson, Inc., or equal.

3.2.12.2 Washer. The oblong washer shall be fabricated of 1/2 hard brass, dull black finish conforming to composition 1 or 2 of QQ-B-613 in the dimensions as shown on Drawings 5-4-642, 5-4-647, 5-4-657 and 5-4-715.

3.2.13 Pipe, aluminum alloy. The aluminum alloy pipe shall conform to 6061-T6, schedule 40, 1-1/4-inch nominal pipe size, or ASTM B 241.

3.3 Preservation. Preservation shall be level A or commercial, as

Source: https://assist.dla.mil -- Downloaded: 202610-21T20:52Z
Check the source to verify that this is the currentversion before use.

3.2.14 Bar, aluminum alloy. The aluminum alloy bar for the lunette support and the inner top support (see Drawing 5-4-718) shall conform to 6061-T6 of QQ-A-225/8.

3.2.15 Pins, tent.

3.2.15.1 Metal. The metal tent pin shall be type II, 12-inches long conforming to MIL-P-501.

3.2.15.2 Wood. The wooden tent pin shall be size 1 conforming to MIL-P-2383.

3.2.16 Slips, tent line. The nylon tent line slip shall conform to type II of MIL-S-1734.

3.2.17 Steel, carbon bar. The steel used to fabricate the diagonal side support spindle (see Drawing 5-4-659) shall conform to identification number 1211, 1212, 1213, or 1215, round form, cold finished, as specified in ASTM A 108.

3.2.18 Steel, corrosion-resisting bar. The corrosion-resisting steel bar for the lunette support rod (see Drawing 50-4-659) shall conform to the 300 series as specified in QQ-S-763.

3.2.19 Pretreating coating. The pretreating coating shall conform to MIL-C-10578.

3.2.20 Primer. The primer shall conform to composition G or L, as applicable, color Y or T, of TT-P-1757.

3.2.21 Enamel. The enamel shall conform to TT-E-529. The color shall correspond to Olive Drab color No. 24087.

3.3 Construction. The construction shall conform to the drawings listed in section 2 and to the requirements specified herein.

3.3.1 Stitching, machine.

3.3.1.1 Types of stitching. All stitch types, except bartacking shall conform to FED-STD-751 as follows:

For all stitching, except stitching indicated by "Z" on the drawings.	- Type 301, 5 to 7 stitches per inch.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

For stitching indicated by "Z" on drawings.	- Type 401, 5 to 7 stitches per inch. Chain portion of stitching shall not appear on outside of tent.
For bartacking	- Bartack, 7/8 plus or minus 1/16 inch long, 1/8 ± 1/32 inch wide (bight) shall contain 42 stitches.

3.3.1.2 Type 301 stitching. Ends of all stitching shall be backstitched or overstitched 1/2 inch minimum except when caught in other stitching or turned under in a hem. Thread tension shall be maintained so that there will be no loose stitching resulting in puckering of material sewn. The lock shall be embedded in the material sewn.

3.3.1.2.1 Repairs of type 301 stitching. Repairs of type 301 stitching shall be as follows:

a. When thread breaks or bobbin run-outs occur during sewing, the stitching shall be repaired by restarting the stitching a minimum of 1 inch behind the end of the stitching. 1/

b. Thread breaks or two or more consecutive skipped stitches or run-off stitches noted during inspection of the item (in-process or end item) shall be repaired by overstitching. The stitching shall start a minimum of 1 inch before the defective area (1/2 inch on box, box and cross, and W-W stitching) and continue a minimum of 1 inch beyond the defective area onto the existing stitching. Loose or excessively tight stitching shall be repaired by removing the defective stitching, without damaging the materials, and restitching in the required manner. 1/

1/ When making the above repairs, the ends of the stitching are not required to be backstitched.

3.3.1.3 Type 401 stitching. Thread tension shall be maintained so that there will be no loose stitching. Both ends of all seams or stitching produced with a 401 stitch type, when not turned under in a hem or held down by other stitching, shall have a 1/2 to 3/4 inch chain extending beyond each end. The looper (under thread) shall always be on the inside of the tent or cover. All repairs shall be made in accordance with 3.3.1.2.1a or 3.3.1.2.1b. Repairs may be made using 301 stitch type.

Source: https://assist.dla.mil -- Downloaded: 202610-21T20:52Z
Check the source to verify that this is the currentversion before use.

3.3.1.4 Automatic stitching. Automatic stitching machines may be used to perform any of the required stitch patterns provided the requirements for stitch pattern, stitches per inch, and size and type of thread are met, and at least three tying, overlapping, or backstitches are used to secure the ends of the stitching.

3.3.1.5 Thread ends. All thread ends that are visible on the finished item shall be trimmed to a length of not more than 1/4 inch.

3.3.1.6 Lubrication of thread. The addition of any lubricant to the polyester sewing thread prior to or during the sewing operation is prohibited.

3.3.1.7 Stitching margins. Unless otherwise specified, all stitch margins shall be 1/8, +1/16 -0 inch.

3.3.1.8 Bartacking. Bartacking shall be free of thread breaks or loose stitching.

3.3.2 Attachment of slide fasteners. The length of any slide fastener chain shall be such that after the slide fastener is sewed on, the tape shall not be puckered and the slider shall operate freely. Care shall be exercised to trim all thread ends and maintain specified distances between edges of fabric attached to slide fastener tape so that there will be no interference with the operation of the slider.

3.3.3 Setting of snap fasteners. If a hole is punched before inserting the male or female part of the style 2 snap fastener, it shall be smaller than the outside diameter of the fastener tube so that the tube must be forced through the hole. The fasteners shall be securely clinched. Roll of the clinched eyelet of the assembled fastener component shall not contain more than three scores (splits).

3.3.4 Setting of grommets. Holes punched to receive the grommets shall be smaller than the outside diameter of the grommet barrel so that the barrel must be forced through the hole. The grommets shall be securely clinched without cutting the materials. Roll of the clinched grommet shall not contain splits.

3.3.5 Setting of eyelets. Eyelets shall be securely clinched without splitting. The tolerance for location of eyelets for 1/4-turn stud fasteners shall be limited to $\pm$ 1/8 inch (noncumulative).

3.3.6 Wicking of sewing thread (cup test). There shall be no dripping of water through the tent stitching when the tent is tested as specified in 4.5.2. The cup test is intended to insure that non-wicking thread has been utilized and that no lubrication has been added to the polyester thread prior to or during the sewing operation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

3.3.7 Replacement of defective components. During the spreading, cutting, and manufacturing process, components of the tent having material defects or damages that are classified as defects in 4.4.3 or 4.4.5 shall be removed from production and replaced with non-defective and properly matched components.

3.3.8 Splicing of cloth. There shall be no splicing of roof, wall, or tent cover panels. Splicing of reinforcements and sod cloth sections will be permitted and, if performed, shall conform to the following requirements:

a. No more than two splices per reinforcement or sod cloth section permitted.

b. The shortest length of any spliced piece shall be not less than 2 feet.

c. Pieces shall be joined as shown on Drawings 5-4-713, 5-4-655, 5-4-645 and 5-4-640.

3.3.9 Repairs. All necessary repairs shall be affected in accordance with Department of the Army Field Manual FM 10-16, except that handsewn patches, or cemented patches other than is specified herein will not be acceptable. Cemented patches on holes, cuts, or tears not more than 1-inch in diameter or length, using cement specified in MIL-C-2399, shall be permitted. A maximum of three cemented patches per tent shall be allowable without prior authorization from the contracting officer. All other repairs shall require contracting officer authorization. Repairs required as a result of failure of the cup test, and when authorized by the contracting officer, shall be performed by treating with a compound conforming to type I, class 1, shade olive drab of TT-P-595, prior to retesting (see 6.6).

3.3.10 Welding. All welding shall be as specified on drawings. Materials to be welded shall be free from rust, scale, corrosion, oil, water, and other matter. Welds shall be sound and free from flash, porosity, cracks, and incomplete fusion.

3.3.11 Finish of frame. Exterior surfaces of frame including pipe fittings and adjusting brackets (except the threads of bolts and screws) shall be prepared for painting by treating with a diluted compound specified in 3.2.19. After thorough drying, exterior surface of the pipe, fittings, and adjusting bracket, except as noted above, shall be coated with primer specified in 3.2.20. When dry, primed surfaces shall be coated with enamel specified in 3.2.21.

3.3.12 Fusing of ends of synthetic cord, webbing and tape. All ends of synthetic cord, webbing, and tape shall be fused. The apparatus used to fuse the ends shall be capable of providing sufficient heat to provide a smooth edge and with the cut ends of the yarns all fused together. Fusing of the ends shall be accomplished prior to being assembled for stitching.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

3.4 Marking.

3.4.1 Tents. All tent markings shall conform to DDD-L-20.

3.4.1.1 Special marking. The marking "US" in the size characters and in the location shown on the drawings shall conform to type IV, class 9. Class 9 markings shall be clearly legible after subjection to accelerated weathering.

3.4.1.2 Identification label. Identification labels shall be stitched to the tents in the locations shown on the drawings and shall conform to type VI, class 6. The label size shall be 3-1/2 inches by 5-1/2 inches minimum with a blank space of at least 1-1/4 inches provided at the bottom for the Department of Defense Inspector's Stamp.

3.4.1.3 Erection instruction label. Labels for erection instructions shall conform to type VI, class 7 and shall be stitched to the tents in the locations shown on the drawings. The labels shall be proportionate copies of Drawing 5-4-716 (Tent, Console, Range Only Radar, CW Acquisition Radar), Drawing 4-4-643 (Tent Pulse Acquisition Radar, Front), Drawing 5-4-648 (Tent, Pulse Acquisition Radar, Aft), or Drawing 5-4-658 (Tent, Maintenance Missile Test Shop), whichever is applicable, as reproduced from glossy prints of these drawings (see 6.5). The size of the labels shall be, borderline to borderline, 15 $\pm$ 1/4 inches in the longer dimension, with a minimum 1/2-inch margin outside of the borderline on all sides.

3.4.2 Frames. Frame members shall be permanently and distinctly stamped or marked when specified. One support of each frame assembly, after finishing, shall be marked for identification with the letters "U.S." in characters 3/4-inch high and the name of the manufacturer or brand or mark of such known characters identifiable with the manufacturer and the number and year of the contract in characters 1/2-inch high. Other markings on frame components shall be as specified in applicable drawings.

3.4.2.1 Assembly instructions. Instruction marking shall be stenciled in yellow in the size and location shown on the applicable drawings.

3.5 Workmanship. The tent shall conform to the quality of product established by this specification and the occurrence of defects shall not exceed the applicable acceptable quality levels.

3.5.1 General. The tent, including all parts and accessories, shall be constructed and finished in a workmanlike manner with particular attention given to removal of burrs and sharp edges, accuracy of dimensions, thoroughness of welding, painting, alignment of parts and assemblies, and the tightness of screws, bolts etc. Threaded fastener holes shall be accurately punched or drilled and shall have burrs removed. Threaded fasteners shall not be broken, cracked, or stripped. Grommets and snaps shall not be damaged or split. Cloth components shall be clean and free of holes, cuts, tears or cloth defects such as multiple floats or broken or missing yarns. Webbing and tape shall not have

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

frayed or scalloped edges and rope components shall be free of cuts or breaks. Thread tension shall be maintained so that there will be no loose stitching, and seam allowances shall be maintained with seams properly sewn so that no runoffs, twists, pleats, or open seams shall result. Care shall be taken in the sewing to see that no needle chews occur. All closures utilized for erection and closing of the tent shall be properly adjusted before the tent is prepared for delivery to the Government.

3.5.2 Welding. Welded joints shall be such that grinding of the finished weld shall not be a requirement except when specified on a drawing. All surfaces to be welded shall be cleaned in accordance with good commercial practice and shall be free from scale, paint, grease, and other foreign materials. Welds shall have thorough penetration, good fusion and shall be free from scabs, blisters, abnormal pock marks, cracks, voids, slag inclusions, and other harmful defects. Welded assemblies shall be cleaned to remove any scale, oxidation products, and excess flux. Any acid used in cleaning shall be completely neutralized and removed.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.1.2 Responsibility for dimensional requirements. Unless otherwise specified in the contract or purchase order, the contractor is responsible for ensuring that all specified dimensions have been met. When dimensions cannot be examined on the end item, inspection shall be made at any point, or at all points in the manufacturing process necessary to assure compliance with all dimensional requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for the defects specified in 4.4.3, 4.4.4, 4.4.5 and 4.4.6, and tested for the characteristics specified in 4.4.7. The presence of any defect shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.4.1.1 Component testing. The polyester cloth shall be tested in accordance with table I. The lot size shall be expressed in yards. The sample unit shall be 1 1/2 yards long by the full width of the fabric. The inspection level shall be S-1 and the acceptable quality level (AQL), expressed in terms of defects per hundred units shall be 6.5.

TABLE I. Component tests

Component	Characteristic	Paragraph requirement	Test method 1/ or paragraph
Cloth, polyester	Weave	3.2.2	Visual 2/
	Texture	3.2.2	5050
	Breaking strength	3.2.2	5100
	Weight	3.2.2	5041
	Spray rating	3.2.2	5526
	Air permeability	3.2.2	5450
	Luminous transmission	3.2.2	4.5.1

1/ Applicable tests as referenced in FED-STD-191.

2/ The number of determinations shall be one and the results reported as pass or fail.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

4.4.2 In-process inspection. Inspection shall be made of the following operations or assemblies to establish conformance to specified requirements. Whenever nonconformance is noted, correction shall be made to the items affected and to the operation. Items which cannot be corrected shall be removed from production.

a. There shall be no lubrication of polyester sewing thread prior to or during the sewing operations for compliance with 3.3.1.6.

b. Holes punched to receive snap fasteners shall be in compliance with 3.3.3.

c. Holes punched to receive grommets shall be in compliance with 3.3.4.

d. Materials to be welded shall be clean and welds shall be sound and free of defects for compliance with 3.3.10.

e. Exterior surfaces of frame members shall be prepared for painting and are primed for compliance with 3.3.11.

4.4.3 End item visual examination. The end items shall be examined for the defects listed in table II. The tents shall be examined in an erected position to make the interior easily accessible for examination. The lot size shall be expressed in units of tents. The sample size shall be one tent. The inspection level shall be II and the AQL, expressed in terms of defects per hundred units, shall be 10 for major defects, 25 for major and minor A combined defects, and 100 for total (major, minor A, and minor B combined) defects.

TABLE II. End item visual defects

Examine	Defect	Classification Major	Minor A	Minor B
Fabric	Cut, tear, or hole (including exposed drill hole) greater than 1/8 inch in length or diameter on tent:			
	-on roof	101		
	-on wall		201	

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

TABLE II. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Fabric (cont'd)	Cut, tear or hole (including exposed drill hole) 1/8 inch or less in length or diameter on tent:			
	-more than 20 holes:			
	-on roof	102		
	-on wall		202	
	-more than 10 but not more than 20 holes:			
	-on roof		203	
	-on wall			301
	-more than 5 but not more than 10 holes:			
	-on roof or wall			302
Tie tapes	Edge frayed or scalloped			303
Hardware	Broken	103		
	Malformed:			
	-fails to perform intended function	104		
	-but will perform intended function		204	
	Corroded area			304
	Burr or sharp edge which may cause injury in handling or damage to fabric	105		
Grommets	Improperly set, two or more teeth exposed (except where grommet is set as specified but is in an area of unequal thickness which prevents uniform clinching)			305
	Clinched loosely, allowing grommet to move in hole			306
	Clinched excessively tight, damaged, split, or cutting fabric	106		
	Insecurely clinched, i.e., grommets or washers become disengaged	107		
Eyelets and washers (1/4 turn stud fasteners)	Clinched excessively tight, cutting fabric	108		
	Insecurely clinched, i.e., eyelets or washers become disengaged	109		
	Any split			307

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

TABLE II. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Snap fasteners	Clinched excessively tight: cutting fabric, or splits	110		
	Insecurely clinched, i.e., socket or stud becomes disengaged	111		
	Located more than 1/8 inch from where specified			308
Rope components	Any cut; any break:			
	-on guy line		205	
	-on wall reefing line			309
Seams and stitching	Open seam on stitch type 301:			
	-more than 1/4 inch but not more than 1 inch			310
	-more than 1 inch		206	
	Open seam on stitch type 401:			
	-one row of stitching open for 1 inch or less			311
	-one row of stitching open for more than 1 inch:			
	-on wall			312
	-on roof		207	
	-both rows of stitching open (not necessarily at same location):			
	-on wall			313
	-on roof	112		
	NOTE: A seam shall be classified as open when two or more consecutive stitches joining a seam are broken, or when one or more skipped or run-off stitches occur. On doublestitched seams, a seam shall be classified as open when either one or both sides of a seam are open.			
	Raw edges caught in stitching:			
	-more than 1 inch but not more than 3 inches			314
	-more than 3 inches		208	

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

TABLE II. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Seams and stitching (cont'd)	Thread breaks: -overstitched less than 1 inch on stitch type 401 or 301			315
	NOTE: Thread breaks not overstitched shall be classified as open seams.			
	Skipped stitches: -overstitched less than 1 inch on stitch type 401 or 301		209	
	NOTE: Skipped stitches not overstitched shall be classified as open seams			
	Needle chews resulting in cut, tear or hole (see cut, tear or hole)			
	One or more required rows of stitching omitted (except on boxstitching)	113		
Boxstitching	Incomplete: -one row of stitching omitted			316
	-two or more rows of stitching omitted		210	
Bartacking	Any bartacking less than specified length by more than 1/8-inch			317
	One or more bartacks omitted	114		
	Any boxstitching less than specified length by more than 1/8 inch		211	
Stitching ends	Overstitched less than 1/2 inch on stitch type 301 (except where ends are held down by other stitching, turned under in a hem, or where stitching is performed automatically)		212	
	Secured with less than 3 tying, overlapping or backstitches when automatic stitching is performed			318

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

TABLE II. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Seams	Seams pleated:			
	-on roof		213	
	-on walls			319
Seam type	Wrong seam type	115		
Stitch type	Wrong stitch type	116		
Stitch tension	Loose, resulting in an exposed bobbin or top thread, for more than 6 inches		214	
	Tight, as evidenced by puckering on fabric, for more than 6 inches		215	
Stitches per inch	Less than minimum specified (except on panel joining seams):			
	-one stitch			320
	-two or more stitches		216	
	Less than minimum specified on panel joining seams		217	
	More than maximum specified:			
	-one stitch			321
	-two or more stitches		218	
	NOTE: Variation in the number of stitches per inch, caused by the operator speeding up the machine and pulling the fabric in order to sew over heavy places or heavy seams or in turning corners, shall be classified as follows: a. Within the minor "A" defect classification - minor "B" defect b. Within the minor "B" defect classification - no defect			
Stitching gage	Not as specified		219	

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

TABLE II. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Stitching margin	Larger than specified:			
	-for more than 2 inches but not more than 4 inches in length			322
	-for more than 4 inches in length		220	
Stitching indicated by "Z" on drawings	Chain portion of stitching shows on outside of tent		221	
Mends, darns or patches	Repairs not in accordance with Department of the Army Field Manual FM 10-16 or not authorized by the contracting officer (except as otherwise specified) (see 3.3.9)	117		
Components and assembly	Any component part not fabricated of applicable referenced material	118		
	Any component part omitted	119		
Construction details				
Hems	Twisted or pleated			323
	Constructed with partial turnunder when double turnunder is required		222	
Reinforcements	Improperly applied, causing excessive fullness on reinforcement or reinforced parts			324
Tent lines	One or more lines omitted	120		
	Eye splice omitted	121		
	Eye splice not as specified		223	
	Free ends of lines not finished as specified			325
Footstops	One footstop omitted			326
	Two or more footstops omitted	122		
	Ends not finished as specified		224	

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

TABLE II. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Construction details (cont'd)				
Cloth splicing	Splice in roof or wall	123		
	Number of splices per reinforcement or sod cloth section more than specified		225	
	Spliced pieces not joined as shown on Drawings 5-4-640, 5-4-646, 5-4-651, and 5-4-713		226	
	Length of spliced pieces less than specified		227	
Slide fasteners	Slider jams or fails to interlock chain	124		
	Any tape improperly assembled causing failure of chain to effect a smooth and secure closure	125		
	Wrong length	126		
	Width not as specified	127		
	Puckering of tape	128		
	Broken or missing scoops	129		
	Thong omitted	130		
	NOTE: The inspector shall pull slide fasteners three or four times to an open and closed position to determine proper function and effectiveness of each fastener.			
Labels	Omitted, incorrect, illegible or misplaced:			
	-instruction		228	
	-indentification			327
Marking "U.S." and nomenclature	Omitted, incorrect, illegible or or misplaced			328

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

TABLE II. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Construction details (cont'd)				
Cleanness	Grease or oil stains			329
	Thread ends not trimmed to 1/4 inch or less:			
	-in slide fastener area		229	
	-in any other area			330

4.4.4 End item dimensional examination. The end items shall be examined for the defects listed in table III. The tents shall be examined in an erected position to make the interior easily accessible for examination. The lot size shall be expressed in units of tents. The sample unit shall be one tent. The inspection level shall be S-4 and the AQL, expressed in terms of defects per hundred units, shall be 2.5 for major defects, 15 for major and minor A combined defects, and 40 for total (major, minor A, and minor B combined) defects.

TABLE III. End item dimensional defects

Examine	Defect	Classification Major	Minor A	Minor B
Overall dimensions	Smaller than specified dimensions less applicable minus tolerance indicated on drawings	101		
	Larger than specified dimensions and applicable plus tolerance indicated on drawings			301
Component dimensions	Smaller than specified dimensions less applicable minus tolerance indicated on drawings, but not smaller than specified dimensions less twice the applicable minus tolerance			302

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

TABLE III. End item dimensional defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Component dimensions (cont'd)	Smaller than specified dimensions less twice the applicable minus tolerance indicated on drawing		201	
	Larger than specified dimensions and applicable plus tolerance indicated on drawings			303
Tie tapes	Finished length less than specified by more than 1 inch		202	
Rope components	Finished length of lines less than specified by more than 2 inches, footstops less than specified by more than 1/2 inch		203	
Hems	Hems required to finish less than 3/4 inch in width: -less than specified			304
	Hems required to finish more than 3/4 inch in width: -less than specified by more than 1/4 inch			305
Reinforcements	Finished dimensions less than specified by more than 1/2 inch			306
Location dimensions	Under or over specified dimensions by more than 1/4 inch			307

4.4.5 End item visual examination of frames. The frame assembly shall be examined for the defects listed in table IV. The lot size shall be expressed in units of frames. The sample unit shall be one frame. The inspection level shall be II and the AQL, expressed in terms of defects per hundred units, shall be 4.0 for major defects, 10 for major and minor A combined defects, and 25 for total (major, minor A, and minor B combined) defects.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

TABLE IV. End item visual defects (frames only)

Examine	Defect	Classification Major	Minor A	Minor B
Metal frames finish	Area of thin film; i.e., primer or base metal shows through; or not finished:			
	-1 square inch or less of bare metal			301
	-more than 1 square inch	101		
	Color of finish not as specified		201	
	Wet or tacky; i.e., will mark off if touched		202	
	Soft run	102		
	Foreign matter embedded in finish			302
	Not adherent; i.e., blistering, peeling or flaking	103		
	Scratched through prime coat, 1 inch or more in length			303
	Finishing material on threads of bolts or screws		203	
Construction and workmanship	Any component (including bolts, screws) missing, fractured, split, bowed, sprung, or bent out of shape	104		
	Rough or sharp edges		204	
	Casting unsound; e.g., porous, warped, cracked, fractured, distorted, deformed, or contains a blow hole or a sink mark	105		
Metal fasteners	Cap screws not modified as specified	106		
	Slot, in support, not threaded where required	107		
	Bolt or screw thread does not mate with thread in tee, elbow or support	108		
	Washer missing			304
Welding	Missing, burned through, porous, cracked, fractured or not fused	109		
	Not smooth and uniform, flash, scale or flux deposits not removed		205	
	Not type or size shown on drawings		206	

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

TABLE IV. End item visual defects (frames only) (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Assembly	Component will not assemble to matching part	110		
	Undue force or special tool required to assemble mating parts	111		
Marking (identification and instruction)	Missing, incomplete, misspelled, illegible, not specified type, size or color; not applied in specified location			305

4.4.6 End item dimensional examination. The frames shall be examined for conformance to the dimensions specified on the drawings that can be determined on the end items without damaging or disassembling the end items. The lot size shall be expressed in units of frames. The sample unit shall be one frame. The inspection level shall be S-3 and the AQL, expressed in terms of defects per hundred units, shall be 4.0. Any dimension not within the specified tolerance shall be classified as a defect.

4.4.7 End item testing. The end items shall be tested as specified in 4.5.2 for compliance with 3.3.6. The lot shall consist of all completely fabricated tents offered for inspection at one time. The sample unit shall be one completely fabricated tent. The inspection level shall be S-3. Failure in any area shall be cause for rejection of the lot.

4.4.8 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.
Materials	Any component missing, damaged, or not as specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

Examine	Defect
Workmanship	Inadequate application of components, such as: incomplete sealing or closure of flap, improper taping, loose strapping, or inadequate stapling. Bulged or distorted container.
Content	Number per container is more or less than required.

4.4.9 Palletization examination. The fully packaged and palletized end items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load, fully packaged. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement
Palletization	Pallet pattern not as specified Interlocking of loads not as specified Load not bonded with required straps as specified
Weight	Exceeds maximum load limits
Marking	Omitted; incorrect; illegible; of size, location, sequence, or method of application

4.5 Methods of inspection.

4.5.1 Luminous transmission of polyester fabric.

4.5.1.1 Equipment.

4.5.1.1.1 Light source. Light source shall consist of an artificial daylight lamp (e.g., Macbeth 7500 ± 200K) or natural north daylight. The luminance at the sample position shall not be less than 100 foot-candles.

4.5.1.1.2 Light meter. The light meter shall be corrected for photopic sensitivity function. A Weston Photronic Foot-Candle Meter, Model 6.4 is suitable apparatus for measuring luminance of transmitted light.

Source: https://assist.dla.mil -- Downloaded: 202610-21T20:52Z
Check the source to verify that this is the currentversion before use.

4.5.1.2 Method. Place the photo-sensitive detector of the light meter on a plane essentially perpendicular to the direction of the incident light. Measure the luminance of the incident light and record in foot-candles (I_o). This measurement of intensity may fluctuate if natural daylight is used on a day with variable cloudiness. Place the sample directly over the detector on the light meter and record the luminance of the transmitted light in foot-candles (I).

4.5.1.3 Calculations. Record the ratio I/I_o for at least three samples. Multiply the mean ratio for the replicates by 100 and report as percent luminous transmission. A luminous transmission value of less than 40 percent shall be cause for rejection of the lot.

4.5.2 Wicking of sewing thread (cup test). The tent shall be tested in each of two areas as follows: at an intersection of a horizontal and vertical seam such as at an intersection of a side wall and roof; and on a roof panel seam. Suspend the seamed section of the test fabric in the center of a 6 ± 1/8 inch diameter hoop and form a depression with the seamed fabric in the hoop to a depth of 1 ± 1/4 inch. Slowly pour 500 mL of water at 77°F ± 4°F into the cupped area (depression) and observe the under surface of the fabric for water penetration. Any wicking of water along the sewing thread, identified by a discoloration or darkening of the thread within 5 minutes after water is poured, shall constitute a failure. Water leakage through the needle holes or between the plies of the lapped seamed fabric shall not be considered a failure.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Frame, tent, assembly. Each disassembled tent frame assembly shall be neatly bundled together and securely tied in not less than three places along the length with cotton twine or cord. All elbows and tees shall be attached to the shorter applicable frame support member by means of the set screws. The other set screws shall be left in the elbows or tees. The loose hardward items consisting of bolts, cap screws, flat washers, lockwashers, plain nuts, and retaining rings shall be grouped according to frame assembly type and each individual group placed in an end opening drawstring type bag made from unbleached cotton sheeting cloth. The bagged hardware items shall then be securely tied to the applicable tent frame assembly with cotton twine or cord. The rod and spindle supports (Tents: Front and Aft) shall be cushioned and secured in place.

Source: https://assist.dla.mil -- Downloaded: 202610-21T20:52Z
Check the source to verify that this is the current version before use.

5.1.1.2 Tent, console, without frame assembly. Each console tent shall be laid flat with the front opening facing up and smoothly folded. The slide fasteners shall be closed and attached guy lines tucked within the folds. Each folded tent shall be compactly rolled and securely tied in not less than three places along the length with cotton twine or cord. The length of each rolled and tied tent shall measure a minimum of 48 inches and a maximum of 96 inches.

5.1.1.3 Pins, tent. The metal and wood tent pins specified in 3.2.15 shall be bundled together in the quantities specified in table V in identical item groups and securely tied with twine or cord approximately 2 inches from each end.

TABLE V. Quantity of wood and metal tent pins

Tent	Quantity	
	Wood	Metal
Range Only Radar, CW Acquisition Radar and CW Illuminator Radar	18	18
Pulse Acquisition Radar, Front	19	19
Pulse Acquisition Radar, Aft	16	16
Maintenance Missile Test Shop	20	20

5.1.2 Commercial. Tents shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

5.2.1 Level A. In each complete tent (consisting of a tent, a frame assembly and tent pins), or one frame assembly when procured separately, or one tent when procured separately, preserved as specified in 5.1, shall be packed in a wood-cleated plywood box conforming to overseas type, style A, of PPP-B-601. Each box shall be closed and reinforced with the appendix of PPP-B-601.

5.2.2 Level B. In each complete tent (consisting of a tent, a frame assembly and tent pins), or one frame assembly when procured separately, or one console tent when procured separately, preserved as specified in 5.1, shall be packed as specified in 5.2.1, except a domestic-type box is acceptable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

5.2.3 Commercial. Tents or tent components when procured separately, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

5.3 Palletization. When specified (see 6.2), tents or tent components packed as specified in 5.2, that are not provided with skids, shall be palletized. The boxes shall be palletized on a 4-way entry pallet in accordance with load type I of MIL-STD-147. Pallet types shall be type I (4-way entry), type IV, or type V in accordance with MIL-STD-147. Pallets shall be fabricated from wood groups I, II, III, or IV of MIL-STD-731. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L, or film bonding means O or P. Pallet patterns shall be in accordance with the appendix of MIL-STD-147.

5.4 Marking. In addition to any special marking required by the contract or purchase order, shipping containers and palletized unit loads shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The tents are designed to provide protection for personnel engaged in operation of radar equipment related to the Hawk Missile System in cold and cold-wet areas.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number, and date of this specification.
b. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).
c. When first article is required (see 3.1, 4.3, and 6.3).
d. Levels of preservation and packing (see 5.1 and 5.2).
e. When separate procurements of tent components (frame, tent assembly and tent console without frame assembly) are desired (see 5.2.1, 5.2.2 and 5.2.3)
f. When palletization is required (see 5.3).

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in acquisition documents regarding arrangements for selection, inspection, and approval of the first article.

Source: https://assist.dla.mil -- Downloaded: 202610-21T20:52Z
Check the source to verify that this is the current version before use.

6.4 Sample. For access to samples and a list of approved water repellent compounds, address the contracting activity issuing the invitation for bids.

6.5 Copies of drawings. Glossy prints of drawings of the labels specified in 3.4.1.3 may be obtained from the contracting activity.

6.6 Seam retreatment. A satisfactory method of applying the textile compound for the repair of leaking seams is as follows:

a. A suitable volume of textile compound conforming to type I, class I, shade olive drab of TT-P-595, shall be thoroughly stirred and diluted with an equal volume of petroleum solvent (Stoddard solvent or equivalent). Thoroughly stir the mixture again before use.

b. Prior to application of the compound, the tents must be dry. Special attention must be taken to insure adequate ventilation and that proper fire preventive measures are taken since the compound is flammable.

c. Two coats of the textile compound shall then be applied to the seams (on the outside of the tent only). A 4-inch wide stiff brush is recommended for use. The first coat shall be air dried for a minimum of 4 hours prior to application of the second coat. Elapsed time between coats may be reduced by providing a supply of hot air to evaporate the solvent more quickly. In this manner, a second coat may be applied as soon as the first coat is dry to the touch. After the application of the second coat, the treated tent shall be allowed to air dry for a period of at least 24 hours.

6.6.1 Seams to be treated. Seams which have failed the test specified in 4.5.2 shall be treated as follows:

a. Failure at roof panel lap seams - treat all roof panel lap seams.

b. Failure at stitching joining roof and wall, including reinforcement on roof - treat all stitching on eave and roof reinforcement.

6.7 International standardization agreements. Certain provisions of this specification are the subject of international standardization agreement as cited in NATO, STANAG NO. 2882, relative to camouflage requirements for tents, shelters and subsidiary components. When amendment, revisions, or cancellation of this document is proposed which will affect or violate the international agreement concerned, the preparing activity will take appropriate reconciliation action through international standardization channels including departmental standardization offices, if required.

Source: https://assist.dla.mil -- Downloaded: 202610-21T20:52Z
Check the source to verify that this is the currentversion before use.

6.8 Subject term (key word) listing.

Frame supported
PAR
Radar
Shelter

6.9 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:

Army - GL
Air Force - 99

Review activities:

Army - MI
Air Force - 82
DLA - CT

Preparing activity:

Army - GL

(Project 8340-0513)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:52Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-T-43182D	TENTS, MISSILE SYSTEM EQUIPMENT CONSOLE (HAWK)

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2025-10-21T20:52Z
Check the source to verify that this is the current version before use.