INCH-POUND

MIL-C-22442/15D(AS)
15 September 1989
SUPERSEDING
MIL-C-22442/15C(AS)
26 May 1989

MILITARY SPECIFICATION SHEET

CABLE ASSEMBLY, RADIO FREQUENCY (AIRCRAFT AUDIO), CX-4832A/AR

Inactive for new design after 2 September 1988.
For new design use MIL-C-22442/19.

This specification sheet is approved for use by the Naval Air Systems Command, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the cable described herein shall consist of this document and the latest issue of specification MIL-C-22442.




FIGURE 1. Cable assembly CX-4832/AR P/N M22442/15-1.

AMSC N/A FSC 5995

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T12:25Z
Check the source to verify that this is the current version before use.




FIGURE 2. Cable assembly P/N M22442/15-1 CX-4832/AR schematic diagram.

APPLICABLE DOCUMENTS:

MIL-J-641	Jack, Telephone, General Specification for
MIL-R-6855	Rubber, Synthetic Sheets, Strips, Molded or Extruded Shapes
MIL-C-10392	Cord, Electrical (Audio, Miniature)

REQUIREMENTS:

1. The cable (cord) shall be in accordance with MIL-C-10392 Type WM-59A/U.

2. The weight of the cable assembly shall not be greater than 3 ounces.

3. The stay cord shall be firmly attached to the connectors.

4. Material for molded parts shall be black synthetic rubber, MIL-R-6855, Class II, Type A, Grade 60.

5. Single conductors shall have a nominal cross sectional area of 404 circular MILs (No. 24 AWG) and shall be in accordance with specification MIL-C-10392 except that the outer separator and jacket shall be omitted.

6. The single conductor connector shall be made of half-hard brass finished with white nickel plate to 0.0004 inch minimum depth. The finished dimensions shall be as shown in Figure 1.

7. Sleeve P/N M22442/2-3 shall be supplied with each cable assembly.

8. The terminal block shall have dimensions and details shown in Figures 1 and 2 and shall have provision for mounting on a pilot's helmet. The pins only, from jack JJ-048, shall be molded in the terminal block and shall be in accordance with MIL-J-641.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T12:25Z
Check the source to verify that this is the current version before use.

9. The following DC resistance checks shall be made:

   (a) Contact A of terminal block to contact 1 of P/N M22442/2-2 less than 2 ohms.

   (b) Contact B of terminal block to contact 2 of P/N M22442/2-2 less than 2 ohms.

   (c) Earphone terminal "C" and contact 3 of P/N M22442/2-2 less than 2 ohms.

   (d) Earphone terminals "D" and "E" to contact 5 of P/N M22442/2-2 less than 2 ohms.

   (e) Earphone terminal "F" to contact 4 of P/N M22442/2-2 less than 2 ohms.

10. The cable assembly shall be tested in accordance with the tests listed in Table I.

NOTES:

1. All dimensions are in inches.

2. Tolerances are molded parts $\pm$.05, metal parts $\pm$.005 inches unless otherwise specified.

3. Mylar identification plates may be used as an alternate method.

Preparing Activity:
Navy - AS
Project No. 5995-N133

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T12:25Z
Check the source to verify that this is the current version before use.

TABLE I.

Inspection	Requirement Paragraph	Test Paragraph	Group I Qualification Tests	Group II Quality Conformance Test 100%	Group III Sample Testing Per 4.5.1
GROUP A (ALL SAMPLE UNITS) 1/					
Visual & Mechanical Inspection	3.1 & 3.4	4.6.2	X	X	
Soldering	3.4.24	4.6.2.1	X	X	
Continuity	3.5.3	4.6.5	X	X	
GROUP B					
Dielectric Withstanding Voltage	3.5.5	4.6.7	X		X
Gauging 1/	3.5.6	4.6.8	X		X
Pull Test 1/	3.5.7	4.6.9	X		X
Bend Relief Flexibility	3.5.10	4.6.12	X		X
Durometer Hardness	3.5.16	4.6.18	X		X
GROUP C					
Low Temperature Flexibility	3.5.11	4.6.13	X		X
Durability 1/	3.5.13	4.6.15	X		X
Ozone Resistance 1/	3.5.14	4.6.16	X		X
Jacket Elongation	3.5.15	4.6.17	X		X
GROUP D 1/					
Temperature-Altitude 2/	3.6.1	4.7	X		
Salt Fog	3.6.2	4.7	X		
Shock	3.6.6	4.7	X		
Humidity	3.6.6	4.7	X		
Thermal Shock	3.6.6	4.7	X		

1/ Minimum tests for QPL retention (see paragraph 4.4.4)
2/ Steps 3 and 12 only

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T12:25Z
Check the source to verify that this is the current version before use.