FED. SUP CLASS
2620

THE TIRE SHALL BE IN ACCORDANCE WITH THE APPLICABLE REQUIREMENTS

OF MIL-R-7726 EXCEPT AS SPECIFIED HEREIN

SIZE	PLY RATING	STATIC LOAD RATING LBS.	INFL. PRESS. PSI RATED	BURST PRESS. PSI MIN.	BEAD WIDTH IN. MAX.	WEIGHT LBS. MAX.	STATIC UNBAL OZ-IN MAX.	TREAD	MOLD SKID DEPTH MIN.	DEFLEC. +3% -4%
28x7.7	1/14 TL	11,000	195	685	1.75	42.0	14	2/RIB	.30	32%

1/TL Tubeless

2/ At least three, but not more than seven continuous circumferential ribs - fabric tread

RIM DATA:

WIDTH BETWEEN FLANGES (INCH)	LEDGE DIAMETER (INCH)	FLANGE HEIGHT (INCH)	MIN. LEDGE WIDTH (INCH)	MIN. FLANGE WIDTH (INCH)	FLANGE RADIUS (INCH)	HEEL RADIUS (INCH)	FLANGE EDGE RADIUS (INCH)
6.0	14.0	1.0	1.75	.750	.5	.25	.125

THE TIRE COVERED BY THIS DRAWING SHALL BE SUITABLE FOR USE AND PROVIDE REASONABLE SERVICE LIFE DURING ALL NORMAL OPERATIONS AT TAKE-OFF SPEEDS OF NOT MORE THAN 200 MPH AND LANDING SPEEDS OF NOT MORE THAN 185 MPH.

THE TIRE SHALL WITHSTAND WITHOUT FAILURE THE FOLLOWING TESTS:

TIRE 1:

DYNAMIC TEST - THE TIRE SHALL SATISFACTORILY WITHSTAND 50 CYCLES OF TEST "A" FOLLOWED BY 100 CYCLES OF TEST "B" WITHOUT EVIDENCE OF FAILURE.

TEST A - THE TIRE SHALL BE LANDED AGAINST A FLYWHEEL ROTATING AT A PERIPHERAL SPEED OF 200 MPH (174 KNOTS). THE FLYWHEEL SPEED SHALL THEN BE DECREASED UNTIL A ROLL DISTANCE OF 9000 FEET HAS BEEN COVERED, AT WHICH TIME THE TIRE SHALL BE UNLANDED. THE AVERAGE DECELERATION RATE SHALL BE 4.5 FT/SEC/SEC BETWEEN 200 AND 100 MPH, AND IS UNSPECIFIED BELOW 100 MPH. THE TIRE LOAD SHALL BE INCREASED TO 1000 LBS IN 2 TO 4 SECONDS AFTER LANDING AND THEN FURTHER INCREASED LINEARLY WITH TIME TO A VALUE OF 11,000 LBS IN 49 TO 54 SECONDS AFTER LANDING. THE LOAD SHALL THEN BE MAINTAINED AT 11,000 LBS UNTIL THE TIRE IS UNLANDED. THE TIRE DEFLECTION AT RATED LOAD ON THE FLYWHEEL SHALL BE THE SAME AS OBTAINED WITH THE RATED LOAD AND INFLATION PRESSURE ON A FLAT PLATE.

TEST B - THE TEST CYCLE SHALL BE IDENTICAL TO THE LOW SPEED (90 TO 0 MPH) DYNAMIC TEST DESCRIBED IN SPECIFICATION MIL-T-5041. THE TIRE DEFLECTION AT RATED LOAD ON THE FLYWHEEL SHALL BE THE SAME AS OBTAINED WITH THE RATED LOAD AND INFLATION PRESSURE ON A FLAT PLATE.

TIRE 2:

GOVT LAB TEST - THIS TIRE SHALL BE REBUILT FROM THE SAME BATCH AS TEST TIRE 1 AND SHALL BE IDENTICALLY PROCESSED. THIS TIRE SHALL NOT BE CONTRACTOR TESTED AND SHALL BE PROVIDED FOR GOVERNMENT LABORATORY TESTING.

SECTION - A REPRESENTATIVE SECTION OF TIRE 1 AND TIRE 2 SHALL BE SUBMITTED TO A GOVERNMENT LABORATORY AS SPECIFIED PER MS 3377.

AIR RETENTION - THE TUBELESS TIRE SHALL BE INFLATED TO A PRESSURE OF 280 PSI AND ALLOWED TO STAND FOR A PERIOD OF 4 HOURS AT WHICH TIME THE PRESSURE DROP DUE TO GROWTH SHALL BE REPLACED. THE TIRE SHALL THEN STAND FOR AN ADDITIONAL 12 HOURS AT WHICH TIME THE PRESSURE SHALL BE MEASURED AND THE TIRE INSPECTED. THE AIR PRESSURE LOSS SHALL NOT EXCEED 5 PERCENT AND THE TIRE SHALL NOT REVEAL ANY APPEARANCE OR PERFORMANCE DEFECTS, SUCH AS SIDEWALL BLISTERS, TREAD SEPARATION, ETC.

NOTES -

1. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID, OR REQUEST FOR PROPOSAL, EXCEPT THAT REFERENCE ADOPTED INDUSTRY STANDARDS SHALL GIVE THE DATE OF THE ISSUE ADOPTED.
2. FOR DESIGN FEATURE PURPOSES, THIS STANDARD TAKES PRECEDENCE OVER PROCUREMENT DOCUMENTS REFERENCED HEREIN.

APPROVED 18 FEB 1969 REVISED (A) 29 DEC 1981

(A) REVISED AND REDRAWN

P.A. NAVY - AS Other Cost	TITLE: TIRE, PNEUMATIC, AIRCRAFT, REBUILT, 28 x 7.7 (200 MPH) TYPE VII (NAVY)	MILITARY STANDARD MS 3384(AS)
PROCUREMENT SPECIFICATION MIL-R-7726	SUPERSEDES:	SHEET 1 OF 1

DD FORM 672-1 PREVIOUS EDITIONS OF THIS FORM ARE OBSOLETE PROJECT NO 7670-N222 PLATE NO. 17709

This standard has been approved by the NAVAL AIR SYSTEMS COMMAND Department of the NAVY and shall be used by that activity. All other military activities are required to employ this standard where suitable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:03Z
Check the source to verify that this is the current version before use.